**QUEEN'S
UNIVERSITY
BELFAST**

High shear granulation of binary mixtures: Effect of powder composition on granule properties: Effect of powder composition on granule properties

Mangwandi, C., JiangTao, L., Albadarin, A. B., Dhenge, R. M., & Walker, G. M. (2015). High shear granulation of binary mixtures: Effect of powder composition on granule properties: Effect of powder composition on granule properties. *Powder Technology*, 270(Part B), 424-434. <https://doi.org/10.1016/j.powtec.2014.06.021>

Published in:
Powder Technology

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

Copyright © 2014 Elsevier B.V. This is the author's version of a work that was accepted for publication in Powder Technology. Changes resulting from the publishing process, such as peer review, editing, corrections, structural formatting, and other quality control mechanisms may not be reflected in this document. Changes may have been made to this work since it was submitted for publication. A definitive version was subsequently published in Powder Technology, vol 270, Part B, January 2015, doi:10.1016/j.powtec.2014.06.021.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

HIGH SHEAR GRANULATION OF BINARY MIXTURES: EFFECT OF POWDER COMPOSITION ON GRANULE PROPERTIES.

Chirangano Mangwandi^{*1}, Liu JiangTao¹, Ahmad B. Albadarin^{1,2}, Ranjit M. Dhenge³,
Gavin M. Walker^{1,2}

¹School of Chemistry and Chemical Engineering, Queen's University Belfast,
Belfast BT9 5AG, Northern Ireland UK

²Materials Surface Science Institute,
Department of Chemical and Environmental Sciences,
University of Limerick, Ireland.

³Particle Products Group, Depart. Chemical and Biological Eng., University of Sheffield,
Mappin Street, Sheffield S1 3D, UK

Corresponding Author details:

Tel: +44 (0) 28 9097 4378

Fax: +44 (0) 28 9097 6524

E-mail: c.mangwandi@qub.ac.uk

1

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

ABSTRACT

The granular product being designed in this work required the use of two different powders namely limestone and teawaste; these materials have different bulk and particle densities. The overall aim of the project was to obtain a granular product in the size range 2 to 4mm. The two powders were granulated in different proportions using carboxymethylcellulose (CMC) as the binder. The effect of amount of binder added, relative composition of the powder, and type of teawaste on the product yield was studied. The results show that the optimum product yield was a function of both relative powder composition and the amount of binder used; increasing the composition of teawaste in the powder increased the amount of binder required for successful granulation. An increase in the mass fraction of teawaste in the powder mix must be accompanied by an increase in the amount of binder to maintain the desired product yield.

KEYWORDS

Binary-mixture, high shear granulation, attrition; contact angle; wetting; granule strength

1. Introduction

High shear wet granulation process (HSWG) is a size enlargement process that involves conversion of primary powder particles into larger entities with improved characteristics. Some of the advantages of HSWG include increased bulk densities, improved flow properties, reduced powder segregation and better handling properties. HSWG has been applied in several industries for example detergent, food, pharmaceutical and agricultural, to enhance the powder processability [1-5].

Granulation of a mixture of powders is very common especially in the pharmaceutical industries where several powder components are required to perform different functionalities. Some of the common mixtures used in the pharmaceutical industries are lactose/ micro crystalline cellulose (MCC) [6-8]; lactose / mannitol [9] and starch/lactose [10-14]. In most granulation applications the raw materials are of comparable bulk densities.

Granulation of binary mixtures of powders has always proven to be a challenge especially if the powders have differing physical properties. Some of the challenges encountered include segregation of the powder particles during the mixing, preferential nucleation of the component. This often leads to a granular product with inhomogeneous composition. The interaction between the powder particles and the binder particle is crucial. In-fact wettability of the powder components has a significant influence on the success or failure of the granulation process as it impacts the nucleation process. Contact angle measurements are used to indicate the degree of wetting of solid surface by liquid droplets. The high values of contact angle show low wettability whilst, small values of contact angle show high wettability. For instance, if one of the components of the powder is hydrophobic this could result in preferential granulation of the hydrophilic component [15]. It has also been shown

1 that as the hydrophobicity of formulation increases the average size of the granules decreases
2 and the granule structure depend on the formulation wettability [16].

3 Percolation theory has been used to describe wet agglomeration of binary mixtures in high
4 shear mixer in by other researchers [17]. According to their theory it was concluded that if
5 the components exhibit similar growth properties the growth properties would be additive.
6 However, if the components show different growth properties the mixing ratio of the
7 components would control the growth properties of the mixture or intermediate growth
8 properties would be exhibited.

9 In the current research project, granulation of two different powder materials was
10 necessary to produce a product for application as an improved soil conditions. Each of the
11 components; limestone and teawaste perform different roles. Limestone modifies the pH of
12 acidic soils while teawaste improves the soil texture introduces organic matter in the soil. In
13 the current study the challenge faced was that the two powders have huge difference in the
14 density which often leads to segregation of the components; limestone ($\sim 2700 \text{ kg/m}^3$) is
15 denser than teawaste ($\sim 800 \text{ kg/m}^3$).

16 The aim of this research was to investigate the effect of the relative compositions of the
17 teawaste and limestone on product yield, attrition strength and granule mass mean size.
18 Optimum binder requirements of the different formulations were also investigated. The effect
19 of washing teawaste on binder requirement and other granules properties was also studied.

20

2. Experimental Methods

2.1 Materials Characterisation

2.1.1 XRD and particle size analysis of the powders

Limestone powder supplied by Kilwaughter Chemicals Ltd, UK, was used as one of the raw materials. X-ray diffraction (XRD) analysis of the powder limestone that it was mainly composed of calcite and quartz minerals [4]. Value tea purchased from Tesco was used as the second powder component in the granulation experiments. It was used in two forms, first as received referred to as fresh tea (FT) and secondly it was washed in fresh hot water and dried to simulate used tea (UT). The particle size distributions of limestone and used-tea measured by Malvern Mastersizer are shown in Fig. 1. The mass median diameters (d_{50}) of limestone, FT and UT powders were $31.5 \pm 4.5 \mu\text{m}$; $311 \pm 10 \mu\text{m}$ and $413 \pm 31 \mu\text{m}$ respectively. The other attributes of the particle size distributions are summarised in Table 1.

[Fig. 1]

[Table 1]

Carboxymethylcellulose (CMC) salt supplied by Calbiochem, UK was used to make binder in this research project. A homogenous mix was obtained adding the CMC powder to the vortex formed by stirring the deionized water with an impeller rotating at high speed (490 rpm) over a period of 30 minutes. The CMC concentration in the solution was 5g/L. The binder solution was stored in sealed jars until use. The viscosity of the binder solution was measured with Brookfield Viscometer RVDV-II Pro (Brookfield Engineering Laboratories, USA) was found to be ~6600 mPas.

- 1 The comparison between the specific pore volume and surface area of teaswaste and
- 2 limestone particles obtained from literature [18-20] is summarised in

Table 2. The table shows the surface area and specific pore volume of teawaste (UT) is higher than that of limestone.

[Table 2]

2.1.2 Fourier Transform Infrared (FTIR) spectroscopy

FT-IR was principally employed as a qualitative technique for the assessment of the chemical structure of fresh tea (FT) and the used tea (UT). The IR spectra of the samples were recorded on a PerkinElmer Spectrum 100 spectrophotometer to characterize the change in the functional groups of the material surface before and after washing with hot water (using a KBr disk technique in the range of $400 - 4000 \text{ cm}^{-1}$). The results for the analysis are shown in Fig. 2. The results do not show any significant difference between the two samples as the main peaks are still present in both samples.

[Fig.2]

2.1.3 Contact angle measurements

The interaction between the binder droplets and the powder was analysed using the contact angle measurement. The goniometer method is the most common, simple and practical method to measure the contact angle. The contact angles on the prepared surfaces were monitored using a FTA1000B goniometer instrument (First Ten Angstroms Inc., USA). For each sample, five different readings were recorded and the contact angle values were averages of the five measurements made on different points of the sample surface. Measurements were obtained on loose beds and on compacted beds (tablets). 50 g binary mixtures of teawaste and limestone with teawaste mass fractions of 0, 0.25, 0.5, 0.75 and 1.0 were obtained by mixing teawaste and limestone in the granulator for 5 minutes. For loose bed tests, small homogenous 0.5g samples were taken from the binary mix and particles were spread on to a glass plate to form a thin layer. The contact angle was then measured by

introducing the binder droplet (volume of ~15 µl). For the second set of measurements, samples of the 0.5g were collected from the binary powder mix and then compressed into tablets by applying a load of 8kN using a manual hydraulic press (Atlas 15T Manual Hydraulic Press, Specac Inc. USA). **Fig. 3** shows the particle distribution on the surfaces of the tablets with different compositions. It can be seen in these images that the number of teawaste particles on the surface increases as the mass teawaste mass fraction is increased as expected. The images also show that the teawaste particles are angular and fibre. Binder droplet was then introduced on the tablet surface to measure the contact angle. Typical images recorded during the measurements are shown in **Fig. 4**.

[Fig. 3]

[Fig. 4]

2.2 Production of the granules and drying

The granulation experiments were carried out in a small bench scale high shear granulator; Kenwood (KM070, Kenwood, UK). The granulator has a stainless steel mixing bowl with a total capacity of 6.7 L and is also equipped with two blade impeller which also undergoes “planetary mixing” motion around the mixer during granulation. The rotational speed of the impeller can be varied between 100 and 213 rpm.

A parameter λ is defined in the following equation (Eq. 1) was used to indicate the powder composition:

$$\lambda = \frac{m_{tea}}{m_{tot}} \quad (1)$$

where m_{tea} is the mass of tea and m_{tot} is the total mass of powder (limestone + teawaste), respectively.

1 This binary mix was pre-mixed for about half a minute at an impeller speed of 103 rpm.
2 At the end of the pre-mixing stage the granulator was stopped to allow addition of the
3 granulating fluid. After addition of the required amount binder the wet mass was mixed for
4 half a minute and the granulator was interrupted at the end of this period to allow removal of
5 caking material from the walls of the vessel. Granulation was then continued for a further 30
6 seconds to give total granulation time of a minute.

7 In preliminary studies experiments to compare the performance of the three different
8 powders; fresh tea, used tea and limestone were carried out. This involved granulating the
9 three different powders using same granulation and formulation conditions; the CMC binder
10 with a concentration of 5g/L was used. The same procedure described above was used.

11 Different masses of binder were added to the binary mixture to give different liquid to
12 solid ratio according to Table 1. Unless stated otherwise, the total batch size of was 50 g.

13 The factors that were investigated are liquid/solid ratio, powder composition and teawaste
14 type (particle size). The list of experiment carried out is shown in Table 3.

15 **[Table 3]**

16 After granulation, each batch of granules was transferred into flat aluminium trays with
17 dimensions 236 x 297 x 59 mm, ensuring that the granules were evenly spread on the tray
18 surface. The granule trays were then transferred into an oven (Binder FD249, Binder GmbH,
19 Germany) and dried for 12 hours pre-set at temperature of 60 °C. Subsequent to drying the
20 granules were allowed to cool to room temperature and then stored in sealed bags until
21 needed.

2.3 Product characterisation

2.3.1 Size Analysis

Retsch sieves (Retsch GmbH, Germany) were used for the size analysis and the aperture sizes of the sieves ranged from 350 to 4000 μm . The stack of sieves with the granules was placed on an orbital sample shaker, Stuart Orbital Shaker, supplied by Cole-Parmer UK. The speed of the shaker was set to 180 rpm and the sieving duration to 5 min.

The goal of the granulation was to make granules in the size range 2 to 4 mm which is the typical size range of commercial fertiliser granules. The percentage of granules in this size range was referred to as the product yield (η) is calculated by following equation;

$$\eta = \left(\frac{m_r}{m_B} \right) \times 100\% \quad (2)$$

where m_r is the mass of granules in required size range and m_B is the mass of total granules produced in a batch.

The mass mean granule size was determined from the sieve analysis data using the following equation;

$$\bar{d}_m = \frac{\sum_{i=1}^n m_i \bar{x}}{\sum_{i=1}^n m_i} \quad (3)$$

where m_i is mass of granules in the interval x_i to x_{i+1} with an arithmetic average size of $\bar{x}$.

2.3.2 Attrition Test

The granule attrition strength was determined using the method previously described in [4]. In this procedure a sample of the granules (5 grams) is subjected to attrition forces by shaking them mechanically on a sieve shaker and recording the mass loss as a function of

time. Granules in the size range 2 to 4 mm were used in this test. The attrition loss which is defined as the percentage mass of the granules due to attrition was calculated using;

$$A_r(t) = \frac{m(t)}{m_0} \times 100\% \quad (4)$$

where $m(t)$ is the mass of the granules retained on the sieve at the end of the test and m_0 is the initial mass of the sample.

The attrition resistance constant, κ , was determined by fitting the A_r versus time plots to equation;

$$A_r(t) = 100 \exp(-\frac{t}{\kappa}) \quad (5)$$

In Eq. (5), the attrition resistance coefficient, κ , can be interpreted as the time it takes to loss 63.3% by mass due to attrition. A higher attrition resistance coefficient indicates better resistance of the material to attrition. The difference in the resistance of the granules from the different batches to attrition is evaluated using this coefficient.

2.3.3 Granule Strength measurements

The strength of granules in the size range 1 to 2 mm was determined from compression of a bed of granules in a confined cylindrical die using a method previously described in [12, 21]. The beds of granules were compressed to a maximum compression force of 500 N using a compression test speed of 10 mm/min. The force-displacement data obtained during the compression of bed or granules were analysed using a method described previously [11, 12, 21-23] to obtain the single granule strength. Eq (6) was fitted to the plot of $\ln P$ versus natural strain to obtain the granule strength parameter.

$$\ln P = \ln\left(\frac{\tau}{\alpha}\right) + \alpha \varepsilon + \ln(1 - e^{-\alpha \varepsilon}) \quad (6)$$

In Eq (6) α is a pressure coefficient, τ the Adams parameter, P is the applied pressure and ε is the natural strain.

3. Results & discussion

3.1 Effect of powder composition on wettability

Contact angle measurements can be used as an indication of the degree of wetting between a liquid and solid surface; high values of contact angle ($>90^\circ$) indicate low wettability whilst low contact angles ($<90^\circ$) indicate high wettability [24]. Contact angle measurements of the CMC droplet with surfaces of different compositions are presented in Fig. 5. It is clear from these results that the contact angle increased as the composition of the teawaste in the binary mixture was increased. For measurements taken on a loose powder bed, the values of contact angle for pure samples of teawaste and limestone were 131.82° and 110.87° respectively; showing that limestone exhibit better wettability to the CMC droplet compared to teawaste. Binary mixtures of teawaste and limestone had intermediate values of contact angles. Contact angles measurements were also repeated on smoother surfaces (compacted powder bed, tablets) and similar trends were obtained i.e. increasing the composition. The contact angle of the CMC droplet was lower on the pure limestone tablet surface (83.35°) compared to the teawaste tablet surface (116.85°).

[Fig. 5]

Contact angles measurements on compacted surfaces were lower than those on loose powder beds in all cases. The difference in these measured values of contact angle from loose powder bed and compacted powder bed can be attributed to difference in the surface roughness. The compacted surface have smoother surface compared to the loose surface which is in agreement with earlier reports from literature [25].

Comparison of the surface roughness of compacted powder bed and loose powder bed was done by capturing the images of the surfaces and analysing the images with ImageJ software. The highest of the peaks in the images are proportional to the height of the surface asperities. The results presented in Fig. 6 show that the compacted surface has a relatively smoother surface compared to the loose powder bed.

[Fig 6]

3.2 Influence of powder type on size and granule size distribution

Preliminary granulation experiments of the three different powders using the same binder and granulation conditions showed that for the same amount of binder and similar granulation condition, the limestone powder was the easiest to granulate followed by fresh tea and then used tea. The results shown in Fig. 7 show that the mean size of the granules obtained increased in the order; $UT < FT < Limestone$. The means size of the granules also produces when limestone was the powder was twice that of fresh tea and thrice that of used tea. The observed trends are to be expected considering the difference in the particle sizes and pore sizes of the particles reported in Table 2. The pore volume of used teawaste is higher than that of limestone by several orders of magnitude. It would be logical to expect the pore volume of the used teawaste to be higher than that of fresh tea since washing of the teawaste is expected to open the pores.

[Fig. 7]

3.3 Effect of Liquid/solid Ratio

Liquid to solid ratio is one of the most important variables in granulation; hence several reports in literature have investigated the influence of this variable on the granulation process [12, 13, 26]. In this work it is expressed as ratio of mass of binder to mass of powder being

granulated. For the same powder mass the higher the liquid to solid ratio the higher the amount of binder added. The results presented in this section were obtained for tests in which powder was a mixture of limestone and fresh tea, (w/w) ratio of the teawaste to limestone was kept constant at 0.75. The role of binder in granulation is to form bridges or bond between the powder primary particles. Greater availability of binder should promote granule growth due to increased probability of bond formation. Typical cumulative size distribution plots of batches of granules formed using different liquid to solid ratios is shown in Fig. 8(a).

[Fig. 8]

Increasing the liquid to solid ratio results in the cumulative size distribution curve shifting to the right (see Fig. 8 (a)). Fig. 8(b) shows the plot of granule mass mean size as a function of binder concentration. It is interesting to note that the presence of tea in the powder formulation (75%) alters the amount of binder required for successful granulation. Higher than usual liquid to solid ratios were used to ensure significant change in the size distribution of the particles. Increasing the liquid to solid ratio for 0.95 to 1.15 resulted in an increase in granule mean size from about 2.5 to about 3.35mm.

The effect of amount of the binder used during granulation on the product yield is shown in Fig. 9. Whereas, increasing the amount of binder causes a monotonic increase in the average size of the batch, slightly different trend was observed in terms of product yield. Increasing the liquid to solid ratio from 0.95 to 1.0 causes an increase in the product yield though a further increase beyond this value caused a reduction in the product yield. This can be explained by rapid increase in the overgrowth of the granules which result in formation of coarse granules i.e. granules with size greater than product. A similar observation had been made in our previous work [4].

[Fig. 9]

Attrition is a size reduction mechanism whereby a granule loses mass by loss of particles at the surface of the particles due to friction when the granules rub against each other or other surfaces. The attrition resistance coefficient gives an indication of the how strong are the granules can resist attrition. The results presented in Fig. 9 show the effect of the binder concentration on the attrition strength of the granules. For this formulation increasing the liquid to solid ratio from 0.95 to 1.05 does not significantly change the attrition resistance of the granules. However a further increase of the liquid to solid ratio to 1.1 and above results in huge increase in the attrition resistance of the granules.

A higher attrition coefficient indicates the granules have strong resistance to attrition as it would take a longer time to reduce loss particles from the peripherals of the granules due attrition. When fresh tea (FT) is used in the formulation at a mass fraction of 0.75, increasing in the liquid to solid ratio results in increase in the attrition resistance. This is in agreement with earlier results reported in literature [4, 27, 28].

3.4 Effect of teawaste to limestone ratio

A series of granulation experiments were carried out using different powder of different compositions of teawaste and limestone powder. The amount of binder required to achieve successful granulation increased with increasing content of teawaste. As expected the mean granule size increased with increasing binder concentration. It is interesting to note in Fig. 10(a) the shift to the right of the linear plots as the tea composition is increased. The shift of the curves to the right as the teawaste mass fraction is increase can be explained by more binder requirement of formulation with more teawaste. Increasing the teawaste mass fraction increases the mean particle size of the powder. The specific surface area of the teawaste is higher than that of limestone powder. Also the specific pore volume of the former is higher than that of the later (see Table 2). The higher specific pore volume of the teawaste may be associated with the high binder requirements of the powder; the binder that is added during

granulation first fills the pore structure in the powder. Once the pores have been filled or are saturated additional binder becomes available at the surface of the teawaste particles. It is the binder that is available at the surface of the particle that contributed to agglomeration process. It can be postulated that presence of large specific pore volume reduces the amount of binder available for agglomeration.

Increasing the mass fraction of the teawaste in the formulation is expected to result in an increase both the specific surface area of the binary mixture. This explained the increase in the binder requirement as the mass fraction of teawaste is increased. Therefore, the shift of the plots to the right is consistent with literature as more binder is required for granulation of larger primary particles [29-31].

It has also been reported in literature [30] that an increase in particle size should be accompanied by an increase in the binder viscosity to ensure granule growth, however, in this work the viscosity of the binder was not changed as the composition of the powder was changed.

[Fig. 10]

The amount of binder used in the granulation was varied to determine the optimum liquid to solid ratio for the different formulations; this is the liquid to solid ratio at which maximum product yield is achieved. The plots of yield versus liquid to solid ratio, for granulation of different mass fractions of FT and limestone are presented in Fig. 10(b). It can be noticed from this plot that the three different formulations peak at different values of liquid to solid ratios. The optimum liquid to solid ratio for $\lambda = 0.25, 0.5$ and 0.75 are $0.5, 0.9$ and 1.45 , respectively. For the same granulation conditions, to maintain the same level of product yield one has to increase the amount of binder used. Increasing the tea mass fraction increased the

proportion of large particles in the mixture. The larger primary particles grow mainly by layering mechanism, where they capture fine particles, but for this to happen the particles have to be covered by a layer of binder and more binder is required to achieve this [32, 33]. Another possible explanation could be the difference in the porosities of the two powders.

The attrition resistance coefficients of the granules with different proportions of teawaste (FT) are shown in Fig. 11. At teawaste mass fractions of 0.25 and 0.75, the attrition resistance coefficient increases monotonically with binder content whereas at mass fraction of the 0.5, it increases and then levels off. The results show that as the mass fraction of teawaste in the formulation is increased, more binder will be required to obtain granules with the same attrition resistance.

[Fig. 11]

The results shown presented earlier in Fig. 5 show that the wettability of the binary mixture decreased as the teawaste mass fraction increased. It is probable that changes in the granulation mechanisms occur when the composition of the binary mixture changes which can lead to differences in granule sizes and size distributions.

3.5 Effect of tea type

The influence of washing the tea before granulation was investigated. The results show that the granule size distributions and the mechanical properties of the granules are indeed affected with pre-treatment of the tea. Washing the tea affects the amount of binder required during granulation. Used tea requires more binder to achieve the same level of granulation as the fresh tea. When two formulations having different teawaste to limestone ratios are granulated for the same duration, at the same impeller speed using the same amount of binder, batches with different size distributions were obtained. Fig. 12 shows the difference between the cumulative size distribution of the UT and FT batches for $\lambda = 0.75$ and liquid to

solid ratio of 1.15. Results from FTIR analysis shown in Fig. 2 show that the functional groups of the tea are not changed by washing the tea since the dominant peaks for the two samples are similar. The difference in the granule size distributions can therefore not be explained by different chemical interactions. One possible hypothesis to explain the results is that washing the teawaste to produce used-tea altered the particle size distribution of tea, which resulted in different granulation mechanism. Washing the tea might have removed the finer particles from the sample, leaving behind larger particle. The larger particles that are left behind require more binder to bind them together. This is further confirmed by the shift to the right by the results presented in Fig. 12(a).

[Fig. 12]

Fig. 12(b) shows the FT is more sensitive to change in liquid to solid ratio; very small changes in the liquid to solid ratio results in significant changes in the granule mean sizes. The other type of teawaste, UT, is less sensitive to changes in the liquid to solid ratio. The differences in the granulation behaviour could be due to difference in the initial particles size distributions of the two types of powder. For the same liquid to solid ratio and other constant variables, FT granules would have a larger granule mean size.

The effect of tea type on the product yield is shown in Fig. 13. Fig. 13 reiterates the point shown in earlier results; more binder will be required to granulate UT compared to FT. For instance, to get a product yield of 78% one would need to use a liquid to solid ratio of about 1.5 when granulating a mixture of used tea and limestone compared to about 1 if fresh tea is used. It can also be noted that the optimum liquid to solid ratio for UT is about 1.5 compared to around 1 for the other type of teawaste.

[Fig. 13]

The attrition test results for granules from the two different types of tea are presented in Fig. 14(a) and (b). Fig. 14(a) shows variation of attrition ratio as a function of time. The attrition ratio falls at a slower rate of the FT granules compared to the UT granules. At the end of testing period about 99.7% of FT granules survive attrition compared to 99.2% for the UT granules.

[Fig. 14]

The attrition resistance coefficients of the two types of granules are compared in Fig. 14(b); the FT granules have stronger resistance to attrition compared to UT granules. This could be due to differences in the structure of the granules caused by differences in the particle size distributions in each of the individual granules. It must also be noted that different amounts of binder were used in producing the granules.

For a given set of operating conditions the rate of consolidation is dependent on the amount of binder [10, 34]. In the case of high viscosity binder, the rate of consolidation decreases with increasing binder content. In the current work, a high viscosity binder was used, therefore, it is then expected that the rate of consolidation of the granules was lower for the cases where high level of binder were used i.e. granulation used tea and formulation with higher portions of teawaste.

3.6 Effect of formulation variables on granule tensile strength

The strength of granules produced under different formulation conditions are summarized in Fig. 15. The responses of granule strength to changes in the liquid to solid ratio seem to be influenced by the amount mass ratio of teawaste in the formulation. It can be seen in Fig. 15 (a) that when fresh teawaste is used at lower ratios of teawaste in increasing the liquid to solid ratio results in an initial increase in the granules strength. At higher binder concentrations the UT granules have higher strength compared to the FT granules. The

1 difference between the strength of the FT granules and UT granules widens as the amount of
2 the binder is increased. When mass fraction of the teawaste is increased to 0.5 different trends
3 are observed; increasing the teawaste composition results in a reduction in the granules
4 strength for both UT and FT granules (see Fig. 15 (b)). One would expect the UT granules to
5 have exhibit higher strength compared to FT granules since higher liquid to solid ratio was
6 used in their production, but the converse was observed. On increasing the mass teawaste
7 mass fraction further to 0.75 (see Fig. 15(c)) a different trends are observed for UT and FT;
8 for FT increasing the liquid to solid ratios results in an increase in the granule strength; the
9 opposite is observed for the later. Despite the higher levels of liquid to solid ratios used when
10 the teawaste mass fraction is increased in the formulation, there is no noticeable increase in
11 the strength of the granules. The granule strength decreases with increasing teawaste mass
12 fraction (see Fig. 15 (d)), this is in agreement with results from our previous work [35].

13 **[Fig. 15]**

14 **4. Conclusions**

15 The granule size distributions, granules strength, product yield are all affected by the relative
16 composition of teawaste; type of teawaste used and amount of the binder added during
17 granulation. Changing teawaste mass fraction changes the wettability of the binary mixture.
18 The amount of teawaste added to the formulation affects the amount of binder required for
19 effective granulation which in turn affects the final properties of the granules produced.
20 Washing the teawaste and drying the tea before granulation also have an influence of the
21 amount of binder required for granulation. Used tea requires more binder for effective
22 granulation compared to fresh tea. The strength of granules with high portion of teawaste
23 (whether used or fresh) was shown to be lower than that of formulations with lower portion
24 of teawaste.

1 **ACKNOWLEDGEMENTS**

- 2 The authors would like to express their gratitude to Kilwaughter Chemical Company for
- 3 providing the limestone.

REFERENCES

1. Chateau, M.E., et al., *Processing a detergent powder formulation: Direct compression, and high shear wet granulation followed by compression*. Powder Technology, 2005. **157**(1-3): p. 191-198.
2. Landillon, V., et al., *Flowability, cohesive, and granulation properties of wheat powders*. Journal of Food Engineering, 2008. **86**(2): p. 178-193.
3. Germana, S., S.J.R. Simons, and J. Bonsall, *Reactive binders in detergent granulation: Understanding the relationship between binder phase changes and granule growth under different conditions of relative humidity?* Industrial and Engineering Chemistry Research, 2008. **47**(17): p. 6450-6458.
4. Mangwandi, C., et al., *Alternative method for producing organic fertiliser from anaerobic digestion liquor and limestone powder: High Shear wet granulation*. Powder Technology, 2013. **233**(0): p. 245-254.
5. Di Martino, P., et al., *Physico-chemical and technological properties of sodium naproxen granules prepared in a high-shear mixer-granulator*. Journal of Pharmaceutical Sciences, 2008. **97**(12): p. 5263-5273.
6. Campisi, B., et al., *Melt granulation in a high shear mixer: optimization of mixture and process variables using a combined experimental design*. Chemometrics and Intelligent Laboratory Systems, 1999. **48**(1): p. 59-70.
7. Cavinato, M., et al., *The development of a novel formulation map for the optimization of high shear wet granulation*. Chemical Engineering Journal, 2010. **164**(2-3): p. 350-358.
8. Chitu, T.M., D. Oulahna, and M. Hemati, *Rheology, granule growth and granule strength: Application to the wet granulation of lactose-MCC mixtures*. Powder Technology, 2011. **208**(2): p. 441-453.
9. Schaefer, T., *Melt pelletization in a high shear mixer. X. Agglomeration of binary mixtures*. International Journal of Pharmaceutics, 1996. **139**(1-2): p. 149-159.
10. Le, P.K., et al., *A microscopic study of granulation mechanisms and their effect on granule properties*. Powder Technology, 2011. **206**(1-2): p. 18-24.
11. Mangwandi, C., et al., *Effect of impeller speed on mechanical and dissolution properties of high-shear granules*. Chemical Engineering Journal, 2010. **164**(2-3): p. 305-315.
12. Mangwandi, C., et al., *Effect of batch size on mechanical properties of granules in high shear granulation*. Powder Technology, 2011. **206**(1-2): p. 44-52.
13. Mangwandi, C., et al., *An investigation of the influence of process and formulation variables on mechanical properties of high shear granules using design of experiment*. International Journal of Pharmaceutics, 2012. **427**(2): p. 328-336.
14. Podczek, F. and M. Sharma, *The influence of particle size and shape of components of binary powder mixtures on the maximum volume reduction due to packing*. International Journal of Pharmaceutics, 1996. **137**(1): p. 41-47.
15. Charles-Williams, H., et al., *Granulation behaviour of increasingly hydrophobic mixtures*. Powder Technology, 2013. **238**(0): p. 64-76.
16. Nguyen, T.H., W. Shen, and K. Hapgood, *Effect of formulation hydrophobicity on drug distribution in wet granulation*. Chemical Engineering Journal, 2010. **164**(2-3): p. 330-339.
17. Usteri, M. and H. Leuenberger, *Agglomeration of binary mixtures in a high-speed mixer*. International Journal of Pharmaceutics, 1989. **55**(2-3): p. 135-141.

18. Albadarin, A.B., et al., *Influence of solution chemistry on Cr(VI) reduction and complexation onto date-pits/tea-waste biomaterials*. Journal of Environmental Management, 2013. **114**(0): p. 190-201.
19. Kuo, H.-P., et al., *A study of the ash production behavior of spent limestone powders in CFBC*. Advanced Powder Technology, 2014. **25**(1): p. 472-475.
20. Wang, W. and I. Bjerle, *Modeling of high-temperature desulfurization by Ca-based sorbents*. Chemical Engineering Science, 1998. **53**(11): p. 1973-1989.
21. Mangwandi, C., et al., *Influence of fill factor variation in high shear granulation on the post granulation processes: Compression and tablet properties*. Powder Technology, 2014. **263**(0): p. 135-141.
22. Adams, M.J., M.A. Mullier, and J.P.K. Seville, *Agglomerate strength measurement using a uniaxial confined compression test*. Powder Technology, 1994. **78**(1): p. 5.
23. Mangwandi, C., et al., *Optimisation of high shear granulation of multicomponent fertiliser using response surface methodology*. Powder Technology, 2013. **238**(0): p. 142-150.
24. Hapgood, K.P. and B. Khanmohammadi, *Granulation of hydrophobic powders*. Powder Technology, 2009. **189**(2): p. 253-262.
25. Yuan, T. and T.R. Lee, eds. *Contact Angle and Wetting Properties*. Surfaces Science Techniques, ed. G. Bracco and B. Holst. Vol. 51. 2013, Springer: Berlin.
26. Ma, H., et al., *Low shear granulation of pharmaceutical powders: Effect of formulation on granulation and tablet properties*. Chemical Engineering Journal, 2010. **164**(2-3): p. 442-448.
27. Verkoeijen, D., et al., *Determining granule strength as a function of moisture content*. Powder Technology, 2002. **124**(3): p. 195-200.
28. Watano, S. and K. Miyanami, *Image processing for on-line monitoring of granule size distribution and shape in fluidized bed granulation*. Powder Technology, 1995. **83**(1): p. 55-60.
29. Mackaplow, M.B., L.A. Rosen, and J.N. Michaels, *Effect of primary particle size on granule growth and endpoint determination in high-shear wet granulation*. Powder Technology, 2000. **108**(1): p. 32-45.
30. Schaefer, T., D. Johnsen, and A. Johansen, *Effects of powder particle size and binder viscosity on intergranular and intragranular particle size heterogeneity during high shear granulation*. European Journal of Pharmaceutical Sciences, 2004. **21**(4): p. 525-531.
31. Tu, W.-D., et al., *The effect of powder size on induction behaviour and binder distribution during high shear melt agglomeration of calcium carbonate*. Powder Technology, 2008. **184**(3): p. 298-312.
32. Johansen, A. and T. Schaefer, *Effects of interactions between powder particle size and binder viscosity on agglomerate growth mechanisms in a high shear mixer*. European Journal of Pharmaceutical Sciences, 2001. **12**(3): p. 297-309.
33. Realpe, A. and C. Velazquez, *Growth kinetics and mechanism of wet granulation in a laboratory-scale high shear mixer: Effect of initial polydispersity of particle size*. Chemical Engineering Science, 2008. **63**(6): p. 1602-1611.
34. Iveson, S.M., J.D. Litster, and B.J. Ennis, *Fundamental studies of granule consolidation part 1: Effects of binder content and binder viscosity*. Powder Technology, 1996. **88**(1): p. 15-20.
35. Mangwandi, C., et al., *Development of a value-added soil conditioner from high shear co-granulation of organic waste and limestone powder*. Powder Technology, 2014. **252**(0): p. 33-41.

List of Tables

Table 1: comparison of particle size distribution parameters of UT, FT and limestone powders.

Table 2: Comparison of BET surface area and specific pore volume of Teawaste (UT) and limestone.

Table 3: Summary of experimental variables used in the different granulation experiments

List of Figures

Fig. 1: Particle Size distributions of the different powders used in the granulation experiments.

Fig. 2: comparison of FTIR spectrum of UF and FT. The characteristic peaks; 1- 3400 cm^{-1} ; 2 - 2928 cm^{-1} ; 3 - 2854 cm^{-1} ; 4- 1737 cm^{-1} ; 5- 1640 cm^{-1} ; 6 - 1297 cm^{-1} ; 7 - 1060 cm^{-1}

Fig. 3: Comparison of the surfaces of tablets produced from powders with different compositions.

Fig. 4: Typical images showing contact angle measurements on surfaces with the different powder compositions (a) to (c) loose powder bed (d) to (f) measurements on tablet surfaces.

Fig. 5: Effect of powder composition on contact angle.

Fig. 6: comparison of roughness of surfaces on which contact angles were measured (a) tablet surfaces (a) layer of particles (un-compacted surface).

Fig. 7: Effect of the powder type on the granule mean size and granule size distribution (a) Mean granule sizes (b) granule size distribution. Experimental conditions were as follows; Liquid to solid ratio 0.4; binder type - CMC, granulation time - 4 minutes and impeller speed - 203 rpm.

Fig. 8 Typical cumulative size distribution curves for batches of granules composed of teawaste (fresh tea) and limestone (0.75 % TW (w/w), (b) Plot of mass mean granules size as a function of liquid to solid ratio.

Fig. 9: Effect of liquid / solid ratio on product yield and resistance to attrition. Type tea: Fresh Tea; tea mass fraction 0.75

Fig. 10: Effect of teawaste to limestone ratio on (a) Granule mean size (b) Product yield.

Fig. 11: Effect of teawaste mass fraction on the attrition strength of the granules.

Fig. 12: (a) Effect of tea type on the granule size distribution. (b) Effect of tea type on granule mass size.

Fig. 13: Effect of tea type on product yield for teawaste mass fraction of 0.75.

Fig. 14: Effect of tea type on the attrition strength of the granules. Teawaste mass fraction of 0.5.

Fig. 15: Variation of granules strength with liquid to solid ratio for formulations of different teawaste ratios (a) $\lambda = 0.25$ (b) $\lambda = 0.5$ and (c) $\lambda = 0.75$. (d) Effect of teawaste fraction on granule strength. Open symbols - Used Tea (UT) and closed symbols- Fresh Tea (FT).

1

2

Table 1: comparison of particle size distribution parameters of UT, FT and limestone powders.

<i>Powder Type</i>	<i>Parameter</i>			
	d_{10} [μm]	d_{50} [μm]	d_{90} [μm]	<i>Span</i>
Limestone	4.7 ± 0.1	32 ± 5	114 ± 5	3.49 ± 0.13
UT	197 ± 4	413 ± 31	1065 ± 22	2.00 ± 0.36
FT	143 ± 3	311 ± 10	681 ± 31	1.73 ± 0.03

3

4

1

Table 2: Comparison of BET surface area and specific pore volume of Teawaste (UT) and limestone.

Material	Specific Pore Volume	BET Surface Area	Reference (s)
	$\times 10^{-4} \text{ [cm}^3\text{/g]}$	$\text{[m}^2\text{/g]}$	
Teawaste (UT)	45.1	30.04	[18]
Limestone	3.33 – 3.76	0.35 – 1.04	[19-20]

2

Table 3: Summary of experimental variables used in the different granulation experiments

Tea Type	Ranges of Values of liquid/ solid ratios		
	$\lambda = 0.25$	$\lambda = 0.50$	$\lambda = 0.75$
Fresh Tea (FT)	0.3 - 0.5	0.7 - 0.85	0.95 - 1.15
Use Tea (UT)	0.35 - 0.55	0.8 - 1.0	1.10 - 1.5

Fig. 1: Particle Size distributions of the different powders used in the granulation experiments.

Fig. 2: comparison of FTIR spectrum of UF and FT. The characteristic peaks; 1- 3400 cm^{-1} ; 2 – 2928 cm^{-1} ; 3 – 2854 cm^{-1} ; 4- 1737 cm^{-1} ; 5-1640 cm^{-1} ; 6 - 1297 cm^{-1} ; 7 - 1060 cm^{-1}

(a) $\lambda = 0.25$

(b) $\lambda = 0.50$

(c) $\lambda = 0.75$

Fig. 3: Comparison of the surfaces of tablets produced from powders with different compositions.

(a) $\lambda = 0.25$

(b) $\lambda = 0.50$

(c) $\lambda = 0.75$

(d) $\lambda = 0.25$, tablet

(e) $\lambda = 0.50$, tablet

(f) $\lambda = 0.75$, tablet

1

2

Fig. 4: Typical images showing contact angle measurements on surfaces with the different powder compositions (a) to

3

(c) loose powder bed (d) to (f) measurements on tablet surfaces.

Fig. 5: Effect of powder composition on contact angle.

(a)

(b)

Fig. 6: comparison of roughness of surfaces on which contact angles were measured (a) tablet surfaces (a) layer of particles (un-compacted surface).

(a)

(b)

Fig. 7: Effect of the powder type on the granule mean size and granule size distribution (a) Mean granule sizes (b) granule size distribution. Experimental conditions were as follows; Liquid to solid ratio 0.4; binder type - CMC, granulation time - 4 minutes and impeller speed – 203 rpm.

(a)

(b)

Fig. 8 Typical cumulative size distribution curves for batches of granules composed of teawaste (fresh tea) and limestone (0.75 % TW (w/w)), (b) Plot of mass mean granules size as a function of liquid to solid ratio.

Fig. 9: Effect of liquid / solid ratio on product yield and resistance to attrition. Type tea: Fresh Tea; tea mass fraction 0.75

(a)

(b)

Fig. 10: Effect of teawaste to limestone ratio on (a) Granule mean size (b) Product yield.

1

2

3

Fig. 11: Effect of teawaste mass fraction on the attrition strength of the granules.

4

5

(a)

(b)

Fig. 12: (a) Effect of tea type on the granule size distribution. (b) Effect of tea type on granule mass size.

Fig. 13: Effect of tea type on product yield for teawaste mass fraction of 0.75.

(a)

(b)

Fig. 14: Effect of tea type on the attrition strength of the granules. Teawaste mass fraction of 0.5.

1

2

(a)

(b)

(c)

(d)

3

4

5

6

Fig. 15: Variation of granules strength with liquid to solid ratio for formulations of different teawaste ratios (a) $\lambda = 0.25$ (b) $\lambda = 0.5$ and (c) $\lambda = 0.75$. (d) Effect of teawaste fraction on granule strength. Open symbols - Used Tea (UT) and closed symbols- Fresh Tea (FT).