

Effect of Impeller Design on Homogeneity, Size and Strength of Pharmaceutical Granules produced by High Shear Wet Granulation

Mirza, Z., Liu, J., Glocheux, Y., Albadarin, A. B., Walker, G. M., & Mangwandi, C. (2015). Effect of Impeller Design on Homogeneity, Size and Strength of Pharmaceutical Granules produced by High Shear Wet Granulation. *Particuology*, *23*, 31-39. https://doi.org/10.1016/j.partic.2014.12.009

Published in: Particuology

Document Version: Peer reviewed version

Queen's University Belfast - Research Portal: Link to publication record in Queen's University Belfast Research Portal

Publisher rights

© 2015 Elsevier Ltd. This manuscript version is made available under the CC-BY-NC-ND 4.0 license http://creativecommons.org/licenses/bync-nd/4.0/ which permits distribution and reproduction for non-commercial purposes, provided the author and source are cited.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

Open Access

This research has been made openly available by Queen's academics and its Open Research team. We would love to hear how access to this research benefits you. – Share your feedback with us: http://go.qub.ac.uk/oa-feedback

1	EFFECT OF IMPELLER DESIGN ON HOMOGENEITY, SIZE AND STRENGTH OF
2	PHARMACEUTICAL GRANULES PRODUCED BY HIGH SHEAR WET GRANULATION
3	Chirangano Mangwandi ^{1*} , Zakaria Mirza ¹ , Liu JiangTao ¹ , Yoann Glocheux ¹ ,
4	Ahmad B. Albadarin ^{1,2}
5	¹ Sch. of Chemistry and Chemical Engineering, Queen's University Belfast, Belfast BT9 5AG,
6	Northern Ireland UK
7	² Synthesis & Solid State Pharmaceuticals Center (SSPC),
8	Department of Chemical and Environmental Science,
9	University of Limerick, Ireland.
10	
11	
12	Corresponding author
13	E-mail: <u>c.mangwandi@qub.ac.uk</u> (C. Mangwandi),
14	Tel. +44(0)289 097 4378
15	Fax. +44 (0) 289 097 6524
16	

17 ABSTRACT

18 Design of small mixer impellers is not tailored for granulation as they are intended for a 19 wide range of processes. The Kenwood KM070 was employed as a standard apparatus to 20 undertake this investigation. Five different impeller designs with different shapes and surface 21 areas were used. The aim of this research was to evaluate the performances of these impellers to provide guidance on the selection and design for the purposes of granulation. Lactose 22 23 granules were produced using wet granulation with water as the binder. The efficacy of 24 respective granulates was measured by adding an optically sensitive tracer. This was used to 25 determine variation of active ingredient across random samples of granules from the same size 26 classes. It was found that impeller design influenced the homogeneity of the granules and 27 therefore can affect final product performance. The variation of active ingredient across 28 granule of different sizes was also investigate. The study shows that small granules were more 29 potent when compared to the larger granules.

30 KEYWORDS

Granules strength; impeller design; homogeneity; high shear granulation; lactosemonohydrate

34 **1. INTRODUCTION**

35 Granulation is a size enlargement unit operation in which granular products are produced by 36 sticking together powdery particles with a binder. It has wide applications in several industries 37 for instance pharmaceuticals, detergent industries, fine chemicals and fertiliser industries. 38 Particle agglomeration in wet granulation improves the bulk properties of the formulation by 39 enhancing the flow properties, reducing the dustiness and also the improving the compression 40 properties. Several studies investigated the effect of granulation parameters in the high shear 41 mixer on product attributes and demonstrated that control of process parameters is necessary to 42 obtain product with the desired attributes (Campbell et al., 2011; Johansson and Alderborn, 43 2001; Mangwandi et al., 2010; Mangwandi et al., 2012; Mangwandi et al., 2013a; Niklasson et 44 al., 2005; Shiraishi et al., 1994). The final product properties are influenced by the process 45 parameters and formulation attributes. In addition to formulation and process variables there 46 are equipment variables which can influence the properties of the granule. Examples of these 47 variables are the type and shape of the vessel, the presence of a chopper (Chitu et al., 2011) and 48 nozzle.

The main source of energy in high shear granulation is power dissipation by impeller rotation. The main task of the impeller is to agitate the powder particles and ensure that they are always in continuous motion and to ensure collision between binder particle and powder particles. The other purpose of the impeller is to ensure proper mixing of the materials being granulated. Previous work done in mixing of fluid systems has shown that the design of the impeller has a significant effect on the flow of the fluid (Jirout and Rieger, 2011; Kacunic et al., 2012; Khare and Niranjan, 2002; Kumaresan and Joshi, 2006).

56 There are scant papers in literature discussing the effect of impeller design on the 57 granulation process (Campbell et al., 2011; Knight et al., 2001; Niklasson et al., 2005; Schaefer

et al., 1993; Smith et al., 2010; Voinovich et al., 1999). Work done by Schaefer et al. 1993 on the effect of equipment variables on granulation revealed that the impeller blade design affects the shape of the granules formed (Schaefer et al., 1993). Granules that are more spherical were obtained if an impeller with a curved blade was used whilst granulating using a flat blade impeller resulted in formation of irregular shaped granules.

63 The Kenwood food processer (Kenwood, KM070) which has been used as a lab scale high 64 shear mixture in previous studies (Mangwandi et al., 2013a; Mangwandi et al., 2013b, c) 65 comes with different impellers since it is designed for mixing a range of different materials. 66 Images of the different impeller design are shown in Fig. 1. In the previous studies (Mangwandi et al., 2013a; Mangwandi et al., 2013b, c) only one type of impeller was used, the High 67 68 Temperature Flexible Beater (HTFB - 14). The aim of this paper is to evaluate the 69 performance of the other impellers in high shear wet granulation in terms of extent of mixing, 70 strength of the granules formed and the size distributions. The extent of mixing will be 71 evaluated using the method used in previous work (Mangwandi et al., 2011; Mangwandi et al., 72 2014; Mangwandi et al., 2013c).

73 2. MATERIALS & METHOD

74 2.1 Materials

Lactose monohydrate powder, supplied by Sigma Aldrich GmbH, was used as the main
excipient. Methylene Blue (MB) - high purity biological strain, produced and supplied by
Sigma Aldrich, was used as a model active ingredient.

78

79 **2.2 Binder Preparation and Granulation**

80 All granulation experiments were performed in a Kenwood processor (KM 70). Six 81 granulation experiments were done in triplicates. The granulation conditions used in all the 82 experiments are summarised in Table 1. The purpose of experiments 1 and 2 was to check 83 whether addition of methylene blue (MB) to the granulation liquid had any effect on the 84 granulation properties. The same type of impeller was used in these experiments. Experiments 85 2 to 6 were used to investigate the effect of impeller type on the batch homogeneity, granule 86 mechanical strength and shape. Methylene blue was added to deionised water to produce a MB 87 solution, with a concentration of 20 ppm.

88 2.3 Material Characterisation

By Data were collected on the powdered samples using a Philips Xpert Pro-Pan-Analytical diffractometer. The instrument used a monochromated Cu Ka lamp radiating at lambda value of 1.5406 Armstrong. The samples were housed in a flat plate sample holder and analysed through a 2θ range of $5 - 40^{\circ}$, using 0.16713° steps over a period of 12 minutes. XRD patterns for alpha lactose powder, granulated lactose with water and granulated lactose with watermethylene blue are shown in Fig. 2. No structural change is noticed in lactose; therefore methylene blue can be used as an inert tracer to monitor lactose granulation in water.

96 2.4 Granule Drying and Size Analysis

After granulation each batch of granules was transferred to flat aluminium trays with dimensions 236 mm X 297 mm X 59 mm, ensuring that the granules were evenly spread on the tray surface. The granule trays were then transferred to an oven (Binder FD249, Binder GmbH, Germany) pre-set to a temperature of 60 °C and dried for 12 hours. After drying the granules were allowed to cool to room temperature and then stored in sealed bags until further needed.

102 Retsch sieves (Retsch GmbH, Germany) were used in the size analysis and the aperture 103 sizes used were as follows; 350, 500, 600, 710, 1000, 1180, 1400, 1700, 2000, 2360, 3350, and 4000 μm. The stack of sieves with the granules was placed on an orbital sample shaker, Stuart
Orbital Shaker, supplied by Cole-Parmer UK. The speed of the shaker was set to 180 rpm and
the sieving duration to 5 min.

107 The targeted range of granule size in the experiments undertaken was 0.2 to 4 mm which is 108 the typical size range of pharmaceutical granules (Summers and Aulton, 1988). The percentage 109 of granules in this size range was referred to as the product yield (Ψ) and is calculated by the 110 following equation;

111
$$\Psi = \left(\frac{m_{pro}}{m_{Bat}}\right) \times 100\%$$
 Eq. 1

where m_{pro} is the mass of granules in the required size range and m_{Bat} is the mass of total granules produced in a batch. Granules in the size range 0.5 to 4 mm were considered to be the product, whilst those below and above this range were considered to be fines and oversize granules respectively.

116 **2.5 Determination of Homogeneity across granules of same size**

Ten random samples of approximately 1 g of granules in the required size range were withdrawn from each batch. Colloids were prepared from each of the samples by adding the granules to 50 ml of de-ionised water. The concentration of the methylene blue solution was obtained by measuring the absorbance of the solution at a single wavelength of 664 nm and calculating the concentration from the previously determined calibration equation. The uniformity coefficient was calculated using the following equation (Mangwandi et al., 2011; Mangwandi et al., 2013c; Mangwandi et al., 2015);

124
$$\kappa = \frac{S}{\hat{c}}$$
 Eq. 2

125 where \hat{c} is the mean of the samples and *S* is the standard deviation of methylene blue 126 concentration in the samples;

127
$$S = \sqrt{\frac{\sum_{i} (c_i - \hat{c})^2}{n - 1}}$$
 Eq. 3

In Eq. (3) above, n, is the total number of samples analysed and c_i is the MB concentration in the i^{th} sample.

MB concentration in granules for each particle size of granules was analysed in the sameway and the concentration distribution in function of the particles sizes were plotted.

132 The homogeneity coefficient can then be defined as;

133
$$\eta = 1 - \kappa$$
 Eq. 4

where κ is as define in *Eq. 2* and $0 \le \eta \le 1$. A value of homogeneity coefficient of 1 is assigned to a completely homogeneous distribution of the pseudo active ingredient while a low value of η indicates poor distribution.

137 **2.6 Methylene Blue distribution across different size classes**

The distribution of the MB across different size of the granules was measured by dissolving a known mass of granules in a known volume of distilled water and measuring the absorbance of the colloid at a wavelength of 664 nm using a spectrophotometer. The concentration (in ppm) of the colloid was calculated using Eq. 5. The concentration of the MB in dry sample (mg/g) was then determined from;

143
$$C_{_{MB,exp}}(x_i) = c_{_{MB}} \times \left(\frac{m_{_{MB}}}{m_p}\right) \times \left(\frac{m_{_s(x_i)}}{V}\right)$$
 Eq. 5

144 where m_{MB} is the mass of MB added to the batch; m_p is total mass of powder (mass of 145 lactose and MB added; $m_s(x_i)$ mass of sample granules from size class x_i used in 146 measurement; V (in litres) is the volume of dissolution medium.

147 2.7 Granules Strength Analysis

The strength of granules in the size range 2000 to 2360 μ m was determined from diametric compression of the single granules using the method described previously (Mangwandi et al., 2010; Mangwandi et al., 2007). Eq. 6 was used to determine the granule strength from the failure load, F_f , and the granule diameter, D, which is measured as the distance between the fixed platen and the movable platen, when first contact is made between the granule (Hiramatsu and Oka, 1966);

154
$$\sigma = 2.8 \times \left(\frac{F_f}{\pi D^2}\right)$$
 Eq. 6

155 **2.8 Shape Analysis**

156 The shape of the granules from different batches was analysed using an Eyecon 3D particle 157 imager (Innopharmalabs, Ireland). The Eyecon device is able to measure particles size from 50-158 3000 µm. The device applies blue, green, and red light to the analysed objects and several 159 images are generated. Irregular particle shapes are mapped by the software and several 160 measurements are logged. The characteristics of the granule size distribution; d₁₀, d₅₀, d₉₀, d_{max} 161 , d_{min} and, aspect ratio are presented in report form at the end of the measurement. The particle 162 size measurements are taken directly from the image analysis and there is no model applied to 163 the data.

164 **3. RESULTS & DISCUSSION**

165 **3.1 Effect of addition of MB**

Preliminary results show that addition of MB to the formulation did not significantly affect the granulation process. The granule size distribution and the strength of formulation with and without MB are shown in Fig. 3 and Table 1 respectively. The results are to be expected considering the low level of concentration of the MB used.

170 **3.2 Effect of Impeller Design on Granule size distribution**

The impeller design has an impact on the average granule size and the granule size distributions of the batches. The results are presented in Fig. 4 (a). It is noticeable from this Fig. that for all the batches there was a large percentage of granules bigger than 4000 μ m. The presence of these large granules could be attributed to the higher liquid to solid ratio used in the experiments. The mass mean diameter of the granules was calculated according to:

176
$$\overline{d} = \frac{\sum_{i=1}^{n} \overline{m_i \overline{x}}}{\sum_{i=1}^{n} \overline{m_i}} Eq. 7$$

177 where m_i is mass of granules in the interval x_i to x_{i+1} with an average size of \overline{x} .

178 One Way Repeated measures ANOVA statistical analysis, performed using Sigma Plot V. 179 11 (Systat Software Inc, USA) on the averages from three measurements for each of the 5 180 experiments showed that the differences in the average values were greater than would be expected by chance; there is a statistically significant difference (P = 0.037). The distribution 181 182 of the granules between the three categories i.e. fines, product and coarse granules is shown in 183 Fig. 4 (c). The largest fraction of oversized granules is obtained when the impeller ST-17 is 184 employed. Using this impeller produces negligible amount of fines. It seems that this impeller 185 is ineffective in breaking down the oversized particles. The minimum level of oversized

granules was obtained when the SPPW-15 impeller was used. The highest fraction of product 186 187 was obtained when the HTFB-14 impeller was used. It must be pointed out that there is no 188 significant difference between the product fractions for the SSPW-15 and the HFTB-14 189 impellers. There is no statistically significant difference between the product yield values from 190 the batches produced using the SSPW-15 and the HTFB-14 impellers, which is around 40 %. 191 The use of the impellers SSKB-13 and ST-17 result in formation of a larger fraction of the 192 coarse granules which would necessitate inclusion of a size reduction step to convert the 193 oversize product into usable product.

194 **3.3 Effect on MB content distribution**

195 Fig. 5 shows variation of the MB concentration in the samples of granules taken from 196 different sizes. It is evident from this figure that the finer granules have a higher concentration 197 compared to larger granules. Granules in the size range 1 to 4 mm have almost similar MB 198 concentrations for all the cases. This is not always the case when using drug molecules. 199 Different views have been expressed regarding the drug distribution across granules of 200 different sizes. Differences in solubility and particle size differences between the filler and 201 drug material have been cited as reasons contributing to inhomogeneity (Ojile et al., 1982; Selkirk, 1976). It has also been reported that granulations involving drugs or active ingredients 202 203 that are finer compared to filler material can result in smaller granules that have higher drug 204 composition compared to the other granules (Egermann and Reiss, 1988). However this could 205 not be used to explain the distribution of MB shown in Fig. 5 because MB was added to the 206 binder solution form during granulation. Previous work has also shown that larger granules 207 have higher binder content compared to the smaller granules (Scott et al., 2000). Therefore one 208 can expect larger granules to have higher composition of MB, since they should contain more 209 binder. It can also be observed from Fig. 5 that the batches produced by HTFB-14 impeller had

the least variation in the MB concentration across all sizes whilst that produced by ST-17exhibited the largest variation.

The homogeneity coefficient based on samples taken from all sizes was determined to compare the efficacy of mixing by the different impellers; the results are presented in Fig. 6. It is apparent from this figure that HTFB-14 had the largest value of homogeneity coefficient implying that better mixing was achieve using this impeller. ST-17 impeller produced batches which showed the greatest inhomogeneity. This is also supported by the observation that the same batch had the highest presence of oversized granules.

218 **3.4 Effect of impeller design on granule homogeneity**

219 The homogeneity of the granules from the 5 experiments were analysed for three difference 220 size ranges; 710-1000 µm, 1000 to 1180 µm and 3350 to 4000 µm in accordance to the method 221 described in section 2.3. The results are presented in Fig. 7 (a). For the granules in the size 222 range 710 to 1000 µm, the concentration of MB is in the range 0.4 to 0.85 ppm. The highest 223 concentration of granules for this case was obtained when using the impeller HFTB-14. The 224 MB concentration of granules in this range was similar for the impellers SSKB-13 and the 225 SSPW-15. Granules obtained using the ST-17 impeller had the least concentration of MB. For 226 the next size class investigated, 1000 to 1180 µm, the concentration of MB ranges from 0.52 to 227 0.64 ppm. The variability of the MB concentration for this size range across the batches was 228 lower than that for the 710 to 1000 µm size class. The greatest variability in concentration of 229 the MB in the granules across batches was observed for the larger granules (3350 to 4000 µm).

The theoretical average dry concentration of the MB in the granules can be determined fromthe following equation (Mangwandi et al., 2013c):

232
$$\overline{C}_{i,theo} = \frac{m_{bin} \tilde{c}_{i,bin}}{m_{bat}}$$
 Eq. 8

In Eq. (8), m_{bin} is the expected mass of binder in the granule, $\tilde{c}_{i,bin}$ is the MB concentration in the binder, m_{bat} is the mass of the wet batch of granules and V is the volume of deionised water used to dissolve 1g of granules during the test.

Substituting the correct values of the mass of binder used in the granulation experiment (40 g) and the concentration of the MB in the binder solution (20 ppm) and mass of each batch 0.20 kg gives a theoretical average concentration of 4 ppm. It is then clear from Fig. 7(a) that all the granules tested in this study had below average concentration of the MB.

240 For most of the impellers, granules with different sizes have significantly different 241 concentration of MB; for the SSD-16 and SSPW-15 impellers, the MB concentration decreased 242 with increasing granule size. When the ST-17 impeller is used, granules in the size range 710 -243 1000 µm had similar concentration to those in the 3350 µm to 4000 µm range. The granules 244 produced by the impeller HTFB-14 had most similar concentrations of MB. This would give 245 the impression that granulating using an impeller would result in better distribution of the MB 246 across granules of different sizes (see the circle in Fig. 7 (a)). There are previous results in 247 literature describing the binder distribution in high shear granulation and showing that larger 248 granules have higher binder content compared to smaller granules (Osborne et al., 2010; 249 Reynolds et al., 2004; Smith et al., 2010). In another article (Ramachandran et al., 2008), it is 250 reported that granules in the mid-range contain the highest amount of binder compared to the 251 small and large granules. Fig. 7(b) shows the uniformity coefficient of the MB in granules of 252 different sizes produced by different impeller design. The Homogeneity coefficient gives an 253 indication of variability of the MB across each size class. The homogeneity is defined in such a 254 way that a higher value of the coefficient indicates greater variability (less homogeneity) whilst 255 a lower value would indicate better homogeneity (less variability). There is variation in the 256 homogeneity coefficient both across granules made from the same impeller (different sizes)

and also variation across granules of the same size but produced by different impeller. No definite correlation could be identified between the impeller type and the homogeneity coefficient. For the SSKB-13, HTFB-14 and SHD impellers the results show that the homogeneity coefficient is lower for the larger granules compared to the smaller granules. This would imply that there is larger variation in the concentration of MB in the samples taken from larger granules. For the other two impellers the highest value of homogeneity coefficient is obtained from samples of granules of intermediate size.

264 **3.5 Effect of Impeller Design on Granule Strength**

265 Statistical analysis of the five groups of strength data (one from each of the impellers) using 266 Kruskal-Wallis One Way ANOVA analysis showed that differences in the median values 267 among the treatment groups was higher than would be expected from chance; there is a statistical significant difference (P = 0.004). This implies that the different impellers produced 268 269 granules of different strength. However, All Pairwise comparison between the five groups of 270 granules showed that strength data from the SPPW-15 impeller was significantly different form 271 the other four impellers; differences between the other groups was less significant. Summary of 272 the ANOVA analysis results is shown in Fig. 8.

The strength distribution curves of granules produced from the different impeller designs are shown in Fig. 9. It is evident from the figure that the granules from the batch produced by impeller SSPW-15 differed significantly from the rest of the batches and this impeller produced the strongest granules. The variation in the strength results was highest when the SSKB-13 impeller was used and the least variation was obtained when the HFTB impeller was used. Fig. 9 (b) also shows that the largest scatter in the strength data was for granules produced by the impeller SSKB-13.

280

281 3.6 Effect of Impeller Design on granule shape

282 The images shown in Fig. 10 are of granules in the size range 1000 - 1180 µm produced by 283 the different types of impeller. It can be noticed from the images that the granules have 284 irregular shape and rough surfaces irrespective of the type of the impeller. For this particular 285 size range and other size ranges investigated 710 - 1000 μ m; 2000 – 2360 μ m and 2800 - 3350 286 μ m, the impeller design does not seem to have an influence on the shape of the structure of the granules formed. Images of the granules are shown in Fig. 11 This is contrary to earlier work 287 288 (Schaefer et al., 1993) which reported that impeller design has a slight impact on the granule 289 shape.

The shape of the granules was analysed from images, using the aspect ratio as an indicator of sphericity. The closer the value of the aspect ratio to 1 the less elongated the particle; the further the value from 1, the more elongated is the particle. The average shape factors of granules from different size ranges produced by different impeller are presented in Fig. 12.

It is quite clear from Fig. 12 that, for the granule in the size range $710 - 1000 \mu m$, the type of impeller has no influence on the aspect ratio of the granules. The granules in the size ranges $710 - 1000 \mu m$ and $1000 - 1180 \mu m$ have similar average aspect ratios. The average values of aspect ratio for the granules in the 2360 - 3350 μm range are higher than those of the smaller granules for all five groups of granules. For all impeller designs, the smaller granules are less elongated than the larger granules.

The effect of the impeller design on granule attributes is summarised in Table 2. The impellers are ranked from 5 to 1, 5 being the best based on maximising that particular granule attribute. It shows which of the impellers to choose if the aim is to maximise the listed attribute. For instance, for maximum granule strength, the SSPW-15 is the one to choose. In terms of better product yield there are two candidates, SSPW-15 and HTFB-14, since the 305 product yield from these two do not differ significantly. Overall the HTFB impeller has a 306 highest score compared to the other impellers.

307 4. CONCLUSIONS

308 It has been shown that the choice of the impeller has an influence on granule size 309 distribution, the granule mean size, and the strength and extent of mixing during granulation. In terms of homogeneity of the pseudo active ingredient, the HTFB impeller outperformed the 310 311 other impellers. The impeller type does not seem to have a significant influence on the shape of 312 granules formed. For the size range investigated in this work, granules of the highest strength 313 were produced when impeller SSPW-15 was employed whereas the highest granule mean size 314 was obtained with the ST-17. Whilst the different impeller designs performed differently 315 depending which granule property one is looking at, the HTFB-14 seems to be the one to choose if one is looking for an impeller that gives better mixing, good product yield and 316 317 reasonable granule strength.

318 **REFERENCES**

CAMPBELL, G.A., CLANCY, D.J., ZHANG, J.X., GUPTA, M.K., OH, C.K., 2011.
CLOSING THE GAP IN SERIES SCALE UP OF HIGH SHEAR WET
GRANULATION PROCESS USING IMPELLER POWER AND BLADE DESIGN.
POWDER TECHNOLOGY 205, 184-192.

CHITU, T.M., OULAHNA, D., HEMATI, M., 2011. WET GRANULATION IN
LABORATORY-SCALE HIGH SHEAR MIXERS: EFFECT OF CHOPPER
PRESENCE, DESIGN AND IMPELLER SPEED. POWDER TECHNOLOGY 206, 3443.

EGERMANN, H., REISS, W., 1988. EFFECT OF PARTICLE SIZE OF DRUG AND
 DILUENT ON DRUG DISTRIBUTION IN GRANULE SIZE FRACTIONS. ACTA
 PHARMACEUTICAL TECHNOLOGY 34, 5S.

HIRAMATSU, Y., OKA, Y., 1966. DETERMINATION OF THE TENSILE STRENGTH
OF ROCK BY A COMPRESSION TEST OF AN IRREGULAR TEST PIECE.

332 INTERNATIONAL JOURNAL OF ROCK MECHANICS AND MINING SOCIETY 3,
 333 89-99.

JIROUT, T., RIEGER, F., 2011. IMPELLER DESIGN FOR MIXING OF
 SUSPENSIONS. CHEMICAL ENGINEERING RESEARCH AND DESIGN 89, 1144 1151.

JOHANSSON, B., ALDERBORN, G., 2001. THE EFFECT OF SHAPE AND
POROSITY ON THE COMPRESSION BEHAVIOUR AND TABLET FORMING
ABILITY OF GRANULAR MATERIALS FORMED FROM MICROCRYSTALLINE
CELLULOSE. EUROPEAN JOURNAL OF PHARMACEUTICS AND
BIOPHARMACEUTICS 52, 347-357.

KACUNIC, A., AKRAP, M., KUZMANIC, N., 2012. EFFECT OF IMPELLER TYPE
AND POSITION IN A BATCH COOLING CRYSTALLIZER ON THE GROWTH OF
BORAX DECAHYDRATE CRYSTALS. CHEMICAL ENGINEERING RESEARCH
AND DESIGN 91, 274-285.

KHARE, A.S., NIRANJAN, K., 2002. THE EFFECT OF IMPELLER DESIGN ON GAS
HOLD-UP IN SURFACTANT CONTAINING HIGHLY VISCOUS NON-NEWTONIAN
AGITATED LIQUIDS. CHEMICAL ENGINEERING AND PROCESSING: PROCESS
INTENSIFICATION 41, 239-249.

KNIGHT, P.C., SEVILLE, J.P.K., WELLM, A.B., INSTONE, T., 2001. PREDICTION
 OF IMPELLER TORQUE IN HIGH SHEAR POWDER MIXERS. CHEMICAL
 ENGINEERING SCIENCE 56, 4457-4471.

KUMARESAN, T., JOSHI, J.B., 2006. EFFECT OF IMPELLER DESIGN ON THE
 FLOW PATTERN AND MIXING IN STIRRED TANKS. CHEMICAL ENGINEERING
 JOURNAL 115, 173-193.

MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2010. EFFECT
 OF IMPELLER SPEED ON MECHANICAL AND DISSOLUTION PROPERTIES OF
 HIGH-SHEAR GRANULES. CHEMICAL ENGINEERING JOURNAL 164, 305-315.

MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2011. EFFECT
OF BATCH SIZE ON MECHANICAL PROPERTIES OF GRANULES IN HIGH
SHEAR GRANULATION. POWDER TECHNOLOGY 206, 44-52.

MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2012. AN
INVESTIGATION OF THE INFLUENCE OF PROCESS AND FORMULATION
VARIABLES ON MECHANICAL PROPERTIES OF HIGH SHEAR GRANULES
USING DESIGN OF EXPERIMENT. INTERNATIONAL JOURNAL OF
PHARMACEUTICS 427, 328-336.

MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2014.
 INFLUENCE OF FILL FACTOR VARIATION IN HIGH SHEAR GRANULATION

369 ON THE POST GRANULATION PROCESSES: COMPRESSION AND TABLET
 370 PROPERTIES. POWDER TECHNOLOGY 263, 135-141.

MANGWANDI, C., ALBADARIN, A.B., AL-MUHTASEB, A.A.H., ALLEN, S.J.,
WALKER, G.M., 2013A. OPTIMISATION OF HIGH SHEAR GRANULATION OF
MULTICOMPONENT FERTILISER USING RESPONSE SURFACE
METHODOLOGY. POWDER TECHNOLOGY 238, 142-150.

MANGWANDI, C., CHEONG, Y.S., ADAMS, M.J., HOUNSLOW, M.J., SALMAN,
A.D., 2007. THE COEFFICIENT OF RESTITUTION OF DIFFERENT
REPRESENTATIVE TYPES OF GRANULES. CHEMICAL ENGINEERING
SCIENCE 62, 437-450.

MANGWANDI, C., JIANGTAO, L., ALBADARIN, A.B., ALLEN, S.J., WALKER,
G.M., 2013B. ALTERNATIVE METHOD FOR PRODUCING ORGANIC FERTILISER
FROM ANAEROBIC DIGESTION LIQUOR AND LIMESTONE POWDER: HIGH
SHEAR WET GRANULATION. POWDER TECHNOLOGY 233, 245-254.

MANGWANDI, C., JIANGTAO, L., ALBADARIN, A.B., ALLEN, S.J., WALKER,
G.M., 2013C. THE VARIABILITY IN NUTRIENT COMPOSITION OF ANAEROBIC
DIGESTATE GRANULES PRODUCED FROM HIGH SHEAR GRANULATION.
WASTE MANAGEMENT 33, 33-42.

MANGWANDI, C., ZAINAL, N.A., JIANGTAO, L., GLOCHEUX, Y., ALBADARIN,
A.B., 2015. INVESTIGATION OF INFLUENCE OF PROCESS VARIABLES ON
MECHANICAL STRENGTH, SIZE AND HOMOGENEITY OF PHARMACEUTICAL
GRANULES PRODUCED BY FLUIDISED HOT MELT GRANULATION. POWDER
TECHNOLOGY 272, 173-180.

NIKLASSON, B.I., JANSSON, A., KARLSSON, M., FOLESTAD, S., RASMUSON, A.,
2005. EMPIRICAL TO MECHANISTIC MODELLING IN HIGH SHEAR
GRANULATION. CHEMICAL ENGINEERING SCIENCE 60, 3795-3803.

OJILE, J.E., MACFARLANE, C.B., SELKIRK, A.B., 1982. DRUG DISTRIBUTION
 DURING MASSING AND ITS EFFECT ON DOSE UNIFORMITY IN GRANULES.
 INTERNATIONAL JOURNAL OF PHARMACEUTICS 10, 99-107.

398 OSBORNE, J.D., SOCHON, R.P.J., CARTWRIGHT, J.J., DOUGHTY, D.G.,
399 HOUNSLOW, M.J., SALMAN, A.D., 2010. BINDER ADDITION METHODS AND
400 BINDER DISTRIBUTION IN HIGH SHEAR AND FLUIDISED BED GRANULATION.
401 CHEMICAL ENGINEERING RESEARCH AND DESIGN 89, 553-559.

402 RAMACHANDRAN, R., POON, J.M.H., SANDERS, C.F.W., GLASER, T.,
403 IMMANUEL, C.D., DOYLE III, F.J., LITSTER, J.D., STEPANEK, F., WANG, F.-Y.,
404 CAMERON, I.T., 2008. EXPERIMENTAL STUDIES ON DISTRIBUTIONS OF
405 GRANULE SIZE, BINDER CONTENT AND POROSITY IN BATCH DRUM

406 GRANULATION: INFERENCES ON PROCESS MODELLING REQUIREMENTS
 407 AND PROCESS SENSITIVITIES. POWDER TECHNOLOGY 188, 89-101.

408 REYNOLDS, G.K., BIGGS, C.A., SALMAN, A.D., HOUNSLOW, M.J., 2004. NON409 UNIFORMITY OF BINDER DISTRIBUTION IN HIGH-SHEAR GRANULATION.
410 POWDER TECHNOLOGY 140, 203-208.

SCHAEFER, T., TAAGEGAARD, B., THOMSEN, L.J., GJELSTRUP KRISTENSEN,
H., 1993. MELT PELLETIZATION IN A HIGH SHEAR MIXER. V. EFFECTS OF
APPARATUS VARIABLES. EUROPEAN JOURNAL OF PHARMACEUTICAL
SCIENCES 1, 133-141.

- 415 SCOTT, A.C., HOUNSLOW, M.J., INSTONE, T., 2000. DIRECT EVIDENCE OF
 416 HETEROGENEITY DURING HIGH-SHEAR GRANULATION. POWDER
 417 TECHNOLOGY 113, 205-213.
- 418 SELKIRK, A.B., 1976. THE EFFECT OF SOLUTE MIGRATION ON THE
 419 DISTRIBUTION OF BORAX THROUGHOUT A BATCH OF GRANULES. JOURNAL
 420 OF PHARMACY AND PHARMACOLOGY 28, 512-514.

421 SHIRAISHI, T., KONDO, S., YUASA, H., KANAYA, Y., 1994. STUDIES ON THE
422 GRANULATION PROCESS OF GRANULES FOR TABLETING WITH A HIGH
423 SPEED MIXED. I. PHYSICAL PROPERTIES OF GRANULES FOR TABLETING.
424 CHEMICAL AND PHARMACEUTICAL BULLETIN 42, 932-936.

425 SMITH, R.M., LIU, L.X., LITSTER, J.D., 2010. BREAKAGE OF DROP NUCLEATED
426 GRANULES IN A BREAKAGE ONLY HIGH SHEAR MIXER. CHEMICAL
427 ENGINEERING SCIENCE 65, 5651-5657.

428 SUMMERS, M., AULTON, M.E., 1988. GRANULATION, IN: AULTON, M.E. (ED.),
429 PHARMACEUTICS: THE SCIENCE OF DOSAGE FORM DESIGN, 7TH ED.
430 CHURCHILL LIVINGSTONE.

431 VOINOVICH, D., CAMPISI, B., MONEGHINI, M., VINCENZI, C., PHAN-TAN-LUU,
432 R., 1999. SCREENING OF HIGH SHEAR MIXER MELT GRANULATION PROCESS
433 VARIABLES USING AN ASYMMETRICAL FACTORIAL DESIGN.
434 INTERNATIONAL JOURNAL OF PHARMACEUTICS 190, 73-81.

435

436

438 NOMENCLATURE

\overline{c} ,	Concentration of [ppm]
\overline{d}	Average granules size[mm]
D	Granule diameter (mm)
F	Force [N]
т	mass [g]
n	Number of samples analysed [-]
V	Volume of dissolution medium [ml]
S	Standard deviation of the methylene blue concentration [ppm]
x	Arithmetic average size of the granules in the range[mm]

439

440 Greek letters

η	Homogeneity coefficient [-]
κ	Average granules size[mm]
σ	Granule strength [Nmm ⁻² or MPa]
Ψ	Product yield [%]

441

442 Subscripts

bat	batch
bin	binder
exp	Experimental value
f	failure
i	Sample index
MB	Methylene blue
р	powder
pro	product
S	sample
theo	Theoretical value

443

444 Abbreviation

API	Active Pharmaceutical
HTFB	High Temperature Flexible Beater
MB	Methylene blue
SDH	Spiral Dough Hook
SSKB	Stainless Steel K Beater
SSPW	Stainless Steel Power Whisk
ST	Stirring Tool
XRD	X Ray Diffraction

Table 1: Summary of process and granulation parameters.

Experiment No.	Impeller type	Impeller speed (rpm)	Granulation Time (min)	Mass of lactose Powder	Binder	Liquid to solid Ratio
1	HTFB-14	160	4	200	water	0.2
2	HTFB-14	160	4	200	Water + MB	0.2
3	SSKB-13	160	4	200	Water + MB	0.2
4	SSPW-15	160	4	200	Water + MB	0.2
5	SDH-16	160	4	200	Water + MB	0.2
6	ST-17	160	4	200	Water + MB	0.2

		Impeller	Granule
	Binder	Туре	Strength (MPa)
	Water	HTFB-14	0.60 ± 0.06
	Water + MB	HTFB-14	0.65 ± 0.08
451			
452			
453			

Table 2: Comparison of the strength of granules produced from different binders. N.B. Errors indicate
 Standard error in the mean

Impeller type	Product Yield	Homogeneity	Granule Strength	Granule Mean Size
SSKB-13	2	2	2	4
HTFB-14	5	5	3	2
SSPW-15	4	4	5	1
SDH-16	3	3	4	3
ST-17	1	1	1	5

454 Table 3: Summary of effect of impeller design on granule attributes.



Fig. 1: Images of the different impeller designs used in the granulation experiments (a) Stainless steel power whisk (SSPW-15) b) Spiral Dough Hook (SDH-16) c)Stirring Tool (ST-17) d) High Temperature

- Flexible Beater (HTFB-14) e) Stainless Steel K Beater (SSKB-13)



Fig. 2: XRD patterns of samples alpha lactose, granulated lactose from water and water-methylene blue solution.



470 Fig. 3: Comparison of size distributions of batch of granules produced using water and MB solution471 binders.





Impeller Type [-]



Fig. 4: (a) Typical cumulative granule size distribution plots for experiments 2 to 6. (b) Granule mass
 mean size as a function of impeller type (c) mass distribution of the granules between fines, product and
 oversized granules. N.B The plots are average of three replicate experiments.



Fig. 5: The variation of MB concentration with size class for batches of granules produced with different
 impeller designs.



Fig. 6: Variation of homogeneity coefficient across different sizes for batches produced with different
 impellers.







Data source: Data 2 in Notebook1

Group	Ν	Missing	Median	25%	75%
SSKB-13	25	0	0.686	0.418	0.896
HTFB-14	25	0	0.571	0.344	0.994
SSPW-15	25	0	0.998	0.679	1.563
SDD-16	25	0	0.621	0.350	0.870
ST-17	25	0	0.492	0.321	0.655

H = 15.242 with 4 degrees of freedom. (P = 0.004)

The differences in the median values among the treatment groups are greater than would be expected by chance; there is a statistically significant difference (P = 0.004)

To isolate the group or groups that differ from the others use a multiple comparison procedure.

All Pairwise Multiple Comparison Procedures (Student-Newman-Keuls Method) :

Diff of Ranks	q	P<0.05
928.000	5.123	Yes
759.000	5.232	Yes
683.000	6.268	Yes
620.000	8.506	Yes
308.000	2.123	No
139.000	1.276	Do Not Test
63.000	0.864	Do Not Test
245.000	2.248	Do Not Test
76.000	1.043	Do Not Test
169.000	2.319	Do Not Test
	Diff of Ranks 928.000 759.000 683.000 620.000 308.000 139.000 63.000 245.000 76.000 169.000	Diff of Ranks q 928.000 5.123 759.000 5.232 683.000 6.268 620.000 8.506 308.000 2.123 139.000 1.276 63.000 0.864 245.000 2.248 76.000 1.043 169.000 2.319

495

496 Fig. 8: Statistical analysis of the granule strength data from batches produce with different impellers.

497

498





Fig. 9: Effect of impeller type on the strength of the granules.



(a) HTFB-13

(b) HTFB-14



505

Fig. 10: Images showing the shape and structure of the granules from different batches produced using different impellers. 506 507



0.71 mm



1.0 mm





2.0 mm



Fig. 11: Images showing the shape and structure of the granules of different sizes from the same batch



512 Fig. 12: Effect of impeller design on the aspect ratio of granules of different sizes.