**QUEEN'S
UNIVERSITY
BELFAST**

Effect of Impeller Design on Homogeneity, Size and Strength of Pharmaceutical Granules produced by High Shear Wet Granulation

Mirza, Z., Liu, J., Glocheux, Y., Albadarin, A. B., Walker, G. M., & Mangwandi, C. (2015). Effect of Impeller Design on Homogeneity, Size and Strength of Pharmaceutical Granules produced by High Shear Wet Granulation. *Particuology*, 23, 31-39. <https://doi.org/10.1016/j.partic.2014.12.009>

Published in:
Particuology

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

© 2015 Elsevier Ltd. This manuscript version is made available under the CC-BY-NC-ND 4.0 license <http://creativecommons.org/licenses/by-nc-nd/4.0/> which permits distribution and reproduction for non-commercial purposes, provided the author and source are cited.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

**EFFECT OF IMPELLER DESIGN ON HOMOGENEITY, SIZE AND STRENGTH OF
PHARMACEUTICAL GRANULES PRODUCED BY HIGH SHEAR WET GRANULATION**

Chirangano Mangwandi^{1*}, Zakaria Mirza¹, Liu JiangTao¹, Yoann Glocheux¹,

Ahmad B. Albadarin^{1,2}

¹Sch. of Chemistry and Chemical Engineering, Queen's University Belfast, Belfast BT9 5AG,

Northern Ireland UK

²Synthesis & Solid State Pharmaceuticals Center (SSPC),

Department of Chemical and Environmental Science,

University of Limerick, Ireland.

Corresponding author

E-mail: c.mangwandi@qub.ac.uk (C. Mangwandi),

Tel. +44(0)289 097 4378

Fax. +44 (0) 289 097 6524

17 **ABSTRACT**

18 Design of small mixer impellers is not tailored for granulation as they are intended for a
19 wide range of processes. The Kenwood KM070 was employed as a standard apparatus to
20 undertake this investigation. Five different impeller designs with different shapes and surface
21 areas were used. The aim of this research was to evaluate the performances of these impellers
22 to provide guidance on the selection and design for the purposes of granulation. Lactose
23 granules were produced using wet granulation with water as the binder. The efficacy of
24 respective granulates was measured by adding an optically sensitive tracer. This was used to
25 determine variation of active ingredient across random samples of granules from the same size
26 classes. It was found that impeller design influenced the homogeneity of the granules and
27 therefore can affect final product performance. The variation of active ingredient across
28 granule of different sizes was also investigate. The study shows that small granules were more
29 potent when compared to the larger granules.

30 **KEYWORDS**

31 Granules strength; impeller design; homogeneity; high shear granulation; lactose
32 monohydrate

33

1. INTRODUCTION

Granulation is a size enlargement unit operation in which granular products are produced by sticking together powdery particles with a binder. It has wide applications in several industries for instance pharmaceuticals, detergent industries, fine chemicals and fertiliser industries. Particle agglomeration in wet granulation improves the bulk properties of the formulation by enhancing the flow properties, reducing the dustiness and also the improving the compression properties. Several studies investigated the effect of granulation parameters in the high shear mixer on product attributes and demonstrated that control of process parameters is necessary to obtain product with the desired attributes (Campbell et al., 2011; Johansson and Alderborn, 2001; Mangwandi et al., 2010; Mangwandi et al., 2012; Mangwandi et al., 2013a; Niklasson et al., 2005; Shiraishi et al., 1994). The final product properties are influenced by the process parameters and formulation attributes. In addition to formulation and process variables there are equipment variables which can influence the properties of the granule. Examples of these variables are the type and shape of the vessel, the presence of a chopper (Chitu et al., 2011) and nozzle.

The main source of energy in high shear granulation is power dissipation by impeller rotation. The main task of the impeller is to agitate the powder particles and ensure that they are always in continuous motion and to ensure collision between binder particle and powder particles. The other purpose of the impeller is to ensure proper mixing of the materials being granulated. Previous work done in mixing of fluid systems has shown that the design of the impeller has a significant effect on the flow of the fluid (Jirout and Rieger, 2011; Kacunic et al., 2012; Khare and Niranjana, 2002; Kumaresan and Joshi, 2006).

There are scant papers in literature discussing the effect of impeller design on the granulation process (Campbell et al., 2011; Knight et al., 2001; Niklasson et al., 2005; Schaefer

et al., 1993; Smith et al., 2010; Voinovich et al., 1999) . Work done by Schaefer et al. 1993 on the effect of equipment variables on granulation revealed that the impeller blade design affects the shape of the granules formed (Schaefer et al., 1993). Granules that are more spherical were obtained if an impeller with a curved blade was used whilst granulating using a flat blade impeller resulted in formation of irregular shaped granules.

The Kenwood food processor (Kenwood, KM070) which has been used as a lab scale high shear mixture in previous studies (Mangwandi et al., 2013a; Mangwandi et al., 2013b, c) comes with different impellers since it is designed for mixing a range of different materials. Images of the different impeller design are shown in Fig. 1. In the previous studies (Mangwandi et al., 2013a; Mangwandi et al., 2013b, c) only one type of impeller was used, the High Temperature Flexible Beater (HTFB - 14). The aim of this paper is to evaluate the performance of the other impellers in high shear wet granulation in terms of extent of mixing, strength of the granules formed and the size distributions. The extent of mixing will be evaluated using the method used in previous work (Mangwandi et al., 2011; Mangwandi et al., 2014; Mangwandi et al., 2013c).

2. MATERIALS & METHOD

2.1 Materials

Lactose monohydrate powder, supplied by Sigma Aldrich GmbH, was used as the main excipient. Methylene Blue (MB) - high purity biological strain, produced and supplied by Sigma Aldrich, was used as a model active ingredient.

2.2 Binder Preparation and Granulation

All granulation experiments were performed in a Kenwood processor (KM 70). Six granulation experiments were done in triplicates. The granulation conditions used in all the experiments are summarised in Table 1. The purpose of experiments 1 and 2 was to check whether addition of methylene blue (MB) to the granulation liquid had any effect on the granulation properties. The same type of impeller was used in these experiments. Experiments 2 to 6 were used to investigate the effect of impeller type on the batch homogeneity, granule mechanical strength and shape. Methylene blue was added to deionised water to produce a MB solution, with a concentration of 20 ppm.

2.3 Material Characterisation

Data were collected on the powdered samples using a Philips Xpert Pro-Pan-Analytical diffractometer. The instrument used a monochromated Cu Ka lamp radiating at lambda value of 1.5406 Armstrong. The samples were housed in a flat plate sample holder and analysed through a 2θ range of $5 - 40^\circ$, using 0.16713° steps over a period of 12 minutes. XRD patterns for alpha lactose powder, granulated lactose with water and granulated lactose with water-methylene blue are shown in Fig. 2. No structural change is noticed in lactose; therefore methylene blue can be used as an inert tracer to monitor lactose granulation in water.

2.4 Granule Drying and Size Analysis

After granulation each batch of granules was transferred to flat aluminium trays with dimensions 236 mm X 297 mm X 59 mm, ensuring that the granules were evenly spread on the tray surface. The granule trays were then transferred to an oven (Binder FD249, Binder GmbH, Germany) pre-set to a temperature of 60°C and dried for 12 hours. After drying the granules were allowed to cool to room temperature and then stored in sealed bags until further needed.

Retsch sieves (Retsch GmbH, Germany) were used in the size analysis and the aperture sizes used were as follows; 350, 500, 600, 710, 1000, 1180, 1400, 1700, 2000, 2360, 3350, and

4000 μm . The stack of sieves with the granules was placed on an orbital sample shaker, Stuart Orbital Shaker, supplied by Cole-Parmer UK. The speed of the shaker was set to 180 rpm and the sieving duration to 5 min.

The targeted range of granule size in the experiments undertaken was 0.2 to 4 mm which is the typical size range of pharmaceutical granules (Summers and Aulton, 1988). The percentage of granules in this size range was referred to as the product yield (Ψ) and is calculated by the following equation;

$$\Psi = \left(\frac{m_{pro}}{m_{Bat}} \right) \times 100\% \quad \text{Eq. 1}$$

where m_{pro} is the mass of granules in the required size range and m_{Bat} is the mass of total granules produced in a batch. Granules in the size range 0.5 to 4 mm were considered to be the product, whilst those below and above this range were considered to be fines and oversize granules respectively.

2.5 Determination of Homogeneity across granules of same size

Ten random samples of approximately 1 g of granules in the required size range were withdrawn from each batch. Colloids were prepared from each of the samples by adding the granules to 50 ml of de-ionised water. The concentration of the methylene blue solution was obtained by measuring the absorbance of the solution at a single wavelength of 664 nm and calculating the concentration from the previously determined calibration equation. The uniformity coefficient was calculated using the following equation (Mangwandi et al., 2011; Mangwandi et al., 2013c; Mangwandi et al., 2015);

$$\kappa = \frac{S}{\hat{c}} \quad \text{Eq. 2}$$

125 where $\hat{c}$ is the mean of the samples and S is the standard deviation of methylene blue
126 concentration in the samples;

$$127 \quad S = \sqrt{\frac{\sum_i (c_i - \hat{c})^2}{n - 1}} \quad \text{Eq. 3}$$

128 In Eq. (3) above, n , is the total number of samples analysed and c_i is the MB concentration in
129 the i^{th} sample.

130 MB concentration in granules for each particle size of granules was analysed in the same
131 way and the concentration distribution in function of the particles sizes were plotted.

132 The homogeneity coefficient can then be defined as;

$$133 \quad \eta = 1 - \kappa \quad \text{Eq. 4}$$

134 where κ is as define in *Eq. 2* and $0 \leq \eta \leq 1$. A value of homogeneity coefficient of 1 is assigned
135 to a completely homogeneous distribution of the pseudo active ingredient while a low value of
136 η indicates poor distribution.

137 **2.6 Methylene Blue distribution across different size classes**

138 The distribution of the MB across different size of the granules was measured by dissolving
139 a known mass of granules in a known volume of distilled water and measuring the absorbance
140 of the colloid at a wavelength of 664 nm using a spectrophotometer. The concentration (in
141 ppm) of the colloid was calculated using Eq. 5. The concentration of the MB in dry sample
142 (mg/g) was then determined from;

$$c_{MB,exp}(x_i) = c_{MB} \times \left(\frac{m_{MB}}{m_p} \right) \times \left(\frac{m_s(x_i)}{V} \right) \quad Eq. 5$$

where m_{MB} is the mass of MB added to the batch; m_p is total mass of powder (mass of lactose and MB added; $m_s(x_i)$ mass of sample granules from size class x_i used in measurement; V (in litres) is the volume of dissolution medium.

2.7 Granules Strength Analysis

The strength of granules in the size range 2000 to 2360 μm was determined from diametric compression of the single granules using the method described previously (Mangwandi et al., 2010; Mangwandi et al., 2007). Eq. 6 was used to determine the granule strength from the failure load, F_f , and the granule diameter, D , which is measured as the distance between the fixed platen and the movable platen, when first contact is made between the granule (Hiramatsu and Oka, 1966);

$$\sigma = 2.8 \times \left(\frac{F_f}{\pi D^2} \right) \quad Eq. 6$$

2.8 Shape Analysis

The shape of the granules from different batches was analysed using an Eyecon 3D particle imager (Innopharmalabs, Ireland). The Eyecon device is able to measure particles size from 50-3000 μm . The device applies blue, green, and red light to the analysed objects and several images are generated. Irregular particle shapes are mapped by the software and several measurements are logged. The characteristics of the granule size distribution; d_{10} , d_{50} , d_{90} , d_{max} , d_{min} and, aspect ratio are presented in report form at the end of the measurement. The particle size measurements are taken directly from the image analysis and there is no model applied to the data.

3. RESULTS & DISCUSSION

3.1 Effect of addition of MB

Preliminary results show that addition of MB to the formulation did not significantly affect the granulation process. The granule size distribution and the strength of formulation with and without MB are shown in Fig. 3 and Table 1 respectively. The results are to be expected considering the low level of concentration of the MB used.

3.2 Effect of Impeller Design on Granule size distribution

The impeller design has an impact on the average granule size and the granule size distributions of the batches. The results are presented in Fig. 4 (a). It is noticeable from this Fig. that for all the batches there was a large percentage of granules bigger than 4000 μm . The presence of these large granules could be attributed to the higher liquid to solid ratio used in the experiments. The mass mean diameter of the granules was calculated according to:

$$\bar{d} = \frac{\sum_{i=1}^n m_i \bar{x}}{\sum_{i=1}^n m_i} \quad \text{Eq. 7}$$

where m_i is mass of granules in the interval x_i to x_{i+1} with an average size of $\bar{x}$.

One Way Repeated measures ANOVA statistical analysis, performed using Sigma Plot V. 11 (Systat Software Inc, USA) on the averages from three measurements for each of the 5 experiments showed that the differences in the average values were greater than would be expected by chance; there is a statistically significant difference ($P = 0.037$). The distribution of the granules between the three categories i.e. fines, product and coarse granules is shown in Fig. 4 (c). The largest fraction of oversized granules is obtained when the impeller ST-17 is employed. Using this impeller produces negligible amount of fines. It seems that this impeller is ineffective in breaking down the oversized particles. The minimum level of oversized

granules was obtained when the SPPW-15 impeller was used. The highest fraction of product was obtained when the HTFB-14 impeller was used. It must be pointed out that there is no significant difference between the product fractions for the SSPW-15 and the HTFB-14 impellers. There is no statistically significant difference between the product yield values from the batches produced using the SSPW-15 and the HTFB-14 impellers, which is around 40 %. The use of the impellers SSKB-13 and ST-17 result in formation of a larger fraction of the coarse granules which would necessitate inclusion of a size reduction step to convert the oversize product into usable product.

3.3 Effect on MB content distribution

Fig. 5 shows variation of the MB concentration in the samples of granules taken from different sizes. It is evident from this figure that the finer granules have a higher concentration compared to larger granules. Granules in the size range 1 to 4 mm have almost similar MB concentrations for all the cases. This is not always the case when using drug molecules. Different views have been expressed regarding the **drug** distribution across granules of different sizes. Differences in solubility and particle size differences between the filler and **drug** material have been cited as reasons contributing to inhomogeneity (Ojile et al., 1982; Selkirk, 1976). It has also been reported that granulations involving drugs or active ingredients that are finer compared to filler material can result in smaller granules that have higher drug composition compared to the other granules (Egermann and Reiss, 1988). However this could not be used to explain the distribution of MB shown in Fig. 5 because MB was added to the binder solution form during granulation. Previous work has also shown that larger granules have higher binder content compared to the smaller granules (Scott et al., 2000). Therefore one can expect larger granules to have higher composition of MB, since they should contain more binder. It can also be observed from Fig. 5 that the batches produced by HTFB-14 impeller had

the least variation in the MB concentration across all sizes whilst that produced by ST-17 exhibited the largest variation.

The homogeneity coefficient based on samples taken from all sizes was determined to compare the efficacy of mixing by the different impellers; the results are presented in Fig. 6. It is apparent from this figure that HTFB-14 had the largest value of homogeneity coefficient implying that better mixing was achieved using this impeller. ST-17 impeller produced batches which showed the greatest inhomogeneity. This is also supported by the observation that the same batch had the highest presence of oversized granules.

3.4 Effect of impeller design on granule homogeneity

The homogeneity of the granules from the 5 experiments were analysed for three different size ranges; 710-1000 μm , 1000 to 1180 μm and 3350 to 4000 μm in accordance to the method described in section 2.3. The results are presented in Fig. 7 (a). For the granules in the size range 710 to 1000 μm , the concentration of MB is in the range 0.4 to 0.85 ppm. The highest concentration of granules for this case was obtained when using the impeller HTFB-14. The MB concentration of granules in this range was similar for the impellers SSKB-13 and the SSPW-15. Granules obtained using the ST-17 impeller had the least concentration of MB. For the next size class investigated, 1000 to 1180 μm , the concentration of MB ranges from 0.52 to 0.64 ppm. The variability of the MB concentration for this size range across the batches was lower than that for the 710 to 1000 μm size class. The greatest variability in concentration of the MB in the granules across batches was observed for the larger granules (3350 to 4000 μm).

The theoretical average dry concentration of the MB in the granules can be determined from the following equation (Mangwandi et al., 2013c):

$$\bar{C}_{i,theo} = \frac{m_{bin}\tilde{C}_{i,bin}}{m_{bat}} \quad Eq. 8$$

233 In Eq. (8), m_{bin} is the expected mass of binder in the granule, $\tilde{c}_{i,bin}$ is the MB concentration
234 in the binder, m_{bat} is the mass of the wet batch of granules and V is the volume of deionised
235 water used to dissolve 1g of granules during the test.

236 Substituting the correct values of the mass of binder used in the granulation experiment (40
237 g) and the concentration of the MB in the binder solution (20 ppm) and mass of each batch
238 0.20 kg gives a theoretical average concentration of 4 ppm. It is then clear from Fig. 7(a) that
239 all the granules tested in this study had below average concentration of the MB.

240 For most of the impellers, granules with different sizes have significantly different
241 concentration of MB; for the SSD-16 and SSPW-15 impellers, the MB concentration decreased
242 with increasing granule size. When the ST-17 impeller is used, granules in the size range 710 -
243 1000 μm had similar concentration to those in the 3350 μm to 4000 μm range. The granules
244 produced by the impeller HTFB-14 had most similar concentrations of MB. This would give
245 the impression that granulating using an impeller would result in better distribution of the MB
246 across granules of different sizes (see the circle in Fig. 7 (a)). There are previous results in
247 literature describing the binder distribution in high shear granulation and showing that larger
248 granules have higher binder content compared to smaller granules (Osborne et al., 2010;
249 Reynolds et al., 2004; Smith et al., 2010). In another article (Ramachandran et al., 2008), it is
250 reported that granules in the mid-range contain the highest amount of binder compared to the
251 small and large granules. Fig. 7(b) shows the uniformity coefficient of the MB in granules of
252 different sizes produced by different impeller design. The Homogeneity coefficient gives an
253 indication of variability of the MB across each size class. The homogeneity is defined in such a
254 way that a higher value of the coefficient indicates greater variability (less homogeneity) whilst
255 a lower value would indicate better homogeneity (less variability). There is variation in the
256 homogeneity coefficient both across granules made from the same impeller (different sizes)

and also variation across granules of the same size but produced by different impeller. No definite correlation could be identified between the impeller type and the homogeneity coefficient. For the SSKB-13, HTFB-14 and SHD impellers the results show that the homogeneity coefficient is lower for the larger granules compared to the smaller granules. This would imply that there is larger variation in the concentration of MB in the samples taken from larger granules. For the other two impellers the highest value of homogeneity coefficient is obtained from samples of granules of intermediate size.

3.5 Effect of Impeller Design on Granule Strength

Statistical analysis of the five groups of strength data (one from each of the impellers) using Kruskal-Wallis One Way ANOVA analysis showed that differences in the median values among the treatment groups was higher than would be expected from chance; there is a statistical significant difference ($P = 0.004$). This implies that the different impellers produced granules of different strength. However, All Pairwise comparison between the five groups of granules showed that strength data from the SPPW-15 impeller was significantly different from the other four impellers; differences between the other groups was less significant. Summary of the ANOVA analysis results is shown in Fig. 8.

The strength distribution curves of granules produced from the different impeller designs are shown in Fig. 9. It is evident from the figure that the granules from the batch produced by impeller SSPW-15 differed significantly from the rest of the batches and this impeller produced the strongest granules. The variation in the strength results was highest when the SSKB-13 impeller was used and the least variation was obtained when the HFTB impeller was used. Fig. 9 (b) also shows that the largest scatter in the strength data was for granules produced by the impeller SSKB-13.

3.6 Effect of Impeller Design on granule shape

The images shown in Fig. 10 are of granules in the size range 1000 - 1180 μm produced by the different types of impeller. It can be noticed from the images that the granules have irregular shape and rough surfaces irrespective of the type of the impeller. For this particular size range and other size ranges investigated 710 - 1000 μm ; 2000 – 2360 μm and 2800 - 3350 μm , the impeller design does not seem to have an influence on the shape of the structure of the granules formed. **Images of the granules are shown in Fig. 11** This is contrary to earlier work (Schaefer et al., 1993) which reported that impeller design has a slight impact on the granule shape.

The shape of the granules was analysed from images, using the aspect ratio as an indicator of sphericity. The closer the value of the aspect ratio to 1 the less elongated the particle; the further the value from 1, the more elongated is the particle. The average shape factors of granules from different size ranges produced by different impeller are presented in Fig. 12.

It is quite clear from Fig. 12 that, for the granule in the size range 710 - 1000 μm , the type of impeller has no influence on the aspect ratio of the granules. The granules in the size ranges 710 - 1000 μm and 1000 - 1180 μm have similar average aspect ratios. The average values of aspect ratio for the granules in the 2360 - 3350 μm range are higher than those of the smaller granules for all five groups of granules. For all impeller designs, the smaller granules are less elongated than the larger granules.

The effect of the impeller design on granule attributes is summarised in Table 2. The impellers are ranked from 5 to 1, 5 being the best based on maximising that particular granule attribute. It shows which of the impellers to choose if the aim is to maximise the listed attribute. For instance, for maximum granule strength, the SSPW-15 is the one to choose. In terms of better product yield there are two candidates, SSPW-15 and HTFB-14, since the

product yield from these two do not differ significantly. Overall the HTFB impeller has a highest score compared to the other impellers.

4. CONCLUSIONS

It has been shown that the choice of the impeller has an influence on granule size distribution, the granule mean size, and the strength and extent of mixing during granulation. In terms of homogeneity of the pseudo active ingredient, the HTFB impeller outperformed the other impellers. The impeller type does not seem to have a significant influence on the shape of granules formed. For the size range investigated in this work, granules of the highest strength were produced when impeller SSPW-15 was employed whereas the highest granule mean size was obtained with the ST-17. Whilst the different impeller designs performed differently depending which granule property one is looking at, the HTFB-14 seems to be the one to choose if one is looking for an impeller that gives better mixing, good product yield and reasonable granule strength.

REFERENCES

CAMPBELL, G.A., CLANCY, D.J., ZHANG, J.X., GUPTA, M.K., OH, C.K., 2011. CLOSING THE GAP IN SERIES SCALE UP OF HIGH SHEAR WET GRANULATION PROCESS USING IMPELLER POWER AND BLADE DESIGN. *POWDER TECHNOLOGY* 205, 184-192.

CHITU, T.M., OULAHNA, D., HEMATI, M., 2011. WET GRANULATION IN LABORATORY-SCALE HIGH SHEAR MIXERS: EFFECT OF CHOPPER PRESENCE, DESIGN AND IMPELLER SPEED. *POWDER TECHNOLOGY* 206, 34-43.

EGERMANN, H., REISS, W., 1988. EFFECT OF PARTICLE SIZE OF DRUG AND DILUENT ON DRUG DISTRIBUTION IN GRANULE SIZE FRACTIONS. *ACTA PHARMACEUTICAL TECHNOLOGY* 34, 5S.

HIRAMATSU, Y., OKA, Y., 1966. DETERMINATION OF THE TENSILE STRENGTH OF ROCK BY A COMPRESSION TEST OF AN IRREGULAR TEST PIECE.

332 **INTERNATIONAL JOURNAL OF ROCK MECHANICS AND MINING SOCIETY 3,**
333 **89-99.**

334 **JIROUT, T., RIEGER, F., 2011. IMPELLER DESIGN FOR MIXING OF**
335 **SUSPENSIONS. CHEMICAL ENGINEERING RESEARCH AND DESIGN 89, 1144-**
336 **1151.**

337 **JOHANSSON, B., ALDERBORN, G., 2001. THE EFFECT OF SHAPE AND**
338 **POROSITY ON THE COMPRESSION BEHAVIOUR AND TABLET FORMING**
339 **ABILITY OF GRANULAR MATERIALS FORMED FROM MICROCRYSTALLINE**
340 **CELLULOSE. EUROPEAN JOURNAL OF PHARMACEUTICS AND**
341 **BIOPHARMACEUTICS 52, 347-357.**

342 **KACUNIC, A., AKRAP, M., KUZMANIC, N., 2012. EFFECT OF IMPELLER TYPE**
343 **AND POSITION IN A BATCH COOLING CRYSTALLIZER ON THE GROWTH OF**
344 **BORAX DECAHYDRATE CRYSTALS. CHEMICAL ENGINEERING RESEARCH**
345 **AND DESIGN 91, 274-285.**

346 **KHARE, A.S., NIRANJAN, K., 2002. THE EFFECT OF IMPELLER DESIGN ON GAS**
347 **HOLD-UP IN SURFACTANT CONTAINING HIGHLY VISCOUS NON-NEWTONIAN**
348 **AGITATED LIQUIDS. CHEMICAL ENGINEERING AND PROCESSING: PROCESS**
349 **INTENSIFICATION 41, 239-249.**

350 **KNIGHT, P.C., SEVILLE, J.P.K., WELLM, A.B., INSTONE, T., 2001. PREDICTION**
351 **OF IMPELLER TORQUE IN HIGH SHEAR POWDER MIXERS. CHEMICAL**
352 **ENGINEERING SCIENCE 56, 4457-4471.**

353 **KUMARESAN, T., JOSHI, J.B., 2006. EFFECT OF IMPELLER DESIGN ON THE**
354 **FLOW PATTERN AND MIXING IN STIRRED TANKS. CHEMICAL ENGINEERING**
355 **JOURNAL 115, 173-193.**

356 **MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2010. EFFECT**
357 **OF IMPELLER SPEED ON MECHANICAL AND DISSOLUTION PROPERTIES OF**
358 **HIGH-SHEAR GRANULES. CHEMICAL ENGINEERING JOURNAL 164, 305-315.**

359 **MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2011. EFFECT**
360 **OF BATCH SIZE ON MECHANICAL PROPERTIES OF GRANULES IN HIGH**
361 **SHEAR GRANULATION. POWDER TECHNOLOGY 206, 44-52.**

362 **MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2012. AN**
363 **INVESTIGATION OF THE INFLUENCE OF PROCESS AND FORMULATION**
364 **VARIABLES ON MECHANICAL PROPERTIES OF HIGH SHEAR GRANULES**
365 **USING DESIGN OF EXPERIMENT. INTERNATIONAL JOURNAL OF**
366 **PHARMACEUTICS 427, 328-336.**

367 **MANGWANDI, C., ADAMS, M.J., HOUNSLOW, M.J., SALMAN, A.D., 2014.**
368 **INFLUENCE OF FILL FACTOR VARIATION IN HIGH SHEAR GRANULATION**

369 ON THE POST GRANULATION PROCESSES: COMPRESSION AND TABLET
 370 PROPERTIES. POWDER TECHNOLOGY 263, 135-141.

371 MANGWANDI, C., ALBADARIN, A.B., AL-MUHTASEB, A.A.H., ALLEN, S.J.,
 372 WALKER, G.M., 2013A. OPTIMISATION OF HIGH SHEAR GRANULATION OF
 373 MULTICOMPONENT FERTILISER USING RESPONSE SURFACE
 374 METHODOLOGY. POWDER TECHNOLOGY 238, 142-150.

375 MANGWANDI, C., CHEONG, Y.S., ADAMS, M.J., HOUNSLOW, M.J., SALMAN,
 376 A.D., 2007. THE COEFFICIENT OF RESTITUTION OF DIFFERENT
 377 REPRESENTATIVE TYPES OF GRANULES. CHEMICAL ENGINEERING
 378 SCIENCE 62, 437-450.

379 MANGWANDI, C., JIANGTAO, L., ALBADARIN, A.B., ALLEN, S.J., WALKER,
 380 G.M., 2013B. ALTERNATIVE METHOD FOR PRODUCING ORGANIC FERTILISER
 381 FROM ANAEROBIC DIGESTION LIQUOR AND LIMESTONE POWDER: HIGH
 382 SHEAR WET GRANULATION. POWDER TECHNOLOGY 233, 245-254.

383 MANGWANDI, C., JIANGTAO, L., ALBADARIN, A.B., ALLEN, S.J., WALKER,
 384 G.M., 2013C. THE VARIABILITY IN NUTRIENT COMPOSITION OF ANAEROBIC
 385 DIGESTATE GRANULES PRODUCED FROM HIGH SHEAR GRANULATION.
 386 WASTE MANAGEMENT 33, 33-42.

387 MANGWANDI, C., ZAINAL, N.A., JIANGTAO, L., GLOCHEUX, Y., ALBADARIN,
 388 A.B., 2015. INVESTIGATION OF INFLUENCE OF PROCESS VARIABLES ON
 389 MECHANICAL STRENGTH, SIZE AND HOMOGENEITY OF PHARMACEUTICAL
 390 GRANULES PRODUCED BY FLUIDISED HOT MELT GRANULATION. POWDER
 391 TECHNOLOGY 272, 173-180.

392 NIKLASSON, B.I., JANSSON, A., KARLSSON, M., FOLESTAD, S., RASMUSON, A.,
 393 2005. EMPIRICAL TO MECHANISTIC MODELLING IN HIGH SHEAR
 394 GRANULATION. CHEMICAL ENGINEERING SCIENCE 60, 3795-3803.

395 OJILE, J.E., MACFARLANE, C.B., SELKIRK, A.B., 1982. DRUG DISTRIBUTION
 396 DURING MASSING AND ITS EFFECT ON DOSE UNIFORMITY IN GRANULES.
 397 INTERNATIONAL JOURNAL OF PHARMACEUTICS 10, 99-107.

398 OSBORNE, J.D., SOCHON, R.P.J., CARTWRIGHT, J.J., DOUGHTY, D.G.,
 399 HOUNSLOW, M.J., SALMAN, A.D., 2010. BINDER ADDITION METHODS AND
 400 BINDER DISTRIBUTION IN HIGH SHEAR AND FLUIDISED BED GRANULATION.
 401 CHEMICAL ENGINEERING RESEARCH AND DESIGN 89, 553-559.

402 RAMACHANDRAN, R., POON, J.M.H., SANDERS, C.F.W., GLASER, T.,
 403 IMMANUEL, C.D., DOYLE III, F.J., LITSTER, J.D., STEPANEK, F., WANG, F.-Y.,
 404 CAMERON, I.T., 2008. EXPERIMENTAL STUDIES ON DISTRIBUTIONS OF
 405 GRANULE SIZE, BINDER CONTENT AND POROSITY IN BATCH DRUM

GRANULATION: INFERENCES ON PROCESS MODELLING REQUIREMENTS AND PROCESS SENSITIVITIES. POWDER TECHNOLOGY 188, 89-101.

REYNOLDS, G.K., BIGGS, C.A., SALMAN, A.D., HOUNSLOW, M.J., 2004. NON-UNIFORMITY OF BINDER DISTRIBUTION IN HIGH-SHEAR GRANULATION. POWDER TECHNOLOGY 140, 203-208.

SCHAEFER, T., TAAGEGAARD, B., THOMSEN, L.J., GJELSTRUP KRISTENSEN, H., 1993. MELT PELLETIZATION IN A HIGH SHEAR MIXER. V. EFFECTS OF APPARATUS VARIABLES. EUROPEAN JOURNAL OF PHARMACEUTICAL SCIENCES 1, 133-141.

SCOTT, A.C., HOUNSLOW, M.J., INSTONE, T., 2000. DIRECT EVIDENCE OF HETEROGENEITY DURING HIGH-SHEAR GRANULATION. POWDER TECHNOLOGY 113, 205-213.

SELKIRK, A.B., 1976. THE EFFECT OF SOLUTE MIGRATION ON THE DISTRIBUTION OF BORAX THROUGHOUT A BATCH OF GRANULES. JOURNAL OF PHARMACY AND PHARMACOLOGY 28, 512-514.

SHIRAISHI, T., KONDO, S., YUASA, H., KANAYA, Y., 1994. STUDIES ON THE GRANULATION PROCESS OF GRANULES FOR TABLETING WITH A HIGH SPEED MIXED. I. PHYSICAL PROPERTIES OF GRANULES FOR TABLETING. CHEMICAL AND PHARMACEUTICAL BULLETIN 42, 932-936.

SMITH, R.M., LIU, L.X., LITSTER, J.D., 2010. BREAKAGE OF DROP NUCLEATED GRANULES IN A BREAKAGE ONLY HIGH SHEAR MIXER. CHEMICAL ENGINEERING SCIENCE 65, 5651-5657.

SUMMERS, M., AULTON, M.E., 1988. GRANULATION, IN: AULTON, M.E. (ED.), PHARMACEUTICS: THE SCIENCE OF DOSAGE FORM DESIGN, 7TH ED. CHURCHILL LIVINGSTONE.

VOINOVICH, D., CAMPISI, B., MONEGHINI, M., VINCENZI, C., PHAN-TAN-LUU, R., 1999. SCREENING OF HIGH SHEAR MIXER MELT GRANULATION PROCESS VARIABLES USING AN ASYMMETRICAL FACTORIAL DESIGN. INTERNATIONAL JOURNAL OF PHARMACEUTICS 190, 73-81.

438 **NOMENCLATURE**

$\bar{c}$,	Concentration of [ppm]
$\bar{d}$	Average granules size[mm]
D	Granule diameter (mm)
F	Force [N]
m	mass [g]
n	Number of samples analysed [-]
V	Volume of dissolution medium [ml]
S	Standard deviation of the methylene blue concentration [ppm]
x	Arithmetic average size of the granules in the range[mm]

439

440 **Greek letters**

η	Homogeneity coefficient [-]
κ	Average granules size[mm]
σ	Granule strength [Nmm^{-2} or MPa]
Ψ	Product yield [%]

441

442 **Subscripts**

bat	batch
bin	binder
exp	Experimental value
f	failure
i	Sample index
MB	Methylene blue
p	powder
pro	product
s	sample
$theo$	Theoretical value

443

444 **Abbreviation**

API	Active Pharmaceutical
HTFB	High Temperature Flexible Beater
MB	Methylene blue
SDH	Spiral Dough Hook
SSKB	Stainless Steel K Beater
SSPW	Stainless Steel Power Whisk
ST	Stirring Tool
XRD	X Ray Diffraction

445

446 **Table 1: Summary of process and granulation parameters.**

Experiment No.	Impeller type	Impeller speed (rpm)	Granulation Time (min)	Mass of lactose Powder	Binder	Liquid to solid Ratio
1	HTFB-14	160	4	200	water	0.2
2	HTFB-14	160	4	200	Water + MB	0.2
3	SSKB-13	160	4	200	Water + MB	0.2
4	SSPW-15	160	4	200	Water + MB	0.2
5	SDH-16	160	4	200	Water + MB	0.2
6	ST-17	160	4	200	Water + MB	0.2

447

448

449 **Table 2: Comparison of the strength of granules produced from different binders. N.B. Errors indicate**
450 **Standard error in the mean**

Binder	Impeller Type	Granule Strength (MPa)
Water	HTFB-14	0.60 ± 0.06
Water + MB	HTFB-14	0.65 ± 0.08

451

452

453

454 **Table 3: Summary of effect of impeller design on granule attributes.**

Impeller type	Product Yield	Homogeneity	Granule Strength	Granule Mean Size
SSKB-13	2	2	2	4
HTFB-14	5	5	3	2
SSPW-15	4	4	5	1
SDH-16	3	3	4	3
ST-17	1	1	1	5

455

456

457

458

459

460

461

462

Fig. 1: Images of the different impeller designs used in the granulation experiments (a) Stainless steel power whisk (SSPW-15) b) Spiral Dough Hook (SDH-16) c) Stirring Tool (ST-17) d) High Temperature Flexible Beater (HTFB-14) e) Stainless Steel K Beater (SSKB-13)

463

464

465 **Fig. 2: XRD patterns of samples alpha lactose, granulated lactose from water and water-methylene blue**
466 **solution.**

467

468

Fig. 3: Comparison of size distributions of batch of granules produced using water and MB solution binders.

Fig. 4: (a) Typical cumulative granule size distribution plots for experiments 2 to 6. (b) Granule mass mean size as a function of impeller type (c) mass distribution of the granules between fines, product and oversized granules. N.B The plots are average of three replicate experiments.

Fig. 5: The variation of MB concentration with size class for batches of granules produced with different impeller designs.

Fig. 6: Variation of homogeneity coefficient across different sizes for batches produced with different impellers.

488

489

490

491

492

493

494

Fig. 7: (a) Methylene blue concentration of granules from different sieve fractions (b) Variation of the granules' homogeneity coefficient with impeller design.

Data source: Data 2 in Notebook1

Group	N	Missing	Median	25%	75%
SSKB-13	25	0	0.686	0.418	0.896
HTFB-14	25	0	0.571	0.344	0.994
SSPW-15	25	0	0.998	0.679	1.563
SDD-16	25	0	0.621	0.350	0.870
ST-17	25	0	0.492	0.321	0.655

H = 15.242 with 4 degrees of freedom. (P = 0.004)

The differences in the median values among the treatment groups are greater than would be expected by chance; there is a statistically significant difference (P = 0.004)

To isolate the group or groups that differ from the others use a multiple comparison procedure.

All Pairwise Multiple Comparison Procedures (Student-Newman-Keuls Method) :

Comparison	Diff of Ranks	q	P<0.05
SSPW-15 vs ST-17	928.000	5.123	Yes
SSPW-15 vs HTFB-14	759.000	5.232	Yes
SSPW-15 vs SDD-16	683.000	6.268	Yes
SSPW-15 vs SSKB-13	620.000	8.506	Yes
SSKB-13 vs ST-17	308.000	2.123	No
SSKB-13 vs HTFB-14	139.000	1.276	Do Not Test
SSKB-13 vs SDD-16	63.000	0.864	Do Not Test
SDD-16 vs ST-17	245.000	2.248	Do Not Test
SDD-16 vs HTFB-14	76.000	1.043	Do Not Test
HTFB-14 vs ST-17	169.000	2.319	Do Not Test

Fig. 8: Statistical analysis of the granule strength data from batches produce with different impellers.

500

501

502

503

504

Fig. 9: Effect of impeller type on the strength of the granules.

(a) HTFB-13

(b) HTFB-14

(c) SSPW-15

(d)- SDD-16

(e) ST-17

Fig. 10: Images showing the shape and structure of the granules from different batches produced using different impellers.

0.71 mm

1.0 mm

2.0 mm

3.35 mm

Fig. 11: Images showing the shape and structure of the granules of different sizes from the same batch

Fig. 12: Effect of impeller design on the aspect ratio of granules of different sizes.