Deoxygenation in anisole decomposition over bimetallic catalysts supported on HZSM-5

Zhang, J., Fidalgo, B., Wagland, S., Shen, D., Zhang, X., & Gu, S. (2019). Deoxygenation in anisole decomposition over bimetallic catalysts supported on HZSM-5. *Fuel*, 238, 257-266.
<https://doi.org/10.1016/j.fuel.2018.10.129>

Published in:
Fuel

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

Copyright 2018 Elsevier.

This manuscript is distributed under a Creative Commons Attribution-NonCommercial-NoDerivs License (<https://creativecommons.org/licenses/by-nc-nd/4.0/>), which permits distribution and reproduction for non-commercial purposes, provided the author and source are cited.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

Deoxygenation in anisole decomposition over bimetallic catalysts supported on HZSM-5

Jiajun Zhang^{a, b, c}, Beatriz Fidalgo^c, Stuart Wagland^c, Dekui Shen^{a,*}, Xiaolei Zhang^{b,*},
Sai Gu^d

* Corresponding author: D.S., e-mail address: 101011398@seu.edu.cn

X.Z., email address: xiaolei.zhang@qub.ac.uk

^a Key Laboratory of Energy Thermal Conversion and Control of Ministry of Education,
Southeast University, Nanjing, China

^b School of Mechanical and Aerospace Engineering, Queen's University Belfast,
Belfast, United Kingdom

^c School of Water, Energy and Environment, Cranfield University, Cranfield, United
Kingdom

^d Faculty of Engineering and Physical Sciences, University of Surrey, Surrey, United
Kingdom

Abstract:

This work investigated the deoxygenation reaction in anisole decomposition over HZSM-5 (HZ(25)) zeolite supported bimetallic catalysts to produce benzene, toluene and xylene (BTX). Experiments were performed in order to evaluate the synergistic effect between the two active metals with the focus on the effect of temperature, metal type, and metal loading ratio. Experimental results showed that 1%Ni-1%Mo/HZ(25) led to both the highest BTX yield (i.e. 30.0 wt.%) and selectivity (i.e. 83.7%). On the contrary, bimetallic catalysts containing Fe were less effective in promoting the BTX production. It was identified that the optimum temperature for BTX production over

1%Ni-1%Mo/HZ(25) catalysts was 500°C. Characterization of fresh and spent catalysts showed microcrystal particles of bi-metal loadings highly dispersed on the zeolite surface, and some agglomeration of metallic particles were also observed. Large amount of carbonaceous deposit was observed on the spent catalysts mainly in the form of amorphous. Density Functional Theory (DFT) modelling was carried out in order to study the adsorption energy of anisole and phenol molecules onto Ni-Mo, Ni-Fe and Mo-Fe surfaces; and the interactions between phenol molecule and bimetal surfaces were further analysed. All the analysed bimetal surfaces exhibited strong interactions with the adsorbed molecule. Ni-Mo surface declined electrons energy levels mainly around 1.5 eV in the adsorbate molecule and released the highest adsorption energy; while Ni-Fe and Mo-Fe surface led to more electrons exchange with the adsorbate during the adsorption. The modelling results agreed well with experiments by revealing that the strong binding between phenolic compounds (Phs) and the Ni-Mo based catalysts bimetal surface would lead to a higher BTX production in the deoxygenation reaction in the decomposition of anisole.

Abbreviations: BTX, benzene, toluene and xylene; Phs, phenolic compounds; AHs, aromatic hydrocarbons; PAHs, polycyclic aromatic hydrocarbons

Key words: lignin; catalytic decomposition; deoxygenation; anisole; bimetallic supported catalyst; phenolic compounds

1. Introduction

In the context of the bio-based economy, lignin is a major source of aromatic compounds [1–3]. Fast pyrolysis of lignin followed by bio-oil upgrading is a promising route for retrieving aromatic hydrocarbons (AHs) for further application as fuels and fuel additives [4–6]. Methoxy compounds abundantly exist in primary liquid products

derived from fast pyrolysis of lignin, and the catalytic deoxygenation is favourable for their upgrading into AHs compounds [7]. Anisole (or methoxybenzene) is typically used as model compound of the methoxyl-based lignin-derived compounds, since the methoxy functionality is the only one present in the molecule [8]. The decomposition of anisole is a two-step process which consists of transmethylation and deoxygenation reactions [9–11]. The first step, transmethylation, primarily yields methyl-containing phenolics (Phs) and subsequently aids the formation of AHs [12–16]. During the deoxygenation step, the Phs further react to produce AHs, naphthenic hydrocarbons and even cycloalkanes [9–11]. Catalysts consisting of active metals dispersed on a solid support have showed favourable catalytic activity on the fast pyrolysis of lignin and the upgrading of the derived bio-oil for the production of AHs [11,17,18]. It has been identified that acid zeolite (i.e. HBeta, HZSM-5 etc.) is the most widely investigated support, although other supports have also been studied including metal oxides (i.e. SiO_2 , Al_2O_3 etc.) and carbon nanofibers [19–23]. Transition metals have exhibited high catalytic active for the reforming process [19,24–26].

Deoxygenation during the catalytic decomposition of anisole has been largely investigated over single noble metal catalyst supported on an inert solid [19,22,27–30]. The reaction over bi-functional catalysts, i.e. a base metal and an acid solid support, has been paid less attention. The literature on the deoxygenation over bi-functional catalysts with two metals deposited on an acid solid support is even scarcer. However, acid solid supported bimetallic catalysts are of great interest to be applied to the catalytic reforming of bio-oil. This is because the second metal can act as a promoter in the catalyst simultaneously favouring for the yield and selectivity of desired products, and impeding the polycondensation reactions of the aromatics [31]. Significant research on the activity of these catalysts in deoxygenation reaction during the catalytic

decomposition of model compounds, such as anisole, is required in order to properly assess the effect on lignin-derived bio-oil.

This work aims to investigate the deoxygenation reaction in the decomposition of anisole over zeolite supported bimetallic catalysts for the production of the BTX fraction (benzene, toluene, and xylene). Our previous study has reported the excellent performance of 1%Ni/HZ(25) and 1%Mo/HZ(25) in the decomposition of anisole [32], besides, our modelling work also revealed that Ni and Mo led to high adsorption energy in anisole adsorption, and Fe resulted in a low energy adsorption [33]. In this study, combinations of Ni, Mo and Fe active metal sites were evaluated. Based on previous experimental work, severe carbonaceous deposit was observed over Ni and Mo based catalysts [32]. Fe is used in this study to tune the strong adsorption of catalysts and alleviate the severe deposit, so the loading ratio of Fe is kept the same as Ni and Mo. Anisole decomposition experiments were run in a fluidized bed reactor to evaluate the effect of temperature, type of bimetallic catalyst, and metal loading ratio on the BTX yield and selectivity. Finally, DFT modelling was carried out to reveal effects of alloy loadings on the decomposition of reactants in microscopic scale by analysing the interaction of reactant molecules and bimetallic surfaces.

2. Materials and methods

2.1. Materials

Anisole was supplied by Aladdin Reagents Co., Ltd. The HZSM-5 (Si/Al=25, HZ(25)) zeolite catalyst was provided by Nankai University Catalyst Co., Ltd, China. Chemicals used for the synthesis of the catalysts, i.e. nickel nitrite hexahydrate ($\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$), ammonium molybdate tetrahydrate ($(\text{NH}_4)_6\text{Mo}_7\text{O}_{24} \cdot 4\text{H}_2\text{O}$), iron nitrate nonahydrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$) and citric acid, were supplied by Aladdin Reagents Co., Ltd. The chemicals used for calibration in GC-MS were supplied by Aladdin Reagents Co., Ltd.

Analytical purity chemicals were used. Standard gaseous species, N_2 , and H_2 used for the calibration and operation of GC-FID were supplied by Nanjing Shangyuan Industrial Gas Plant at a purity of 99.999 %.

2.2. Methods

2.2.1. Catalyst preparation and characterisation

Bimetallic catalysts were synthesized by wet impregnation of the support, HZ(25), with aqueous solutions of the metal precursor, i.e. $Ni(NO_3)_2 \cdot 6H_2O$, $(NH_4)_6Mo_7O_{24} \cdot 4H_2O$ or $Fe(NO_3)_3 \cdot 9H_2O$ depending on the targeted active metal (see Supplementary Material S1 for full details). It is worth mentioning that citric acid (~20 g) was used for dissolving the precursors of Mo-Fe due to its ability to ligate the metals and inhibit precipitate formation [34]. The impregnation mixtures were stirred with a magnetic stirrer for 24 h at room temperature (~25 °C). Water was removed by evaporation at 80 °C and dried at 110 °C for 12 h, followed by calcination in air at 500°C for 6 h in a muffle furnace. The calcined catalyst precursors were subsequently crushed and sieved to a particle size range between 60-80 mesh. The catalysts were reduced in-situ with 25 vol.% H_2/N_2 (total flow rate of 500 mL/min) for 2 h before the experiments. Reduction temperature was 600°C in the case of Ni-Fe/HZ(25) catalyst [35,36], and 800°C for both Ni-Mo/HZ(25) and Mo-Fe/HZ(25) [37–39]. Zeolite supported bimetallic catalysts with various metal loadings were prepared. They were denoted as x%M-y%N/HZ(25), where M (= Ni or Mo) and N (= Mo or Fe) are the active metals, x is the loading ratio of M, and y is the loading ratio of N. The following catalysts supported on HZ(25) were synthesized and tested: 0.5%Ni-1%Mo, 1%Ni-1%Mo, 1%Ni-0.5Mo%, 1%Ni-1%Fe and 1%Mo-1%Fe.

Both fresh (reduced) and spent bimetal/HZ(25) catalysts were analyzed by TEM-EDS in order to investigate the morphology of metal active sites and carbonaceous deposits on the zeolite support, and to determine the existing elements on the sample surface.

The specimens were prepared by ultrasonic dispersion of catalyst samples in ethanol before dropping the suspension to a copper/nickel grid. A TEM Tecnai G2 T20 from FEI Ltd was used for the analyses of catalyst sample. Images of the microstructure, the relevant selected area electron diffraction (SAED) patterns, and Fast Fourier Transform (FFT) images of the specimens were acquired. Energy Dispersive Spectrometer (EDS) tests were performed using Genesis 2000 from EDAX Ltd.

2.2.2. Experiment

Experiments were carried out in the bench scale fluidised bed reactor (Diameter*Height mm = 32mm×600mm); further details of the rig can be found in literature [10,32]. Nitrogen was used as fluidising gas. The minimum fluidisation velocity (U_{mf}) was 0.027m/s in all experiments, and it was determined as described in literature [40]. The actual experimental flow velocity was adjusted by means of cold experiments, and set to approximately two times the U_{mf} .

In each experiment, 50 g of fresh catalyst were placed inside the reactor and fluidised by a N₂ flow rate of 154 L/h. A total amount of 8.3 g of liquid anisole was placed in a syringe pump at the beginning of the experiment and pumped into the reactor at a constant flow rate. Anisole flow rate and reaction time were 50 g/h and 10 min, respectively. The outflow stream was passed through a three stages quench traps to collect the liquid product. The effect of type of bimetal active sites was investigated by experiments carried out over 1%Ni-1%Mo/HZ(25), 1%Ni-1%Fe/HZ(25), 1%Mo-1%Fe/HZ(25) at 500°C. Experiments over 1%Ni-1%Mo/HZ(25) at 400 °C, 500 °C and 600 °C were performed in order to evaluate the effect of temperature. The effect of the bimetal loadings was investigated by the experiments carried out over 1%Ni-1%Mo/HZ(25), 1%Ni-0.5%Mo/HZ(25) and 0.5%Ni-1%Mo/HZ(25) at 500°C. Details of the operating conditions for each experiment are given in Table 1.

After diluting to a constant volume of 150 mL, the collected liquid fraction was analysed by GC-MS in an Agilent GC7890 gas chromatograph-mass spectrometer equipped with a capillary column DB-5ms (30 m x 250 μ m x 0.25 μ m). The injector temperature was 270°C. The oven temperature was increased from 40 °C (held for 3 min) to 180 °C (held for 2 min) at a heating rate of 5 °C/min, and then heated at a rate of 10°C/min up to 280°C and held for 2 min. The running time for each GC-MS analysis was 45 min. The mass spectrometer was operated in electron ionization (EI) mode at 70 eV and the spectra were obtained from m/z 35-550. The column was calibrated with external standards, and the products were quantified by total ion and identified using the database of NIST library database. The amount of carbonaceous deposits on the spent catalyst was determined by thermogravimetric analysis with a SETSYS-1750 CS Evolution TG Instrument. Approximately 15 mg of sample were charged and heated from room temperature (~25°C) up to 900°C at a heating rate of 20 °C/min and air flow rate of 20 mL/min. The sample was kept at 900°C for 15 min to ensure total burn-out of the carbonaceous deposits. Non-condensable gaseous products were analysed in a GC-FID equipped with a SE54 column. 1 μ L of gas sample was injected into the injector kept at 270°C. Helium at a flow rate of 6.3 mL/min was used as carrier gas. The initial column temperature was 40°C (equilibration time of 2 min), and the maximum temperature was 300°C. Total analysis time was 45 min. The mass of liquid fraction, carbon deposit fraction and gas fraction were determined after each experiment. The liquid, carbon deposits and gas yields were determined as a percentage of the initial mass of anisole. The standard deviation of the liquid and carbonaceous deposit yields were evaluated by the repeating experiments; further details are provided in Supplementary Material S2. Based on the analyses, bulk difference over 1wt.% for liquid yields and over 4wt.% for solid yields were mainly considered in this study.

2.2.3.DFT Modelling

The first-principle density functional theory plus dispersion (DFT-D) calculations were implemented in the DMol³ module available in Materials Studio 2016 from BIOVIA [41,42]. The double numerical plus polarization (DNP) basis set was used to calculate the valence orbital of all the atoms, including a polarization p-function on all hydrogen atoms. The numerical basis sets in DMol³ was utilised because they minimize or even eliminate basis set superposition error (BSSE), contrary to Gaussian basis sets, in which BSSE can be a serious problem [43,44]. The generalized gradient corrected approximation (GGA) [45] treated by the Perdew–Burke–Ernzerhof (PBE) exchange-correlation potential with long-range dispersion correction via Grimme's scheme was used for the calculations [46]. The self-consistent field (SCF) procedure was used with a convergence threshold of 10^{-6} au on the energy and electron density. Geometry optimizations were performed with a convergence threshold of 0.002 Ha/Å on the gradient, 0.005 Å on displacements, and 10^{-5} Ha on the energy. The real-space global cut-off radius was set to 5 Å. No symmetry constraints were used for any cluster models. All the adsorbent models were based on doped slabs of bimetal crystals. Moreover, the models exclude the zeolite support in order to avoid its influence and solely investigate the effect of the bimetals. Pre-adsorption and post-adsorption models were established for the adsorption of anisole and phenol molecules, as two of the most frequent compounds interacting with the metal surface during the anisole decomposition. Adsorbates were placed paralleled to the adsorbent as shown in Supplementary Material S12 to S14. Geometry optimization was implemented to every model before energy was calculated. The adsorption energy was determined by the energy difference of the system before and after the adsorption process. All the energies were calculated at 0 K in the modelling. More detailed analyses of the

interactions between phenol and the bimetal surfaces were carried out, since Phs are the actual reactants in the deoxygenation reaction.

3. Results and discussion

3.1 Effect of the type of metal combination on deoxygenation reaction over bimetal/HZ(25) catalysts

Experiments with 1%Ni-1%Mo/HZ(25), 1%Ni-1%Fe/HZ(25) and 1%Mo-1%Fe/HZ(25) catalysts were carried out at 500°C (experiments DO2, DO6 and DO7 respectively in Table 1) to investigate the effect of the bimetal type on the deoxygenation stage of the decomposition of anisole. The anisole conversion and grouped yields of liquid, gas and solid (carbonaceous deposits) products are shown in Table 1. Anisole conversion was 100% for the three experiments. The products mainly consisted of liquids and carbonaceous deposits, with the gas fraction being negligible. These gas products primarily contained alkanes and olefins, as shown in Supplementary Material S8. Regardless the bimetal catalyst used, similar yields of the liquid products (ranging from 34.5 wt.% to 38.7 wt.%) and the carbonaceous deposits (ranging from 61.0 wt.% to 63.9 wt.%) were obtained.

The effect of the type bimetal/HZ(25) catalysts on the liquid product distribution obtained from the deoxygenation reaction in the anisole decomposition process is shown in Fig. 1. Liquid products comprised AHs and Phs. In all cases, AHs mainly consisted of the BTX fraction, and Phs primarily included phenol and cresols, in agreement with previously reported results [47]. The bimetal Ni-Mo (experiment DO2) gave rise to high AHs yield and BTX selectivity, i.e. 33 wt.% and 83.7 wt.% respectively; with only 2.8 wt.% of the liquid products being Phs. The combination Ni-Fe (experiment DO6) led to both the lowest AHs yield and BTX yield and selectivity (27.4, 24.3 and 70.3 wt.% respectively). On the contrary, the highest Phs yield of 7.1 wt.%, mainly

227 composed of phenol, was obtained from DO6. The bimetal Mo-Fe yielded the highest
228 amount of AHs (33.9 wt.%). However, it showed a BTX selectivity of 78.9 wt.%, lower
229 than that obtained over Ni-Mo.

230 Table 1 Conversion, product recovery and product yields (in wt.% of reactant) from anisole decomposition x%M-y%N/HZ(25).

No.	Bimetal /HZ(25)	T (°C)	Conversion (%)	Product recovery (%)	Liquid products					Gas yield	Solid yield
					Liquid yield				BTX selectivity (%) ^a		
					Total	Phs	AHs	BTX ^d			
T2 ^b	HZ(25)	500	100.0	n.d.	41.2	10.0	31.2	23.6	57.1	n.d.	42.0
D2 ^b	1%Ni	500	100.0	99.4	31.3	2.4	28.8	25.6	81.9	0.2	68.0
D7 ^b	1%Mo	500	100.0	100.0	38.8	3.6	35.2	30.0	77.4	0.5	60.7
DO1	1%Ni-1%Mo	400	99.6	100.0	38.8 ^c	32.7	5.8	4.7	12.3	0.0	61.1
DO2		500		99.8	35.8	2.8	33.0	30.0	83.7	0.1	63.9
DO3		600		98.0	21.0	0.0	21.0	20.5	97.5	0.3	76.7
DO4	1%Ni-0.5%Mo	500	100.0	97.7	31.6	2.8	28.8	25.4	80.3	0.1	66.0
DO5	0.5%Ni-1%Mo	500		100.3	33.5	3.6	29.9	26.0	77.6	0.1	66.7
DO6	1%Ni-1%Fe	500		97.6	34.5	7.1	27.4	24.3	70.3	0.3	62.8
DO7	1%Mo-1%Fe	500		100.0	38.7	4.7	33.9	30.5	78.9	0.4	61.0

231 ^a Selectivity calculated with respect to the total liquid yield, included unreacted anisole; ^b data is derived from reference [10,32]; ^c The value considers
232 unreacted anisole. ^d The individual selectivity of benzene, toluene and xylene of the experiments in this study is specified in Supplementary Material S3.

233

Our research group has recently reported the conversion of anisole over non-metal HZSM-5 zeolite [10]. Compared to the results previously reported, both the yield and selectivity of BTX have been enhanced by the addition of the bimetallic sites (on average by 20% and 36% respectively) [10,32]. The improvement is attributed to an increment in the conversion of Phs towards BTX, and indicates that the studied supported bimetallic catalysts may promote the deoxygenation of Phs. Our research group has also investigated the anisole decomposition over single metal loaded HZSM-5 [32]. In that work, 1%Ni/HZ(25) was observed to give rise to very high BTX selectivity (81.9 %), while 1%Mo/HZ(25) gave rise to higher yield of BTX yield (30.0 wt.%) but lower selectivity (77.4 %). When comparing to the liquid product yields obtained over 1%Ni-1%Mo/HZ(25), it is observed that the bimetallic catalyst seemed to retain both the high BTX yield achieved over 1%Mo/HZ(25), and the high BTX selectivity obtained from 1%Ni/HZ(25). The improvement in the yield and selectivity of BTX is related to the lower formation of carbonaceous deposit compared to the case of 1%Ni/HZ(25) (63.9 wt.% vs. 68.0 wt.%), and the lower PAH yield compared to the case of 1%Mo/HZ(25) (3.05 wt.% vs. 5.22 wt.%). This result confirms the hypothesis that the combination of Ni and Mo active sites as a HZ(25) supported bimetallic catalyst promotes a synergetic effect on the catalytic activity for the deoxygenation stage of the decomposition of anisole.

Fig. 1 Influence of the type of bimetal/HZ(25) catalysts on the liquid product yields obtained from anisole decomposition. Reaction temperature = 500°C

Compared to 1%Ni/HZ(25) [32], the combination of 1%Ni-1%Fe/HZ(25) resulted in a decrease in carbonaceous deposits. This result implies that Fe may moderate the deactivation of the catalyst by alleviate the polycondensation reactions over catalyst surface [48]. However, the BTX yield and selectivity were also reduced because of the lower conversion of Phs. Compared to 1%Mo/HZ(25) [32], the combination of 1%Mo-1%Fe/HZ(25) showed negligible impact on BTX yield and carbonaceous deposit yield, and a slight increase in BTX selectivity. The results suggest that the addition of Fe sites to the catalyst restrict the catalytic activity of Ni site and have almost no improvement on the catalytic activity of Mo sites. Therefore, among the three bimetallic catalyst supported on zeolite, 1%Ni-1%Mo exhibited better catalytic activity towards the production of BTX, giving rise to both higher yield and selectivity. Consequently, this bimetallic catalyst was selected for further investigation of the effect of temperature and metal loadings.

3.2 Effect of temperature on deoxygenation reaction over bimetal/HZ(25) catalysts

Anisole decomposition over the 1%Ni-1%Mo/HZ(25) catalyst was performed at 400, 500, and 600 °C (DO1, DO2, and DO3 in Table 1, respectively) to investigate the effect of temperature on the deoxygenation stage. Total conversion of anisole was achieved at all temperatures, with the liquid and carbonaceous deposits being the main products at this temperature range. The total liquid product yield decreased significantly with temperature from 38.4 wt.% (excluding undecomposed anisole) at 400°C to 21.0 wt.% at 600°C. On the contrary, the yield of carbonaceous deposits increased correspondingly from 61.1 wt.% at 400°C to 76.7 wt.% at 600°C. Trace gas products were produced (further details are shown in Supplementary Material S8).

The change in the liquid product distribution with temperature is shown in Fig. 2. At 400°C, Phs were the main compounds in the liquid fraction; they accounted for 32.7 wt.% of the total products and consisted mainly of phenol, ortho-cresol and para-cresol. The AHs fraction only constituted 5.8 wt.% of the total products, and mainly contained BTX (over 80 wt.% of the AHs), and naphthalene and its derivatives. On the contrary, the Phs yield was 2.8 wt.% and the AHs yield was 33.0 wt.% of the total product at 500°C. The liquid fraction contained 83.7% of BTX. At 600°C, no Phs were detected, and the AHs yield was 21.0 wt.%. Despite the decrease in the total AHs fraction compared to that at 500°C, the BTX fraction increased up to a selectivity of 97.5%, with benzene being the main product. The results point that the transmethylation reaction primarily occurred at 400°C, and the deoxygenation reaction occurred at 500°C and higher. This confirms that the “transition temperature”(at which the transition from prevalence of transmethylation to prevalence of deoxygenation happens) in the decomposition of anisole over the bimetallic based catalysts is the same as that

294 observed in the decomposition over the sole HZ(25) [10] and single metal/HZ(25) [32]
295 catalysts.

296
297 Fig. 2 Influence of temperature on the liquid product yields obtained from anisole
298 decomposition over 1%Ni-1%Mo/HZ(25)

299 The results in Table 1 show that an increase in temperature from 400°C to 600°C
300 enhanced carbonaceous deposition, with a simultaneous reduction in the liquid
301 products. The effect of temperature on the distribution of liquid products is also
302 noticeable, as shown in Fig. 2. The increase in temperature from 400 to 500°C resulted
303 in a rapid decrease of Phs, since they are intermediate compounds in the anisole
304 decomposition and are consumed by deoxygenation and polycondensation reactions at
305 higher temperatures [29,32]. Indeed, no Phs were detected at 600°C. Similar results
306 were obtained over single metal catalyst supported on zeolite and reported by our
307 research group [32]. From 500 to 600°C, a preferential decrease in polycyclic aromatic
308 hydrocarbons (PAHs) was observed, simultaneously contributing to a decrease of the

AHs yield of around 12 wt.% and an increase in BTX selectivity of approximately 14%. These results suggest that, at higher temperatures, PAHs were involved in polycondensation reactions to form carbonaceous deposits [32]. The occurrence of these polycondensation reactions resulted in more than 76 wt.% of carbonaceous deposit at expense of the liquid yield, while simultaneously releasing hydrogen. Considering the BTX yield and selectivity values obtained at different temperatures over 1%Ni-1%Mo/HZ(25), the temperature of 500°C is regarded as a fair compromise for optimum operating temperature as high Phs conversion is achieved while polycondensation is moderate.

3.3 Effect of metal loading on deoxygenation reaction over bimetal/HZ(25) catalysts

Experiments of anisole decomposition over the catalysts of 1%Ni-1%Mo/HZ(25) (DO2), 1%Ni-0.5%Mo/HZ/25 (DO4) and 0.5Ni-1%Mo/HZ(25) (DO5) at 500°C to investigate the effect of metal loading ratio on the deoxygenation reaction. As shown in Table 1, anisole was completely converted in all the cases, and rather similar product yields were obtained over the three catalysts (from 63.9 wt.% to 66.7 wt.% for carbonaceous deposits, and from 31.6 wt.% to 35.8 wt.% for liquid products). Gaseous products were negligible (as shown in Supplementary Material S8). The influence of the metal loading on the liquid product distribution is depicted in Fig. 3.

The composition of liquid fraction exhibited little variation for the three experiments, and mainly consisted of BTX, phenol, cresols, naphthalene, methyl naphthalene and trace of phenanthrene. The highest yields of AHs and BTX were obtained over 1%Ni-1%Mo/HZ(25) (experiment DO2). The decrease in the Mo loading from 1 to 0.5 wt.% (experiment DO4) resulted in the decrease of around 4.5 wt.% for both AHs and BTX yields, while no change was observed in the yield of Phs. It was also observed that

BTX selectivity only had a slight decrease when the Mo loading was reduced. This implies that a loading of 0.5 wt.% Mo may still exhibit good synergistic effect with Ni active sites in assisting promoting the formation of BTX products, as discussed in Section 3.2. Negligible change of carbonaceous deposit yield was observed, indicating polycondensation reactions is not sensitive to change of the loading of Mo. The results agree reported conclusion that the ability of Mo active sites hinder polycondensation reactions and prevent further reaction of liquid products especially AHs [32].

Fig. 3 Influence of metal loading on the liquid product yields obtained from deoxygenation reaction over x%Ni-y%Mo/HZ(25) catalysts. Reaction temperature = 500°C

The decrease in the Ni loading from 1.0 to 0.5 wt.% (experiments DO2 and DO5, respectively) gave rise to a reduction in the yield of AHs of around 3.0 wt.%, and in the yield and selectivity of BTX of around 4.0 wt.% and 6.0 wt.% respectively. The decrease in AHs and particularly BTX fraction is related to the increase in the yields of

both Phs and PAH compounds. The results reflect the key role of Ni sites in promoting BTX selectivity by converting more Phs to mono AHs in the deoxygenation reactions. The change in BTX yield when reducing the amount of Ni (i.e. DO5 vs. DO2 results) also supports the argument of the synergistic effect of Ni in assisting Mo to promote the yield of BTX. When comparing the products obtained over 0.5%Ni-1%Mo/HZ(25) and 1%Mo/HZ(25) [32], it can be observed that the addition of 0.5%Ni preserved the BTX selectivity despite the yields of AHs and BTX decreased in favour of more carbonaceous deposits. The results indicate that the addition of 0.5 wt.%Ni to 1%Mo/HZ(25) was observed to be actually detrimental to the performance of the catalyst because polycondensation is promoted. The addition of 1.0 wt.% Ni to 1%Mo/HZ(25) promoted the BTX selectivity despite the fact that the amount of carbonaceous deposit also increase. The results suggest that the selection of the Ni/Mo loading ratio of the catalyst is not trivial, and it determines the synergetic effect between both active metals.

3.4 Characterization of fresh and spent catalysts

Fresh catalysts were analysed by TEM-EDS to evaluate the surface morphology of the active metals. The catalysts 1%Ni-1%Mo/HZ(25), 1%Ni-1%Fe/HZ(25), and 1%Mo-1%Fe/HZ(25) were observed at four resolutions (500nm, 100nm, 50nm and 20nm). In addition, the spent 1%Ni-1%Mo/HZ(25) catalyst from experiment DO2 was analysed to characterize the carbonaceous deposits on the surface.

Representative TEM micrographs of the fresh catalyst are shown in Fig. 4 (a), (b) and (c), and Supplementary Material S4 to S6 respectively. In all cases, the bimetal active sites were found to be highly dispersed on the zeolite surface and in the form of microcrystals, as pointed by the SAED patterns shown in the Supplementary Material S4 to S6 [49,50]. The bimetallic particles showed diameters around 10 nm, in line with what literature reported [35], although the individual particles were difficult to

375 distinguish due to the unclear boundaries. In addition, giant particles (over 20nm) were
376 observed in the fresh catalysts of Ni-Mo and Ni-Fe loaded HZ(25) as shown in Fig. 4,
377 whose formation is attributed to the likely occurrence of bimetal agglomeration caused
378 by the high adsorption ability of Ni during the catalyst reduction [51].

(a)

(b)

(c)

(d)

Fig. 4 TEM micrographs for the fresh catalysts: (a) 1%Ni-1%Mo/HZ(25) (b) 1%Ni-1%Fe/HZ(25), (c) 1%Mo-1%Fe/HZ(25); and (d) the spent catalysts 1%Ni-1%Mo/HZ(25) after experiment DO2

Representative TEM micrograph of the spent 1%Ni-1%Mo/HZ(25) catalyst is shown in Fig. 4 (d), and Supplementary Material S9. Cloud-shaped carbonaceous deposits were observed, covering the metal particles to the point that they were almost non-visible. Nevertheless, no further agglomeration of particles was observed compared to the fresh catalyst. The carbonaceous deposits exhibited amorphous nature, also confirmed by the absence of diffraction circles in the Fast Fourier Transform (FFT) image (provided in Supplementary Material S9).

The surface of the three fresh catalysts and the spent catalysts were analysed by EDS tests in order to identify and quantify the main elements present in the surface, as shown in Table 2 and Supplementary Material S7 and S10. For each of the fresh catalysts, the active metal species were found to be in a concentration around 1 wt.% (based on the whole catalyst sample), in close agreement with the designed loading ratio. In the case of the spent catalyst, carbon element accounting for around 10 wt.% of the unit catalyst sample. In the case of the identified oxygen element, it should be noticed that oxygen could be both present in the carbonaceous deposit and be part of the zeolite structure oxygen, but the technique is not able to distinguish between them. The results of TEM-EDS showed that most of the surface area of the spent bimetallic-based catalyst was covered by amorphous carbonaceous deposits.

Table 2 EDS surface characterisation of fresh and spent bimetallic catalyst supported on HZ(25)

Fresh Catalyst (/HZ(25))			Spent Catalyst(/HZ(25))
1%Ni-1%Mo	1%Ni-1%Fe	1%Mo-1%Fe	1%Ni-1%Mo

Ele	wt.%	Atomic%	wt.%	Atomic%	wt.%	Atomic%	wt.%	Atomic %
Ni	1.1	0.4	1.3	0.5	-	-	0.6	0.2
Mo	1.0	0.2	-	-	0.8	0.2	1.0	0.2
Fe	-	-	1.4	0.5	1.3	0.5	-	-
C	-	-	-	-	-	-	10.2	15.9
O	-	-	-	-	-	-	48.1	56.5

To further evaluate the separate performance of each metal active site in the optimal catalyst, the life of each active sites in the catalyst of Ni-Mo/HZ(25) was assessed by the conversion of anisole over Ni active site (Ni/HZ(25)) and Mo active site (Mo/HZ(25)) respectively in a time range of 100 minutes. Results showed that both active sites were stable during the decomposition of anisole, and the conversion over both active sites remained over 85% after the 100min reaction. Details are shown in Supplementary Material S11.

3.5 DFT modelling of anisole and phenol onto the surface of bimetal crystals

To further elucidate the findings from experiments, the interaction and adsorption energy of anisole and phenol, reactant molecules during the anisole decomposition process, onto bimetal crystals were analysed by means of DFT modelling.

The adsorption energy for anisole and phenol adsorption onto each bimetal surface is shown in Table 3. The highest adsorption energy for both anisole and phenol molecules was observed in the case of Ni-Mo alloy, in accord with the highest production of Ni-Mo bimetal loading shown in the experiments. The adsorption energy values were lower for those alloys containing Fe, and Ni-Fe surface showed the lowest adsorption energy for both adsorbates. This agrees with the experimental results that Ni-Fe and Mo-Fe contained catalysts may moderate the deactivation of the catalyst by

weakening the high adsorption capability of Ni-Mo loading. The difference in the adsorption energy values between Ni-Fe and Mo-Fe agrees with the lower adsorption energy previously observed for anisole adsorption on Ni compared to anisole adsorption on Mo [33].

Table 3 Adsorption energy of anisole and phenol onto the bimetal surfaces

Bimetal Surface	Adsorption energy (kcal/mol)	
	Anisole	Phenol
Ni-Mo	72.67	79.88
Ni-Fe	43.08	45.41
Mo-Fe	63.99	60.67

The interaction between the alloy adsorbent and the phenol as model adsorbate was further evaluated by the analysis of the electron distribution vibration in the phenol molecule, as shown in Fig. 5, Fig. 6 and Fig. 7. As the catalytic performance of the bimetallic sites on the deoxygenation reactions highly depends on their ability to disturb the oxygen in the phenolic molecules [52–54], the contribution of oxygen to the overall Density of States (DOS) change in the phenol molecule was also determined. Electrons in s, p, d orbitals were considered for these cases.

434

(a)

(b)

435

436

(c)

(d)

437

Fig. 5 Density of States (DOS) of Phenol: (a) approaching to Ni-Mo; (b) adsorbed on

438

Ni-Mo. Oxygen contribution to DOS, Partial DOS (PDOS): (c) approaching to Ni-Mo; (d)

439

adsorbed on Ni-Mo.

440

441

(a)

(b)

442

443

(c)

(d)

Fig. 6 Density of States (DOS) of Phenol: (a) approaching to Ni-Fe; (b) adsorbed on Ni-Fe. Oxygen contribution to DOS, Partial DOS (PDOS): (c) approaching to Ni-Fe; (d) adsorbed on Ni-Fe.

Fig. 7 Density of States (DOS) of Phenol: (a) approaching to Mo-Fe; (b) adsorbed on Mo-Fe. Oxygen contribution to DOS, Partial DOS (PDOS): (c) approaching to Mo-Fe; (d) adsorbed on Mo-Fe.

Phenol molecule exhibited similar DOS profiles when approaching to (distance above 5 Å) the three alloys (plot (a) in Fig. 5, Fig. 6 and Fig. 7). Nevertheless, the energy level of the electrons in the phenol molecule was 0.5 eV higher when approaching to Mo-Fe alloy compared to Ni-Mo and Ni-Fe alloys. This result indicates that the types of metals in the alloy had little impact on the phenol molecule before the adsorption took place,

when the distance between adsorbate and adsorbent was larger than 5 Å. It can be observed from the spectra before the adsorption that the electrons in s orbital of the phenol molecule were primarily located at low energy levels (between -18 and -10 eV), while higher energy levels (between -12 and -1 eV) were occupied by p electrons. Nevertheless, it is worth noting that some s orbital electrons were also present in higher energy levels (between -10 to -4 eV), indicating the hybridization of orbitals within the phenol molecule. Once phenol molecule was adsorbed onto the bimetal surfaces (as shown in plot (b) in Fig. 5, Fig. 6 and Fig. 7), the DOS spectra for both the s and p electrons showed displacement of energy levels and changes in value of states, particularly at energy levels higher than -10 eV. These changes varied depending on the alloy. In the case of the phenol adsorbed on Ni-Mo alloy, the energy level of most electrons in s and p orbitals decreased about 1.5 eV. This relates to the contribution to the energy released by the whole system during the adsorption process, which is an exothermic process. The change in energy also reveals a more stable structure of the molecule compared to that prior to adsorption. In the case of Ni-Mo, the value of DOS changed especially at the energy levels above -4 eV; electrons were gained from Ni-Mo alloy at some of the energy levels during the adsorption process. This is related to the electron exchange between the phenol molecule and the adsorbent surface, and confirms the chemisorption between the phenol molecule and Ni-Mo alloy [55]. Similar change of DOS values was observed for the adsorption of phenol onto Ni-Fe and Mo-Fe alloys. However, the displacement of the energy levels for each orbital was lower compared to the adsorption on Ni-Mo. this agrees with the results that Fe contained alloys led to lower adsorption energy compared to Ni-Mo. In the case of Ni-Fe surface, the adsorbed phenol molecule showed a small displacement of energy level but more gained electrons, mainly in p orbital at energy levels above -2 eV. This result agrees with the predicted lowest adsorption energy for Ni-Fe and shown in Table 3. At the same time, it implies that Fe had more significant electron back-donation transfer to the

absorbed phenol molecule, which may give rise to strong interaction between Ni-Fe alloy surface and the adsorbate molecule [55]. Larger displacement of energy level of the orbital electrons was observed in the case of Mo-Fe compared to Ni-Fe. This result points that Mo led to higher adsorption energy than Ni [33]. The increased density of p orbital electrons at high energy levels also confirms that Fe effectively interacted with the adsorbate by electron transfer.

Plots (c) and (d) in Fig. 5, Fig. 6 and Fig. 7 show the Partial DOS (PDOS) of the oxygen atom in the phenol molecule before and after adsorption onto each alloy. The PDOS spectra of the oxygen were similar regardless the difference in alloy composition. In the three cases, it was found that most electrons in s orbital were located at high energy levels ranged from -9 to -3 eV, hybridized with p electrons. After adsorption, the energy of frontier orbitals of the oxygen atom in the case of the Ni-Mo system showed the largest decrease in the energy level (> 1 eV). Simultaneously, a slight decrease of magnitude of the DOS values at most of the energy levels except an increase of the values mainly at high energy levels above -4 eV were observed. The changes of DOS values were more significant for Ni-Fe and Mo-Fe. These results indicate the strong impact of the metallic surfaces on the electron distribution of the oxygen atom. It is inferred that the changes in p electrons may include the two non-hybridized 2p orbital electrons of oxygen atom that engage in π -p conjugation; consequently making the hydroxyl group more reactive and favouring the deoxygenation reactions.

The electron transition and change in energy levels of the oxygen atom resemble those of the phenol molecule, and the influence of the type of metals in the alloy is similar to both the phenol molecule and the oxygen atom. Ni and Mo generate stronger binding with the adsorbate molecule by releasing more energy during the adsorption, while Fe gives rise to more electron exchange between the metallic surface and the adsorbate [55].

Although the three bimetal surfaces show strong interaction with the reactant molecules, the stronger binding exhibited by the Ni-Mo surface could benefit more the deoxygenation reaction in the decomposition of anisole in promoting the yield and selectivity towards desirable products based on the experimental results.

4. Conclusion

In this work, experiments of anisole decomposition were carried out over bi-metals loaded HZ(25). The experimental results showed that Ni-Mo could combine the positive effects of respective Ni and Mo by maintaining the high yield of BTX for 30 wt.% while promoting the its selectivity to 83.7%. 1% was the optimal loading ratio for the bi-metal synergistic effect. 500°C was found to be a compromise temperature for the BTX production in the deoxygenation reactions, giving rise to high selectivity of BTX with moderate polycondensation of both Phs and AHs. Fe showed negative effect as part of the bi-metal in promoting the BTX yield and selectivity in the decomposition of anisole. The TEM-EDS test to fresh catalysts confirmed the actual bi-metal loadings agreed with the designed value, and showed the microcrystal particles of the bi-metal loadings had fuzzy boundaries and readily agglomerated after the reduction. TEM-EDS test of the spent 1%Ni-%Mo/HZ(25) showed evidence of amorphous carbon deposited after the reaction. DFT modelling revealed that Ni-Mo alloy promoted the decline in electrons energy levels and consequently exhibited the highest adsorption energy, while Fe was more effective in back-donating electrons between the surface and the frontier orbitals in the adsorbate. A stronger binding caused by Ni-Mo loading made it more efficient for the deoxygenation during anisole decomposition, in line with the experimental results.

Author information

Corresponding Authors

D.S.: 101011398@seu.edu.cn

537 X.Z.: xiaolei.zhang@qub.ac.uk

538 **Author Contributions**

539 All authors have given approval to the final version of the manuscript.

540 **Notes**

541 The authors declare no competing financial interest.

542 **Acknowledgement**

543 The authors would like to acknowledge financial support from the National Natural
544 Science Foundation of China (project references: 51476034 and 51628601), Natural
545 Science Foundation of Jiangsu Province (project reference: BK20161423), the FP7
546 Marie Curie iComFluid (project reference: 312261), and the Leverhulme Trust
547 Research Grant (project reference: RPG-2017-254).

548 **References**

- 549 [1] Boerjan W, Ralph J, Baucher M. Lignin Biosynthesis. *Annu Rev Plant Biol*
550 2003;54:519–46. doi:10.1146/annurev.arplant.54.031902.134938.
- 551 [2] Lancefield CS, Westwood NJ. The synthesis and analysis of advanced lignin
552 model polymers. *Green Chem* 2015;17:4980–90. doi:10.1039/C5GC01334H.
- 553 [3] Liu W-JJ, Jiang H, Yu H-QQ. Thermochemical conversion of lignin to functional
554 materials: a review and future directions. *Green Chem* 2015;17:4888–907.
555 doi:10.1039/C5GC01054C.
- 556 [4] Bridgwater AV V. Review of fast pyrolysis of biomass and product upgrading.
557 *Biomass and Bioenergy* 2012;38:68–94. doi:10.1016/j.biombioe.2011.01.048.
- 558 [5] Bridgwater AV V, Peacocke GVC. Fast pyrolysis processes for biomass. *Renew*
559 *Sustain Energy Rev* 2000;4:1–73.

- 560 [6] Jung KA, Woo SH, Lim S-R, Park JM. Pyrolytic production of phenolic
561 compounds from the lignin residues of bioethanol processes. *Chem Eng J*
562 2015;259:107–16. doi:10.1016/j.cej.2014.07.126.
- 563 [7] Shen DK, Gu S, Luo KH, Wang SR, Fang MX. The pyrolytic degradation of
564 wood-derived lignin from pulping process. *Bioresour Technol* 2010;101:6136–46.
565 doi:10.1016/j.biortech.2010.02.078.
- 566 [8] Hurff SJ, Klein MT. Reaction pathway analysis of thermal and catalytic lignin
567 fragmentation by use of model compounds. *Ind Eng Chem Fundam*
568 1983;22:426–30. doi:10.1021/i100012a012.
- 569 [9] Zhu X, Mallinson RG, Resasco DE. Role of transalkylation reactions in the
570 conversion of anisole over HZSM-5. *Appl Catal A Gen* 2010;379:172–81.
571 doi:10.1016/j.apcata.2010.03.018.
- 572 [10] Zhang J, Fidalgo B, Shen D, Xiao R, Gu S. Mechanism of transmethylation in
573 anisole decomposition over HZSM-5: Experimental study. *J Anal Appl Pyrolysis*
574 2016;122:323–31. doi:10.1016/j.jaap.2016.09.009.
- 575 [11] Li X, Chen G, Liu C, Ma W, Yan B, Zhang J. Hydrodeoxygenation of lignin-
576 derived bio-oil using molecular sieves supported metal catalysts: A critical review.
577 *Renew Sustain Energy Rev* 2017;71:296–308. doi:10.1016/j.rser.2016.12.057.
- 578 [12] Meng Q, Fan H, Liu H, Zhou H, He Z, Jiang Z, et al. Efficient Transformation of
579 Anisole into Methylated Phenols over High-Silica HY Zeolites under Mild
580 Conditions. *ChemCatChem* 2015;7:2831–5. doi:10.1002/cctc.201500479.
- 581 [13] Prasomsri T, To AT, Crossley S, Alvarez WE, Resasco DE. Catalytic conversion
582 of anisole over HY and HZSM-5 zeolites in the presence of different hydrocarbon
583 mixtures. *Appl Catal B Environ* 2011;106:204–11.
584 doi:10.1016/j.apcatb.2011.05.026.

- 585 [14] Wang K, Dong X, Chen Z, He Y, Xu Y, Liu Z. Highly selective synthesis of para-
586 cresol by conversion of anisole on ZSM-5 zeolites. *Microporous Mesoporous*
587 *Mater* 2014;185:61–5. doi:10.1016/j.micromeso.2013.11.007.
- 588 [15] Cornella J, Gómez-Bengoa E, Martin R. Combined experimental and theoretical
589 study on the reductive cleavage of inert C-O bonds with silanes: Ruling out a
590 classical Ni(0)/Ni(II) catalytic couple and evidence for Ni(I) intermediates. *J Am*
591 *Chem Soc* 2013;135:1997–2009. doi:10.1021/ja311940s.
- 592 [16] Mackie CJ, Doolan RK, Nelson FP. Kinetics of the thermal decomposition of
593 methoxybenzene(anisole). *J Phys Chem C* 1989;93:664–70. doi:0022-
594 365418912093-0664\$01.50/0 Lin.
- 595 [17] Song Q, Wang F, Cai J, Wang Y, Zhang J, Yu W, et al. Lignin depolymerization
596 (LDP) in alcohol over nickel-based catalysts via a fragmentation–hydrogenolysis
597 process. *Energy Environ Sci* 2013;6:994. doi:10.1039/c2ee23741e.
- 598 [18] Saidi M, Samimi F, Karimipourfard D, Nimmanwudipong T, Gates BC,
599 Rahimpour MR. Upgrading of lignin-derived bio-oils by catalytic
600 hydrodeoxygenation. *Energy Environ Sci* 2014;7:103–29.
601 doi:10.1039/C3EE43081B.
- 602 [19] Zhu X, Lobban LL, Mallinson RG, Resasco DE. Bifunctional transalkylation and
603 hydrodeoxygenation of anisole over a Pt/HBeta catalyst. *J Catal* 2011;281:21–9.
604 doi:10.1016/j.jcat.2011.03.030.
- 605 [20] Runnebaum RC, Nimmanwudipong T, Block DE, Gates BC. Catalytic conversion
606 of compounds representative of lignin-derived bio-oils: a reaction network for
607 guaiacol, anisole, 4-methylanisole, and cyclohexanone conversion catalysed by
608 Pt/ γ -Al₂O₃. *Catal Sci Technol* 2012;2:113–8. doi:10.1039/C1CY00169H.
- 609 [21] Xiong J, Kan T, Li X, Ye T, Li Q. Effects of Current upon Electrochemical

610 Catalytic Reforming of Anisole. *Chinese J Chem Phys* 2010;23:693–700.
611 doi:10.1088/1674-0068/23/06/693-700.

612 [22] González-Borja MA, Resasco DE. Anisole and Guaiacol Hydrodeoxygenation
613 over Monolithic Pt–Sn Catalysts. *Energy & Fuels* 2011;25:4155–62.
614 doi:10.1021/ef200728r.

615 [23] Mu W, Ben H, Ragauskas A, Deng Y. Lignin Pyrolysis Components and
616 Upgrading-Technology Review. *Bioenergy Res* 2013;6:1183–204.
617 doi:10.1007/s12155-013-9314-7.

618 [24] Jin S, Xiao Z, Li C, Chen X, Wang L, Xing J, et al. Catalytic hydrodeoxygenation
619 of anisole as lignin model compound over supported nickel catalysts. *Catal*
620 *Today* 2014;234:125–32. doi:10.1016/j.cattod.2014.02.014.

621 [25] Laurent E, Delmon B. Study of the hydrodeoxygenation of carbonyl, carboxylic
622 and guaiacyl groups over sulfided CoMo/ γ -Al₂O₃ and NiMo/ γ -Al₂O₃ catalyst.
623 *Appl Catal A Gen* 1994;109:97–115. doi:10.1016/0926-860X(94)85005-4.

624 [26] Mukundan S, Konarova M, Atanda L, Ma Q, Beltramini J. Guaiacol
625 hydrodeoxygenation reaction catalyzed by highly dispersed, single layered MoS
626 2/C. *Catal Sci Technol* 2015;5:4422–32. doi:10.1039/C5CY00607D.

627 [27] Khromova SA, Smirnov AA, Bulavchenko OA, Saraev AA, Kaichev V V.,
628 Reshetnikov SI, et al. Anisole hydrodeoxygenation over Ni–Cu bimetallic
629 catalysts: The effect of Ni/Cu ratio on selectivity. *Appl Catal A Gen*
630 2014;470:261–70. doi:10.1016/j.apcata.2013.10.046.

631 [28] Smirnov A, Khromova S, Bulavchenko O, Kaichev V, Saraev A, Reshetnikov S,
632 et al. Effect of the Ni/Cu ratio on the composition and catalytic properties of
633 nickel-copper alloy in anisole hydrodeoxygenation. *Kinet Catal* 2014;55:69–78.
634 doi:10.1134/S0023158414010145.

- 635 [29] Pichaikaran S, Arumugam P. Vapour phase hydrodeoxygenation of anisole over
636 ruthenium and nickel supported mesoporous aluminosilicate. *Green Chem*
637 2016;18:2888–99. doi:10.1039/C5GC01854D.
- 638 [30] Ghampson IT, Pecchi G, Fierro JLG, Videla A, Escalona N. Catalytic
639 hydrodeoxygenation of anisole over $\text{Re-MoO}_x/\text{TiO}_2$ and $\text{Re-VO}_x/\text{TiO}_2$
640 catalysts. *Appl Catal B Environ* 2017;208:60–74.
641 doi:10.1016/j.apcatb.2017.02.047.
- 642 [31] Alonso DM, Wettstein SG, Dumesic JA. Bimetallic catalysts for upgrading of
643 biomass to fuels and chemicals. *Chem Soc Rev* 2012;41:8075.
644 doi:10.1039/c2cs35188a.
- 645 [32] Zhang J, Fidalgo B, Kolios A, Shen D, Gu S. Mechanism of deoxygenation in
646 anisole decomposition over single-metal loaded HZSM-5: Experimental study.
647 *Chem Eng J* 2018;336:211–22. doi:10.1016/j.cej.2017.11.128.
- 648 [33] Zhang J, Fidalgo B, Shen D, Zhang X, Gu S. Mechanism of hydrodeoxygenation
649 (HDO) in anisole decomposition over metal loaded Brønsted acid sites: Density
650 Functional Theory (DFT) study. *Mol Catal* 2018;454:30–7.
651 doi:10.1016/j.mcat.2018.05.015.
- 652 [34] Whiffen VML, Smith KJ, Straus SK. The influence of citric acid on the synthesis
653 and activity of high surface area MoP for the hydrodeoxygenation of 4-
654 methylphenol. *Appl Catal A Gen* 2012;419–420:111–25.
655 doi:10.1016/j.apcata.2012.01.018.
- 656 [35] Nie L, De Souza PM, Noronha FB, An W, Sooknoi T, Resasco DE. Selective
657 conversion of m-cresol to toluene over bimetallic Ni-Fe catalysts. *J Mol Catal A*
658 *Chem* 2014;388–389:47–55. doi:10.1016/j.molcata.2013.09.029.
- 659 [36] Yang J, Chen M-Q, Wang Y-S, Yang Z-L, Liu S-M, Liang T. Hydrogen

660 production via catalytic steam reforming of m-cresol over Ni-Fe/HZSM-5 catalyst.
 661 Mod Chem Ind 2016;36:146–9. doi:10.16606/j.cnki.issn0253-4320.2016.08.035.

662 [37] Özdemir E, Yeniova H, Alibeyli R. Catalytic Conversion of a Mesitylene and n -
 663 Decane Mixture in the Presence of Hydrogen Over ZSM-5 Based Catalysts. Pet
 664 Sci Technol 2014;32:1598–606. doi:10.1080/10916466.2012.668155.

665 [38] Smirnov A, Khromova S, Ermakov DY, Bulavchenko O, Saraev A, Aleksandrov
 666 P, et al. The composition of Ni-Mo phases obtained by NiMoOx-SiO2 reduction
 667 and their catalytic properties in anisole hydrogenation. Appl Catal A Gen
 668 2016;514:224–34. doi:10.1016/j.apcata.2016.01.025.

669 [39] Rensel DJ, Rouvimov S, Gin ME, Hicks JC. Highly selective bimetallic FeMoP
 670 catalyst for C-O bond cleavage of aryl ethers. J Catal 2013;305:256–63.
 671 doi:10.1016/j.jcat.2013.05.026.

672 [40] Fogler HS. Chemical Reactors. vol. 168. Washington, D.C: American Chemical
 673 Society; 1981. doi:10.1021/bk-1981-0168.

674 [41] Delley B. An all-electron numerical method for solving the local density functional
 675 for polyatomic molecules. J Chem Phys 1990;92:508–17. doi:10.1063/1.458452.

676 [42] Delley B. From molecules to solids with the DMol3 approach. J Chem Phys
 677 2000;113:7756. doi:10.1063/1.1316015.

678 [43] Elanany M, Koyama M, Kubo M, Selvam P, Miyamoto A. Periodic density
 679 functional investigation of Bronsted acidity in isomorphously substituted
 680 chabazite and AlPO-34 molecular sieves. Microporous Mesoporous Mater
 681 2004;71:51–6. doi:10.1016/j.micromeso.2004.03.018.

682 [44] Kalita B, Deka RC. DFT study of CO adsorption on neutral and charged Pdn(n =
 683 1-7) clusters. Eur Phys J D 2009;53:51–8. doi:10.1140/epjd/e2009-00044-6.

- 684 [45] Perdew JP, Burke K, Ernzerhof M. Generalized Gradient Approximation Made
685 Simple. *Phys Rev Lett* 1996;77:3865–8. doi:10.1103/PhysRevLett.77.3865.
- 686 [46] Grimme S. Semiempirical GGA-type density functional constructed with a long-
687 range dispersion correction. *J Comput Chem* 2006;27:1787–99.
688 doi:10.1002/jcc.20495.
- 689 [47] Bredenberg JB-S, Huuska M, Rätty J, Korpio M. Hydrogenolysis and
690 hydrocracking of the carbon-oxygen. *J Catal* 1982;77:242–7.
- 691 [48] Wang J, Jin L, Li Y, Hu H. Preparation of Fe-Doped Carbon Catalyst for
692 Methane Decomposition to Hydrogen. *Ind Eng Chem Res* 2017;56:11021–7.
693 doi:10.1021/acs.iecr.7b02394.
- 694 [49] Martínez A, López C, Márquez F, Díaz I. Fischer–Tropsch synthesis of
695 hydrocarbons over mesoporous Co/SBA-15 catalysts: the influence of metal
696 loading, cobalt precursor, and promoters. *J Catal* 2003;220:486–99.
697 doi:10.1016/S0021-9517(03)00289-6.
- 698 [50] González O, Pérez H, Navarro P, Almeida LC, Pacheco JG, Montes M. Use of
699 different mesostructured materials based on silica as cobalt supports for the
700 Fischer–Tropsch synthesis. *Catal Today* 2009;148:140–7.
701 doi:10.1016/j.cattod.2009.03.030.
- 702 [51] Ardiyanti AR, Khromova SA, Venderbosch RH, Yakovlev VA, Heeres HJ.
703 Catalytic hydrotreatment of fast-pyrolysis oil using non-sulfided bimetallic Ni-Cu
704 catalysts on a δ -Al₂O₃ support. *Appl Catal B Environ* 2012;117–118:105–17.
705 doi:10.1016/j.apcatb.2011.12.032.
- 706 [52] Hernández JMG, Anotá EC, de la Cruz MTR, Melchor MG, Cocolletzi GH. First
707 principles studies of the graphene-phenol interactions. *J Mol Model*
708 2012;18:3857–66. doi:10.1007/s00894-012-1382-7.

- 709 [53] Honkela ML, Björk J, Persson M. Computational study of the adsorption and
710 dissociation of phenol on Pt and Rh surfaces. *Phys Chem Chem Phys*
711 2012;14:5849. doi:10.1039/c2cp24064e.
- 712 [54] Wang R, Zhang D, Liu C. DFT study of the adsorption of 2,3,7,8-
713 tetrachlorodibenzo-p-dioxin on pristine and Ni-doped boron nitride nanotubes.
714 *Chemosphere* 2017;168:18–24. doi:10.1016/j.chemosphere.2016.10.050.
- 715 [55] Hensley AJR, Wang Y, McEwen J-S. Adsorption of phenol on Fe (110) and Pd
716 (111) from first principles. *Surf Sci* 2014;630:244–53.
717 doi:10.1016/j.susc.2014.08.003.
- 718