The Nature of Magnetoelectric Coupling in $\text{Pb}(\text{Zr,Ti})\text{O}_3\text{-Pb}(\text{Fe,Ta})\text{O}_3$

Evans, D. M., Alexe, M., Schilling, A., Kumar, A., Sanchez, D., Ortega, N., Katiyar, R. S., Scott, J. F., & Gregg, J. M. (2015). The Nature of Magnetoelectric Coupling in $\text{Pb}(\text{Zr,Ti})\text{O}_3\text{-Pb}(\text{Fe,Ta})\text{O}_3$. *Advanced Materials*, 27(39), 6068-6073. <https://doi.org/10.1002/adma.201501749>

Published in:
Advanced Materials

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights
© 2015 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim
This is the accepted version of the following article: FULL CITE,
which has been published in final form at <http://onlinelibrary.wiley.com/doi/10.1002/adma.201501749/abstract>

General rights
Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy
The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

DOI: 10.1002/((adma.201501749))

Article type: Communication

The Nature of Magnetoelectric Coupling in $\text{Pb}(\text{Zr,Ti})\text{O}_3\text{-Pb}(\text{Fe,Ta})\text{O}_3$

Donald M. Evans, Marin Alexe, Alina Schilling, Ashok Kumar, Dilsom Sanchez, Nora Ortega, Ram S.

*Katiyar, James F. Scott and J. Marty Gregg**

D.M. Evans, A. Schilling, J. M. Gregg

Centre for Nanostructured Media, School of Maths and Physics, Queen's University Belfast,

Belfast BT7 1NN, Northern Ireland. U. K.

Email: m.gregg@qub.ac.uk

M. Alexe

Department of Physics, University of Warwick, Coventry, CV4 7AL, U. K.

A. Kumar

National Physical Laboratory, New Delhi, Delhi 110012, India.

D. Sanchez, N. Ortega, R. Katiyar

Institute for Functional Nanomaterials, University of Puerto Rico, PO Box 23334, San Juan,

00931-3334, Puerto Rico.

J. F. Scott

School of Chemistry, University of St Andrews, St Andrews, KY16 9ST. Scotland. U. K.

School of Physics & Astronomy, University of St Andrews, North Haugh, St Andrews, KY16

9SS. Scotland. U. K.

Keywords: multiferroics, magnetocapacitance, ferroics, coupling

The last decade has seen an explosion of research activity in multiferroic materials. This has partly been driven by fundamental interest, but partly also by the exciting prospect of new forms of functional devices. In most cases, envisioned device performance requires distinct room temperature coupling between the magnetic moment and the electrical polarisation: under ambient conditions, an applied electric or magnetic field must simultaneously alter both the material's electrical dipole configuration and its magnetic state. A key stumbling block for progress has been that, despite concerted effort, very few single-phase materials have been discovered in which strongly coupled behaviour has been categorically and unequivocally established at room temperature. One candidate system is the $\text{Pb}(\text{Zr,Ti})\text{O}_3\text{-Pb}(\text{Fe,Ta})\text{O}_3$ (PZTFT) solid solution, where promising initial observations have been made, which demand more careful and systematic examination. In this paper, the ferroelectric behaviour and dielectric response of single crystal PZTFT lamellae have been mapped as a function of applied magnetic field. Significant switching of ferroelectric domains using magnetic fields was observed; in addition, strong hysteretic magnetocapacitance effects were noted. A Landau Free Energy approach was used to demonstrate that P^2M^2 coupling behaviour was generally evident, but that for magnetic fields applied perpendicular to the lamella surface (those responsible for ferroelectric switching), asymmetric coupling terms (such as PM) were more important.

In 1964, Hans Schmid was the first to observe the simultaneous existence of ferroelectricity and ferromagnetism in a single material: the synthetic boracite $\text{Ni}_3\text{B}_7\text{O}_{13}\text{I}$ ^[1]. Two years later, Ascher *et al.* ^[2] revealed that the magnetic moment and polarisation in this boracite were coupled, such that an applied magnetic field could cause complete reversal of the ferroelectric polarisation. This breakthrough discovery was somewhat academic, until the recent renaissance of interest in multiferroics prompted more serious consideration of the device potential of the magnetoelectric coupling phenomenon ^[3, 4].

Given the immense effort devoted by Schmid and coworkers towards finding the first single-phase multiferroic, it is a little ironic that most recent progress towards magnetoelectric

applications has primarily involved mixed-phase systems in composite structures ^[5-13]. Single-phase materials unfortunately usually suffer from two main drawbacks: firstly, the vast majority of them are only multiferroic at cryogenic temperatures ^[14-20]; secondly, their magnetoelectric coupling coefficients tend to be somewhat lower than in dual-phase multilayers. In fact, Ramesh and coworkers have recently even suggested that the archetypical room temperature single-phase multiferroic, BiFeO₃, might most usefully be used in a composite device ^[21].

Nevertheless, there are specific applications and device geometries in which a single layer of a phase-pure magnetoelectric multiferroic would still be desirable. This is particularly true when seeking to use multiferroics as insulating layers in tunnel junction-based devices (such as the spin-filter suggested by Bibes ^[3]), as the thicknesses needed for tunnelling are not commensurate with those needed for dynamic interlayer elastic coupling. Equally, in memory applications, low power electrical switching of magnetisation could be significantly faster in single-phase multiferroics than in composites (supersonic switching is possible, if electronic coupling mechanisms are active). Thus, the drive to discover new phase-pure room temperature multiferroics, beyond BiFeO₃, continues. Several candidate materials have recently been identified, such as the Bi-based aurivillius oxides ^[22], GaFeO₃ thin films ^[23] and perovskite oxides within the Pb(Zr,Ti)O₃-Pb(Fe,Ta)O₃ (PZTFT) solid solution ^[24-28]. The properties of this latter group will be the focus of this article. Some relevant observations have already been made: after initial reports in which room temperature multiferroicity and magnetoelectric coupling had been suggested ^[24, 27] the wider phase transition behaviour in the PZTFT solid solution was investigated by Schiemer *et al.* ^[26]. By monitoring elastic resonance frequency, magnetisation, and dielectric loss they established that ferroelastic, magnetic and ferroelectric anomalies occurred at the same temperatures; such coincident phase transitions strongly suggest coupling among all three ferroic order parameters. A number of theoretical investigations ^[29-31] have attempted to explain the anomalously high ferromagnetic Curie Temperature in this material. In addition, Glinchuk *et al.*

^[31] have predicted the size of the coupling and in what compositions its existence is expected.

However, categorical experimental information on the exact form of the coupling is still lacking.

Here, we report the manner in which applied magnetic fields change both the ferroelectric behaviour (domain states) and dielectric response of single crystal PZTFT lamellae. We observe that ferroelectric switching, in the plane of the lamella, can be induced by perpendicular magnetic fields applied parallel to a pseudocubic $[\bar{1}10]_{pc}$ direction; moreover, we observe distinct magnetocapacitance phenomena, which vary as a function of the orientation of the applied magnetic field. Free energy analysis of the magnetocapacitance suggests that biquadratic P^2M^2 coupling is most significant when fields are applied in the plane of the lamella, but least significant when applied in the perpendicular orientation, where asymmetric terms (such as bilinear PM coupling) become more important. This is consistent with the magnetic field-induced ferroelectric switching observed.

To enable our investigation, thin single crystal platelets, or lamellae, were cut from the interior of individual grains of PZTFT ceramic using Focused Ion Beam (FIB) milling. As has been done in previous research ^[32-34], these lamellae were integrated into simple capacitor devices by placing them across an interelectrode gap (of the order of a few microns in thickness) between coplanar thin film platinum electrodes. The crystallographic orientation was determined by FIB-cutting a second lamella, parallel to the first, from the same PZTFT grain, transferring onto a carbon-coated 3mm diameter grid and investigating using electron diffraction, in a 200kV Field Emission Transmission Electron Microscope. All data presented herein relate to lamellae cut parallel to $\{\bar{1}10\}_{pc}$ planes and oriented in the capacitor structure with a $[001]_{pc}$ direction parallel to the electrode-ferroelectric interface and a $[110]_{pc}$ direction perpendicular to the electrode-ferroelectric interface and parallel to the electric field, when a potential difference was applied across the platinum electrodes. Successful device fabrication and basic magnetoelectric coupling were checked: remanent domain configurations, mapped by Piezoresponse Force Microscopy (PFM), after switching from a fully poled initial state with both electric and magnetic fields, were

found to be comparable (**figure 1**). It was noted, however, that after the initial switching had been induced magnetically, subsequent reversal of the magnetic field produced progressively more modest changes in the ferroelectric domain configuration; the fully poled initial state could not be recovered unless an electric field was used. Currently, this observation is not understood, but such “fatigue” in the magnetically-induced ferroelectric switching may be a feature of local elastic field interactions between ferroelastic domain variants and an associated progressive accumulation of pinned domain walls.

Magnetocapacitance was monitored using an Agilent bridge E4980A Precision LCR meter; capacitors were mounted in a cryostat with in-situ magnetic field capability. Initial measurements were taken without any magnetic field, to confirm the double-peaked capacitance-voltage ($C(V)$) response characteristic of a switching ferroelectric. As can be seen in figure 2(a), the magnitude of the peaks in the $C(V)$ response were approximately the same at positive and negative voltage. When these measurements were repeated under an applied magnetic field of 1 Tesla (oriented along $[\bar{1}10]_{pc}$, perpendicular to the plane of the PZTFT lamella – the same direction as had been responsible for the magnetic-field induced ferroelectric switching in figure 1), changes in the $C(V)$ characteristic resulted: the heights of the peaks in capacitance at positive and negative voltage became distinctly different. In the example shown in **figure 2(a)**, the capacitance peak in the positive sense of applied voltage was suppressed relative to that measured in the negative sense. This relative difference was reversed when the sense of the magnetic field was reversed; however, somewhat consistent with observations of magnetic-field-induced switching of ferroelectric domains, the extent to which the magnetic field altered the relative heights of the peaks in capacitance progressively diminished as the sense of the magnetic field was repeatedly reversed.

Capacitance was then monitored in the absence of a dc voltage bias, but with varying magnetic field. At a range of temperatures (between 10 K to 305 K), the magnetic field was scanned from 0 to +H to -H and back to 0 at a speed of 150 Oe s^{-1} , in three orthogonal

directions $[001]_{pc}$, $[110]_{pc}$ and $[\bar{1}10]_{pc}$ as shown in figure 1). As a representative illustration, datasets taken at 150K and 100kHz are shown in **figure 2 (b)-(d)**. 150K is sufficiently cold to avoid thermal measurement drift and safely away from any of the phase transition temperatures identified in previous work ^[26]; 100kHz is a sufficiently high frequency that space-charge artefacts, which can contribute to magnetocapacitance ^[35], are avoided. As can be seen in the figure, all magnetocapacitance functions were found to be hysteretic; in addition, for all orientations, the absolute changes in capacitance induced by the applied magnetic fields were large (significant fractions of the changes caused by electric fields during switching, seen in the $C(V)$ response, figure 2(a)). The detailed form of the magnetocapacitance function clearly also varied with the orientation of the applied field.

Insight can be gained by considering the dielectric susceptibility (which scales with the capacitance) derived from a compact Landau Free Energy (G) expression given as follows:

$$G = \sum_{i=1}^{\infty} A(i)P^{2i} - E \cdot P + \sum_{j=1}^{\infty} B(j)M^{2j} - H \cdot M + \sum_{k=1}^{\infty} C(k)\epsilon^{2k} - S \cdot \epsilon + \sum_{i,j,k=0}^{\infty} D(i,j,k)P^i M^j \epsilon^k \quad (1)$$

The first pair of terms in this expression captures the symmetric energy expansion in polarisation (P) and the work done by the electric field (E); the second pair of terms captures the equivalent in magnetisation (M) and magnetic field (H) and the third pair in strain (ϵ) and stress (S). The last term is a summation of all possible energy contributions from all possible combinations of coupling among polarisation, magnetisation and strain. $A(i)$, $B(j)$, $C(k)$, $D(i,j,k)$ represent constants, the values of which change with different values of i , j and k . Despite its coarse nature, this equation should capture the essence of multiferroic behaviour, even if underlying order parameters are not completely explored and defined: for example, the use of M alone to describe magnetisation does not distinguish between order parameters associated with spin clustering of Fe^{+3} ions and possible canted antiferromagnetism in PZTFT. A more complete description should probably include terms such as $(L \times M) \cdot P$ and $(L \times M)^2$, where L is sublattice magnetization and M is weak ferromagnetism from canting, as has been emphasized by Fox, Tilley, Scott and

Guggenheim^[36]. However, while such terms are probably important in pure Pb(Fe,Nb)O₃ (PFN) (Peng *et al.*^[37] have shown that both clustering and canting contribute to the net magnetization) they may not be as key in PZTFT: four different ions on the B-site suggests that clustering is apt to dominate. For the moment all such subtleties are subsumed within the order parameter M .

Under equilibrium conditions ($dG/dP=0$), an expression for the electric field can readily be obtained from equation (1). Hence, an expression for the inverse dielectric susceptibility ($dE/dP = \chi^{-1}$) can be given as:

$$\chi^{-1} = \sum_{i=1}^{\infty} A(i) 2i(2i-1)P^{2i-2} + \sum_{i,j,k=0}^{\infty} D(i,j,k) i(i-1)P^{i-2}M^j\epsilon^k \quad (2)$$

If we now consider how the inverse dielectric susceptibility varies as a function of magnetic field, the following expression is obtained:

$$\frac{d\chi^{-1}}{dH} = \sum_{i,j,k=0}^{\infty} D(i,j,k) i(i-1)P^{i-2}j \frac{dM}{dH} M^{j-1}\epsilon^k \quad (3)$$

Thus, importantly, by taking the derivative of the inverse susceptibility (which scales as the inverse capacitance) with respect to magnetic field, and examining it as a function of magnetic field, we can directly and specifically probe the coupling terms in the Landau Free Energy expansion.

Let us consider a simplified form of this equation where $k=0$ (in other words where strain is not explicitly involved in the multiferroic coupling energy). If linear PM coupling were the only active behaviour, $(i-1)$ would be zero and hence the $d\chi^{-1}/dH$ response should be zero for all applied magnetic fields; if quadratic-linear coupling of the form P^2M were the only active coupling, $d\chi^{-1}/dH$ should be proportional to dM/dH ; equally, if dominated by biquadratic terms (P^2M^2 which are always symmetry-allowed) then it should be primarily proportional to $M(dM/dH)$.

To examine the form that M and dM/dH based functions might have in PZTFT, the magnetisation with applied field was measured for the bulk ceramic (the measurement of the $M(H)$ behaviour in the PZTFT lamella was experimentally beyond our capabilities). This is presented in **figure 3(a)** along with tanh fits which allowed analytical determination of dM/dH (**figure 3(b)**) and hence of $-M(dM/dH)$ (**figure 3(c)**). Comparisons of these functions with those experimentally determined from measured magnetocapacitance data (plots of $d(C^{-1})/dH$ against H , **figure 4(a)-(c)**) are quite revealing: with magnetic fields applied parallel to $[001]_{pc}$ (in the plane of the lamella, parallel to the dielectric-electrode interface), the maxima and minima in $d(C^{-1})/dH$ either side of $H=0$, for both increasing and decreasing magnetic fields, show strong similarities to the primary features in the $-M(dM/dH)$ function plotted in figure 3(c). As discussed above, this is consistent with significant biquadratic P^2M^2 coupling from consideration of equation (3). For magnetic fields applied parallel to the $[110]_{pc}$ crystallographic direction (in the plane of the lamella, perpendicular to the dielectric-electrode interface) similar features can be seen, but they are less pronounced, suggesting P^2M^2 coupling is active, but weaker. For fields applied perpendicular to the lamella (parallel to a $[\bar{1}10]_{pc}$ direction), such features are weaker still and, to a first approximation (on the same scale as used in the other two orientations discussed (figure 4(c)), $d(C^{-1})/dH$ is almost invariant. However, the absolute magnetocapacitance effect is the strongest of all orientations examined both at 150K (figure 2(d)) and at room temperature (**figure 4(d)**); in fact, the capacitance changes observed are commensurate with the signature of ferroelectric switching seen in our $C(V)$ measurements (figure 2(a)), so coupling terms are clearly active. Importantly, this is also the field orientation responsible for the room temperature domain switching illustrated in figure 1. Such observations point to the decreasing importance of P^2M^2 and the increasing importance of asymmetric terms in the magnetoelectric response.

Care should be taken not to view the plots presented in figure 4 in an overly simplistic manner. The data in figure 2 show that the value of the measured capacitance changes as magnetic fields are applied for all field orientations. Thus, $d(C^{-1})/dH$ is generally non-zero and

hence, even when the magnetic field is applied along $[\bar{1}10]_{pc}$, perpendicular to the lamellar plane, simple PM terms cannot be the sole components. A more complex behaviour seems likely, that goes beyond the discussion above, in which explicit strain coupling terms are also active. This would be consistent with the research results reported by Schiemer *et al.* ^[26]. To be evaluated fully in future work, magnetoelastic changes should be monitored in conjunction with the kinds of magnetoelectric measurements presented and considered here.

Nevertheless, the orientations of the applied magnetic and electric fields, in relation to the possible orientations of polarisation in the lamella, should be explicitly considered and are illustrated in **figure 5**; rhombohedral symmetry, as one of the options postulated by Dilsom *et al.* ^[27], and the development of $[111]_{pc}$ dipole vectors at 150K are assumed. Applying the magnetic field along $[001]_{pc}$ is distinct by symmetry from the $[110]_{pc}$ and $[\bar{1}10]_{pc}$ directions and so the uniqueness of the strength of the P^2M^2 coupling behaviour inferred, in comparison to the other two directions, is not surprising. However, one might expect symmetry equivalence in behaviour for magnetic fields applied along the $[110]_{pc}$ and $[\bar{1}10]_{pc}$ directions. Such equivalence may indeed be present, but the relative orientation of the electric field used to monitor capacitance is different in the two cases, being parallel to the applied magnetic field in one case and perpendicular to it in the other. The shape of the lamella may also be partly responsible for differences in coupling behaviour observed, as depolarising fields associated with components of polarisation perpendicular to the lamellar surface may bias domain populations to favour those with entirely in-plane polar components.

In summary, the ways in which applied magnetic fields change ferroelectric domain states and the dielectric response of single crystal PZTFT lamellae have been investigated. Magnetic fields have been found to induce significant switching of ferroelectric domains, as had been seen previously; in addition, strong magnetocapacitance effects were noted which were different for different orientations of magnetic field. By considering highly generalised Landau Free Energy expressions, the magnetocapacitance response revealed biquadratic coupling in the plane of the

lamellar PZTFT sample; weaker biquadratic coupling was apparent when the magnetic field was perpendicular to the lamella where it was clear that asymmetric coupling terms were more dominant. The study reaffirms that PZTFT genuinely acts as a single-phase room temperature magnetoelectric multiferroic and highlights complexities in the orientational dependence of coupling effects.

Acknowledgements: JMG, JFS and AS acknowledge financial support from the Engineering and Physical Sciences Research Council (EPSRC) under research contracts: EP/J017191/1, EP/J017825/1 and EP/H00307X/1. DME, JMG and AS acknowledge support from the Northern Ireland Department for Employment and Learning (DEL). DME and JMG thank R. G. P. McQuaid for helpful discussions.

Received: ((will be filled in by the editorial staff))

Revised: ((will be filled in by the editorial staff))

Published online: ((will be filled in by the editorial staff))

- [1] H. Schmid, *Ferroelectrics*, **2012**, 427, 1
- [2] E. Ascher, H. Rieder, H. Schmid, and H. Stossel, *J. Appl. Phys.*, **1966**, 37, 1404
- [3] M. Bibes, *Nat. Mat.*, **2012**, 11, 354
- [4] J. F. Scott, *J. Mater. Chem.*, **2012**, 22, 4567
- [5] S. Roy and S.B. Majumder, *J. of Alloys and Compd.*, **2012**, 538, 153
- [6] C. A. F. Vaz, *J. Phys.: Condens. Matter*, **2012**, 24, 333201
- [7] V. Skumryev, V. Laukhin, I. Fina, X. Martí, F. Sánchez, M. Gospodinov and J. Fontcuberta, *Phys. Rev. Lett.*, **2011**, 106, 057206
- [8] H. Zheng, J. Wang, S. E. Lofland, Z. Ma, L. Mohaddes-Ardabili, T. Zhao, L. Salamanca-Riba, S. R. Shinde, S. B. Ogale, F. Bai, D. Viehland, Y. Jia, D. G. Schlom, M. Wuttig, A. Roytburd, R. Ramesh, *Science*, **2004**, 303, 661
- [9] F. Zavaliche , H. Zheng , L. Mohaddes-Ardabili , S. Y. Yang , Q. Zhan , P. Shafer , E. Reilly, R. Chopdekar , Y. Jia , P. Wright, D. G. Schlom , Y. Suzuki and R. Ramesh, *Nano Lett.* **2005**, **5**, 1793
- [10] S. Geprägs, A. Brandlmaier, M. Opel, R. Gross and S. T. B. Goennenwein, *Appl. Phys. Lett.* **2010**, 96, 142509
- [11] I. Levin, J. Li, J. Slutsker and A. L. Roytburd, *Adv. Mater.* **2006**, 18, 2044
- [12] J. T. Heron, M. Trassin, K. Ashraf, M. Gajek, Q. He, S. Y. Yang, D. E. Nikonov, Y-H. Chu, S. Salahuddin and R. Ramesh, *Phys. Rev. Lett.*, **2011**, 107, 217202
- [13] Tuomas H. E. Lahtinen, Kévin J. A. Franke and Sebastiaan van Dijken, *Scientific Reports* **2012**, 2, 258
- [14] T. Kimura, T. Goto, H. Shintani, K. Ishizaka, T. Arima and Y. Tokura, *Nature*, **2003**, 406, 55
- [15] N. Hur, S. Park, P. A. Sharma, J. S. Ahn, S. Guha and S-W. Cheong, *Nature*, **2004**, 429, 392
- [16] M. Fiebig, Th. Lottermoser, D. Fröhlich, A. V. Goltsev and R. V. Pisarev, *Nature*, **2002**, 419, 818
- [17] Z. J. Huang, Y. Cao, Y. Y. Sun, Y. Y. Xue and C. W. Chu, *Phys. Rev. B*, **1997**, 56, 2623

- [18] V. Scagnoli, U. Staub, Y. Bodenthin, R. A. de Souza, M. García-Fernández, M. Garganourakis, A. T. Boothroyd, D. Prabhakaran and S. W. Lovesey, *Science*, **2011**, 332, 696
- [19] T. Kimura, Y. Sekio, H. Nakamura, T. Siegrist and A. P. Ramirez, *Nature Mater.*, **2008**, 7, 291
- [20] June Hyuk Lee, Lei Fang, Eftihia Vlahos, Xianglin Ke, Young Woo Jung, Lena Fitting Kourkoutis, Jong-Woo Kim, Philip J. Ryan, Tassilo Heeg, Martin Roeckerath, Veronica Goian, Margitta Bernhagen, Reinhard Uecker, P. Chris Hammel, Karin M. Rabe, Stanislav Kamba, Jürgen Schubert, John W. Freeland, David A. Muller, Craig J. Fennie, Peter Schiffer, Venkatraman Gopalan, Ezekiel Johnston-Halperin and Darrell G. Schlom, *Nature*, **2010**, 466, 954
- [21] J. T. Heron, J. L. Bosse, Q. He, Y. Gao, M. Trassin, L. Ye, J. D. Clarkson, C. Wang, Jian Liu, S. Salahuddin, D. C. Ralph, D. G. Schlom, J. Íñiguez, B. D. Huey and R. Ramesh, *Nature*, **2014**, 516, 370
- [22] L. Keeney, T. Maity, M. Schmidt, A. Amann, N. Deepak, N. Petkov, S. Roy, M. E. Pemble and R. W. Whatmore, *J. Am. Ceram. Soc.*, **2013**, 96, 2339
- [23] Somdutta Mukherjee, Amritendu Roy, Sushil Auluck, Rajendra Prasad, Rajeev Gupta and Ashish Garg, *Phys. Rev. Lett.*, **2013**, 111, 087601
- [24] D. M. Evans, A. Schilling, A. Kumar, D. Sanchez, N. Ortega, M. Arredondo-Arechavala, R. Katiyar, J. M. Gregg and J. F. Scott, *Nat. Comms.*, **2013**, 4, 1534
- [25] D. M. Evans, A. Schilling, Ashok Kumar, D. Sanchez, N. Ortega, R. S. Katiyar, J. F. Scott and J. M. Gregg, *Phil. Trans. R. Soc. A*, **2014**, 372, 2009
- [26] J. Schiemer, M. A. Carpenter, D. M. Evans, J. M. Gregg, A. Schilling, M. Arredondo, M. Alexe, D. Sanchez, N. Ortega, R. S. Katiyar, M. Echizen, E. Colliver, S. Dutton and J. F. Scott, *Adv. Funct. Mater.*, **2014**, 24, 2993
- [27] Dilsom A. Sanchez, N. Ortega, Ashok Kumar, R. Roque-Malherbe, R. Polanco, J. F. Scott and Ram S. Katiyar, *AIP Adv.*, **2011**, 1, 042169

- [28] Dilsom A. Sanchez, Nora Ortega, Ashok Kumar, G. Sreenivasulu, Ram S. Katiyar, J. F. Scott, Donald M. Evans, Miryam Arredondo-Arechavala, A. Schilling and J. M. Gregg, *J. Appl. Phys.*, **2013**, *113*, 074105
- [29] R. O. Kuzian, V. V. Laguta and J. Richter, *Phys. Rev. B*, **2014**, *90*, 134415
- [30] R. O. Kuzian, I. V. Kondakova, A. M. Daré and V. V. Laguta, *Phys. Rev. B*, **2014**, *89*, 024402
- [31] M. D. Glinchuk, E. A. Eliseev, A. N. Morozovska, *J. Appl. Phys.*, **2014**, *116*, 054101
- [32] R. G. P. McQuaid, L. J. McGilly, P. Sharma, A. Gruverman and J. M. Gregg, *Nat. Comms.*, **2011**, *2*, 404
- [33] Pankaj Sharma, Raymond G. P. McQuaid, Leo J. McGilly, J. Marty Gregg and Alexei Gruverman, *Adv. Mater.*, **2013**, *25*, 1323
- [34] L. W. Chang, M. McMillen, F. D. Morrison, J. F. Scott and J. M. Gregg, *Appl. Phys. Lett.* **2008**, *93*, 132904
- [35] G. Catalan, *Appl. Phys. Lett.*, **2006**, *88*, 102902
- [36] David L. Fox, D. R. Tilley, J. F. Scott and H. J. Guggenheim, *Phys Rev B*, **1980**, *21*, 2926
- [37] W. Peng, N. Lemée, J. Holc, M. Kosec, R. Blinc and M. G. Karkut, *J. Magn. Magn. Mat.* **2009**, *321*, 1754

Figure 1: Magnetic and electric fields both cause ferroelectric switching. Panels (a) to (d) present piezoresponse force microscopy images (phase superimposed on amplitude) of a lead zirconate titanate-lead iron tantalate (PZTFT) single crystal lamella integrated into a simple coplanar device after the following bias levels and magnetic fields had been applied at room temperature: (a) -15V, (b) +15V, (c) -15V, (d) “+” 3kOe perpendicular to the lamella (parallel to a $[\bar{1}10]_{pc}$ crystallographic direction in the PZTFT). The magnetic field in this orientation has caused switching of ferroelectric domains comparable to that caused by the +15V bias. The lamella dimensions were typically $\sim 10\mu\text{m} \times 5\mu\text{m} \times 0.3\mu\text{m}$.

Figure 2: Effects of magnetic field on capacitance at 150K. Magnetic fields were found to alter the way in which capacitance varied as a function of voltage ($C(V)$) in the PZTFT single crystal capacitor (a). The low field capacitance was monitored as a function of magnetic field only, applied parallel to the $[001]_{pc}$, $[110]_{pc}$ and $[\bar{1}10]_{pc}$ directions (b, c and d respectively) as defined in figure 1. In all cases, the magnetic field caused significant changes in capacitance and the response was hysteretic. For fields applied along $[\bar{1}10]_{pc}$, capacitance changes were comparable with those associated with ferroelectric switching in the $C(V)$ response.

Figure 3: Analysis of the room temperature magnetisation of the bulk PZTFT ceramic.

To gauge the broad manner in which the magnetic field might affect capacitance ($C(H)$), the room temperature magnetisation as a function of field in the bulk ceramic PZTFT was first fitted to two tanh functions (a). This allowed ready calculation of dM/dH and $-M(dM/dH)$ as a function of magnetic field [(b) and (c) respectively]. If P^2M^2 coupling is present in the material (which is always allowed by symmetry), then expectations from Landau free energy expansions are that dC^{-1}/dH should be proportional to $M(dM/dH)$.

Figure 4: Probing the existence and relative magnitude of P^2M^2 coupling in PZTFT. Plots of dC^{-1}/dH as a function of magnetic field applied along the $[001]_{pc}$, $[110]_{pc}$ and $[\bar{1}10]_{pc}$ directions (a, b and c respectively) in the single crystal lamella coplanar capacitor, at 150K. Red data points are for increasing field and blue data points for decreasing field. For magnetic fields applied along $[001]_{pc}$ (parallel to the electrode-dielectric interface and in the plane of the lamella), the plot is similar to that of $-M(dM/dH)$ in figure 3(c). This is consistent with measurable P^2M^2 coupling. The magnitude of the P^2M^2 coupled response is reduced, but still evident, when magnetic fields are along $[110]_{pc}$ (in the plane of the lamella and perpendicular to the electrode-dielectric interface) in (b) and almost imperceptible when the field is along $[\bar{1}10]_{pc}$ (perpendicular to the plane of the lamella) in (c). The minor influence of symmetric P^2M^2 behaviour for fields along $[\bar{1}10]_{pc}$ is consistent with the observed magnetic field-induced ferroelectric switching, which requires asymmetric coupling terms (such as PM). Capacitance still shows a significant dependence on magnetic field in this orientation (not explained by PM coupling), even at room

temperature (d), and so the reality is probably that more complex coupling behaviour involving explicit strain terms occurs.

Figure 5: Magnetic and electric field directions in relation to suspected polar vector

orientations. The directions of the applied magnetic fields in relation to a cross-section of the PZTFT lamella capacitor structure are shown schematically in (a). In (b) is a stereogram of the polar directions (poles plotted using black filled circles and black rings) associated with the rhombohedral ferroelectric domains suspected at 150K. The orientation of the stereogram in (b) is the same as that of the capacitor cross-section schematic in (a). $H_{[001]}$ is distinct by symmetry from the other two magnetic field directions. However, even the measured magnetocapacitance responses for $H_{[110]}$ and $H_{[110]pc}$ should be expected to differ, as in one case the sensing electric field is parallel to the applied magnetic field, whereas in the other case, it is perpendicular.

Table of Contents Entry:

The coupling between magnetization and polarization in a room temperature multiferroic (PZTFT) is explored by monitoring changes in capacitance that occur when a magnetic field is applied in each of three orthogonal directions. Magnetocapacitance effects, consistent with P^2M^2 coupling, are strongest when fields are applied in the plane of the single crystal sheet investigated.

Keyword: Magnetocapacitance

Donald M. Evans, Marin Alexe, Alina Schilling, Ashok Kumar, Dilsom Sanchez, Nora Ortega,

Ram S. Katiyar, James F. Scott and J. Marty Gregg*

Title: ToC Magnetolectric Coupling in PZTFT