**QUEEN'S
UNIVERSITY
BELFAST**

Whey Protein Complexes with Green Tea Polyphenols: Antimicrobial, Osteoblast-Stimulatory, and Antioxidant Activities

Carson, M., Keppler, J. K., Brackman, G., Dawood, D., Vandrovicova, M., Fawzy El-Sayed, K., Coenye, T., Schwarz, K., Clarke, S., Skirtach, A. G., & Douglas, T. EL. (2019). Whey Protein Complexes with Green Tea Polyphenols: Antimicrobial, Osteoblast-Stimulatory, and Antioxidant Activities. *Cells, tissues, organs*.
<https://doi.org/10.1159/000494732>

Published in:
Cells, tissues, organs

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights
© 2019 S. Karger AG, Basel. This work is made available online in accordance with the publisher's policies. Please refer to any applicable terms of use of the publisher.

General rights
Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy
The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

Whey protein complexes with green tea polyphenols: antimicrobial, osteoblast-stimulatory and antioxidant activities

Matthew Carson¹, Julia K. Keppler², Gilles Brackman³, Daniel Dawood⁴, Marta Vandrovцова⁵, Karim Fawzy El-Sayed^{4,6}, Tom Coenye³, Karin Schwarz², Susan A. Clarke¹, Andre G. Skirtach^{7,8}, Timothy E.L. Douglas^{7,9,10*}

¹School of Nursing and Midwifery, Queen's University Belfast, Belfast, United Kingdom, ²Christian-Albrechts-Universität zu Kiel, Department of Food Technology, Institute of Human Nutrition and Food Science, Kiel, Germany, ³Laboratory of Pharmaceutical Microbiology, Ghent University, Ghent, Belgium, ⁴Clinic for Conservative Dentistry and Periodontology, School for Dental Medicine, Christian-Albrechts-University Kiel, Kiel, Germany, ⁵Department of Biomaterials and Tissue Engineering, Institute of Physiology, the Czech Academy of Sciences, Prague, Czech Republic, ⁶Oral Medicine and Periodontology Department, Faculty of Oral and Dental Medicine, Cairo University, Egypt, ⁷Department of Molecular Biotechnology, Faculty of Bioscience Engineering, Ghent University, Belgium, ⁸Centre for Nano- and Biophotonics, Ghent University, Belgium, ⁹Engineering Department, Lancaster University, United Kingdom, ¹⁰Materials Science Institute (MSI), Lancaster University, United Kingdom.

Short title: Combined biological effects of beta-lactoglobulin with green tea polyphenols

* Corresponding author: t.douglas@lancaster.ac.uk

Dr. Timothy E.L. Douglas MSc MEng, Engineering Department, Gillow Avenue, Lancaster University, Lancaster, LA1 4YW, United Kingdom, Tel: + 44 1524 594450

Keywords: whey protein isolate, polyphenol, osteoblast, antibacterial, antioxidant

Abstract

Polyphenols are known for their antimicrobial activity, whilst both polyphenols and the globular protein beta-lactoglobulin (bLG) are suggested to have antioxidant properties and to promote cell proliferation. These are potentially useful properties to have as part of a tissue engineered construct, though it is unknown if they are retained when both compounds are used in combination. In this study, a range of different microbes and an osteoblast-like cell line (hFOB) were used to assess the combined effect of; (1) a green tea extract (GTE), rich in the polyphenol epigallocatechin gallate (EGCG), and (2) a whey protein isolate (WPI), rich in bLG. It was shown that approximately 20–48 % of the EGCG in GTE reacted with WPI. GTE inhibited the growth of gram-positive bacteria, an effect which was potentiated by the addition of WPI. GTE alone also significantly inhibited the growth of hFOB cells after 1, 4 and 7 days of culture. Alternatively, WPI significantly promoted hFOB cell growth in the absence of GTE and attenuated the effect of GTE at low concentrations (64 µg/ml), after 4 and 7 days. Low concentrations of WPI (50 µg/ml) also promoted expression of the early osteogenic marker alkaline phosphatase (ALP) by hFOB cells, whereas GTE inhibited alkaline phosphatase ALP activity. Therefore, the antioxidant effects of GTE can be boosted by WPI, but it is not suitable to be used as part of a tissue-engineered construct due to its cytotoxic effects which negate any positive effect of WPI on cell proliferation.

46 **List of Abbreviations**
47
48 ALP = alkaline phosphatase
49 ANOVA = one-way analysis of variance
50 ATCC = the American Type Culture Collection
51 bLG = beta-lactoglobulin
52 BOF = Bijzonder Onderzoeksfonds (Special Research Fund)
53 CFU = colony forming units
54 DAD = diode array detector
55 ddH₂O = sterile ultra-pure water
56 DFG = Deutsche Forschungsgemeinschaft (German Research Foundation)
57 DMEM = Dulbecco's modified Eagle medium
58 DNA = deoxyribonucleic acid
59 DPPH = 2,2-diphenyl-1-picrylhydrazyl
60 EC = epicatechin
61 ECG = epicatechingallate
62 EGC = epigallocatechine
63 EGCG = epigallocatechin gallate
64 EUCAST = The European Committee on Antimicrobial Susceptibility Testing
65 FRAP = ferric reducing ability of plasma
66 FWO = Fonds voor Wetenschappelijk Onderzoek - Vlaanderen (Research Foundation- Flanders)
67 GTE = green tea extract
68 hFOB = human foetal osteoblast
69 HPLC = high performance liquid chromatography
70 MgCl₂ = magnesium chloride
71 MH broth = Mueller-Hinton broth
72 MIC = minimal inhibitory concentration
73 MRSA = methicillin-resistant *Staphylococcus aureus*
74 NaCl = sodium chlorid
75 NaOH = sodium hydroxide
76 PBS = phosphate buffered saline
77 ROS = reactive oxygen species
78 RPMI medium = Roswell Park Memorial Institute medium
79 S.D. = standard deviation
80 TEAC = Trolox equivalent antioxidant capacity
81 TFA = trifluoroacetic acid
82 WPI = whey protein isolate
83
84
85

Introduction

Antibacterial properties are highly desirable characteristics for bone regeneration materials, especially in oral and maxillofacial surgery due to the high microbial load of the oral cavity (George et al. 1994; Chen et al. 2010; Gosau et al. 2016). Due to the increasing occurrence of antibiotic-resistant bacteria, such as methicillin-resistant *Staphylococcus aureus* (MRSA) (Klein et al. 2016; Kavanagh et al. 2017), there is a pressing need to find alternative low cost antibacterial agents, to which there is little resistance.

Green tea extract (GTE) is known to be rich in polyphenols, which in turn possess antibacterial activity (Zhao et al. 2001; Gharib et al. 2013) (for a review see (Steinmann et al. 2013)). One major polyphenol of GTE is epigallocatechin gallate (EGCG), which shows antibacterial activity against MRSA (Gharib et al. 2013) and is alleged to stimulate the growth and differentiation of bone-forming cells (Vali et al. 2007; Jin et al. 2014). To improve stability of EGCG, it is commonly combined with carrier proteins, such as the globular protein beta-lactoglobulin (bLG) (Keppler et al. 2015). bLG is a major component of whey protein isolate (WPI), derived from milk. It consists of 162 amino acid residues, has a molecular weight of approximately 18.4 kDa and is known to be able to bind hydrophobic molecules (Kontopidis et al. 2004). Besides its application as a carrier protein, bLG has been reported to improve the proliferation of various mammalian cells (Moulti-Mati et al. 1991; Mahmud et al. 2004; Gillespie et al. 2015). It is therefore hypothesised that bLG would also positively influence osteoblast growth, which would be desirable for bone regeneration applications.

Oxidative stress plays an important role in the immune response and has been identified as a pathological inducer in almost all organs (Wauquier et al. 2009). Despite its role in cell signaling, an increased level of oxidative stress can cause bone loss, leading to conditions such as osteoporosis, bone tumor development and inappropriate ingrowth of bone implants. Furthermore, increased levels of reactive oxygen species (ROS) have a supportive effect on osteoclasts, the cells responsible for bone resorption (Garrett et al. 1990; Bai et al. 2005). Thus, antioxidant activity of compounds used during bone substitution could conceivably improve the stability of an implant. EGCG and bLG both have antioxidant activity, which make them excellent candidates as loading agents for bone tissue regeneration (Tong et al. 2000; Tobi et al. 2002; Mann et al. 2015).

Although there is some data available on the micro and cell biological effects of GTE, WPI and their components, the effects of GTE and WPI in combination remain unexplored. It was therefore hypothesized that WPI would influence GTE's antimicrobial and antioxidant activity, as well as its impact on osteoblast growth/differentiation. In the present study, chemical interaction of GTE and WPI was analyzed by centrifugation, ultrafiltration and subsequent high performance liquid chromatography (HPLC) analyses. Antimicrobial activity was tested against a range of bacteria (both Gram-positive and Gram-negative) and fungi, whilst effects on osteoblast proliferation and differentiation were tested using an osteoblastic cell line. Finally, antioxidant properties were investigated using the DPPH (2,2-diphenyl-1-picrylhydrazyl) method. GTE has substantial antimicrobial and antioxidant capability and binds to WPI, which displayed positive effects on osteoblast activity.

Materials and Methods

Materials

125 Unless stated otherwise, all reagents were obtained from Sigma-Aldrich. WPI (BiPRO, Davisco Foods
126 International, Inc., Eden Prairie, US) with 97.7% protein and 75% bLG in dry matter (according to
127 specification) was used as previously described (Serfert et al. 2014; Keppler et al. 2017). GTE, > 95% (obtained
128 from green tea leaves, catechins content>75%, EGCG>65%; according to specification) was purchased from
129 Oskar Tropitzsch e. K. (Marktredwitz, Germany).

130

131 *Material analysis*

132 *Analysis of WPI*

133 The composition of the WPI was determined using a method described previously (Clawin-Radecker et al.
134 2000; Keppler et al. 2014). Briefly, a HPLC HP 1100 system (Agilent Technology, Germany) equipped with a
135 PLRP-S 300 Å 8 µm, 150 × 4.6 mm column (Polymer Laboratories, Varian, Inc.) and a diode array detector
136 (DAD) at 205 nm wavelengths was used. Eluent A was 0.1% trifluoroacetic acid (TFA) in water and eluent B was
137 0.1% TFA in acetonitrile. The following gradient was used: 0 min, 35% B; 1 min, 35% B; 8 min, 38% B; 16
138 min, 42% B; 22 min, 46% B; 22.5 min, 100% B; 23 min, 100% B and 23.5–30 min, 35% B. Flow rate was 1
139 ml/min, the injection volume was 20 µl and the column temperature was set to 40 °C. Standards of bovine
140 serum albumin, alpha-lactalbumin and beta-lactoglobulin were run for identification.

141 *Analysis of GTE*

142 GTE was analysed by HPLC (Agilent 1100, with a DAD at 280 nm wavelength) using a C18-Nucleodur Sphinx
143 125/4 reversed phase column, 5 µm (Macherey-Nagel GmbH & Co. KG, Düren, Germany). Eluent A consisted
144 of water with 0.1 % formic acid, whilst eluent B was acetonitrile with 0.1 % formic acid. The following gradient
145 was used: 0–1 min, 5 % B; 1–10 min, 95 % B; 10–10.5 min, 95 % B; 10.5 – 11 min, 5 % B and 11–12 min, 5 %
146 B. Standards of the GTE components (EGCG, epigallocatechine (EGC), epicatechingallate (ECG) and
147 epicatechin (EC)) were run to identify the respective signals in the GTE. Percentage composition of the
148 components was assessed semiquantitatively, by comparing individual peak areas to the sum of all peak areas.

149

150 *Binding studies*

151 For binding analysis, approximately 4 mg/ml WPI in water were weighed together with GTE in a concentration
152 ratio of 1:0.08 g (w/w), 1:0.16 g (w/w), 1:0.32 g (w/w) and 1:0.64 g (w/w). Subsequently, samples were
153 dissolved in demineralized water for 30min at room temperature with vigorous stirring. For control, solutions of
154 GTE without WPI were prepared at a similar concentration. Vivaspin 2 centrifugal filtration devices
155 (Hydrosart® regenerated cellulose membrane, 10 kDa), from Sartorius AG (Göttingen, Germany), were rinsed
156 with 2ml demineralized water. Following this, 1ml of the respective sample solution (i.e. GTE with and without
157 WPI) was centrifuged, using 4000*g for 2 min at 20 °C - in a swinging-bucket rotor centrifuge. The filtrate and
158 remaining retentate were discarded and replaced again by 1 ml of sample solution. After centrifugation, the
159 filtrate was analysed via HPLC, using the aforementioned method for GTE analysis. As controls, uncentrifuged
160 GTE samples were also analysed, to determine the amount of GTE lost in the membrane during filtration.

161

162 *Antioxidant method (DPPH test)*

163 The radical scavenging activity of the different WPI/GTE complexes was analysed using a modification of the
164 DPPH test described by Harbaum et al. (Harbaum et al. 2008). The DPPH assay was carried out by mixing 1 mL

165 of 0.3 mmol/L 2,2-diphenyl-1-picrylhydrazyl (DPPH radical) in ethanol with 1.95 mL of 25% aqueous ethanol,
166 containing 0.1 M phosphate buffered saline (PBS) buffer. This gave a final 50% ethanolic solution. An initial
167 reading was carried out at 516 nm (initial absorbance approximately 1.3). Subsequently, a 50 µL sample (also
168 dissolved in ethanol) was added, and the absorbance was measured after 10 minutes of reaction time. The
169 antioxidative capacity was given as % inhibition: %inh = $([A_0 - A_1]/A_0) \times 100$, where A₀ is the initial absorbance
170 of the standard and A₁ is the absorbance of the sample.

171

172 *Antibacterial studies*

173 *Staphylococcus aureus* ATCC 700699, ET199 and LMG10147, *Staphylococcus epidermidis* ET086 and *P.*
174 *aeruginosa* ATCC9027 were cultured aerobically in Mueller-Hinton broth (MH; Oxoid, Basingstoke, England),
175 at 37°C. *Propionibacterium acnes* LMG 16711 was cultured anaerobically in Reinforced clostridial medium
176 (RCM; Oxoid), at 37°C. *Candida albicans* ATCC MYA-2876 was cultured aerobically in RPMI 1640 medium
177 (Sigma-Aldrich, Diegem, Belgium), at 37°C.

178 Determination of the Minimal Inhibitory Concentration (MIC): MIC of GTE alone or in the presence of WPI
179 (50 or 800 µg/ml) was determined according to the EUCAST broth microdilution protocol, using flat-bottom
180 96-well microtiter plates (TPP, Trasadingen, Switzerland). The inoculum was standardized to approximately $5 \times$
181 10^5 colony forming units (CFU)/ml. The concentration of GTE tested ranged from 0.5 - 1024 µg/ml. The plates
182 were incubated at 37°C for 24 h, and the optical density at 590 nm was determined using a multilabel microtiter
183 plate reader (Envision; Perkin-Elmer LAS, Waltham, MA). MIC was recorded as the lowest concentration of
184 GTE, alone or in combination with WPI, which displayed a similar optical density as that observed in inoculated
185 and blank wells.

186

187 *Cytocompatibility testing using fibroblasts*

188 Human fibroblasts were isolated from the gingiva of seven patients (4 female, aged 21, 25, 20 and 20 years and
189 3 male, aged 36, 21 and 21 years) cultured in cell culture medium (Eagle's minimum essential Medium Alpha
190 modification (Sigma-Aldrich GmbH, Hamburg, Germany), antibiotics (100 U x mL⁻¹ Penicillin, 100 µg x mL⁻¹
191 Streptomycin, Biochrom, Berlin, Germany), 1 % Amphotericin (Biochrom), 15 % fetal bovine serum (FBS)
192 (HyClone, Logan, Utah, USA) and 400 mmol x mL⁻¹ L-Glutamine) for 7 days, then medium was exchanged
193 three times per week Ethical approval (number D444/10) was obtained from University Hospital Schleswig-
194 Holstein, Campus Kiel, Germany. Fibroblasts in the third passage were pooled and 5×10^3 were seeded in 96-
195 well plates, i.e. 1.56×10^4 cells/cm². Cytocompatibility was assessed by incubating cells with medium
196 containing 0, 50 or 800 µg/ml WPI and 0, 64, 128, 256, 512, 1024, 2048 or 4096 µg/ml GTE. Morphology was
197 assessed by light microscopy after 7 days of culture. Medium was changed 3 times during this period.

198

199 *Cytocompatibility testing using hFOB osteoblast-like cells*

200 An immortalized human foetal osteoblast (hFOB) cell line (hFOB 1.19; LGC Standards, USA) was used in this
201 study, cultured in Dulbecco's modified Eagle medium (DMEM)/F12 (1:1) medium, supplemented with 10%
202 FBS, 1% L-glutamine and 0.6% geneticin (all Gibco, Life Technologies, UK). Treatments were prepared at
203 concentrations detailed in section 2.6, filter sterilised (0.22 µm) before use and protected from light. Cells were

seeded at 1×10^5 cells/cm² on 96-well sterile culture plates and given a 24 hour settling period before treatment. For all experimental conditions n=4.

hFOB proliferation

Proliferation was measured by crystal violet staining at 1, 4 and 7 days. After removing culture medium by aspiration, cells were fixed with 100µl of 4% paraformaldehyde solution for 1 hr at room temperature, washed twice with ddH₂O and left to air dry. Cell monolayers were then stained for 30 minutes at room temperature with 100µl of crystal violet solution per well (0.1% concentration), washed twice again in ddH₂O and air dried. Finally, the dye was extracted from monolayers by the addition of 100µl of 1M acidified methanol. Absorbance was read at 585nm using a Tecan GENios microplate reader, and blanked using acidified methanol.

hFOB differentiation

Alkaline phosphatase (ALP), an enzyme produced by maturing osteoblasts, was used as an indicator of cell differentiation. Briefly, cells were grown in complete medium supplemented with 10µM β-glycerophosphate and 50µM ascorbate-2-phosphate for 7, 14 or 21 days, before being washed with an alkaline buffer solution (5M NaCl, 1M Tris-Cl pH 9.5, 1M MgCl₂). Cells were lysed by addition of 250µl of buffer - containing 0.2% Triton X-100 - and left to gently mix for 20 minutes on ice, before being stored at -80°C. Upon testing, 50 µl from each well was added to a test plate in duplicate. 200 µl of conditioned medium, consisting of alkaline buffer solution (Sigma) and p-nitrophenyl phosphate substrate was added to each well. Each test plate was then covered in foil and incubated for 30min at 37°C, allowing the coupled enzymatic reaction to proceed. The reaction was stopped by the addition of 50µl of stop solution (3M NaOH) and absorbance was read at 450nm. Finally, ALP readings were normalised to DNA concentration, determined via PicoGreen assay (in a method according to the manufacturer's protocol), to account for the effect of variances in cell proliferation.

Statistical analysis

Each result set is presented as the mean ± S.D. (Standard Deviation) and has been tested for normality, after undergoing a logarithmic transformation. Differences between treatments were analysed using one-way analysis of variance (ANOVA) with post hoc Tukey's test. All statistics were conducted in SPSS version 19 (IBM, USA). Values of $P \leq 0.05$ were considered significant.

Results

Extract composition and binding

Catechine composition of the GTE (>95 % polyphenols) was analysed by HPLC using external standards for the main components EGCG, EGC (epigallocatechin), ECG (epicatechingallate) and EC (epicatechin). The main catechine of the GTE was EGCG (88.5±0.14%). Only minor fractions of other catechines were present in the order ECG > EGC > EC (i.e., 5.3 ±0.03%, 3.7 ±0.09% and 2.4±0.08%, respectively). WPI was also analysed by HPLC and consisted primarily of bLG AB (75.7±1.4%), with alpha-Lactalbumin (14.7±0.1%) and <4% bovine serum albumin (Keppler et al. 2017).

The combination of GTE and WPI resulted in a non-covalent interaction, which was analysed by ultrafiltration (Figure 1). Of the catechines present, only those which contained an esterified gallic acid, such as EGCG and ECG, showed a significant interaction with WPI. Furthermore, non-covalent binding of catechines to

WPI decreased with increasing GTE concentration (i.e., 43.7 % of the initial EGCG concentration in 64 µg/ml GTE was found to interact with 800 µg/ml WPI, whereas only 30.5 % EGCG reacted after addition of 512 µg/ml GTE). ECG bound in a similar way to WPI, although with a slightly lower binding capacity (i.e., 45.3 % of the initial ECG concentration bound with WPI after addition of 64 µg/ml GTE, and 20.07 % after addition of 512 µg/ml GTE). The loss of catechines due to unspecific membrane interactions and co-precipitation in the GTE during the ultrafiltration method was acceptable (<22 %).

Antioxidant and antibacterial effects of GTE and WPI

In the DPPH test (Figure 2), the antioxidative capacity of WPI and GTE were tested by their capacity to scavenge the free DPPH radical. GTE alone exhibited a scavenging capacity of 20 and 28 % for 64 and 128 µg/ml GTE, respectively. However, the addition of WPI had a significant negative effect on the radical scavenging capacity of GTE. For example, inclusion of 800 µg/ml WPI reduced inhibition to ~13 and ~24 % for 64 and 128 µg/ml GTE, respectively. There was no radical scavenging effect of WPI alone.

For antibacterial activity, results of MIC (Table 1) determination revealed that in the absence of WPI the GTE concentrations required to inhibit growth of the bacteria ranged between 128-256 µg/ml. GTE hindered growth of gram-positive bacteria more strongly than growth of the gram-negative *P. aeruginosa*. Addition of WPI decreased the MIC of GTE towards the gram-positive bacteria *S. aureus* ATCC 700699 and *S. epidermidis* ET086, and in particular *P. acnes* LMG 16711. In contrast, WPI increased the MIC towards the gram-negative *P. aeruginosa* ATCC 9027. The growth of the yeast *C. albicans* ATCC MYA-2876 was not affected by GTE (MIC >1024 µg/ml, regardless of the addition of WPI).

Proliferation of fibroblasts and hFOB

Fibroblasts cultured in the absence of GTE (Figure 3) showed a spindle-like morphology typical of healthy fibroblasts, as did those exposed to all concentrations of WPI (0, 50 and 800 µg/ml). However, increasing concentration of GTE appeared to promote the formation of round, apoptotic bodies, indicating the cells were preparing themselves for phagocytosis and were thus not viable. At a GTE concentration of 64 µg/ml, only a few apoptotic bodies were observed. At 128 µg/ml GTE larger numbers of dead cells were detected, whilst at 256 µg/ml the majority of cells were dead. Higher GTE concentrations (data not shown) resulted in similar results as for 256 µg/ml GTE. Increasing WPI concentration to 50 or 800 µg/ml did not lead to an appreciable reduction in cell death. Hence, GTE concentrations above 128 µg/ml were excluded from further experiments.

For day 1 hFOB cultures, 64 and 128 µg/ml GTE reduced cell proliferation (Figure 4). This effect was not changed by the addition of WPI. At day 4, 64 and 128 µg/ml GTE reduced cell proliferation, but this reduction was attenuated by inclusion of 800 µg/ml WPI. At day 7, reduced cell proliferation was again observed with both 64 and 128 µg/ml GTE, though no attenuating effect of WPI was observed. At all GTE and WPI concentrations, the decrease in cell proliferation with GTE treatment was not a linear relationship.

WPI appears to promote small increases in cell proliferation, as in the absence of GTE 800 µg/ml WPI promoted cell proliferation at day 1 and 7. Furthermore, at 64 µg/ml GTE, proliferation was promoted by 800 µg/ml WPI at day 1 and 4; whilst in the presence of 128 µg/ml GTE, 800 µg/ml WPI promoted proliferation at day 4 only. 50 µg/ml WPI had no significant effect at any time point or GTE concentration.

Images of hFOB cells stained using the crystal violet method (Figure 5) agree with those for fibroblasts (Figure 3), and support crystal violet assay results (Figure 4). For example, hFOB cells cultured in the absence of GTE formed healthy monolayers, though at a GTE concentration of 64 µg/ml markedly fewer cells were observed. Of these, some - but not all cells - displayed an elongated morphology, typical of good adhesion. However, at the highest GTE concentration of 128 µg/ml even fewer cells were observed, providing further evidence of the inhibitory effect of GTE on cell proliferation.

Differentiation of hFOB cells

Only 0 and 64 µg/ml concentrations of GTE were used in differentiation experiments, as 128 µg/ml GTE had a detrimental effect on hFOB proliferation. Day 7 (Figure 6a) timepoint treatments showed the highest overall levels of alkaline phosphatase (ALP) activity. In WPI subgroup, 64 µg/ml GTE treatments showed significantly reduced ALP levels compared to those with no GTE. This trend is maintained at all timepoints, with the exception of the 0 µg/ml WPI subgroup at day 21, where ALP activity is very similar for both GTE treatments. WPI however shows a bell-shaped response, with 50 µg/ml concentrations causing increased ALP activity levels, compared to 0 and 800 µg/ml treatment wells. These increases for the 50 µg/ml treatment group are significant at day 7, significant compared to the 800 µg/ml treatment at day 14, and the 0 µg/ml treatments at day 21.

Discussion

This study aimed to determine the combined effects of GTE and WPI, focusing on traits that would be useful for bone regeneration materials – such as antimicrobial and antioxidant activity, as well as impacts on osteoblast growth/differentiation. Firstly, binding assay results showed that significant complexes between GTE and WPI occurred. This was expected, given that previous studies have reported the binding efficiency of whey proteins with green tea catechins (Keppler et al. 2015). For example, galloylated catechins, such as EGCG and ECG, were found to react most strongly with proteins, and exhibited good antioxidative capacity (Bohin et al. 2012). Due to the nature of the non-covalent reaction, the catechins bound to the protein are always in equilibrium with unbound catechins, explaining the reported 50% binding of this work.

GTE's high radical inhibition capacity was also expected, being mediated by its >95% polyphenol content, of which most take the form of EGCG (Supplementary Figure 1). Previous studies have shown EGCG and ECG to be two of the most potent radical scavenging flavonoids present in GTE (Salah et al. 1995; Hirano et al. 2001). However, the addition of WPI caused a masking effect on GTE scavenging activity, as evidenced by a decrease in its percentage inhibition. Such an effect on protein-bound polyphenols is probably mediated by hydrogen bonds, which occur between the hydroxyl groups of the catechins and the protein (Kanakakis et al. 2011). A similar masking effect was observed for caseins with green tea catechins using the Trolox equivalent antioxidant capacity (TEAC) test (Arts et al. 2001), and for BSA and EGCG complexes using the ferric reducing ability of plasma (FRAP) test (Zorilla et al. 2011). Interestingly, this masking effect on percentage inhibition observed in the present study amounted to a reduction of approximately 4 to 7%, after the addition of 50 and 800 µg/ml WPI, respectively. However, the binding assay showed an interaction of approximately 50 % of the GTE. Therefore, it is likely that binding occurs in a way that leaves antioxidative groups of GTE partially available, even after interaction with the protein.

The main drawback of the DPPH test is the low solubility of DPPH in water, thereby introducing ethanol into the system, which could denature the WPI. It was reported that denatured whey proteins interact more readily with GTE catechines (Keppler et al. 2014), which could result in an overestimation of the masking effect for native WPI. It should be kept in mind that antioxidant assays used here (and in the literature) are optimized to stabilize the radical in solution, which requires either solvents like ethanol or methanol, or the addition of different salts. This will always influence the analysis of antioxidative capacity for protein-polyphenol complexes, because of the sensitivity of non-covalent binding reactions, which are likely altered even by the addition of salts or minor pH value changes.

GTE's anticipated antibacterial activity was confirmed in this study, with its inclusion at concentrations between 128-256 µg/ml inhibiting the growth of all bacteria tested. [This is in agreement with similar work within the field, whereby GTE extracts of various forms were shown to have diverse antibacterial activity – such as against *S. aureus*, *S. epidermidis*, *P. acnes* and *P. aeruginosa* \(Lee et al. 2009a; Sharma et al. 2012; Radji et al. 2013\).](#) In the present study, addition of WPI facilitated GTE's antibacterial activity toward *P. acnes* LMG 16711, with the MIC decreasing from 128 to 32 µg/ml (50 µg/ml WPI) and even 16 µg/ml (800 µg/ml WPI). A similar trend was also seen for *S. aureus* ATCC 700699 and *S. epidermidis* ET086, though MIC reduction was much less pronounced and was likely within the tests margin of error. For the Gram-negative Bacterium *P. aeruginosa* the opposite effect was seen, whereby addition of WPI gave rise to a drastic increase in MIC (from 256 to 1024 µg/ml). Although the reasons behind the differences observed between Gram-positive and Gram-negative bacteria are unclear, the presence of a second (outer) membrane in Gram-negative bacteria may play an important role. It can be speculated that protein-bound catechins are less able to interact with peptidoglycan in the bacterial cell wall, making it difficult for these complexes to cross the outer membrane. EGCG also has a negative charge, which might be a reason for its lower affinity to Gram-negative bacteria (Yoda et al. 2004). [Furthermore, it should be noted that previous work showed *P. aeruginosa* to have a MIC twice that of *S. aureus* \(800 compared to 400 µg/ml\) \(Radji et al. 2013\), which may partly explain the increase in MIC seen after WPI inclusion.](#) Finally, the fungus, *C. albicans*, did not respond at all to GTE treatment (MIC >1024 µg/ml). Previously, it was reported (Hirasawa and Takada 2004) that EGCG had an anti-*C. albicans* effect, which increased with increasing pH and concentration. In our study, pH was 7.4 and the concentration was 1000x lower, which may explain the lack of response seen. However, the mechanism of GTE's anti-*C. albicans* effect remains unclear.

Good antibacterial and antioxidant capacity are both desirable characteristics for regeneration materials, helping support a healthy healing site after bone damage. However, cell response also needs to be determined, to ensure cytocompatibility before clinical application. Fibroblast images (figure 3) helped to give a qualitative insight into GTE and WPI's effect, showing WPI to have no obvious impact on cell adhesion or morphology. However, increasing GTE concentration caused significant changes in cell morphology, attachment and increased mortality. [This is similar to findings of another study, whereby both normal and keloid fibroblasts were shown to decrease proliferation in a dose-dependent manner with EGCG treatment \(Park et al. 2008\).](#) Returning to the present study, fibroblast findings were also mirrored in proliferation results of an osteoblast-like cell line (hFOB 1.19), whereby 800 µg/ml WPI increased cell growth. Alternatively, GTE inclusion reduced proliferation, particularly at later time intervals, and this was only partially mitigated by the addition of WPI.

Field Code Changed

363 Previous work reports that WPI, especially its component bLG, has a mitotic effect on different cell
364 types, which would explain its stimulative effect on hFOB proliferation. [For instance, Gillespie et al. reported](#)
365 [that bLG \(312.5-2500 µg/ml\) improved the proliferation of enteroendocrine cells \(Gillespie et al. 2015\), whilst](#)
366 [another study investigated mouse spleen resting cells. Here, a proliferative effect was found in the concentration](#)
367 [range 50-500 µg/ml, over 12-96 hours \(Mahmud et al. 2004\). For GTE polyphenols, the literature often reports a](#)
368 [positive effect on bone metabolism, such as increased osteoblast maturation and production of mineralised](#)
369 [material \(Ko et al. 2009\). Our opposite finding could be due to the different composition of catechins used in](#)
370 [this study, as work by Ko et al. \(Ko et al. 2009\) did not include EGCG specifically. Alternatively, it may](#)
371 [indicate that even the minimum GTE concentration used in this work was too high, causing suppressive effects](#)
372 [on cell activity. In support of this, other similar studies using osteoblast-like cells tended to use lower](#)
373 [concentrations, compared to the 64 and 128 µg/ml doses of the present study. For example, rat mesenchymal](#)
374 [stem cells \(Ko et al. 2011\), Saos-2 \(Nash and Ward 2016\) and human osteoblast cells \(Vester et al. 2014\) all](#)
375 [showed increased levels of cell differentiation and limited cytotoxicity when treated with GTE concentrations of](#)
376 [around 10 µg/ml \(a maximum of 50 and minimum of 0.01 µg/ml\). Another similar study, testing EGCG,](#)
377 [demonstrated no toxic effect at 10 µg/ml \(Lee et al. 2009b\); and whilst higher concentrations are occasionally](#)
378 [tested, exposure times are generally shorter. For example, rat calvarial osteoblasts were treated with green tea](#)
379 [polyphenols at a 200 µg/ml dose, to prevent alterations upon exposure to H₂O₂; though only for a 1 hour period](#)
380 [\(Park et al. 2003\).](#) Returning to the present study, GTE's inclusion also reduced bLG bioactivity, or
381 bioavailability, which most likely resulted from binding between the two extracts.

382 The final indicator of cell activity investigated was ALP, expressed during osteoblast maturation,
383 which is considered an early marker of osteogenic differentiation (Setzer et al. 2009). Though it was evaluated
384 on days 7, 14 and 21, the highest ALP activity was measured on day 7, in the 50 µg/ml WPI treatment group.
385 The consistently high ALP activity in this treatment, compared to 0 and 800 µg/ml, indicates WPI has an
386 optimal concentration able to stimulate hFOB differentiation. On the other hand, GTE caused a decrease in ALP
387 activity, often reducing the activity levels by 50% or more in wells with no GTE added. This is in agreement
388 with a study (Yamaguchi and Ma 2001) concerning the effect of polyphenols on ALP activity in rat femoral
389 tissues, which concluded that EGCG (0.1 mM) significantly inhibited ALP activity. Furthermore, the current
390 study's results appear to support a previously reported interaction between ALP and polyphenols from the
391 seaweed-derived nutritional supplement Seanol® (Douglas et al. 2016). Here, a similar concentration of
392 polyphenols were used in supplements, which were shown to have reduced release rates during ALP-mediated
393 mineralisation. [However, it is important to note there are also several studies where treatment with GTE](#)
394 [increased osteoblast differentiation, such as with the aforementioned work using rat mesenchymal stem cells](#)
395 [\(Ko et al. 2011\), Saos-2 \(Nash and Ward 2016\), and human osteoblast cells \(Vester et al. 2014\). These cells](#)
396 [showed increased levels of many differentiation indicators, including ALP activity, mineralisation levels and](#)
397 [gene expression for proteins including sclerostin, osteopontin and osteocalcin. The contrasting reports of GTE](#)
398 [both inhibiting and promoting cell differentiation are likely a reflection of the overall concentration and](#)
399 [polyphenol content of each extract tested.](#) Finally, in terms of the present study's interaction effects of GTE and
400 WPI, GTE again reduced WPI bioactivity. However, the presence of 50 or 800 µg/ml WPI did not obviously
401 mitigate the negative effect of 64 µg/ml GTE, indicating more WPI binding is needed to promote hFOB
402 differentiation in these treatments.

Field Code Changed

Field Code Changed

Cell based assay results are arguably the most important when determining a compound or extract's suitability for different applications, such as tissue engineering. GTE's cytotoxicity, whilst slightly mitigated by WPI, makes it unsuitable for inclusion at sites undergoing skeletal regeneration, as it would likely limit osteoblast activity. One related limitation of this work was the minimum GTE concentration tested, of 64 µg/ml. Lower concentrations may have preserved GTE's antimicrobial and antioxidant capacity, whilst also limiting cytotoxicity – especially with WPI inclusion. Similarly, further processing of GTE could have been conducted, to create GTE treatments with different polyphenol compositions and potentially better cytocompatibility.

This work demonstrated the affinity of WPI for components of GTE, and the formation of WPI/GTE complexes. GTE displayed excellent antioxidative capacity, which was not significantly affected by addition of WPI; though some masking effect is possible. Furthermore, GTE showed antimicrobial activity against gram-positive and gram-negative bacteria, with WPI inclusion potentiating this effect on several types of gram-positive bacteria. However, with cells GTE showed cytotoxic and suppressive effects on both fibroblasts and hFOB, especially at concentrations of 128 µg/ml and above. WPI alone though enhanced hFOB proliferation and attenuated the suppressive effect of GTE at 64 µg/ml, to a certain extent. For hFOB differentiation, WPI significantly stimulated ALP activity at a 50 µg/ml concentration, though was less able to attenuate effects of GTE inclusion. These results therefore show that WPI and GTE both have useful properties, but the cytotoxicity of GTE makes it unsuitable for inclusion within a tissue engineered construct.

Acknowledgement and ethical approval, informed consent and conflict of interest statements

FWO, Belgium for a postdoctoral fellowship (T.E.L.D.). BOF of Ghent University for financial support (A.G.S.). DFG, Germany for funding (J.K.K.). N. Mathijs, M. Paymard-Stolz and M. Pfeiler for excellent technical assistance. Ethical approval was obtained from the relevant ethics committee. Informed consent was obtained from patients. The authors have no conflict of interest.

References

- Arts M.J.T.J., Haenen G.R.M.M., Voss H.P. & Bast A. (2001) Masking of antioxidant capacity by the interaction of flavonoids with protein. *Food and Chemical Toxicology* 39:787-791.
- Bai X.C., Lu D., Liu A.L., Zhang Z.M., Li X.M., Zou Z.P., Zeng W.S., Cheng B.L. & Luo S.Q. (2005) Reactive oxygen species stimulates receptor activator of NF-kappa B ligand expression in osteoblast. *Journal of Biological Chemistry* 280:17497-17506.
- Bohin M.C., Vincken J.P., van der Hijden H.T.W.M. & Gruppen H. (2012) Efficacy of Food Proteins as Carriers for Flavonoids. *Journal of Agricultural and Food Chemistry* 60:4136-4143.
- Chen T., Yu W.H., Izard J., Baranova O.V., Lakshmanan A. & Dewhirst F.E. (2010) The Human Oral Microbiome Database: a web accessible resource for investigating oral microbe taxonomic and genomic information. *Database-the Journal of Biological Databases and Curation*
- Clawin-Radecker I., Kiesner C. & Schlimme E. (2000) Analysis of the acid-soluble contents of alpha-lactalbumin, beta-lactoglobulin, serum albumin and of the immunoglobulin fraction in pasteurized milk. *Kieler Milchwirtschaftliche Forschungsberichte* 52:323-334.

Douglas T.E., Dokupil A., Reczynska K., Brackman G., Krok-Borkowicz M., Keppler J.K., Bozic M., Van Der Voort P., Pietryga K., Samal S.K., Balcaen L., van den Bulcke J., Van Acker J., Vanhaecke F., Schwarz K., Coenye T. & Pamula E. (2016) Enrichment of enzymatically mineralized gellan gum hydrogels with phlorotannin-rich *Ecklonia cava* extract Seanol(R) to endow antibacterial properties and promote mineralization. *Biomed Mater* 11:045015.

Garrett I.R., Boyce B.F., Oreffo R.O.C., Bonewald L., Poser J. & Mundy G.R. (1990) Oxygen-Derived Free-Radicals Stimulate Osteoclastic Bone-Resorption in Rodent Bone In vitro and In vivo. *Journal of Clinical Investigation* 85:632-639.

George K., Zafiropoulos G.G.K., Murat Y., Hubertus S. & Nisengard R.J. (1994) Clinical and Microbiological Status of Osseointegrated Implants. *Journal of Periodontology* 65:766-770.

Gharib A., Faezizadeh Z. & Godarzee M. (2013) Therapeutic efficacy of epigallocatechin gallate-loaded nanoliposomes against burn wound infection by methicillin-resistant *Staphylococcus aureus*. *Skin Pharmacol Physiol* 26:68-75.

Gillespie A.L., Calderwood D., Hobson L. & Green B.D. (2015) Whey proteins have beneficial effects on intestinal enteroendocrine cells stimulating cell growth and increasing the production and secretion of incretin hormones. *Food Chem* 189:120-128.

Gosau M., Haupt M., Thude S., Strowitzki M., Schminke B. & Buegers R. (2016) Antimicrobial effect and biocompatibility of novel metallic nanocrystalline implant coatings. *J Biomed Mater Res B Appl Biomater* 104:1571-1579.

Harbaum B., Hubbermann E.M., Zhu Z. & Schwarz K. (2008) Impact of fermentation on phenolic compounds in leaves of pak choi (*Brassica campestris* L. ssp. *chinensis* var. *communis*) and Chinese leaf mustard (*Brassica juncea* coss). *J Agric Food Chem* 56:148-157.

Hirano R., Sasamoto W., Matsumoto A., Itakura H., Igarashi O. & Kondo K. (2001) Antioxidant ability of various flavonoids against DPPH radicals and LDL oxidation. *Journal of Nutritional Science and Vitaminology* 47:357-362.

Hirasawa M. & Takada K. (2004) Multiple effects of green tea catechin on the antifungal activity of antimycotics against *Candida albicans*. *Journal of Antimicrobial Chemotherapy* 53:225-229.

Jin P., Wu H., Xu G., Zheng L. & Zhao J. (2014) Epigallocatechin-3-gallate (EGCG) as a pro-osteogenic agent to enhance osteogenic differentiation of mesenchymal stem cells from human bone marrow: an in vitro study. *Cell Tissue Res* 356:381-390.

Kanakis C.D., Hasni I., Bourassa P., Tarantilis P.A., Polissiou M.G. & Tajmir-Riahi H.A. (2011) Milk beta-lactoglobulin complexes with tea polyphenols. *Food Chemistry* 127:1046-1055.

Kavanagh K.T., Abusaleem S. & Calderon L.E. (2017) The incidence of MRSA infections in the United States: is a more comprehensive tracking system needed? *Antimicrob Resist Infect Control* 6:34.

Keppler J.K., Martin D., Garamus V.M., Berton-Carabin C., Nipoti E., Coenye T. & Schwarz K. (2017) Functionality of whey proteins covalently modified by allyl isothiocyanate. Part 1 physicochemical and antibacterial properties of native and modified whey proteins at pH 2 to 7. *Food Hydrocolloids* 65:130–143.

- 480 [Keppler J.K., Martin D., Garamus V.M. & Schwarz K. \(2015\) Differences in binding behavior of \(-\)-](#)
 481 [epigallocatechin gallate to -lactoglobulin heterodimers \(AB\) compared to homodimers \(A\) and \(B\).](#)
 482 [Journal of Molecular Recognition 28:656-666.](#)
- 483 [Keppler J.K., Sonnichsen F.D., Lorenzen P.C. & Schwarz K. \(2014\) Differences in heat stability and ligand](#)
 484 [binding among beta-lactoglobulin genetic variants A, B and C using H-1 NMR and fluorescence](#)
 485 [quenching. Biochimica Et Biophysica Acta-Proteins and Proteomics 1844:1083-1093.](#)
- 486 [Klein S., Nurjadi D., Eigenbrod T. & Bode K.A. \(2016\) Evaluation of antibiotic resistance to orally](#)
 487 [administrable antibiotics in staphylococcal bone and joint infections in one of the largest university](#)
 488 [hospitals in Germany: is there a role for fusidic acid? Int J Antimicrob Agents 47:155-157.](#)
- 489 [Ko C.H., Lau K.M., Choy W.Y. & Leung P.C. \(2009\) Effects of tea catechins, epigallocatechin, gallic acid, and](#)
 490 [gallic acid gallate, on bone metabolism. J Agric Food Chem 57:7293-7297.](#)
- 491 [Ko C.H., Siu W.S., Wong H.L., Shum W.T., Fung K.P., Lau C.B.S. & Leung P.C. \(2011\) Pro-bone and Antifat](#)
 492 [Effects of Green Tea and Its Polyphenol, Epigallocatechin, in Rat Mesenchymal Stem Cells in Vitro.](#)
 493 [Journal of Agricultural and Food Chemistry 59:9870-9876.](#)
- 494 [Kontopidis G., Holt C. & Sawyer L. \(2004\) Invited review: beta-lactoglobulin: binding properties, structure, and](#)
 495 [function. J Dairy Sci 87:785-796.](#)
- 496 [Lee J.H., Shim J.S., Chung M.S., Lim S.T. & Kim K.H. \(2009a\) In vitro anti-adhesive activity of green tea](#)
 497 [extract against pathogen adhesion. Phytother Res 23:460-466.](#)
- 498 [Lee Y.L., Hong C.Y., Kok S.H., Hou K.L., Lin Y.T., Chen M.H., Wang C.C. & Lin S.K. \(2009b\) An Extract of](#)
 499 [Green Tea, Epigallocatechin-3-Gallate, Reduces Periapical Lesions by Inhibiting Cysteine-rich 61](#)
 500 [Expression in Osteoblasts. Journal of Endodontics 35:206-211.](#)
- 501 [Mahmud R., Matin M.A. & Otani H. \(2004\) Mitogenic effect of bovine beta-lactoglobulin and its proteolytic](#)
 502 [digests on mouse spleen resting cells. Pakistan Journal of Biological Sciences 7:2045-2050.](#)
- 503 [Mann B., Kumari A., Kumar R., Sharma R., Prajapati K., Mahboob S. & Athira S. \(2015\) Antioxidant activity](#)
 504 [of whey protein hydrolysates in milk beverage system. Journal of Food Science and Technology-](#)
 505 [Mysore 52:3235-3241.](#)
- 506 [Moulti-Mati F., Mati A., Capiamont J., Belleville F., Linden G. & Nabet P. \(1991\) Rôle de la beta-](#)
 507 [lactoglobuline dans l'activité proliférative du lactosérum. Lait 71:543-553.](#)
- 508 [Nash L.A. & Ward W.E. \(2016\) Comparison of black, green and rooibos tea on osteoblast activity. Food &](#)
 509 [Function 7:1166-1175.](#)
- 510 [Park G., Yoon B.S., Moon J.H., Kim B., Jun E.K., Oh S., Kim H., Song H.J., Noh J.Y., Oh C. & You S. \(2008\)](#)
 511 [Green tea polyphenol epigallocatechin-3-gallate suppresses collagen production and proliferation in](#)
 512 [keloid fibroblasts via inhibition of the STAT3-signaling pathway. Journal of Investigative Dermatology](#)
 513 [128:2429-2441.](#)
- 514 [Park Y.H., Han D.W., Suh H., Ryu G.H., Hyon S.H., Cho B.K. & Park J.C. \(2003\) Protective effects of green](#)
 515 [tea polyphenol against reactive oxygen species-induced oxidative stress in cultured rat calvarial](#)
 516 [osteoblast. Cell Biology and Toxicology 19:325-337.](#)
- 517 [Radji M., Agustama R.A., Elya B. & Tjampakasari C.R. \(2013\) Antimicrobial activity of green tea extract](#)
 518 [against isolates of methicillin-resistant Staphylococcus aureus and multi-drug resistant Pseudomonas](#)
 519 [aeruginosa. Asian Pac J Trop Biomed 3:663-667; discussion 666.](#)

Salah N., Miller N.J., Paganga G., Tijburg L., Bolwell G.P. & Riceevans C. (1995) Polyphenolic Flavanols as Scavengers of Aqueous-Phase Radicals and as Chain-Breaking Antioxidants. *Archives of Biochemistry and Biophysics* 322:339-346.

Serfert Y., Lamprecht C., Tan C.P., Keppler J.K., Appel E., Rossier-Miranda F.J., Schroen K., Boom R.M., Gorb S., Selhuber-Unkel C., Drusch S. & Schwarz K. (2014) Characterisation and use of beta-lactoglobulin fibrils for microencapsulation of lipophilic ingredients and oxidative stability thereof. *Journal of Food Engineering* 143:53-61.

Setzer B., Bachle M., Metzger M.C. & Kohal R.J. (2009) The gene-expression and phenotypic response of hFOB 1.19 osteoblasts to surface-modified titanium and zirconia. *Biomaterials* 30:979-990.

Sharma A., Gupta S., Sarethy I.P., Dang S. & Gabrani R. (2012) Green tea extract: possible mechanism and antibacterial activity on skin pathogens. *Food Chem* 135:672-675.

Steinmann J., Buer J., Pietschmann T. & Steinmann E. (2013) Anti-infective properties of epigallocatechin-3-gallate (EGCG), a component of green tea. *Br J Pharmacol* 168:1059-1073.

Tobi S.E., Gilbert M., Paul N. & McMillan T.J. (2002) The green tea polyphenol, epigallocatechin-3-gallate, protects against the oxidative cellular and genotoxic damage of UVA radiation. *International Journal of Cancer* 102:439-444.

Tong L.M., Sasaki S., McClements D.J. & Decker E.A. (2000) Mechanisms of the antioxidant activity of a high molecular weight fraction of whey. *Journal of Agricultural and Food Chemistry* 48:1473-1478.

Vali B., Rao L.G. & El-Sohehy A. (2007) Epigallocatechin-3-gallate increases the formation of mineralized bone nodules by human osteoblast-like cells. *J Nutr Biochem* 18:341-347.

Vester H., Holzer N., Neumaier M., Lilianna S., Nussler A.K. & Seeliger C. (2014) Green Tea Extract (GTE) improves differentiation in human osteoblasts during oxidative stress. *Journal of Inflammation-London* 11

Wauquier F., Leotoing L., Coxam V., Guicheux J. & Wittrant Y. (2009) Oxidative stress in bone remodelling and disease. *Trends in Molecular Medicine* 15:468-477.

Yamaguchi M. & Ma Z.J. (2001) Effect of polyphenols on calcium content and alkaline phosphatase activity in rat femoral tissues in vitro. *Biological & Pharmaceutical Bulletin* 24:1437-1439.

Yoda Y., Hu Z.Q., Zhao W.H. & Shimamura T. (2004) Different susceptibilities of *Staphylococcus* and Gram-negative rods to epigallocatechin gallate. *J Infect Chemother* 10:55-58.

Zhao W.H., Hu Z.Q., Okubo S., Hara Y. & Shimamura T. (2001) Mechanism of synergy between epigallocatechin gallate and beta-lactams against methicillin-resistant *Staphylococcus aureus*. *Antimicrob Agents Chemother* 45:1737-1742.

Zorilla R., Liang L., Remondetto G. & Subirade M. (2011) Interaction of epigallocatechin-3-gallate with beta-lactoglobulin: molecular characterization and biological implication. *Dairy Science & Technology* 91:629-644.

Figure captions

559 Figure 1: GTE compounds that were bound to 800 µg/ml WPI, as a function of the GTE [µg/ml] concentration.
560 Abbreviations: EGC, Epigallocatechin; EC, epicatechin; EGCG, epigallocatechin gallate, ECG,
561 epicatechingallate; GTE, green tea extract

563 Figure 2: Antioxidative capacity (DPPH test) of different concentrations of GTE, with or without addition of
564 800 or 50 µg/ml WPI. All values are listed as mean ± standard deviation (n=3). *: p < 0.05

566 Figure 3: Images of fibroblasts cultured in cell culture medium containing different concentrations of GTE
567 (epigallocatechin gallate-rich extract) and WPI (beta-lactoglobulin-rich extract) after 7 d. Scale bar = 100 µm in
568 all cases.

569
570 Figure 4: Data from day 1 (a), 4 (b) and 7 (c) crystal violet assay conducted on hFOB cells. Results are
571 presented as the mean optical density values for each treatment, (n=4, +/- SD). * indicates a significant
572 difference (p<0.05) between the treatment and the 0µg/ml GTE value (within each WPI treatment group). #
573 indicates a significant difference (p<0.05) between the treatment and the respective value for WPI = 0 µg/ml.

574
575 Figure 5: Images taken of hFOBs using an ISH500 camera attached to an OLYMPUS SZX10 microscope at 2x
576 zoom. hFOB cells were fixed and stained with crystal violet 7 days after initial treatment. Scale bar = 1 mm in
577 all cases.

578
579 Figure 6: data from an ALP assay conducted on hFOBs. Cells were given a 24 hour attachment period before
580 being treated with solutions containing different concentrations of GTE and WPI. The assay was conducted on
581 day 7 (a), day 14 (b) and day 21 (c) timepoints. Each ALP reading was normalized to the DNA concentration of
582 the same well, calculated via PicoGreen assay. Results are presented as the mean +/- standard deviation (n=4).
583 *p<0.05 for WPI treatments at 64 µg/ml GTE, compared to WPI treatments of the same concentration at 0µg/ml
584 GTE. #p<0.05 for WPI treatment comparisons at 0 µg/ml GTE.