**QUEEN'S
UNIVERSITY
BELFAST**

Optimisation of rheological parameters, induced bleeding, permeability and mechanical properties of supersulfated cement grouts

Sonebi, M., Abdalqader, A., Fayyad, T., Perrot, A., & Bai, Y. (2020). Optimisation of rheological parameters, induced bleeding, permeability and mechanical properties of supersulfated cement grouts. *Construction and Building Materials*, 262, 1-16. <https://doi.org/10.1016/j.conbuildmat.2020.120078>

Published in:
Construction and Building Materials

Document Version:
Publisher's PDF, also known as Version of record

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

Copyright 2020 Elsevier.

This manuscript is distributed under a Creative Commons Attribution-NonCommercial-NoDerivs License

(<https://creativecommons.org/licenses/by-nc-nd/4.0/>), which permits distribution and reproduction for non-commercial purposes, provided the author and source are cited.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

Optimisation of rheological parameters, induced bleeding, permeability and mechanical properties of supersulfated cement grouts

M. Sonebi¹, A. Abdalqader^{1,2}, T. Fayyad², A. Perrot³, Y. Bai⁴

¹School of Natural and Built Environment, Queen's University Belfast, Belfast, Northern Ireland, UK

²Tracey Concrete Ltd, Northern Ireland, UK

³University Bretagne Sud, Lorient, France

⁴Departement of Civil Engineering, Environmental and Geomatic, University College London, UK

Abstract

Presenting a promising option that could be used to encapsulate nuclear waste material for disposal, supersulfated cement (SSC) is, again, receiving wide attention among research community as a cementitious system that has noteworthy properties. It is also an environmentally friendly cement since it is mainly composed of ground granulated blast furnace slag (GGBS) that is activated by a sulphate source such as gypsum, hemihydrate or anhydrite. Although there is some research on SSC, little research work has focused on modelling the effects of the various parameters using a statistical approach which is the aim of this paper. The effect of dosages of GGBS, anhydrite (ANH) and water-to-binder ratio (W/B) on the fresh and rheological parameters, induced bleeding, permeability, compressibility, and compressive strength of supersulfated grouts was investigated. Then, statistical models and isoresponse curves were developed to capture the significant trends of the tested parameters using factorial design approach. The models suggested that that W/B had significantly higher influence on most of the parameters tested while the influence of GGBS and ANH and their interactions varied depending on the parameter in question. . The findings of this study show the importance of understanding the role of and optimising the relevant key factors in producing SSC fit-for-purpose. The statistical models developed in this paper can facilitate optimizing the mixture proportions of grouts for target performance by reducing the number of trial batches needed.

Keywords: compressive strength, heat of hydration, permeability, induced bleeding, rheology, slump flow, supersulfated cement, yield stress, viscosity

Highlights

- SSC presents a promising option to encapsulate nuclear waste material.
- The constituents' effect on SSC grouts' properties was studied and modelled.
- Factorial design is a powerful tool for optimizing the mixture proportions of SCC.
- W/B had the highest influence on most of the parameters tested.

1. Introduction

Ancient concrete as well as more recent concrete materials reinvented in the nineteenth century have performed well in the past. However, over recent decades, a great challenge had emerged regarding ensuring efficient consumption of natural resources and, hence, there was a pressure to make construction industry more sustainable. Concrete is widely used within the construction industry and contributes to a large extent to the global energy consumption and carbon emission due to the energy intensity and CO₂ emissions associated with cement production. So the industry was looking for ways to become more sustainable [1]. This has resulted in a high demand for new types of cement possessing improved qualities including strength, toughness, and durability as well as being environmentally friendly.

Cements made of industrial waste materials and by-products emerged as one of the sustainable options to traditional Portland cement (PC) because it is mainly manufactured using waste and by-products that require little processing; making the embodied energy and emissions associated with the production process low. Besides its environmental benefits, such materials has a great versatility depending on their components and they can be tailored to make them suitable for a wide range of applications in the structures industry [2].

One of these environmentally friendly cements that was used during the last decades is the supersulfated cement (SSC) which is a cementitious system composed of ground granulated blast furnace slag (GGBS) that is activated by a sulphate source such as gypsum, hemihydrate or anhydrite [3]. Wastes of semi-dry and dry flue gas desulpherisation (FGD) can be used as source of sulphate [4, 5]. SSC has great advantages that make it attractive for use; firstly, it is mainly manufactured using by-products and industrial wastes. Secondly, it has lower CO₂ emissions compared to PC because clinker burning is reduced. The estimated embodied CO₂ of GGBS is 79.6 kgCO₂/tonne which is 10 times lower than that of Portland cement (CEM 1) at 860 kgCO₂/tonne [6]. Besides that, SSC produces much lower heat than PC; and also, SSC

has superior resistance to chemically aggressive environments such as sulfates. Due to the glassy nature of GGBS, composed mainly of monosilicates, GGBS easily dissolves in low to mild alkaline solutions. However, it is required that the alumina content (Al_2O_3) of slag to be no less than 13% to be used effectively in SSC [7]. The most commonly used sources of sulphate is anhydrite because it has lower solubility rate than other sources [8, 9]. To promote the dissolution of slag, PC is added because its hydration yields the formation of calcium hydroxide (CH) which provides the required alkaline environment for slag dissolution. Once the slag is dissolved, the released aluminium, silicon and calcium ions from slag glass react with the calcium sulfate present in the mixture to form two main hydration products: ettringite ($\text{C}_6\text{A}\check{\text{S}}_3\text{H}_{32}$) and calcium silicate hydrate (C-S-H) [10]. Ettringite provides the early strength to SSC mixtures contributing to the strength development while C-S-H is responsible for later strength and the continual increase of strength over time [11, 12]. C-S-H formed in SSC has a Ca/Si ratio between 1.0 and 1.2, which is much lower than that formed in PC mixtures [13]. This means that the chemical composition of slag plays a significant role on the strength development, dissolution of the slags and the amount of hydration products formed.

After being used for long time in construction for special structures, currently, SSC is very rarely used and no longer produced in some areas. According to Baux et al. [14] this happened because of its lack of reactivity. Grounds et al. [10] believed that this is because there is uncertainty over some of its properties which include its long-term stability and durability. One of their main concern surrounding SSC is due to the hydration product ettringite or tri-sulphoaluminate which is known to be unstable in Portland cement and has been found to be expansive in certain environments. Phelipot-Mardel et al. [15] state that this could be because, generally, cement made with blast furnace slag tends to harden more slowly than mortar and concrete made from PC.

The nuclear power is a promising option for the future in the UK and the world in general, however, the nuclear waste is still an obstacle in its way to be a vital option for the future and to gain public acceptance [16]. This can be achieved by making the contaminants to be less mobile or less toxic by ‘waste stabilization’ that results in converting the contaminants from the dissolved phase to a solid phase by reactions such as precipitation, sorption or substitution. This prevents the waste from diffusion to the external environment [16, 17]. Most applications of stabilization are cement-based where the cement forms a low permeability matrix and where the contaminant is incorporated into hydrated phases and then precipitated due to the prevailing pH in the pore solution [18]. This means that the efficiency of the process depends on the

prevailing pH. The pH resulting from cement hydration results in many metal contaminants forming hydroxide or mixed hydroxide solids [17]. Portland cement will tend to result in a higher pH while combining it with lime as well as fly ash, blast furnace slag, and other pozzolanic binders will result in lower pH. The interactions of these binders with waste components determine the extent of treatment [18].

There is a lack of data detailing the assessment criteria and performance of nuclear encapsulation grout/concrete. However, general requirements of a cementitious system for encapsulation can be summarised as follows: an ability to incorporate waste and harden; fluidity of initial cemented mix and potential for remote mixing; low permeability; resistance to water; low temperature rise on setting; workable setting time; low free or unbound water when setting reaction is complete; low internal pH to avoid ongoing reactions such as corrosion; long term durability [16].

The solubility of many heavy metals is low at low pH, and therefore low pH cements, such as SSC, are likely to be particularly desirable cements for nuclear waste management [16–19]. This would help to make the nuclear energy, as a clean and a safe source of energy, a promising alternative for future generations. This, again, has highlighted some of the noteworthy properties of the SSC where not only the pH value that makes SSC a promising option that could be used to encapsulate nuclear waste material for disposal. Also, the heat of hydration in supersulfated cement is much lower than that of OPC and therefore the heat gradient created during hydration between the internal and external surfaces would not be as great and thus less stress caused and less chance of cracking which would be unacceptable with nuclear waste disposal. It has high non-evaporable water content, that is, it's chemically bonded to the silica. Besides that, it has a good durability in aggressive environments, such as structures exposed to seawater or sulfate-bearing groundwater [9, 14, 15, 20–22].

These technical and environmental benefits have re-simulated recent research on this type of cement and brought the attention for re-investigating overcoming its drawbacks to offer a green cement for very essential applications.

Currently, different researches are being carried out on SSC in order to optimize the usage of SSC. Many researchers have examined its various mixture compositions to determine the best compositions for some desirable properties, such as strength, low permeability, faster setting time, etc. A research on slags activated with 15–20% calcium sulfate showed a higher compressive strength in comparison with other mixtures when they examined slags classified

as low-lime high-alumina and when various SSC mixture compositions were examined, with 70–85% slag, 10-25% anhydrite, and 5% Portland cement for alkali activation [15]. Gruskovnjak et al. [8] investigated the effect of alumina content in the slag by examining two types of slag with a high Al_2O_3 percentage content (12%) and low Al_2O_3 percentage content (7.7%). The findings of their study showed that slag with high alumina contents produced more ettringite and higher strength. This was attributed to the higher dissolution rate of high alumina slag. SSC hydration characteristics with different fineness has also been investigated [20]. It showed that when sample particles become finer, the compressive strength is significantly higher. Also, there is some work, which has been done on modifying the mechanical properties of SSC with addition phosphogypsum [19, 23]. Recently, the influence of curing temperature was studied for supersulfated cements made with two slags having different chemical compositions [20]. It was found that SSC made with high-alumina slag resulted in higher strengths and presented a more complex mechanism of hydration that was strongly influenced by the solubility of anhydrite. This is also being shown in [21] where the SSC made using high-alumina slag exhibited higher compressive strength and the use of higher activator contents decreased the compressive strength.

Based on recent researches and the fact that there are many factors and parameters involved in the composition of SSC, there is a demanding need for optimizing the cement grout in order to effectively utilise it to fit for purpose. The current paper aligns with this demand. The effect of GGBS, water-to-binder ratio W/B, and anhydrite dosages on the grout fluidity, rheological properties, induced bleeding, fresh state permeability and compressibility, maximum heat of hydration and compressive strength will be investigated using factorial design approach and analysis. Although there is some research on SSC, little research work has focused on modelling the effects of the various parameters using a statistical approach. Factorial design is a powerful tool and widely used in experiments involving many factors. It can be utilised to study the joint effect of factors on responses or dependent variables, and, to develop models applicable to design and development of experiments. Simulation of models obtained with factorial design can facilitate the test protocol needed to optimize cement grout within a given set of performance criteria.

2. Experimental Programme

2.1 Materials and Test Methods

The grout mixes investigated in this study were prepared with Standard CEM I 42.5N Portland cement (PC) specified by BS EN 197-1. The ground granulated blast furnace slag (GGBS) in accordance to BS EN 15167-2 was used. The chemical composition of CEM I and GGBS are provided in Table 1. Anhydrite (ANH) was used as the source of sulphate in the present study and it was partially or completely replaced the PC. The proportions of the grout mixes are shown in Table 2.

Table 1. Chemical and physical properties of cement and GGBS

Chemical analysis	Material	
	CEM I	GGBS
SiO ₂ (%)	21.01	35.18
Al ₂ O ₃ (%)	4.92	13.96
Fe ₂ O ₃ (%)	2.84	0.25
MgO (%)	2.20	8.18
CaO (%)	64.52	41.21
Na ₂ O (%)	0.20	0.19
K ₂ O (%)	0.71	0.42
SO ₃ (%)	2.53	--
P ₂ O ₅ (%)	0.11	--
LOI (%)	1.26	0.64
Physical analysis		
Specific gravity	3.08	2.91
Specific surface area [m ² /kg]	360	600

Table 2. Mix proportions for the grouts used in the factorial design

Mix No.	Code			W/B	Percentage (%)	
	W/B	GGBS	ANH		GGBS	ANH
M1	-1	-1	-1	0.34	60	0
M2	1	-1	-1	0.44	60	0
M3	-1	1	-1	0.34	60	20
M4	1	1	-1	0.44	60	20
M5	-1	-1	1	0.34	80	0
M6	1	-1	1	0.44	80	0
M7	-1	1	1	0.34	80	20
M8	1	1	1	0.44	80	20
M9	0	0	0	0.39	70	10
M10	0	0	0	0.39	70	10
M11	0	0	0	0.39	70	10
M12	0	0	0	0.39	70	10

169 All grout mixes were prepared in 2 L batches using a high-shear mixer with a 4.5 L capacity.
170 The mixing water was kept at 9.8 ± 0.2 °C to compensate for heat generated during mixing.
171 The cement and GGBS were mixed with ANH in a sequence that started with adding all of the
172 water into the mixer. After one minute, the binder was gradually introduced. The grout was
173 mixed for one minute, followed by 30 seconds of rest. Subsequently, the grout was mixed again
174 for 2 min at a high speed (285 rpm) and for 1 min at the low speed (140 rpm).

175 For all tests the timing is given from zero time, i.e. the time when the cement particles first
176 touch the mixing water. The mini-slump flow test started at 7 min (immediately after the end
177 of mixing). The transparent cone-shaped mould described elsewhere [24] was placed in the
178 centre of a smooth Plexiglas plate. After filling with grout, the cone was gently lifted
179 (approximately 30 s after placement of the grout). When the flow stopped, the spread of the
180 grout was measured with a ruler in two perpendicular directions.

181 Marsh cone test was carried out using a metal cone with an orifice diameter of 10 mm and
182 started at 8 ± 1 min. One litre of grout was poured into the cone. The cone's orifice was opened
183 15 s after pouring the cement grout into the cone. The time taken for each 100 ml of grout to
184 flow through the orifice was recorded, and the measurements were completed upon collecting
185 700 ml of grout.

186 The viscosity of cement grout was determined using a coaxial rotating cylinder viscometer
187 Fann (smooth cylinders, no serration) that determined apparent viscosity at different shear
188 rates. The test was contained in the annular space between an outer cylinder (rotor) with a
189 radius of 18.415 mm and a bob with a radius of 17.245 mm and a height of 3.80 cm. The rotor
190 and bob were plunged into a cup containing 350 ml of sample grout. Viscosity measurements
191 were made when the outer cylinder, rotating at a known speed, caused a viscous drag to be
192 exerted by the fluid. This drag created a torque on the bob, which was transmitted to a precision
193 spring, where its deflection was measured and compared with test conditions and the
194 instrument's constants. The measurement was made for 12 rotor speeds from 0.9 rpm to 600
195 rpm, where the viscometer reading values (θ) were recorded. The value of shear stress τ (Pa)
196 was calculated by including k_1 , torsion constant of spring per unit deflection (N-cm/degree),
197 k_2 , shear stress constant for the effective bob surface (cm^{-3}) and k_3 , shear rate constant [s^{-1}/rpm]
198 [25, 26].

199 Rotor speed was increased step by step, and the viscometer readings were recorded with
200 increasing rotation speeds. The θ reading was taken when the needle in the viscometer was

stabilised, or 30 seconds after the change of speed in cases when the needle had not stabilised due to the thixotropy of the cement grout. The time of θ reading was generally between 5 and 10 seconds.

In this study, the down-curve was chosen for final evaluation because it offered a better description of the rheological behaviour of the grouts, including a structural breakdown phenomenon of inner forces among particles [27]. The values of shear yield stress (the minimum shearing stress required for the fluid to start flowing) and plastic viscosity used the modified Bingham model [28] and are expressed as follows:

$$\tau = \tau_0 + \mu_p \dot{\gamma} + c \dot{\gamma}^2 \quad (1)$$

Where τ_0 is yield stress (Pa), μ_p is plastic viscosity (Pa·s), $\dot{\gamma}$ is shear rate (s^{-1}), and c is a constant.

The cohesion of grout was determined at 30 ± 1 min with a Lombardi plate cohesion meter [29]. A thin galvanized steel plate (100×100×1 mm) was immersed in the grout and hung on a stand placed on an electronic balance. The weight of the grout still present on the plate was recorded when the dripping of the grout had stopped. This test was followed by the fresh density measurement of the grout with a mud balancer. Knowing the fresh density of the grout, it was possible to calculate the thickness on each side of the plate.

The resistance of the fresh grout to induced bleeding was evaluated using a pressure filter. The equipment consists of a pressure vessel, filter paper, which is placed on a sieve, and a graduated cylinder. A 200 ml grout sample is placed in the pressure vessel. After closing the cell, the graduated cylinder is placed under the outlet of the cell. The cell is pressured by compressed air to 0.55 MPa. The volume of water going out through the outlet on the bottom of the cell is recorded at 15 and 30 s, then at every minute up to 10 min, and then at every 5 min up to 30 min [25].

Considering homogeneous bleeding, the results of the induced bleeding tests allow to derive the evolution of the permeability of the sample during its compaction under the applied pressure. The permeability of the material is directly linked to the bleeding rate during the material consolidation until the tested material is able to sustain the applied pressure [30, 31]. It refers to the material ability to slow down the water filtration process.

The measurement of the flow water allows to compute instantaneous W/B ratio and makes it possible to link it with the computed instantaneous permeability at a given time of the test [32–

34]. The water flow is computed by dividing the variation of the measured water mass flowing out the samples by the elapsed time between two successive data sampling. In this study, value of permeability at 1 and 30 minutes are taken and compared. It corresponds to the initial and final permeability of the mixes.

The material compressibility is considered in a soils mechanics way [30, 35]. It corresponds to the ratio of the variation of void ratio (liquid/solid volume ratio) to the variation of logarithm of applied pressure between the initial and the final state of the induced bleeding test. It provides the equilibrium state of the sample under a given applied pressure and is valid for both homogeneous and heterogeneous bleeding [36].

It is worth noting that the computed permeability describes homogeneous bleeding kinetics while compressibility describes the amplitude of the bleeding phenomenon.

Heat of hydration was evaluated by isothermal calorimetry with an eight-channel heat conduction calorimeter maintained at 22°C. This equipment measures heat evolved by comparing the temperatures of a grout sample and an inert reference which are both held under isothermal conditions. The heat flow results are recorded as a function of time. CEM I, GGBS and ANH were blended manually for 30 s. After the addition of water, the grout was blended 10 s by hand and then an additional 50 s mechanically. Polyethylene ampoules were filled with approximately 6 g of each grout, and the experiments were conducted for at least 72 h.

The compressive strength of the grout was determined by crushing three cubes of 50 mm size. After casting, the samples were covered with a polymer sheet (a cling film) to limit evaporation of water and stored in a conditioning room at 20 ± 2 °C for 24 ± 0.5 hours. Afterwards, cubes were demoulded and placed in water at 20 ± 1 °C until tested at 1, 3, 7, and 28 days.

In order to perform the pH test a powder sample of the hardened mixes was required. The test was performed on 1, 7 and 28 day samples. As mixes 9-12 are of identical composition, the reason is explained later in 4.1 derived statistical model, tests were only performed on sample 10. To get the powder with a fineness of 65µm the samples were firstly drained of the acetone. To remove any remaining acetone, they were placed in a vacuum desiccator. The pieces were then ground using a mortar and pestle, passed through a 65 µm sieve, placed in sample bags and returned to the desiccator. The samples had then to be mixed with distilled water to enable the pH test to be performed. A 1:10 ratio of cement to water was used and mixed for 24 hours using a rotating machine. To get the pH reading the samples were put into a centrifuge machine to separate the solid and liquid. At this stage the solution should have a pH equivalent to cement

it was mixed with. To get a pH reading for the samples, a pH device was used where a probe is placed in the solution. The machine was calibrated with three buffer solutions of 7, 10 and 13 pH levels before measuring the pH of the samples.

SEM (scanning electron microscopy) was carried out using a JEOL JSM6400 on flat fractured surface specimens obtained from compression testing at 7-day samples. Prior to SEM testing, the samples were mounted onto metal stubs using carbon paste and coated with gold film to ensure good conductivity. The accelerated voltage was set at 20 kV.

2.2 Statistical Design and Modelling of Experiments

The technique of analysis used in this study was a 2^k factorial experimental design [37] to evaluate the influence of two different levels (maximum and minimum) for each variable on the relevant grout properties. Three key parameters (W/B, ANH, GGBS) that should have significant influence on mix characteristics of supersulfated cements were selected to formulate the mathematical models for evaluating relevant properties (i.e. $k = 3$ in this study, thus the total mixes for the factorial design was $2^3 = 8$). Additionally, a mix at the central point was replicated four times to estimate the experimental error and improve the reliability of the models. The coding and levels of the variables (W/B, and dosages of GGBS and ANH) are given Table 2.

The statistical models are valid for supersulfated grout (SSC) mixes made with W/B, GGBS and ANH in the ranges of 0.34 to 0.44, 60% to 80% and 0% to 20%, respectively. The modelled experimental region consisted of mixtures ranging from coded variables of -1 to $+1$. The coded factors for variables were calculated by:

$$\text{Coded Factor} = (\text{Actual value} - \text{Factor means}) / [\text{Range of factor value} / 2] \quad (2)$$

Hence:

$$\text{Coded W/B} = (\text{Actual W/B} - 0.39) / 0.05$$

$$\text{Coded GGBS} = (\text{Actual GGBS} - 0.7) / 0.1$$

$$\text{Coded Anhydrite} = (\text{Actual ANH} - 0.1) / 0.1$$

The responses modelled were mini-slump, plate cohesion, Marsh cone, yield stress, plastic viscosity, induced bleeding at 1 min, 5 and 30 mins, permeability at 1 min and 30 mins, compressibility and compressive strength at 1, 3, 7 and 28 days. The general model associated

with the two-level factorial design incorporating three independent variables (W/B, GGBS, ANH) is expressed by:

$$Y_1 = a_0 + a_1.W/B + a_2.GGBS + a_3.ANH + a_4.W/B.GGBS + a_5.W/B.ANH + a_6.GGBS.ANH + a_7.W/B.GGBS.ANH + \varepsilon \quad (3)$$

where,

Y_1 : Response (mini slump, marsh cone, plate cohesion, etc.)

a_0 : Overall mean factor effect

a_1 - a_7 : Regression coefficients representing model constants (contribution of independent variables and their interaction to each response)

$a_1.W/B$, $a_2.GGBS$, $a_3.ANH$: Linear effect of factors W/B, GGBS and ANH

$a_4.W/B.GGBS$, $a_5.W/B.ANH$, $a_6.GGBS.ANH$, $a_7.W/B.GGBS.ANH$: Interaction effects of factors W/B, GGBS and ANH

ε : Random error term representing the effects of uncontrolled variables

Analysis of variance (ANOVA) was used to test the significance of regression models, and t-tests were performed to identify the non-significant (NS) variables and second order interactions, which were subsequently eliminated from the derived models. Model coefficients were determined using multi-linear regression analysis based on a normal distribution assumption. The error was assumed to be random and normally distributed, so the residual terms, which represent the difference between the actual and predicted values should exhibit similar properties [37]. The probability value (Prob.) obtained from ANOVA determines the statistical significance of each factor and their interactions. For most of the parameters, the probability that the derived coefficients associated with the various variables influencing each response were limited to 10%. This signifies that there is less than 10% chance or 90% confidence limit that the contribution of a given parameter to the tested response exceeds the value of the specified coefficient. A negative estimate indicates that an increase of the given parameter results in a reduction of the measured response.

3. Results and discussion

The results of the experimental work characterize the behaviour of the mortars with different W/B, ANH and GGBS levels. Table 3 summarises all results of the experimental work performed. The results were used to construct the regression models.

Table 3. Average results from experimental work

Mix	Viscometer					Induced bleeding		
	Mini-slump (mm)	Flow time (s)	Cohesion meter (mm)	Yield value (Pa)	Plastic viscosity (Pa.s)	1min (mL)	5min (mL)	30min (mL)
1	61	230	10.5	19.1	0.923	22.0	47.0	48.0
2	89	25	5.5	9.7	0.323	29.0	78.0	81.0
3	67	200	11.8	17.2	0.802	28.0	58.0	60.5
4	111	12	2.0	8.0	0.199	49.0	86.0	86.0
5	52	360	14.3	25.1	1.203	28.0	52.0	54.0
6	83	69	8.6	9.9	0.403	36.0	70.0	70.0
7	60	250	12.5	21.1	0.980	31.0	58.0	59.0
8	110	13	4.0	7.7	0.224	35.0	91.0	95.0
9	71	150	8.7	10.1	0.617	37.0	72.0	73.0
10	73	102	12.2	10.6	0.681	29.0	62.0	62.0
11	77	192	8.9	12.4	0.660	29.0	64.0	64.5
12	74	83	11.0	10.1	0.641	35.0	71.5	72.0

Table 3. Average results from experimental work (continued)

Mix	Permeability	Permeability	Compre-ssibility	Compressive strength			
	1 min (m/s)	30 min (m/s)		f'c 1d (MPa)	f'c 3d (MPa)	f'c 7d (MPa)	f'c 28d (MPa)
1	2.16E-09	3.17E-09	0.155	29.9	50.6	58.1	70.4
2	5.12E-08	4.18E-09	0.298	16.8	38.3	54.7	55.8
3	4.48E-08	3.66E-09	0.194	21.3	33.4	40.6	52.7
4	3.74E-08	4.25E-09	0.312	14.0	22.3	25.6	40.8
5	4.48E-08	3.42E-09	0.173	23.3	43.4	50.7	53.5
6	5.12E-08	3.95E-09	0.255	13.6	37.1	37.1	44.8
7	4.40E-08	3.61E-09	0.187	10.8	23.2	34.3	53.2
8	4.51E-08	4.33E-09	0.342	6.8	20.0	26.3	47.3
9	4.46E-08	4.02E-09	0.250	19.6	32.8	39.8	59.2
10	4.68E-08	3.71E-09	0.212	17.1	23.2	36.1	55.6
11	4.23E-08	3.79E-09	0.221	20.7	31.3	45.1	56.5
12	5.16E-08	4.00E-09	0.246	18.3	30.1	43.5	52.0

The derived quadratic statistical models of grout for mini-slump, flow time, cohesion plate, yield stress, plastic viscosity, induced bleeding at 1 min, 5 min and 30 min, permeability at 1

min and 30 min, compressibility, and compressive strength at 1, 3, 7 and 28 days are given in Equations (4) to (18) where W/B, GGBS, and ANH are given in codes values.

$$\text{Mini-Slump (mm)} = 78.81 + 19.19 \text{ W/B} + 7.81 \text{ ANH} + 4.44 \text{ W/B.ANH} - 2.94 \text{ GGBS} \quad (4)$$

333

$$\text{Marsh flow time (s)} = 140.4 - 115.3 \text{ W/B} - 26.1 \text{ ANH} + 28.1 \text{ GGBS} \quad (5)$$

335

$$\text{Plate Cohesion meter (\mu m)} = 8.6 - 3.66 \text{ W/B} + 1.22 \text{ GGBS} - 1.07 \text{ ANH} - 0.91 \text{ W/B.ANH} \quad (6)$$

337

$$\text{Yield Value (Pa)} = 14.66 - 5.84 \text{ W/B} - 1.26 \text{ W/B.GGBS} - 1.25 \text{ ANH} + 1.24 \text{ GGBS} \quad (7)$$

339

$$\text{Plastic Viscosity (Pa.s)} = 0.63 - 0.34 \text{ W/B} - 0.078 \text{ ANH} + 0.073 \text{ GGBS}$$

$$- 0.047 \text{ W/B.GGBS} - 0.022 \text{ ANH.GGBS} \quad (8)$$

342

$$\text{Induced Bleeding at 1 min (ml)} = 32.25 + 5.0 \text{ W/B} + 3.5 \text{ ANH} - 2.25 \text{ W/B.ANH.GGBS} \quad (9)$$

344

$$\text{Induced Bleeding at 5 mins (ml)} = 67.5 + 13.75 \text{ W/B} + 5.75 \text{ ANH} \quad (10)$$

346

$$\text{Induced Bleeding at 30 mins (ml)} = 69.19 + 13.81 \text{ W/B} + 5.94 \text{ ANH} \quad (11)$$

348

$$\begin{aligned} \text{Permeability at 1 min (m/s)} \times 10^{-8} &= 4 + 0.615 \text{ W/B} + 0.621 \text{ ANH} - 0.773 \text{ W/B.GGBS} \\ &- 0.426 \text{ W/B.ANH} - 0.446 \text{ ANH.GGBS} \end{aligned} \quad (12)$$

351

$$\begin{aligned} \text{Permeability at 30 min (m/s)} \times 10^{-8} &= 0.382 + 0.035 \text{ W/B} + 0.014 \text{ ANH} \\ &+ 0.008 \text{ W/B.ANH.GGBS} \end{aligned} \quad (13)$$

354

$$\text{Compressibility} = 0.2396 + 0.0623 \text{ W/B} + 0.0194 \text{ ANH} + 0.0012 \text{ W/B.ANH.GGBS} \quad (14)$$

356

$$f'_{c1d} \text{ (MPa)} = 17.05 - 4.26 \text{ W/B} - 3.84 \text{ ANH} - 3.43 \text{ GGBS} + 1.45 \text{ W/B.ANH} \quad (15)$$

358

$$f'_{c3d} \text{ (MPa)} = 32.15 - 8.79 \text{ ANH} - 4.12 \text{ W/B} - 2.61 \text{ GGBS} \quad (16)$$

360

$$f'_{c7d} \text{ (MPa)} = 40.92 - 9.24 \text{ ANH} - 5 \text{ W/B} - 3.83 \text{ GGBS} \quad (17)$$

362

$$f'_{c\ 28\ d} \text{ (MPa)} = 53.48 - 5.15 \text{ W/B} - 3.82 \text{ ANH} - 2.62 \text{ GGBS} + 4.36 \text{ ANH.GGBS} \quad (18)$$

The correlation coefficient of most of the proposed models were higher than 0.90 except for plastic viscosity, compressive strength after 3days and compressive strength after 28days, which have coefficients of 0.70, 0.86 and 0.87, respectively.

Table 4 shows the average measured responses of the four replicate grouts, the coefficients of variation (COV), as well as the estimated errors with a 90% confidence limit for each of the measured properties. The estimated error levels for mini-slump, plate cohesion meter, Marsh cone, yield stress, plastic viscosity, induced bleeding at 1 min, 5 min and 30 mins, permeability at 1 min and 30 min, compressibility, and compressive strengths at 1, 3, 7, 28 days were ± 2.2 mm, ± 0.001 mm, ± 40 s, ± 0.9 Pa, ± 0.02 Pa s, ± 2.8 ml, ± 4.2 ml, ± 4.5 ml, $\pm 3.2 \times 10^{-9}$ (m/s), $\pm 1.3 \times 10^{-10}$ (m/s), ± 0.0153 , ± 1.3 MPa, ± 3.5 MPa, ± 3.3 MPa and ± 2.5 MPa, respectively. The relative experimental errors for mini-slump, plate cohesion meter, Marsh cone, yield stress, plastic viscosity, induced bleeding, permeability, compressibility, compressive strengths were limited to 3-11%. On the other hand, relative error for march cone was up to 30%.

Table 4. Repeatability of test parameters at the central point

Tests	Mini-slump	Plate cohesion	Marsh cone	Yield stress	Plastic viscosity	Induced bleeding at 1 min	Induced bleeding at 5 min	Induced bleeding at 30 min
Mean (n=4)	73.6 mm	0.01 mm	131.8 s	10.8 Pa	0.65 Pa s	32.5 ml	67.4 ml	67.9 ml
Coefficient of variation (%)	3.7	11.5	37.2	10.5	4.2	12.7	7.6	8.0
Estimate error (90% confidence limit)	2.2 mm	0.001 mm	40.2 s	0.9 Pa	0.02 Pa s	2.8 ml	4.2 ml	4.5 ml

Table 4. Repeatability of test parameters at the central point (continued)

Tests	Permeability 1 min $\times 10^{-8}$	Permeability 30 min $\times 10^{-8}$	Compressibility	$f'_{c\ 1d}$	$f'_{c\ 3d}$	$f'_{c\ 7d}$	$f'_{c\ 28d}$
Mean (n=4)	4.63 m/s	0.388 m/s	0.2323	18.9 MPa	29.3 MPa	41.1 MPa	55.8 MPa
Coefficient of variation (%)	8.5	3.9	8	8.4	14.4	9.8	5.3

Estimate error (90% confidence limit)	0.32 (m/s)	0.013 (m/s)	0.0153	1.3 MPa	3.5 MPa	3.3 MPa	2.4 MPa
--	---------------	----------------	--------	------------	------------	------------	------------

3.1 Accuracy of the established models

The ratio of predicted-to-measured properties for grout ranged between 0.87 and 1.15, indicating good accuracy for prediction of mini-slump, plate cohesion, induced bleeding at 1 min, 5 mins and 30 mins, yield stress, plastic viscosity and compressive strength at 1-d, 3-d, 7-d and 28-d. In general, the proposed models for mini-slump, plate cohesion, Marsh cone, and compressive strength appeared to be accurate in predicting fluidity, cohesivity, induced bleeding, permeability at 30 min, compressibility, and compressive strength, with low scatter between measured and predicted values. However, the average values of predicted/measured ratio of yield values were slightly higher (0.74).

3.2 Isoresponses of the proposed models

The isoresponse surfaces and contour plots for mini-slump, plate cohesion, Marsh cone, yield stress plastic viscosity, induced bleeding at 1 min, 5 mins and 30 mins, permeability at 1 min and 30 mins, compressibility, and compressive strength at 1-d, 3-d, 7-d and 28-d were obtained by using response surface methodology (RSM). The isoresponse surfaces and contour plots were obtained from the regression models, and because the models contained interaction and second-order variables, the contour lines were curved.

The proposed statistical models can therefore be used to evaluate the effect of a group of variables on the properties affecting the quality of supersulfated grout. This allowed for the calculation of isoresponse surfaces from the parameters under study outside the experimental domain and the optimisation of their effects. The next sections will discuss the results of each experiment separately.

3.3.1 Mini-slump

As shown in Eq. 4, the mini-slump is influenced in order of significance by W/B ratio, anhydrite proportion, interaction of W/B and ANH, and the percentage of GGBS content. The W/B ratio had the greatest effect on fluidity due to better lubrication of the particles in the paste

[29]. The mini-slump test was accompanied by very low shear. The value of mini-slump is to characterise yield stress [38], therefore higher mini-slump value indicated a lower yield stress. The effect of W/B on the increase of mini-slump was two and half-time than that of ANH (19.2 vs. 7.81 in Eq. 4). However, increased ANH resulted in a 2.7 times greater increase in mini-slump than reduced GGBS (7.81 vs. -2.94 in Eq. 4). Figure 1(a) shows the effect of increased W/B on mini-slump vs. ANH (when GGBS was kept constant at 70%), and Figure 1(b) shows GGBS vs. ANH (when W/B was fixed at 0.39). Based on these figures, it is evident that mini-slump increased significantly when the dosage of W/B and ANH increased.

Fig. 1. Isoresponse curves of mini-slump (mm): (a) W/B vs. ANH, and (b) GGBS vs. ANH

3.3.2 Marsh cone

The time needed for a grout sample to flow through the Marsh cone is proportional to the viscosity of the cement grout; the flow time becomes an index of fluidity, so the longer the flow time, the lower the fluidity. Similar to the previous trends, Eq. 5 shows that the values of Marsh cone are influenced in order of significance by W/B, GGBS and ANH. This is graphically illustrated in Figure 2.

Fig. 2. Isoresponse curves for flow time (s): (a) W/B vs. ANH and (b) GGBS vs. ANH

It can be noted that an increase in W/B and ANH, or a reduction in GGBS, led to decreasing the Marsh cone flow time. For example, at fixed W/B at 0.39 and GGBS of 70%, respectively, the increase in ANH dosage from 5 to 20% led to a marked reduction of the Marsh cone flow time from 170 to 140 s (Figure 2(a)). This behaviour is attributed to the change in plastic viscosity of the grout as will be discussed later.

3.3.3 Cohesion plate

As shown in Eq. 6, the cohesion plate was influenced, in order of magnitude, by the W/B, and the percentage of GGBS and ANH. The increasing W/B had a 3.4 times the influence on the reduction of the cohesion plate test results as the increased ANH (for a GGBS constant). By comparing the effects of W/B and GGBS on plate cohesion, the increased W/B can be interpreted as having approximately a 3 times greater influence on the reduction of plate cohesion values than the increase in GGBS (-3.66 vs. 1.22 in Eq. 6), given that ANH is held constant. The effect of an increase in W/B from 0.34 to 0.44 and ANH from 0% to 20% with a fixed GGBS dosage of 70% is presented in Figure 3(a). Increased W/B led to a decreased cohesion plate value. Conversely, an increase in GGBS increased the cohesion plate value and an increased ANH caused a reduction in cohesion plate (Figure 3(b)).

Fig. 3. Isoresponse curves for plate cohesion meter: (a) W/B vs. ANH, and (b) GGBS vs. ANH

3.3.4 Yield stress

As shown in Eq. 7, yield value was influenced, in order of magnitude, by W/B, and dosages of ANH and GGBS. Based on Figure 4 (a), when W/B was fixed at 0.39, GGBS maintained at 70%, and ANH increased to 5%, the isoresponse curve showed a yield value of 15 Pa. On the other hand, if the proportion of ANH was further increased to 20% while GGBS was maintained at 70%, the yield value decreased to 13.5 Pa. This corresponds with Eq. (7), in which the proportion of W/B and ANH were increased, while GGBS was kept constant, resulting in a reduction in yield stress. An increase in GGBS content resulted in an increase of the yield stress.

Figure 4 (b) shows the isoresponse curve of the yield value with a fixed proportion of GGBS at 70%. When W/B was 0.39 and ANH was 5%, the isoresponse of the predicted yield value was 15.5 Pa. If ANH was increased to 20% while maintaining W/B at 0.39, the isoresponse of the yield value was 13.5 Pa.

It can be interesting to note that the observed results for the yield stress are closed to the one observed with the cohesion plate and mini-slump tests. This is expected as yield stress values can be derived from those two simple tests.

Fig. 4. Isoresponse curves for yield stress (Pa): (a) W/B vs. ANH, and (b) GGBS vs. ANH

3.3.5 Plastic viscosity

Plastic viscosity was influenced, in order of magnitude, by W/B, and the dosages of ANH and GGBS. ANH and GGBS had almost opposite effects on plastic viscosity (-0.078 vs. 0.073 in Eq. 8). As shown in Eq. (8), increased W/B had the greatest primary effect on plastic viscosity (0.34 vs. 0.078 and 0.073). The increased W/B had approximately a 4.4 times greater influence on reducing plastic viscosity than increased ANH or decreased GGBS.

In the isoresponse curve of plastic viscosity shown in Figure 5 (a), when GGBS was fixed at 70%, W/B set at 0.39, and ANH maintained at 5%, the predicted plastic viscosity value was 0.68 Pa.s. On the other hand, if the dosage of ANHB was increased to 20% while maintaining a similar W/B, the plastic viscosity was reduced to 0.55 Pa.s.

In Figure 5 (b), W/B was fixed at 0.39, when GGBS was held at 70% and ANH at 5%, the predicted plastic viscosity was 0.67 Pa.s. However, when ANH was increased to 20% and GGBS was maintained at 70%, the predicted plastic viscosity dropped to 0.55 Pa.s.

Fig. 5. Isoresponse curve for plastic viscosity (Pa.s): (a) W/B vs. ANH, and (b) GGBS vs. ANH

3.3.6 Induced bleeding

The induced bleeding equations for 1 and 5 minutes (Eqs. 9, 10) and 30 minutes (Eq. 11) are very similar. The two influencing factors of induced bleeding are W/B ratio and anhydrite. W/B ratio has the greatest effect, over two times the effect of anhydrite content. Figure 6 shows the isoresponse for bleeding versus the W/B ratio for a fixed value of GGBS at 70%. It can be seen that when an anhydrite value is selected and the W/B ratio is increased the bleeding will also increase. Similarly, if a W/B ratio is selected and the anhydrite content is increased the bleeding will again increase.

Fig. 6. Isoresponse curves for induced bleeding at 1, 5 and 30 min: W/B vs. ANH

3.3.7 Permeability

Figure 7 (a) and (b) showed firstly that the permeability decreased significantly from 1 min to 30 min. Permeability at 1 min was influenced, in order of magnitude, by W/B, and the dosage of ANH. All interactions between 3 parameters had almost opposite effects on permeability (Eq. 12). As shown in Eq. (12), increased W/B and AHN had the greatest primary effect on permeability at 1 min. It seems there is an optimum reached at $W/B = 40$ and AHN at 17%.

Similarly, the permeability at 30 min is affected in order of significance by W/B followed by ANH (Eq. 13). In Figure 7 (b), W/B was fixed at 0.39, when GGBS was held at 70% and ANH at 10%, the predicted permeability was 0.38×10^{-8} (m/s). However, when ANH was increased to 20% and GGBS was maintained at 70%, the predicted permeability increased to 0.40×10^{-8} (m/s).

Fig. 7. Isoresponse curves for permeability at 1 and 30 min: W/B vs. ANH

3.3.8 Compressibility

As shown in Eq. (14), the compressibility was influenced, in order of magnitude, by the W/B, and the percentage of ANH. The interaction between 3 parameters affected also the compressibility. The increasing W/B had a 3.2 times the influence on the increase of the compressibility results as the increased ANH (for a GGBS constant). The effect of an increase in W/B from 0.34 to 0.44 and ANH from 0% to 20% with a fixed GGBS dosage of 70% is presented in Figure 8. Increased W/B led to an increase of compressibility. Similarly, an increase in ANH increased the compressibility.

Fig. 8. Isoresponse curves for compressibility: W/B vs. ANH

530

531 3.3.9 Compressive strength

532 After one day, from Eq. 15, the influencing factors, in order of significance, are W/B ratio,
 533 anhydrite content, GGBS content and the interaction of W/B and ANH. The effect of the first
 534 three was similar but W/B had 1.1 times greater effect than anhydrite and 1.25 times greater
 535 effect than GGBS. While the interaction of W/B and anhydrite had around a third of the
 536 influence of W/B. Figures 9 (a) and (b) show the isoresponses for 1-day compressive strength.
 537 From Figure 9 (a) it can be seen when the GGBS content is fixed at 70% for a given anhydrite
 538 content, increasing the W/B ratio will decrease the strength. Also, if a W/B ratio is selected and
 539 the anhydrite is increased similarly the strength will decrease. From Figure 9 (b) with the W/B
 540 ratio fixed at 0.39, once again an increase in GGBS led to a reduction of compressive strength
 541 at 1 day.

542

543

544 **Fig.9.** Isoresponse curves for compressive strength at 1d: (a) (W/B vs. ANH), and (b) (GGBS
 545 vs. ANH).

546 Eqs. 16, 17 and 18 show the effect of GGBS and ANH percentages on compressive strength at
 547 3-d, 7-d and 28-d. Figures 10, 11, and 12 show the isoresponse of the compressive strength at
 548 3-d, 7-d and 28-d, respectively, with W/B vs, ANH. Increased ANH led to a decrease of 3-d
 549 and 7-d compressive strength. As expected, an Increase in W/B led to a decrease in compressive
 550 strength. The percentage of ANH had a negative effect on compressive strength and showed a
 551 greater influence particularly at 3-d and 7-d (8.79 (3 d) & 9.24 (7d) vs. 3.82 (28 d)). GGBS has
 552 a negative impact on early strength development. The negative effect of GGBS on compressive

strength at early ages is clearly attributable to the fact that up to 80% of cement has been replaced by GGBS, and it takes some time for GGBS to start developing its pozzolanic action at a noticeable level. The results indicate that ANH content influences strength to a greater extent than GGBS at all ages. The SO₃ content was reported to have great influence on the strength [39, 40].

Fig.10. Isoresponse curves for compressive strength at 3d: (a) (W/B vs. ANH), and (b) (GGBS vs. ANH).

Fig.11. Isoresponse curves for compressive strength at 7d: (a) (W/B vs. ANH), and (b) (W/B vs. ANH).

Fig.12. Isoresponse curves for compressive strength at 28d: (a) (W/B vs. ANH), and (b) (ANH vs. GGBS).

3.3.10 Discussion of the effect of W/B, GGBS, and ANH

As expected, the increase of W/B led to an increase in mini-slump, induced bleeding and a reduction in flow time, plate cohesion, yield stress, plastic viscosity and compressive strengths. This can be attributed to more water in the system.

An increase in GGBS content resulted in a reduction of the flow time, plate cohesion, yield stress and plastic viscosity while the fluidity is improved. This was due to the fact the specific gravity of slag is lower than that of PC leading to an increase in the paste volume and thus improving the fluidity of paste.

In case of an increase of ANH proportion, while W/B and GGBS were kept constant, it led to an increased mini-slump and induced bleeding, while the flow time, plate cohesion, yield stress, and plastic viscosity were reduced. This was due to the lower reactivity of ANH resulting in an increase of water needed for lubrication of paste.

As expected, an increase in W/B lead to an increase in induced bleeding, permeability and a decrease in compressibility [33, 35]. This is due to the increase in liquid volume between the particles and to the reduction in the amount of interparticle forces. Globally, the compressibility decreases and the permeability increases with ANH. It can be explained by the reduced specific area and lower reactivity that can lead to more available water in the samples.

3.3.11 Heat of Hydration

Heat of hydration is considered an important factor in the cement design as low heat of hydration reduces the effect of thermal cracking. The heat flow results of the calorimeter test performed over a three days period can be seen in Figure 13.

Fig. 13: Heat flow graphs for first 3 days of reaction.

Figure 13 presents that the largest peaks were in mixes 1, 2, 5 and 6. This shows that these reactions generated the most heat, and that they were quick. Mixes 1 and 2 have the highest OPC content at 40% and this suggests that to lower the heat of the reaction minimal OPC should be used. This is confirmed by the fact that mixes 5 and 6 have the next highest OPC contents, the same percentage as mixes 3, 4 and 9 (one of the repeated mixes) which have anhydrite present. This implies that the presence of anhydrite will lengthen the reaction process and reduce the heat produced during setting significantly. The graph shows this by the absence of a sharp peak, instead a gentle curved hump is shown over a 2-day period whereas the mixes showing a sharp peak occur after about 12 hrs. Mix 7, which has the same solids content as mix 8 but a lower W/B ratio and no cement present, showed the lowest heat flow during the hydration process.

Figure 14 shows the cumulative heat generation during the first 3 days of setting. It is clear that the two mixes (1 and 2) with highest cement content and absence of anhydrite had the highest cumulative heat development over the 3-day period 643J and 594J, respectively. Mixes 3,4,5,6 and 9 which all have 20% OPC content generated similar heat value over the 3 days. Results of mixes containing ANH implies that over the period that the anhydrite did not reduce the cumulative heat generated but slowed the reaction and reduce the peak heat generated. The

graphs also suggest that a higher W/B ratio produced a lower cumulative and peak heat generation.

Fig. 14: Cumulative heat generation curves for first 3 days.

3.3.12 pH measurements

Fig. 15 summarises the results of pH and the nine mixes with different compositions of W/B, the percentages of cement, GGBS and ANH. It is shown that Supersulfated cements (SSCs) have lower pH values (< 12.5 at all ages) than PC, which has a pH of 13.9 [41], making SSC more preferable in essential applications such as nuclear waste encapsulation.

The figure shows that the pH value decreased with time for all samples between 1 and 7 days. Similar trend was observed in the majority of mixes between 7 and 28 days except for sample 2, 5 and 9 which showed slight increase in the pH values. This decrease refers to the consumption of ions in the pore structure due to the hydration process.

Fig. 15. Summary of pore solution pH

The incorporation of ANH replacing the Portland cement (C) results in remarkable decrease in pH at all ages as introducing the ANH reduced the lower initial pH. Likewise, the increase in the content of GGBS led to a decrease in the pH value of the pore structure as GGBS has lower initial pH than Portland cement. The increase of W/B ratio decreased the pH value. This is in agreement with Collier [41] who found that increasing the w/b ratio from 0.5 to 0.6 increased the pH by 1 unit. This was attributed to the increased availability of water in the case of W/B of 0.6 allowing hydration of more cement powder, thereby releasing more hydroxide anions into solution. However, in this study, the W/B ratio did not show a significant effect on lowering the pH. These results are in agreement with [42] which also found that decreasing the pH improved the bulk resistivity of SSC mixtures.

3.3.13 SEM

Figure 16 shows the SEM images of some mixes at various magnifications. The images clearly show the dense and compact structure of the cement after seven days. The dense structure was another requirement from the cement chosen to enclose the waste to prevent leaching. The microstructure consists mainly of C-S-H, the main hydration product, and unhydrated slag grains. C-S-H is formed after the dissolution of slag grains when contacting the water and alkalis and then the ionic species saturate the solution and then precipitate as hydrated phases [8]. There were abundant grains of hydrated and partially hydrated slag grains, some small

647 GGBS particles presented rims of reaction products (e.g. Mix 6-Figure 16 (f) and Mix 9-Figure
648 16 (h)). It was found by [11] that the composition of the reaction rims around slag was similar
649 to that of the C-S-H from PC. However, [12] found that in the C-S-H of SSC is apparently
650 more foil like which is different than the fibrillar morphology of C-S-H in OPC. Mix 3 and
651 Mix 4 (Figure 16 (c) and (d) respectively) exhibits more micro voids in the microstructure
652 which could explain the low strength of these mixes compared to mix 1 and 2. Ettringite was
653 not detected. Ettringite is not the most abundant phase and it is not easy to detect in dried
654 polished samples because it is easily decomposed under the drying conditions of the vacuum
655 of the microscope column [11].

(a) Mix 1 image at 1,100 magnification

(b) Mix 2 image at 900 magnification.

(c) Particle of unreacted slag, mix3, 7 days

(d) An overall image of mix 4 at 7days showing CSH and BFS particles

(e) Mix 5 image at 1100 magnification

(f) Mix 6 image at 2300 magnification

(g) Mix 7 image at 2000 magnification

(h) Mix 9 image at 2700 magnification

Fig. 16. SEM results

4. Conclusions

The paper focused on optimizing the SSC cement grout in order to get the best of it. The effect of GGBS, W/B, and ANH dosages on the grout fluidity, rheological properties, induced bleeding, maximum heat of hydration and compressive strength was investigated using factorial design approach and analysis. The models derived in this study are valid for the experimental area corresponding to grout mixes made with variable levels of W/B, ANH and GGBS in the ranges of 0.34 to 0.44, 0% to 20% by mass of binder, 60% to 80% by mass of binder, respectively. Based on the results from this study, the following conclusions are drawn:

- In comparison to GGBS and ANH, W/B ratio had more pronounced effects on the results of mini-slump, plate cohesion meter, Marsh cone time, yield stress, plastic viscosity, induced bleeding, permeability, compressibility, and compressive strength.

- The increase in the dosage of GGBS led to an increase in the values of plate cohesion meter, Marsh cone time, yield stress and plastic viscosity, while reducing the mini-slump values, maximum hydration, and compressive strength. This is ascribed to the fine nature of GGBS particles and pozzolanic effect.

- While the ANH particles caused a decrease in the maximum of heat of hydration, it increased the induced bleeding, permeability and compressibility due to its dominant effect on increasing the dormant period and increasing the rates of solid sedimentation and induced bleeding water.

- Increasing the dosage of ANH in grout reduced the hydrations kinetic at early-age, and thus reduced the compressive strength at 1d, 3d and 7d. However, this effect diminished at later ages at 28 d in a manner similar to increasing W/B.

- The increase in the dosage of ANH led to an increase in the mini-slump values (fluidity), but a decrease in the values of yield stress, plastic viscosity, plate cohesion, and Marsh cone time. This is attributed to better deflocculation of particles at the fresh state.

- The increase of GGBS percentage delayed the reaction process and decreased the total heat after 3 days, while W/B slightly reduced the total heat it didn't significantly affect the reaction process.

- pH measurements in the present study confirmed the suitability of these mixture to low-pH applications as the increase in both the GGBS and ANH markedly decreased the initial pH, thereby lowering the pH at different ages.

- The modelling and prediction of the response of other points in the experimental domain were therefore possible. Although the models are based on a given set of materials, they can be easily used to generate future results using other materials.

- Dense microstructure was observed for mixes examined in this study. C-S-H is the main reaction product with presence of unreacted slag grains embedded well in the structure. However, some micro voids were observed in mixes containing ANH which led to lower compressive strength of mixes with ANH.

CRedit authorship contribution statement

M.Sonebi. and Y.Bai. did the conceptualization, and the design of investigation as well as performing the experiments. M.Sonebi. carried out the software analysis of the results and the

visualization. M.Sonebi. A.Abdalqader, T. Fayyad, and A.Perrot. analysed the results and wrote the original draft and reviewed and edited the final version.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgments

The authors would like to express their gratitude to P. McCann from QUB and N. Collier from Eden Nuclear and Environment Ltd for their helps for some experiments.

References

1. Schneider M, Romer M, Tschudin M, Bolio H (2011) Sustainable cement production-present and future. *Cement and Concrete Research* 41:642–650. <https://doi.org/10.1016/j.cemconres.2011.03.019>
2. Madloul NA, Saidur R, Hossain MS, Rahim NA (2011) A critical review on energy use and savings in the cement industries. *Renewable and Sustainable Energy Reviews* 15:2042–2060. <https://doi.org/10.1016/j.rser.2011.01.005>
3. EN15743 (2015) BS EN 15743:2010+A1:2015 Supersulfated cement - Composition, specifications and conformity criteria. BSI
4. Khatib JM, Wright L, Mangat PS (2016) Mechanical and physical properties of concrete containing FGD waste. *Magazine of Concrete Research* 68:550–560. <https://doi.org/10.1680/mac.15.00092>
5. Khatib JM, Mangat PS, Wright L (2008) Sulfate resistance of mortar containing simulated FGD waste. *Proceedings of Institution of Civil Engineers: Construction Materials* 161:119–128. <https://doi.org/10.1680/coma.2008.161.3.119>
6. (2020) Specifying Sustainable Concrete
7. Hewlett PC (2004) Lea's Chemistry of Cement and Concrete, fourth edi. Elsevier Science & Technology Books, Oxford
8. Gruskovnjak A, Lothenbach B, Winnefeld F, et al (2008) Hydration mechanisms of super sulphated slag cement. *Cement and Concrete Research* 38:983–992. <https://doi.org/10.1016/j.cemconres.2008.03.004>
9. Grounds T, Nowell D V., Wilburn FW (2003) Resistance of supersulfated cement to strong sulfate solutions. *Journal of Thermal Analysis and Calorimetry* 72:181–190. <https://doi.org/10.1023/A:1023928021602>
10. Grounds T, Nowell D V., Wilburn FW (1995) The influence of temperature and different storage conditions on the stability of supersulphated cement. *Journal of Thermal Analysis* 45:385–394. <https://doi.org/10.1007/BF02548772>

- 734 11. Bazaldúa-Medellín ME, Fuentes AF, Gorokhovskiy A, Escalante-García JI (2015) Early
735 and late hydration of supersulphated cements of blast furnace slag with fluorgypsum.
736 *Materiales de Construcción* 65:e043. <https://doi.org/10.3989/mc.2015.06013>
- 737 12. Matschei T, Bellmann F, Stark J (2005) Hydration behaviour of sulphate-activated slag
738 cements. *Advances in Cement Research* 17:167–178.
739 <https://doi.org/10.1680/adcr.2005.17.4.167>
- 740 13. Richardson IG (2000) Nature of the hydration products in hardened cement pastes.
741 *Cement and Concrete Composites* 22:97–113. [https://doi.org/10.1016/S0958-](https://doi.org/10.1016/S0958-9465(99)00036-0)
742 [9465\(99\)00036-0](https://doi.org/10.1016/S0958-9465(99)00036-0)
- 743 14. Baux C, Phelipot-Mardelé A, Lanos C, et al (2013) PERFORMANCES OF SUPER
744 SULFATED CEMENTS. In: *International Conference on Concrete Under Severe*
745 *Conditions*. pp 1857–1870
- 746 15. Annabelle Phelipot-Mardelé, Gabriel Samson, Christophe Lanos (2015) Super sulfated
747 cement: formulation and uses. In: *Construction Materials ConMat*. Whistler, Canada
- 748 16. Milestone NB (2006) Reactions in cement encapsulated nuclear wastes: need for
749 toolbox of different cement types. *Advances in Applied Ceramics* 105:13–20.
750 <https://doi.org/10.1179/174367606X81678>
- 751 17. Batchelor B (2006) Overview of waste stabilization with cement. *Waste Management*
752 26:689–698. <https://doi.org/10.1016/J.WASMAN.2006.01.020>
- 753 18. Zhang T, Cheeseman CR, Vandeperre LJ (2011) Development of low pH cement
754 systems forming magnesium silicate hydrate (MSH). *Cement and Concrete Research*
755 41:439–442. <https://doi.org/10.1016/j.cemconres.2011.01.016>
- 756 19. Mobasher N, Bernal SA, Provis JL (2016) Structural evolution of an alkali sulfate
757 activated slag cement. *Journal of Nuclear Materials* 468:97–104.
758 <https://doi.org/10.1016/J.JNUCMAT.2015.11.016>
- 759 20. Wang J, Yu B, Gao Y (2014) Hydration Characteristics of Super Sulphated Cement
760 with Different Fineness. In: *Proceedings of the International Conference on Material*
761 *and Environmental Engineering (ICMAEE 2014)*. Atlantis Press, Paris, France
- 762 21. Nägele E (1986) The Zeta-potential of cement: Part II: Effect of pH-value. *Cement and*
763 *Concrete Research* 16:853–863. [https://doi.org/10.1016/0008-8846\(86\)90008-6](https://doi.org/10.1016/0008-8846(86)90008-6)
- 764 22. Jain N, Civil MG-II of M and, 2015 U (2015) Formulation of Sulphate Resistant Super
765 Sulphated Cement Using Fluorogypsum and Granulated Blast Furnace Slag. *IOSR*
766 *Journal of Mechanical and Civil Engineering (IOSR-JMCE)* 12:153–159
- 767 23. Gao YX, Yu BY, Xu FL (2012) Effect of Modified Phosphogypsum on the Mechanical
768 Properties of Super Sulphate Cement. *Applied Mechanics and Materials* 161:264–268.
769 <https://doi.org/10.4028/www.scientific.net/AMM.161.264>
- 770 24. Kantro D (1980) Influence of Water-Reducing Admixtures on Properties of Cement
771 Paste—A Miniature Slump Test. *Cement, Concrete and Aggregates* 2:95–102.
772 <https://doi.org/10.1520/CCA10190J>

- 773 25. Svermova L, Sonebi M, Bartos PJM (2003) Influence of mix proportions on rheology of
774 cement grouts containing limestone powder. *Cement and Concrete Composites* 25:737–
775 749. [https://doi.org/10.1016/S0958-9465\(02\)00115-4](https://doi.org/10.1016/S0958-9465(02)00115-4)
- 776 26. Sonebi M (2006) Rheological properties of grouts with viscosity modifying agents as
777 diutan gum and welan gum incorporating pulverised fly ash. *Cement and Concrete*
778 *Research* 36:1609–1618. <https://doi.org/10.1016/J.CEMCONRES.2006.05.016>
- 779 27. Nehdi M, Rahman M (2004) Effect of Geometry and Surface Friction of Test Accessory
780 on Oscillatory Rheological Properties of Cement Pastes. *ACI Materials Journal*
781 101:416–424. <https://doi.org/10.14359/13428>
- 782 28. Khayat KH, Yahia A (1997) Effect of Welan Gum-High-Range Water Reducer
783 Combinations on Rheology of Cement Grout. *ACI Materials Journal* 94:365–372.
784 <https://doi.org/10.14359/321>
- 785 29. Lombardi G (1985) THE ROLE OF COHESION IN CEMENT GROUTING OF
786 ROCK. In: *Proceedings of Fifteenth Congress on Large Dams*. International
787 Commission on Large Dams. pp 235–261
- 788 30. Perrot A, Rangeard D, Picandet V, Mélinge Y (2013) Hydro-mechanical properties of
789 fresh cement pastes containing polycarboxylate superplasticizer. *Cement and Concrete*
790 *Research* 53:221–228. <https://doi.org/10.1016/J.CEMCONRES.2013.06.015>
- 791 31. Perrot A, Lecompte T, Khelifi H, et al (2012) Yield stress and bleeding of fresh cement
792 pastes. *Cement and Concrete Research* 42:937–944.
793 <http://dx.doi.org/10.1016/j.cemconres.2012.03.015>
- 794 32. Sonebi M, Perrot A (2019) Effect of mix proportions on rheology and permeability of
795 cement grouts containing viscosity modifying admixture. *Construction and Building*
796 *Materials* 212:687–697. <https://doi.org/10.1016/j.conbuildmat.2019.04.022>
- 797 33. Picandet V, Rangeard D, Perrot A, Lecompte T (2011) Permeability measurement of
798 fresh cement paste. *Cement and Concrete Research* 41:330–338.
799 <https://doi.org/10.1016/J.CEMCONRES.2010.11.019>
- 800 34. Perrot A, Rangeard D (2017) Effects of mix design parameters on consolidation
801 behaviour of fresh cement-based materials. *Materials and Structures* 50:117.
802 <https://doi.org/10.1617/s11527-016-0988-0>
- 803 35. Rangeard D, Perrot A, Picandet V, et al (2015) Determination of the consolidation
804 coefficient of low compressibility materials: application to fresh cement-based
805 materials. *Materials and Structures* 48:1475–1483. [https://doi.org/10.1617/s11527-014-](https://doi.org/10.1617/s11527-014-0247-1)
806 [0247-1](https://doi.org/10.1617/s11527-014-0247-1)
- 807 36. Massoussi N, Keita E, Roussel N (2017) The heterogeneous nature of bleeding in
808 cement pastes. *Cement and Concrete Research* 95:108–116.
809 <https://doi.org/10.1016/J.CEMCONRES.2017.02.012>
- 810 37. Montgomery D (2007) *Design and Analysis of Experiments: Second Edition*. John
811 Wiley & Sons

38. Roussel N, Stefani C, Leroy R (2005) From mini-cone test to Abrams cone test: Measurement of cement-based materials yield stress using slump tests. *Cement and Concrete Research* 35:817–822. <https://doi.org/10.1016/j.cemconres.2004.07.032>
39. Mangat PS, Khatib JM, Wright L (2006) Optimum utilisation of FGD waste in blended binders. *Proceedings of Institution of Civil Engineers: Construction Materials* 159:119–127. <https://doi.org/10.1680/coma.2006.159.3.119>
40. Khatib JM, Mangat PS, Wright L (2013) Early age porosity and pore size distribution of cement paste with flue gas desulphurisation (FGD) waste. *Journal of Civil Engineering and Management* 19:622–627. <https://doi.org/10.3846/13923730.2013.793609>
41. Collier NC, Milestone NB, Gordon LE, Ko SC (2014) The suitability of a supersulfated cement for nuclear waste immobilisation. *Journal of Nuclear Materials* 452:457–464. <https://doi.org/10.1016/j.jnucmat.2014.05.078>
42. Masoudi R (2018) Examining compositions, hydration mechanisms and properties of supersulfated cement for use in concrete by Examining compositions , hydration mechanisms and properties of supersulfated cement for use in concrete. University of Toronto