**QUEEN'S
UNIVERSITY
BELFAST**

Photocatalytic removal of the cyanobacterium *Microcystis aeruginosa* PCC7813 and four microcystins by TiO₂ coated porous glass beads with UV-LED irradiation

Pestana, C. J., Noronha, J. P., Hui, J., Edwards, C., Gunaratne, H. Q. N., Irvine, J. T. S., Robertson, P., Capelo-Neto, J., & Lawton, L. (2020). Photocatalytic removal of the cyanobacterium *Microcystis aeruginosa* PCC7813 and four microcystins by TiO₂ coated porous glass beads with UV-LED irradiation. *Science of the Total Environment*, 745, [141154]. <https://doi.org/10.1016/j.scitotenv.2020.141154>

Published in:
Science of the Total Environment

Document Version:
Peer reviewed version

Queen's University Belfast - Research Portal:
[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

© 2020 Elsevier Ltd.

This manuscript is distributed under a Creative Commons Attribution-NonCommercial-NoDerivs License

(<https://creativecommons.org/licenses/by-nc-nd/4.0/>), which permits distribution and reproduction for non-commercial purposes, provided the author and source are cited.

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

**Photocatalytic removal of the cyanobacterium *Microcystis aeruginosa*
PCC7813 and four microcystins by TiO₂ coated porous glass beads with
UV-LED irradiation**

Carlos J. Pestana^{a*}, Jolita Portela Noronha^{a,b}, Jianing Hui^c, Christine Edwards^a, H.
Q. Nimal Gunaratne^d, John T.S. Irvine^c, Peter K.J. Robertson^d, José Capelo-
Neto^b, Linda A. Lawton^a

^a School of Pharmacy and Life Sciences, Robert Gordon University, Aberdeen,
United Kingdom

^b Department of Hydraulic and Environmental Engineering, Federal University of
Ceará, Fortaleza, Brazil

^c School of Chemistry, University of St. Andrews, St. Andrews, United Kingdom

^d School of Chemistry and Chemical Engineering, Queen's University, Belfast,
United Kingdom

*Corresponding author: c.pestana@rgu.ac.uk

Keywords: Cyanobacteria, Photocatalysis, Cyanotoxins, Water Treatment,
Titanium Dioxide, UV-LED

Highlights

- Photocatalytic inhibition of *M. aeruginosa* PCC7813 (7.6×10^5 cells mL⁻¹ d⁻¹)
- 74% removal of four microcystins (intra- and extracellular)
- Porous glass beads made from recycled glass used as catalyst support
- UV irradiance supplied by low energy UV (365 nm) emitting LEDs

Graphical Abstract

Abstract

Cyanobacteria and their toxic secondary metabolites are a challenge in water treatment due to increased biomass and dissolved metabolites in the raw water. Retrofitting existing water treatment infrastructure is prohibitively expensive or unfeasible, hence 'in-reservoir' treatment options are being explored. In the current study, a treatment system was able to photocatalytically inhibit the growth of *Microcystis aeruginosa* and remove released microcystins by photocatalysis using titanium dioxide coated, porous foamed glass beads and UV-LEDs (365 nm). A 35% reduction of *M. aeruginosa* PCC7813 cell density compared to control samples was achieved in seven days. As a function of cell removal, intracellular microcystins (microcystin-LR, -LY, -LW, and -LF) were removed by 49% from 0.69 to 0.35 µg mL⁻¹ in seven days. Microcystins that leaked into the surrounding water from compromised cells were completely

removed by photocatalysis. The findings of the current study demonstrate the feasibility of an in-reservoir treatment unit applying low cost UV-LEDs and porous foamed beads made from recycled glass coated with titanium dioxide as a means to control cyanobacteria and their toxins before they can reach the water treatment plant.

1. Introduction

Cyanobacteria are well known to form blooms in nutrient-rich waters, including drinking water reservoirs. High cell densities challenge water treatment systems by reducing the run time of filters leading to an increased demand of treatment chemicals such as coagulants and disinfectants (De Julio *et al.*, 2010). This problem is often further exacerbated by the release of toxic and/or noxious metabolites produced by the cyanobacteria, further challenging water treatment plant operators and decreasing water security (Chow *et al.*, 1999; Drikas *et al.*, 2001; Velzeboer *et al.*, 1995). The most commonly reported cyanobacterial toxic metabolites are the microcystins. To date at least 247 microcystin congeners have been described (Spoof and Catherine, 2017). The toxicity of microcystins has been recognized as a global issue with the World Health Organisation setting a recommended maximum allowable limit of $1 \mu\text{g L}^{-1}$ in drinking water (WHO, 2017).

Retro-fitting water treatment plants with improved and advanced technology is often prohibitively expensive and/or physically challenging, hence alternative treatment technologies such as in-reservoir treatment need to be explored. The application of algaecides in the reservoir is the simplest form of in-reservoir treatment but studies have shown the negative effects of this practice, such as toxicity to non-target organisms, development of bacterial resistances, increase

of potentially toxic/noxious dissolved metabolites and precursors of disinfection by-products (Bishop *et al.*, 2017; García-Villada *et al.*, 2004; Greenfield *et al.*, 2014; Jančula and Maršálek, 2011).

In recent years, advanced oxidation processes, including titanium dioxide (TiO₂) photocatalysis have been demonstrated to control cyanobacteria and their secondary metabolites. Successful removal of cyanobacterial toxins by TiO₂ nanoparticulate photocatalysis have been reported by a number of studies (Cornish *et al.*, 2000; Liu *et al.*, 2009; Pelaez *et al.*, 2011), especially for the elimination of the commonly occurring group of cyanobacterial toxins, the microcystins. One of the most critical technical challenges that has hampered the application of photocatalysis in water treatment is the removal of the nanoparticulate TiO₂ materials following treatment. The post treatment recovery of TiO₂ is not only a technical challenge but also has ecotoxicological health implications. It has been demonstrated that nanoparticulate TiO₂ can bioaccumulate and damage biota (Heinlaan *et al.*, 2008; Wang *et al.*, 2007; Zhu *et al.*, 2010). Further, the application of nanoparticulate TiO₂ represents a health hazard to operators if inhaled (Grassian *et al.*, 2007). To avoid the problems of free nanoparticulate TiO₂, immobilization of the photocatalyst onto a robust carrier matrix is preferable. Matrices such as activated carbon, metal particles, and glass have been explored, each with inherent advantages and disadvantages (Kinley *et al.*, 2018; Liu *et al.*, 2007; Pestana *et al.*, 2015). Several design parameters have to be considered when applying immobilized TiO₂ in a water treatment context. For example, cyanobacteria occupy different positions in the water column, depending on species and time of the day (Varuni *et al.*, 2017). Thus, to ensure maximum efficiency of immobilized TiO₂, an even distribution throughout the water column is desirable. Surface floating matrices will not

reach cyanobacteria deeper in the water column and likewise heavier matrices that sink will miss cyanobacteria higher up in the water column. The use of semi-bouyant foamed glass beads allows for even distribution in the water column. Additionally, the use of low-cost (ca. USD 0.30 per LED), long life (approximately 100,000 working hours), waterproof UV (365 nm) emitting LEDs to activate TiO₂ would solve a further technological challenge in the application of this *in-situ* treatment system, as in the past supplying cost-effective UV irradiation of the required wavelength has been problematic. While in recent years solar light-driven photocatalysis has been explored for the removal of contaminants of emerging concern, including cyanobacteria and their toxins, the application of this technology at scale suffers from drawbacks compared to the use of for example UV-LEDs (Fagan et al., 2016). There are two major drawbacks to this technology, one is the need to modify TiO₂ to shift its activity into the visible light range, usually achieved doping with other materials such as noble metals, carbon, or nitrogen (Wang et al., 2017, Fotiou et al., 2013). This would increase the cost of the treatment as additional steps and materials are required in the catalyst preparation. The other drawback of solar light-driven catalysis is that sunlight hours vary across the globe and that it is only available for a maximum of 12 h per day, thus rendering a purely solar light-driven treatment system inactive overnight. Recently, we have shown the feasibility of such a system for the photocatalytic removal of microcystin-LR (Gunaratne et al., 2020). Applying a similar technology using TiO₂ coated porous glass beads and UV-emitting LEDs, we now present a bench scale proof-of-principle in-reservoir treatment system that aims to inhibit and eliminate cyanobacteria while simultaneously removing toxins that are released and is energy efficient, thus can be maintained in continuous use to limit cyanobacterial biomass and

dissolved metabolites entering water treatment plants. It is envisaged that the pre-treatment system operates continuously avoiding the formation of intense blooms and keeping the cyanobacterial biomass at a level that allows the conventional water treatment process to completely remove any remaining cyanobacteria, while at the same ensuring that no dissolved toxins enter the plants that are ill equipped to remove dissolved contaminants, rather than a point treatment used when cell numbers or toxin concentrations exceed national threshold levels.

2. Materials and Methods

2.1 Reagents

All reagents for the preparation of artificial fresh water (AFW) and cyanobacterial culture medium BG-11 were of reagent grade, obtained from Fisher Scientific (UK), and used as received. Acetonitrile and methanol were of HPLC grade and obtained from Fisher Scientific (UK). Ultrapure water (18.2 MΩ) was provided by a PURELAB® system (ELGA Veolia, UK). Isoton II Diluent (Beckman Coulter, USA) was used for cell enumeration and biovolume determination.

2.2 Cyanobacterial cell culture

M. aeruginosa PCC7813 was originally obtained from the Pasteur Culture Collection (France) and cultured in sterilized BG-11 medium (Stanier *et al.*, 1971), at 22±1 °C with a 12h/12h light dark cycle at 20 μmol photons m⁻² s⁻¹ under aseptic conditions. *M. aeruginosa* PCC7813 produces four main microcystin analogues (MC-LR, MC-LY, MC-LW, and MC-LF) and does not contain gas vesicles.

2.3 Preparation of TiO₂ coated recycled porous glass beads

Porous recycled foamed glass beads (1-4 mm diameter, Poraver, Germany) were sieved to achieve > 2 mm, then washed with acetone, followed by deionised water in a sonication bath (Scientific Laboratory Supplies Ltd., UK) and dried in an oven at 80 °C for 18 h. After this pre-treatment, beads were coated with titanium dioxide (P25, Rutile/Anatase: 85/15, 99.9 %, 20 nm particle size; Degussa Evonik, Germany) according to a method by Mills *et al.* (2006) with adaptations. In short, a slurry of P25 and water is prepared into which the pre-treated glass beads are submerged. Coated beads are removed from the slurry and allowed to dry, followed by calcination at 550 °C for 3h. Each coating procedure deposits approximately 2% (w/w) of TiO₂ onto the beads. Coatings are repeated until approximately 10% (w/w) of TiO₂ on the beads was achieved. Characterization of the beads and the coating is recorded in the supplementary material (S1 and figure S1).

2.4 Photocatalytic removal of *M. aeruginosa* PCC7813 and microcystins

Artificial fresh water (AFW) was used as an experimental matrix in the photocatalysis investigation, and was prepared according to Akkanen and Kukkonen (2003) by dissolving CaCl₂ (11.8 mg L⁻¹), MgSO₄ (4.9 mg L⁻¹), NaHCO₃ (2.6 mg L⁻¹) and KCl (0.2 mg L⁻¹) in ultrapure water. A three-week-old culture of *M. aeruginosa* PCC7813 was diluted in AFW to achieve a final cell density of 15 x 10⁶ cells mL⁻¹. TiO₂ coated beads (700 mg, equivalent to 0.2% (w/v) TiO₂) were placed in glass mesh pods (70 mm x 10 mm diameter) and placed into 40 mL glass bottles (95 mm x 22 mm diameter) into which 30 mL of the cell suspension was added. Three replicates containing the coated beads was irradiated by a 550 cm² UV-LED panel with 90 individual UV-LEDs (AT

Technologies, UK) providing $2.8 \mu\text{mol photons m}^{-2} \text{ s}^{-1}$ (2.1 mW s^{-1}) at 365 nm and at 100 mm distance (figure 1). Another three replicates, not containing titanium dioxide coated beads was prepared at the same distance from the UV-LEDs functioning as a UV control. While a third set of replicates with TiO_2 coated beads was set up outside of the area of irradiation of the UV-LED panel to act as a no-UV control. Typically, in photocatalysis the dark/no-UV control is performed in complete darkness; however, cyanobacteria are photosynthetic organisms that would not survive the duration of the experiment without light, hence this third set of replicates was maintained in ambient light (no UV irradiation at $13 \mu\text{mol s}^{-1} \text{ m}^{-2}$ cool fluorescent irradiation). To maintain clarity 'TiO₂-control' will be used throughout to identify samples that contain TiO_2 coated glass beads, but are not exposed to UV irradiation. All samples were sparged at 1.5 L min^{-1} with sterile ambient air. After taking a zero-time sample, each replicate was sampled (1.1 mL) daily.

Figure 1: A) Schematic diagram of the UV-LED photocatalytic experimental design (top-down view). 1- air pump, 2- air distribution hub to achieve equal air pressure across all samples, 3- silicone tubing of equal length, 4- TiO₂/UV treatment samples in triplicate, 5- UV control samples in triplicate, 6- UV-LED panel with 90 UV-LEDs (365 nm, 67.5 mW total output) in 9 rows of 10 LEDs; output at 100 mm 2.6 mW s⁻¹, 7- reflective surface; also blocking UV irradiation from LED panel to TiO₂-controls (8), 8- TiO₂-control samples in triplicate, 9- silicone tubing. B) Photographic representation of the reactor and the TiO₂/UV and UV control samples.

2.5 Sample analysis

2.5.1 Cell enumeration and sample pre-treatment

For cell enumeration, cell volume determination, and determination of the average cell diameter of *M. aeruginosa* PCC7813, 0.1 mL of each sample was diluted in 20 mL of Isoton II diluent and analysed by a Multisizer (Beckman

Coulter, USA). For this a 50 µm aperture was used, allowing the determination of particles sized between 1 and 30 µm, particles ranging in size from 2.8 to 6.9 µm were considered intact cells based on published data of cell size ranges for *M. aeruginosa* (Harke *et al.*, 2016; Komárek and Komárková, 2002). This cut-off had to be introduced to ensure that cell fragments smaller than 2.8 µm are not considered cells which would artificially increase the cell densities. For microcystin analysis, the remaining 1 mL of each sample was centrifuged (13000 G) in microcentrifuge tube (1.5 mL) for 10 min to separate cells and medium. The supernatant was evaporated to dryness on an EZ-II Evaporator (Genevac, United Kingdom). The cell pellet was stored at -20 °C until further processing. Prior to analysis, aqueous methanol (80 %) was added to the cell pellets which were subsequently placed in a dispersive extractor for 5 minutes at 2500 rpm and then centrifuged (13000 G). The supernatant was analysed to determine intracellular toxin. The dried extracellular component was also resuspended in aqueous methanol (80%, 150 µL), vortexed and centrifuged (13000 G). The intra- and extracellular microcystins were analysed by HPLC.

2.5.2 High performance liquid chromatography analysis of microcystins

Chromatographic separation of microcystin analogues was carried out using a 2965 separation module with a Symmetry C18 column (2.1 x 150 mm, 5 µm particle size) and a 2996 photodiode array (PDA) detector. Mobile phases were ultrapure water (18.2 MΩ) and acetonitrile both with 0.05% trifluoroacetic acid. Separation was achieved with a linear gradient from 35 to 70% organic phase over 25 min followed by an organic solvent wash (100%) and re-establishment of starting conditions. Column temperature was 40 °C. Scanning range for the

PDA was 200 to 400 nm, with microcystins integrated at 238 nm. The limit of quantification of this method was 5 ng mL⁻¹.

2.5.3 Statistical analysis

All values shown are mean of triplicate treatments with error of one standard deviation. For statistical significance testing results were analyzed using one-way ANOVA. The significance level was set to $p>0.05$ to identify significant differences between results.

3. Results and Discussion

3.1 Photocatalytic removal of *M. aeruginosa* PCC7813

The removal of *M. aeruginosa* PCC7813 in a photocatalytic reactor with TiO₂ coated porous glass beads and UV-LED irradiation was initially investigated. Over the course of seven days treatment the cell concentration of *M. aeruginosa* PCC7813 increased significantly in both controls, UV with no catalyst and no UV irradiation ($p<0.05$ each), achieving 32 and 34 x 10⁶ cells mL⁻¹ respectively, representing a per cent increase of 213 and 226%. There was no statistical difference between the UV- and the TiO₂-controls ($p>0.05$). No effect of the UV only control would be expected as the UV light emitted by the UV-LED is comparatively low in energy at 2.6 mW s⁻¹ and the emitted wavelength is insufficient to be germicidal (germicidal wavelength <254 nm; Ou *et al.*, 2012). On the other hand, in the treatment samples the initial cell concentration (15 x 10⁶ cells mL⁻¹) was significantly reduced to 10 x 10⁶ cells mL⁻¹ (35%, $p=0.00004$) when compared to the TiO₂-control (figure 2). The biovolume of the *M. aeruginosa* PCC7813 culture also decreased over the course of the experiment (66% of the TiO₂- control), which corresponds to and corroborates

the observed decrease in cell density. There was no statistical difference between the two controls with respect to the cell volume ($p>0.05$). The diameter of the intact cells (2.8-6.5 μm) did not significantly change ($p>0.05$) from either the initial cell size at time zero or after seven days treatment when compared to either control (UV with catalyst and no UV irradiation). This indicates that the treatment fragmented the cells into particles smaller than 2.8 μm rather than affect the cell diameter since the mean cell diameter did not change. Cell fragmentation during photocatalytic treatment was also observed by Wang *et al.* (2017) where *M. aeruginosa* (strain 913 from Wuhan Institute of Hydrobiology) cells were treated with floating, expanded perlite particles that were coated with F-Ce doped TiO_2 .

Figure 2: a) Removal of *M. aeruginosa* PCC7813 cells by photocatalysis using TiO₂ coated porous glass beads over a seven-day period under $2.8 \mu\text{mol photons m}^{-2} \text{s}^{-1}$ at 365 nm (2.6 mW s^{-1}) at 100 mm distance, as well as the effect of the treatment on *M. aeruginosa* PCC7813 b) cell volume, and c) mean cell diameter. ($n=3$, Error=1SD)

276 From 48 h onwards, a decline in cell density was observed for the treatment with
277 TiO₂/UV (figure 2a). Other studies have reported the inhibition of *M. aeruginosa*
278 growth by TiO₂ photocatalysis in one hour (Liao *et al.*, 2009; Pinho *et al.*, 2015),
279 however, there are marked differences in the application of the TiO₂
280 photocatalysis in terms of light source, *M. aeruginosa* strain, and presentation of
281 TiO₂. The UV-LED panel employed in the current investigation had a total output
282 of 67.5 mW (with each individual LED having an output of 750 μ W, and the
283 panel having a total of 90 LEDs) providing a very low energy input into the
284 system. By comparison Pinho *et al.* (2015), who investigated the removal of *M.*
285 *aeruginosa* LEGE 91094 (IZANCY-A2) with particulate TiO₂, used simulated solar
286 irradiation at a UV equivalent of 44 W m⁻², and Liao *et al.* (2009), who
287 investigated the effect of silver-doped TiO₂ particulates on an unspecified *M.*
288 *aeruginosa* strain, used a UV-C lamp with 4 W output at 253.7 nm. The UV-LEDs
289 (67.5 mW) deployed in the current investigation use almost sixty times less
290 energy than the 4 W lamp used in the other study. An additional advantage of
291 employing LEDs is their longer life span in comparison to light bulbs, ca. 100,000
292 h compared to ca. 8,000 to 25,000 h for other UV irradiation sources (Heering,
293 2004). Furthermore, while rapid cell death is recorded when nanoparticulate TiO₂
294 is used, the removal of catalyst has been a barrier to deployment of this
295 technology. A particular advantage of the current system is the use of
296 immobilized TiO₂. While the reactive surface area is markedly reduced compared
297 to particulate catalyst systems, immobilized catalyst offers a much more facile
298 post-treatment separation of catalyst and water compared to (nano)particulate
299 TiO₂. In addition, most of these other studies which investigated the inhibition of
300 *M. aeruginosa* by TiO₂ photocatalysis, used modified TiO₂ composite materials.
301 Liao and co-workers (2009) used Ag-doped TiO₂ and Wang *et al.* (2017) used F-

Ce-doped TiO₂ further increasing the photocatalytic activity compared to TiO₂ alone. The doping of TiO₂ offers the advantage of shifting reactivity into the visible spectrum, however, this has to be weighed against the cost of the doping material and the complexity of preparation. Additionally, the intended application has to be considered. The current design is aimed at continuous operation within a reservoir to ease the burden on the water treatment process within a treatment plant. Thus, materials used need to be plentiful, economically affordable, and easy to obtain, which is not the case when doping with, for example, noble metals.

The UV irradiation (365 nm) alone had no observable effect on the cell number, cell volume, or cell diameter (figure 2), which was what might have been expected since antimicrobial UV treatments tend to employ irradiance in the UV-C spectrum of a wavelength of 260 nm and below (Wolfe, 1990). This was demonstrated in the Liao *et al.* (2009) study where approximately 12% difference in the chlorophyll *a* content between an untreated and the UV(C) controls was observed.

3.2 Photocatalytic removal of four microcystin congeners

The strain of *M. aeruginosa* PCC7813 used in the current investigation produces four main microcystin congeners (MC-LR, -LY, -LW, and -LF). During the photocatalysis of *M. aeruginosa* PCC7813 both the intracellular (figure 3) and extracellular (figure 4) microcystin concentrations were monitored. As microcystins are usually encountered in the intracellular space until cell integrity is compromised and the intracellular toxins leak into the surrounding water, monitoring the intracellular concentration during photocatalysis can be used as a proxy measurement of cell integrity. The distribution of the four congeners at

the start of the experiment was MC-LR 58%, MC-LY 9%, MC-LW 14%, and MC-LF 19% of the total intracellular microcystin concentration. A significant ($p=0.0009$ to 0.045) decrease of intracellular toxin concentration was observed for all four microcystin congeners over the course of seven days (figure 3) during photocatalytic treatment. Combined intracellular microcystin content decreased by 49% from 0.69 to $0.35 \mu\text{g mL}^{-1}$. Individually the concentrations for MC-LR, -LY, -LW, and -LF decreased by 53, 34, 60, and 54% respectively from the initial concentration present in the cells. The profile of different intracellular microcystin variants at the end of the seven-day experiment remained largely unchanged, with MC-LR remaining the main congener produced (54%), followed by MC-LF (23%) and MC-LY and MC-LW (11% each). There was no statistical difference *viz* the intracellular toxin concentration in either of the two controls ($p>0.05$). Compared to the TiO_2 and UV with no catalyst controls the concentration of the total intracellular microcystin in the treated samples was reduced by 67% with individual concentrations for MC-LR, -LY, -LW, and -LF decreased by 74, 50, 68, and 71% respectively. It is predicted that decrease in cell density and toxins concentration would continue and be maintained at a low level if this treatment system is used *in-situ* in a reservoir.

Figure 3: Removal of the four main intracellular microcystin analogues (MC-LR, MC-LY, MC-LW, MC-LF) produced by *M. aeruginosa* PCC7813 during a seven-day photocatalytic treatment with TiO₂ coated porous foamed recycled glass beads and UV-LED provided UV irradiation at 2.8 μmol photons m⁻² s⁻¹ at 365 nm (2.6 mW s⁻¹) at a distance of 100 mm. (n=3, Error=1SD)

For most of the congeners the amount of toxin per cell decreased (table 1), which is indicative that some of the cells detected by the particle counter were damaged, but had not yet completely fragmented. Zilliges and co-workers (2011) have observed that intracellular microcystins concentrations decrease as a response to oxidative stress. In their study Zilliges *et al.* (2011) were able to observe intracellular microcystins bind to intracellular proteins in the presence of hydrogen peroxide (0.34 mg L⁻¹). Hydrogen peroxide is a strong oxidizing agent and under UV irradiation hydrogen peroxide can lead to the creation of hydroxyl radicals, an even stronger oxidizing agent. Thus, the oxidative stress response of *M. aeruginosa* exposed to hydrogen peroxide may be comparable to the stress response to TiO₂ photocatalysis (where hydroxyl and superoxide radicals are created), indicating that the decrease in intracellular microcystin concentrations could also be caused by microcystins binding to intracellular proteins although this would require further investigation.

Table 1: Reduction of intracellular microcystin congener concentration in *M. aeruginosa* PCC7813 after seven days of treatment in a photocatalytic reactor under UV-LED irradiation (at 2.8 $\mu\text{mol photons m}^{-2} \text{s}^{-1}$ at 365 nm (2.6 mW s⁻¹)) at 100 mm distance in the presence of TiO₂ coated porous glass beads. ($n=3$, Error=1SD).

MC congener	Time 0 (fg cell ⁻¹)	Time 7d (fg cell ⁻¹)	Per cent reduction
MC-LR	25.8 $\pm$ 2	19.4 $\pm$ 2	25*
MC-LY	3.8 $\pm$ 0.1	3.5 $\pm$ 0.4	8
MC-LW	6.4 $\pm$ 0.4	4.3 $\pm$ 0.6	32*
MC-LF	10.8 $\pm$ 0.7	8.5 $\pm$ 0.8	21*

*difference significant ($p>0.05$)

When the cell integrity of microcystin-producing cyanobacteria is compromised by oxidative processes, the intracellular organic material leaks into the surrounding water, including any microcystins (Daly *et al.*, 2007). Therefore, it is important that water treatment systems either avoid compromising cell integrity or, failing that, the system should also be able to remove microcystins that are

released into the water. Failing to remove the dissolved organic matter,
including microcystins, exacerbates the challenges faced by water treatment
processes, as conventional water treatment is more suited to the removal of
particulate and colloidal than dissolved components (Chow *et al.*, 1999; Li *et al.*,
2012). In the current investigation, extracellular concentrations of the four main
microcystin congeners produced by *M. aeruginosa* PCC7813 were also monitored
(figure 4).

Figure 4: Extracellular microcystins (MC-LR, MC-LW, MC-LF) produced by *M. aeruginosa* PCC7813 during a seven-day photocatalytic treatment with TiO_2 coated porous glass beads and UV-LED provided UV irradiation at $2.8 \mu\text{mol photons m}^{-2} \text{s}^{-1}$ at 365 nm (2.6 mW s^{-1}) at 100 mm distance. ($n=3$, Error=1SD)

At the start of the experiment, relatively low concentrations ($0.02\text{--}0.04\ \mu\text{g mL}^{-1}$) of extracellular MC-LR, MC-LW, and MC-LF were detected, while no extracellular MC-LY was detected. Over the course of seven-day photocatalytic treatment, the extracellular microcystin concentrations remained low, not exceeding $0.05\ \mu\text{g mL}^{-1}$ in the treated samples, and were completely undetectable after day four of the UV/TiO₂ treatment. As the intracellular microcystins concentrations decrease due to loss of structural integrity of the cyanobacterial cells, extracellular toxin concentrations should increase, however this was not observed in the photocatalytically treated samples. Instead the intracellular microcystins were photocatalytically decomposed once they were released into the water. The efficacy of photocatalytic removal of dissolved microcystins has been demonstrated previously (Gunaratne *et al.*, 2020; Lawton *et al.*, 2003; Liu *et al.*, 2009; Pestana *et al.*, 2015). The decreased microcystin concentrations in the TiO₂-control compared to the UV only control can be explained with adsorption of the microcystin congeners onto the surface of the TiO₂ layer on the glass beads, as previously observed (Pestana *et al.*, 2015). The sum of the intracellular and extracellular microcystin concentrations of the TiO₂-control represents the total microcystin. Comparing this to the total microcystins of the photocatalytically treated samples allows the determination of the individual removal of the different microcystin congeners (table 2).

Table 2: Reduction of total microcystins (intra- and extracellular) produced by *M. aeruginosa* PCC7813 after seven days of treatment in a photocatalytic reactor under UV-LED irradiation ($2.8 \mu\text{mol photons m}^{-2} \text{s}^{-1}$ at 365 nm (2.6 mW s^{-1})) at 100 mm distance in the presence of TiO_2 coated porous glass beads. ($n=3$, Error=1SD)

MC congener	Mean total microcystins TiO_2 control ($\mu\text{g mL}^{-1}$)	Mean total microcystins photocatalytic treatment ($\mu\text{g mL}^{-1}$)	Mean Δ total microcystins time 7d ($\mu\text{g mL}^{-1}$)	Mean per cent reduction total microcystins
MC-LR	0.79 ± 0.04	0.19 ± 0.04	0.6 ± 0.07	76 ± 6
MC-LY	0.08 ± 0.01	0.04 ± 0.01	0.04 ± 0.01	55 ± 3
MC-LW	0.15 ± 0.02	0.04 ± 0.01	0.12 ± 0.01	72 ± 2
MC-LF	0.25 ± 0.03	0.08 ± 0.01	0.17 ± 0.03	66 ± 5
Combined	1.28	0.35	0.93	73

In the control samples (UV with no catalyst and TiO_2 with no UV) there were no cell-disrupting processes occurring which would lead to the liberation of microcystins. Thus, as expected, the extracellular microcystins concentrations (MC-LR, -LW, -LF) remained relatively consistent in both control samples over the course of seven days. Lack of cellular disruption is evidenced by the increase in cell numbers over the course of the seven days (figure 2) and intracellular microcystin concentrations (figure 3) in the TiO_2 -control. The doubling rate of *M. aeruginosa* PCC7813 in the TiO_2 -control is approximately seven days (from 1.5×10^6 at time 0 to 3.4×10^6 cells mL^{-1} at time 7 d). Wilson and co-workers (2006) report the average doubling time for environmental isolates of *M. aeruginosa* cultured in BG-11 medium as 2.8 days. In the current study *M. aeruginosa* PCC7813 was placed in artificial fresh water which contained none of the main nutrients required for growth, which can explain the slower doubling rate. Another factor that will affect the growth rate of *M. aeruginosa* is the initial inoculation cell density. In the current study initial cell density was 15×10^6 cells mL^{-1} in 30 mL, which represents a very high inoculation cell density. In a laboratory study Dunn and Manoylov (2016) have demonstrated that *M. aeruginosa* UTEX2385 does not grow as rapidly with a higher (7×10^5 cells mL^{-1})

initial inoculation cell density compared to a lower (1×10^5 cells mL^{-1}) one in Bold's medium under laboratory conditions. No extracellular MC-LY was detected over the entire experimental period in neither the treatment samples or controls. This can be explained by the low intracellular concentrations of MC-LY ($0.06 \mu\text{g mL}^{-1}$) present.

4. Conclusions

In the current study we have demonstrated that a simple photocatalytic system of recycled, TiO_2 coated, porous, foamed glass beads with low level UV irradiation supplied by UV emitting LEDs can successfully inhibit cyanobacterial growth and eliminate released microcystins. The design of the treatment system is readily scalable. The housing of the beads can be increased in size to contain more TiO_2 -coated beads and the application of waterproof UV-LEDs in long strips attached to the side of the bead housing would facilitate the required UV irradiation. These LEDs may be powered by integrated floating solar panels that would provide a self-contained and sustainable treatment system.

The proposed treatment system:

- is energy efficient due to the use of UV emitting LEDs requiring a lower energy in-put compared to conventional bulb light sources (mW power input compared to W)
- could be powered *in situ* by photovoltaic cells to further increase the energy efficiency
- does not exacerbate the treatment challenge of, especially dissolved, cyanobacterial secondary metabolite and intracellular organic material by photocatalytically removing intracellular toxins

- represents a “green” treatment option through the use of recycled materials, catalyst, and low-energy LEDs (which could be further enhanced by the application of photovoltaic cells).

5. Acknowledgements

The authors would like to acknowledge the Engineering and Physical Sciences Research Council (EPSRC) for funding this research [EP/P029280/1]. As per EPSRC requirements, the data will be made publicly available on the Robert Gordon University’s repository, OpenAIR@RGU. Len Montgomery is appreciated for proof-reading the manuscript.

6. References

- Akkanen, J., Kukkonen, J.V.K., 2003. Measuring the bioavailability of two hydrophobic organic compounds in the presence of dissolved organic matter. *Environ. Toxicol. Chem.* 22, 518–524. [https://doi.org/10.1897/1551-5028\(2003\)022<0518:MTBOTH>2.0.CO;2](https://doi.org/10.1897/1551-5028(2003)022<0518:MTBOTH>2.0.CO;2)
- Bishop, W.M., Lynch, C.L., Willis, B.E., Cope, W.G., 2017. Copper-Based Aquatic Algaecide Adsorption and Accumulation Kinetics: Influence of Exposure Concentration and Duration for Controlling the Cyanobacterium *Lyngbya wollei*. *Bull. Environ. Contam. Toxicol.* 99, 365–371. <https://doi.org/10.1007/s00128-017-2134-2>
- Chow, C.W.K., Drikas, M., House, J., Burch, M.D., Velzeboer, R.M.A., 1999. The impact of conventional water treatment processes on cells of the cyanobacterium *Microcystis aeruginosa*. *Water Res.* 33, 3253–3262. [https://doi.org/10.1016/S0043-1354\(99\)00051-2](https://doi.org/10.1016/S0043-1354(99)00051-2)
- Cornish, B.J.P., Lawton, L. A., Robertson, P.K.J., 2000. Hydrogen peroxide

495 enhanced photocatalytic oxidation of microcystin-LR using titanium dioxide.
 496 Appl. Catal. B Environ. 25, 59–67. [https://doi.org/10.1016/S0926-](https://doi.org/10.1016/S0926-3373(99)00121-6)
 497 3373(99)00121-6
 498 Daly, R.I., Ho, L., Brookes, J.D., 2007. Effect of chlorination on *Microcystis*
 499 *aeruginosa* cell integrity and subsequent microcystin release and
 500 degradation. Environ. Sci. Technol. 41, 4447–4453.
 501 <https://doi.org/10.1021/es070318s>
 502 De Julio, M., Fioravante, D.A., De Julio, T.S., Oroski, F.I., Graham, N.J.D., 2010.
 503 A methodology for optimising the removal of cyanobacteria cells from a
 504 brazilian eutrophic water. Brazilian J. Chem. Eng. 27, 113–126.
 505 <https://doi.org/10.1590/S0104-66322010000100010>
 506 Drikas, M., Chow, C.W.K., House, J., Burch, M., 2001. Using coagulation,
 507 flocculation and settling to remove toxic cyanobacteria. J. Am. Water Work.
 508 Assoc. 100–111.
 509 Dunn, R.M., Manoylov, K.M., 2016. The Effects of Initial Cell Density on the
 510 Growth and Proliferation of the Potentially Toxic Cyanobacterium *Microcystis*
 511 *aeruginosa*. J. Environ. Prot. 07, 1210–1220.
 512 <https://doi.org/10.4236/jep.2016.79108>
 513 Fagan, R., McCormack, D.E., Dionysiou, D.D., Pillai, S.C., 2016. A review of solar
 514 and visible light active TiO₂ photocatalysis for treating bacteria,
 515 cyanotoxins, and contaminants of emerging concern. Mater. Sci. Semicond.
 516 Process 42(1), 2–14.
 517 Fotiou, T., Triantis, T.M., Kaloudis, T., Pastrana-Martinez, L.M., Likodimos, V.,
 518 Falaras, P., Silva, A.M.T., Hiskia, A., 2013. Photocatalytic degradation of
 519 microcystin-LR and off-odor compounds in water under UV-A and solar light
 520 with nanostructured photocatalyst based on reduced graphene oxide-TiO₂

521 composite. Identification of intermediate products. Ind. Eng. Chem. Res.
 522 52(39), 13991-14000.

523 García-Villada, L., Rico, M., Altamirano, M., Sánchez-Martín, L., López-Rodas, V.,
 524 Costas, E., 2004. Occurrence of copper resistant mutants in the toxic
 525 cyanobacteria *Microcystis aeruginosa*: Characterisation and future
 526 implications in the use of copper sulphate as algaecide. Water Res. 38,
 527 2207–2213. <https://doi.org/10.1016/j.watres.2004.01.036>

528 Grassian, V.H., O'Shaughnessy, P.T., Adamcakova-Dodd, A., Pettibone, J.M.,
 529 Thorne, P.S., 2007. Inhalation exposure study of Titanium dioxide
 530 nanoparticles with a primary particle size of 2 to 5 nm. Environ. Health
 531 Perspect. 115, 397–402. <https://doi.org/10.1289/ehp.9469>

532 Greenfield, D.I., Duquette, A., Goodson, A., Keppler, C.J., Williams, S.H., Brock,
 533 L.M., Stackley, K.D., White, D., Wilde, S.B., 2014. The Effects of Three
 534 Chemical Algaecides on Cell Numbers and Toxin Content of the
 535 Cyanobacteria *Microcystis aeruginosa* and *Anabaenopsis* sp. Environ.
 536 Manage. 54, 1110–1120. <https://doi.org/10.1007/s00267-014-0339-2>

537 Gunaratne, H.Q.N., Pestana, C.J., Skillen, N., Hui, J., Saravanan, S., Edwards,
 538 C., Irvine, J.T.S., Robertson, P.K.J., Lawton, L.A., 2020. 'All in one' photo-
 539 reactor pod containing TiO₂ coated glass beads and LEDs for continuous
 540 photocatalytic destruction of cyanotoxins in water. Environ. Sci. Water Res.
 541 Technol. 6, 945-950. <https://doi.org/10.1039/c9ew00711c>

542 Harke, M.J., Steffen, M.M., Gobler, C.J., Otten, T.G., Wilhelm, S.W., Wood, S.A.,
 543 Paerl, H.W., 2016. A review of the global ecology, genomics, and
 544 biogeography of the toxic cyanobacterium, *Microcystis* spp. Harmful Algae
 545 54, 4–20. <https://doi.org/10.1016/j.hal.2015.12.007>

546 Heering, W., 2004. UV-sources - Basics, Properties and Applications. Int. Ultrav.

547 Assoc. 6, 7–13.

548 Heinlaan, M., Ivask, A., Blinova, I., Dubourguier, H.C., Kahru, A., 2008. Toxicity
 549 of nanosized and bulk ZnO, CuO and TiO₂ to bacteria *Vibrio fischeri* and
 550 crustaceans *Daphnia magna* and *Thamnocephalus platyurus*. Chemosphere
 551 71, 1308–1316. <https://doi.org/10.1016/j.chemosphere.2007.11.047>

552 Jančula, D., Maršálek, B., 2011. Critical review of actually available chemical
 553 compounds for prevention and management of cyanobacterial blooms.
 554 Chemosphere 85, 1415–1422.
 555 <https://doi.org/10.1016/j.chemosphere.2011.08.036>

556 Kinley, C.M., Hendrikse, M., Calomeni, A.J., Geer, T.D., Rodgers, J.H., 2018.
 557 Solar Photocatalysis Using Fixed-Film TiO₂ for Microcystins from Colonial
 558 *Microcystis aeruginosa*. Water. Air. Soil Pollut. 229, 167.
 559 <https://doi.org/10.1007/s11270-018-3791-4>

560 Komárek, J., Komárková, J., 2002. Review of the European *Microcystis*
 561 morphospecies (Cyanoprokaryotes) from nature. Fottea 2, 1–24.

562 Lawton, L.A., Robertson, P.K.J., Cornish, B.J.P.A., Marr, I.L., Jaspars, M., 2003.
 563 Processes influencing surface interaction and photocatalytic destruction of
 564 microcystins on titanium dioxide photocatalysts. J. Catal. 213, 109–113.
 565 [https://doi.org/10.1016/S0021-9517\(02\)00049-0](https://doi.org/10.1016/S0021-9517(02)00049-0)

566 Li, L., Gao, N., Deng, Y., Yao, J., Zhang, K., 2012. Characterization of
 567 intracellular & extracellular algae organic matters (AOM) of *Microcystic*
 568 *aeruginosa* and formation of AOM-associated disinfection byproducts and
 569 odor & taste compounds. Water Res. 46, 1233–1240.
 570 <https://doi.org/10.1016/j.watres.2011.12.026>

571 Liao, X., Wang, X., Zhao, K., Zhou, M., 2009. Photocatalytic inhibition of
 572 cyanobacterial growth using silver-doped TiO₂ under UV-C light. J. Wuhan

Univ. Technol. Mater. Sci. Ed. 24, 402–408.
<https://doi.org/10.1007/s11595-009-3402-8>

Liu, I., Lawton, L.A., Bahnemann, D.W., Liu, L., Proft, B., Robertson, P.K.J.,
 2009. The photocatalytic decomposition of microcystin-LR using selected
 titanium dioxide materials. *Chemosphere* 76, 549–553.
<https://doi.org/10.1016/j.chemosphere.2009.02.067>

Liu, Y., Yang, S., Hong, J., Sun, C., 2007. Low-temperature preparation and
 microwave photocatalytic activity study of TiO₂-mounted activated carbon. *J.*
Hazard. Mater. 142, 208–215.
<https://doi.org/10.1016/j.jhazmat.2006.08.020>

Mills, A., Wang, J., Crow, M., 2006. Photocatalytic oxidation of soot by P25 TiO₂
 films. *Chemosphere* 64, 1032–1035.
<https://doi.org/10.1016/j.chemosphere.2006.01.077>

Ou, H., Gao, N., Deng, Y., Qiao, J., Wang, H., 2012. Immediate and long-term
 impacts of UV-C irradiation on photosynthetic capacity, survival and
 microcystin-LR release risk of *Mircocystis aeruginosa*. *Water Res.* 46, 1241-
 1250. <https://doi.org/10.1016/j.watres.2011.12.025>

Pelaez, M., de la Cruz, A.A., O'Shea, K., Falaras, P., Dionysiou, D.D., 2011.
 Effects of water parameters on the degradation of microcystin-LR under
 visible light-activated TiO₂ photocatalyst. *Water Res.* 45, 3787–3796.
<https://doi.org/10.1016/j.watres.2011.04.036>

Pestana, C.J., Edwards, C., Prabhu, R., Robertson, P.K.J., Lawton, L.A., 2015.
 Photocatalytic degradation of eleven microcystin variants and nodularin by
 TiO₂ coated glass microspheres. *J. Hazard. Mater.* 300, 347–353.
<https://doi.org/10.1016/j.jhazmat.2015.07.016>

Pinho, L.X., Azevedo, J., Brito, A., Santos, A., Tamagnini, P., Vilar, V.J.P.,

599 Vasconcelos, V.M., Boaventura, R.A.R., 2015. Effect of TiO₂ photocatalysis
 600 on the destruction of *Microcystis aeruginosa* cells and degradation of
 601 cyanotoxins microcystin-LR and cylindrospermopsin. Chem. Eng. J. 268,
 602 144–152. <https://doi.org/10.1016/j.cej.2014.12.111>
 603 Spoof, L., Catherine, A., 2017. Appendix 3, tables of microcystins and
 604 nodularins, in: Meriluoto, J., Spoof, L., Codd, G.A. (Eds.), Handbook of
 605 Cyanobacterial Monitoring and Cyanotoxin Analysis. John Wiley & Sons,
 606 Chichester, UK, pp. 526–537.
 607 Stanier, R.Y., Kunisawa, R., Mandel, M., Cohen-Bazire, G., 1971. Purification and
 608 properties of unicellular blue-green algae (order Chroococcales). Bacteriol.
 609 Rev. 35, 171–205. <https://doi.org/10.1128/membr.35.2.171-205.1971>
 610 Varuni, P., Menon, S.N., Menon, G.I., 2017. Phototaxis as a Collective
 611 Phenomenon in Cyanobacterial Colonies. Sci. Rep. 7, 1–10.
 612 <https://doi.org/10.1038/s41598-017-18160-w>
 613 Velzeboer, R., Drikas, M., Donati, C., Burch, M., Steffensen, D., 1995. Release of
 614 Geosmin by *Anabaena circinalis* Following Treatment with Aluminum Sulfate.
 615 Water Sci. Technol. 31, 187–194.
 616 Wang, J., Zhou, G., Chen, C., Yu, H., Wang, T., Ma, Y., Jia, G., Gao, Y., Li, B.,
 617 Sun, J., Li, Y., Jiao, F., Zhao, Y., Chai, Z., 2007. Acute toxicity and
 618 biodistribution of different sized titanium dioxide particles in mice after oral
 619 administration. Toxicol. Lett. 168, 176–185.
 620 <https://doi.org/10.1016/j.toxlet.2006.12.001>
 621 Wang, Xin, Wang, Xuejiang, Zhao, J., Song, J., Wang, J., Ma, R., Ma, J., 2017.
 622 Solar light-driven photocatalytic destruction of cyanobacteria by F-Ce-
 623 TiO₂/expanded perlite floating composites. Chem. Eng. J. 320, 253–263.
 624 <https://doi.org/10.1016/j.cej.2017.03.062>

- WHO, 2017. Guidelines for Drinking-water Quality: fourth edition incorporating the first addendum. Geneva.
- Wilson, A.E., Wilson, W.A., Hay, M.E., 2006. Intraspecific variation in growth and morphology of the bloom-forming cyanobacterium *Microcystis aeruginosa*. Appl. Environ. Microbiol. 72, 7386–7389.
<https://doi.org/10.1128/AEM.00834-06>
- Wolfe, R.L., 1990. Ultraviolet disinfection of potable water: Current technology and research needs. Environ. Sci. Technol. 24, 768–773.
<https://doi.org/10.1021/es00076a001>
- Zhu, X., Chang, Y., Chen, Y., 2010. Toxicity and bioaccumulation of TiO₂ nanoparticle aggregates in *Daphnia magna*. Chemosphere 78, 209–215.
<https://doi.org/10.1016/j.chemosphere.2009.11.013>
- Zilliges, Y., Kehr, J.C., Meissner, S., Ishida, K., Mikkat, S., Hagemann, M., Kaplan, A., Börner, T., Dittmann, E., 2011. The cyanobacterial hepatotoxin microcystin binds to proteins and increases the fitness of *Microcystis* under oxidative stress conditions. PLoS One 6(3): e17615.
<https://doi.org/10.1371/journal.pone.0017615>