**QUEEN'S
UNIVERSITY
BELFAST**

Low pressure carbon dioxide solubility in lithium-ion batteries based electrolytes as a function of temperature. Measurement and prediction

Dougassa, Y. R., Tessier, C., El Ouatani, L., Anouti, M., & Jacquemin, J. (2013). Low pressure carbon dioxide solubility in lithium-ion batteries based electrolytes as a function of temperature. Measurement and prediction. *The Journal of Chemical Thermodynamics*, 61, 32-44. <https://doi.org/10.1016/j.jct.2012.12.025>

Published in:

The Journal of Chemical Thermodynamics

Document Version:

Peer reviewed version

Queen's University Belfast - Research Portal:

[Link to publication record in Queen's University Belfast Research Portal](#)

Publisher rights

This is the author's version of a work that was accepted for publication in The Journal of Chemical Thermodynamics. Changes resulting from the publishing process, such as peer review, editing, corrections, structural formatting, and other quality control mechanisms may not be reflected in this document. Changes may have been made to this work since it was submitted for publication. A definitive version was subsequently published in The Journal of Chemical Thermodynamics, [VOL 61, (2013)]

General rights

Copyright for the publications made accessible via the Queen's University Belfast Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

The Research Portal is Queen's institutional repository that provides access to Queen's research output. Every effort has been made to ensure that content in the Research Portal does not infringe any person's rights, or applicable UK laws. If you discover content in the Research Portal that you believe breaches copyright or violates any law, please contact openaccess@qub.ac.uk.

Accepted Manuscript

Low pressure carbon dioxide solubility in lithium-ion batteries based electrolytes as a function of temperature. Measurement and prediction

Yvon Rodrigue Dougassa, Cécile Tessier, Loubna El Ouatani, Mérièm Anouti, Johan Jacquemin

PII: S0021-9614(13)00018-9
DOI: <http://dx.doi.org/10.1016/j.jct.2012.12.025>
Reference: YJCHT 3409

To appear in: *J. Chem. Thermodynamics*

Received Date: 16 December 2012
Accepted Date: 31 December 2012

Please cite this article as: Y.R. Dougassa, C. Tessier, L.E. Ouatani, M. Anouti, J. Jacquemin, Low pressure carbon dioxide solubility in lithium-ion batteries based electrolytes as a function of temperature. Measurement and prediction, *J. Chem. Thermodynamics* (2013), doi: <http://dx.doi.org/10.1016/j.jct.2012.12.025>

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

**Low pressure carbon dioxide solubility in lithium-ion
batteries based electrolytes as a function of temperature.**

Measurement and prediction

**Yvon Rodrigue Dougassa,¹ Cécile Tessier,² Loubna El Ouatani,²
Mérièm Anouti,^{1,*} and Johan Jacquemin^{3,*}**

¹ Université François Rabelais, Laboratoire PCMB (EA 4244), équipe Chimie-physique des Interfaces et des Milieux Electrolytiques (CIME), Parc de Grandmont, 37200 Tours, France.

² Direction de la Recherche - SAFT, SAFT, 33000 Bordeaux, France.

³ CenTACat, School of Chemistry and Chemical Engineering, Queen's University Belfast, Belfast, BT9 5AG Northern Ireland, UK.

* corresponding authors: meriem.anouti@univ-tours.fr ; johan.jacquemin@qub.ac.uk

* corresponding authors: meriem.anouti@univ-tours.fr ; johan.jacquemin@qub.ac.uk

Abstract

We present in this study the effect of nature and concentration of lithium salt, such as the lithium hexafluorophosphate, LiPF_6 ; lithium tris(pentafluoroethane)-trifluorophosphate LiFAP; lithium bis(trifluoromethylsulfonyl)imide, LiTFSI, on the CO_2 solubility in four electrolytes for lithium ion batteries based on pure solvent that include ethylene carbonate (EC), dimethyl carbonate (DMC), ethyl methyl carbonate (EMC), diethyl carbonate (DEC), as well as, in the EC:DMC, EC:EMC and EC:DEC (50:50) wt % binary mixtures as a function of temperature from (283 to 353) K and atmospheric pressure. Based on experimental solubility values, the Henry's law constant of the carbon dioxide in these solutions with the presence or absence of lithium salt was then deduced and compared with reported values from the literature, as well as with those predicted by using COSMO-RS methodology within COSMOthermX software. From this study, it appears that the addition of $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF_6 salt in alkylcarbonate solvents decreases their CO_2 capture capacity. By using the same experimental conditions, an opposite CO_2 solubility trend was generally observed in the case of the addition of LiFAP or LiTFSI salts in these solutions. Additionally, in all solutions investigated during this work, the CO_2 solubility is greater in electrolytes containing the LiFAP salt, followed by those based on the LiTFSI case. The precision and accuracy of the experimental data reported therein, which are close to (1 and 15) %, respectively. From the variation of the Henry's law constant with temperature, the partial molar thermodynamic functions of dissolution such as the standard Gibbs energy, the enthalpy, and the entropy, as well as the mixing enthalpy of the solvent with CO_2 in its hypothetical liquid state were calculated. Finally, a quantitative analysis of the CO_2 solubility evolution was carried out in the EC:DMC (50:50) wt % binary mixture as the function of the LiPF_6 or LiTFSI concentration in solution to elucidate how ionic species modify the CO_2 solubility in alkylcarbonates-based Li-ion electrolytes by investigating the salting effects at $T = 298.15 \text{ K}$ and atmospheric pressure.

Keywords

Solubility, CO_2 , LiPF_6 , LiTFSI, LiFAP, alkylcarbonate, lithium-ion batteries

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1. Introduction

Most liquid electrolytes used in commercial lithium-ion batteries are obtained by dissolving a lithium salt in a specific alkylcarbonate mixture. Currently, the most suitable electrolytes for lithium ion battery remain the mixture of the lithium hexafluorophosphate, LiPF_6 with cyclic carbonates like ethylene carbonate (EC) or propylene carbonate (PC) and linear carbonates such as dimethyl carbonate (DMC), ethyl methyl carbonate (EMC) and diethyl carbonate (DEC) [1]. However, it is well described into the literature that LiPF_6 is thermally unstable and decomposes in LiF and PF_5 , as well as, that LiPF_6 and PF_5 can react with residual water to form HF [2-4]. Despite these technological issues, LiPF_6 is still used as the reference salt in Li-ion batteries for more than a decade because of its unique properties in Li-ion devices providing good ionic conductivity of the electrolyte, as well as, based-on its ability to passivate an aluminium current collector, and to participate to the passivation layer on the negative electrode [5-7]. Furthermore, the selection of another safer lithium salt to be dissolved in alkylcarbonates is of great importance, but this change influences the physical, thermal and transport properties of the electrolyte [8,9]. According to the structure similarity between the hexafluorophosphate and tris(pentafluoroethane)-trifluorophosphate anions, the lithium tris(pentafluoroethane)trifluorophosphate LiFAP , is currently investigated by several groups to limit potentially these property changes [6]. Lithium imide salts are also potentially a good alternative to LiPF_6 since these salts could both improve the chemical and thermal stability of the electrolyte. Particularly, the lithium bis(trifluoromethylsulfonyl)imide, LiTFSI salt, which is well known to be more stable and safer than LiPF_6 [10], even if it were clearly pointed-out in the literature that LiTFSI salt is more corrosive than LiPF_6 towards the aluminium collector [11-14]. Additionally, the performance of a lithium ion battery depends also to a great extent on the stability of electrolyte solution, because the high voltage of the battery may cause the decomposition of lithium salt or organic solvents [15-17]. This decomposition of the electrolyte limits the battery lifetime [18,19]. For example, it is reported in the literature that the oxidation reaction of the Li-ion electrolyte at high potentials leads to the formation of CO_2 when high potentials are applied to the electrode, which increases the pressure inside the sealed cell [19-21]. Furthermore, the carbon dioxide formation also

changes the composition of the electrolyte driven by the solubility of the carbon dioxide in this solution. These effects caused by the formation of the carbon dioxide can be evaluated with the prior knowledge of the CO₂ solubility in electrolyte solutions. Furthermore, the salt selection and effects on the CO₂ solubility in electrolytes can be analysed in detail by comparing the CO₂ solubility in solutions with or without a lithium salt. Many authors have reported in the literature the CO₂ solubility in classical alkylcarbonate solvents [22-38], but generally, these studies are basically focused on pure alkylcarbonate solvents and on their mixtures without the presence of lithium salt. However, the CO₂ solubility in classical Li-ion electrolytes depends not only on the pressure and temperature, but also on the salt structure and its concentration in solution. The salting effect in solvents containing a specific salt needs to be investigated, nevertheless, to date very few CO₂ solubility data in alkylcarbonate are available in the literature, especially for solutions containing lithium salts.

Herein, we report first, the solubility of carbon dioxide in eight lithium ion batteries based electrolytes containing 1 mol·dm⁻³ lithium salt, LiPF₆ or LiTFSI, dissolved in a pure alkylcarbonate solvent, EC, DMC, EMC, DEC, as a function of temperature from (283 to 353) K and atmospheric pressure. The comparison of these experimental results along with those reported previously by our group in the case of the CO₂ solubility in pure carbonate solvents [22,23] permits the quantification of the effect of the presence of lithium salt on the carbon dioxide absorption by the pure carbonate solvent. Secondly, by using the same methodology, we report in this paper the effect of the presence or the absence of 1 mol·dm⁻³ lithium salt (LiPF₆, LiTFSI or LiFAP) on the CO₂ solubility in three different (50:50) wt % binary mixtures of alkylcarbonate solvents such as EC:DMC, EC:EMC and EC:DEC as a function of temperature. From these results, Henry's law constants and dissolution properties to include the Gibbs energy, the standard enthalpy and entropy of dissolution, as well as the mixing enthalpy of the solvent with CO₂ in its hypothetical liquid state were then deduced. Thirdly, we present a quantitative analysis of the CO₂ solubility evolution with the salting effects in the EC:DMC (50:50) wt % binary mixture as the function of the LiPF₆ or LiTFSI concentration in solution. Finally, the CO₂ solubility in these electrolytes has been then calculated by the COSMO-RS methodology by using directly the COSMOthermX chemical engineering software. These calculated values are then compared with

experimental values to evaluate the predictive capability of the CO₂ solubility in electrolytes for Li-ion batteries applications.

2. Experimental

2.1 Materials and mixtures preparations

Highly pure (GC grade, mass fraction purity > 0.9999) ethylene carbonate (EC), dimethylcarbonate (DMC), ethyl methyl carbonate (EMC), and diethyl carbonate (DEC) were obtained from Aldrich and were used as received. The highly pure (mass fraction 0.9999) lithium salts such as: lithium hexafluorophosphate (LiPF₆) and lithium bis(trifluoromethylsulfonyl)imide (LiTFSI) purchased from Sigma Aldrich and from Solvionic, respectively, were kept and used under a dry atmosphere in a glove box. All electrolytes containing the LiFAP salt were purchased from Merck with mass fraction purity greater than 0.9999. All LiFAP electrolytes were kept and used under a dry atmosphere in a glove box and then were used as received from the manufacturer.

Studied solvents mixtures were prepared by mass with an accuracy of $\pm 1 \times 10^{-4}$ g using a Sartorius 1602 MP balance under a dry atmosphere in a glove box, and kept inside the glove box before further analyses. Alkylcarbonate mixtures studied into this work have been prepared by mass at 25 °C and are denoted in mass fraction as follow: EC:DMC (50:50) wt %, EC:EMC (50:50) wt %, and EC:DEC (50:50) wt %. Based on these mixtures, electrolytes based on lithium salts, LiX (with X = PF₆⁻, or TFSI⁻), were then prepared by dissolving a salt into the solvent and the concentrations of lithium salts in solutions are reported in mol·dm⁻³.

As the experimental setup used to determine the amount of CO₂ dissolved in solutions is based on a chemical titration methodology, NaOH (0.5 mol·dm⁻³) and HCl (1 mol·dm⁻³) solutions, were used as received from Sigma Aldrich (Riedel-de Haen). Prior to any measurement, HCl (0.2 mol·dm⁻³) solutions, which were prepared using double distilled water and the HCl (1 mol·dm⁻³) commercial solution, were standardized from the NaOH commercial solution using potentiometric titration. Additionally, prior to any solubility measurement, solvents and electrolytes were analyzed for water content using

coulometric Karl-Fischer (Coulometer 831 - Metrohm) titration. The water content of selected solvents and electrolytes, measured before and after their preparations, is close to $(10 \pm 1) 10^{-6}$.

The gases used (AGA/Linde Gaz) have the following specifications: carbon dioxide, mole fraction purity of 0.99995; and argon, mole fraction purity of 0.999997. All gases were used as received from the manufacturer. Information (*i.e.* source, abbreviation, purity, and water content) for each chemical sample studied in this paper are summarized in table 1.

2.2 Experimental Methods

The density of pure liquids, binary liquid mixtures and investigated electrolytes were measured by using a pycnometer (5 cm^3) immersed in a water bath at $T = 298.15 \text{ K}$. The temperature control is ensured within $\pm 0.01 \text{ K}$ by means of a JULABO thermostated bath. The pycnometer was firstly calibrated at $T = 298.15 \text{ K}$ with degassed water at atmospheric pressure using reference data from Wagner and Pruss [39]. More than three measurements were performed for each density measurement reported therein. The accuracy of the reported density values is better than $\pm 5 \times 10^{-2} \text{ g} \cdot \text{cm}^{-3}$.

The experimental apparatus used during the CO_2 solubility measurements reported in this present work is based on a chemical titration technique, which was already described by our group elsewhere [22,23], and schematically represented herein in figure 1. Under a dry atmosphere in a glove box, a known quantity of electrolyte, determined gravimetrically with an accuracy of $\pm 1 \times 10^{-4} \text{ g}$ using a Sartorius 1602 MP balance, was first placed into equilibrium cell (EqC) equipped with a septum to avoid air and moisture contaminations during measurements. The EqC was then immersed in a water bath maintained at constant temperature, T_{exp} , using a PID temperature controller and accurately measured with a calibrated $100 \text{ } \Omega$ platinum resistance thermometer within accuracy better than $\pm 0.1 \text{ K}$. The electrolyte was then saturated with CO_2 at atmospheric pressure by dissolving the gas in the liquid phase at constant temperature during 1 hour to reach the equilibrium. Furthermore, different equilibrium times were also examined to ensure that the saturation had been reached in each case. When the saturation was achieved an argon flow was used to displace the amount of

dissolved CO₂ in the solvent from the equilibrium cell to the titration cell, which contains a known concentration of NaOH aqueous solution. To ensure that a solvent-free (Ar + CO₂) gas mixture was introduced in the NaOH titration cell, the gas mixture was first passed through an ethanol bath at $T = 193$ K, which retains the solvent from the gas stream. The displaced quantity of dissolved CO₂ then reacts with NaOH solution by forming sodium carbonate (*e.g.* Na₂CO₃). The aqueous solution containing the sodium carbonate as well as the non-reacted NaOH was finally titrated by a known concentration of HCl solution, C_{HCl} as described in figure S1 of the supporting information, where, the first and second peaks correspond to the titrations of non-reacted NaOH and sodium carbonate, respectively. The difference of volumes between these two peaks, ΔV_{HCl} , calculated by using the derivative method of the pH with the respect to the HCl volume added, is directly link to the amount of dissolved CO₂ in the solution, n_2^{liq} :

$$n_2^{\text{liq}} = \Delta V_{\text{HCl}} \cdot C_{\text{HCl}} \quad (1)$$

2.3 Data analysis

The solubility of the CO₂ in studied solvent can be expressed in mole fraction of CO₂ in solution, x_2 :

$$x_2 = \frac{n_2^{\text{liq}}}{n_{\text{solv}}^{\text{liq}} + n_2^{\text{liq}}} \quad (2)$$

where n_2^{liq} is the amount of CO₂ dissolved in the liquid solution and $n_{\text{solv}}^{\text{liq}} = n_1^{\text{liq}} + n_3^{\text{liq}}$ is the amount of solvent in the liquid phase introduced in the equilibrium cell, with n_1^{liq} being the amount of alkylcarbonate solvents and n_3^{liq} the amount of lithium salt in the liquid solution.

Henry's law constants can be then calculated from the CO₂ mole fraction solubility as:

$$K_H = \lim_{x_2 \rightarrow 0} \frac{f_2(p, T, x_2)}{x_2} \approx \frac{\phi_2(p_{\text{exp.}}, T_{\text{exp.}}) p_{\text{exp.}}}{x_2} \quad (3)$$

where f_2 is the fugacity of the CO_2 and ϕ_2 its fugacity coefficient calculated from the compilation of Dymond and Smith [40] at atmospheric pressure, $p_{\text{exp.}}$ and fixed temperature, $T_{\text{exp.}}$.

The determination of the solubility at different temperatures from (283 to 353) K is simply done by changing the water bath set point and by repeating the same saturation and titration procedures. Each measurement was run in triplicate to avoid any experimental error. To represent the CO_2 solubility in selected solutions as a function of temperature, experimental data were then correlated in the whole temperature range by using the following empirical equation:

$$\ln \left(\frac{K_H(T)}{p^0} \right) = \sum_{i=0}^n A_i (T/\text{K})^{-i} \quad (4)$$

The coefficients A_i obtained in the fit are reported in the whole manuscript together with the relative absolute average deviation, *RAAD* obtained for each solute calculated as:

$$RAAD = \frac{1}{N} \left| \frac{Y_{\text{exptl.}} - Y_{\text{calcd.}}}{Y_{\text{calcd.}}} \right| = \frac{1}{N} |\delta| \quad (5)$$

where N is the total number of data points, $Y_{\text{exptl.}}$ and $Y_{\text{calcd.}}$ are the experimental and calculated data for the studied property, respectively. δ is the relative deviation between experimental and calculated data.

By using the equation 4, it is then possible to calculate the dissolution properties of the standard Gibbs energy, enthalpy and entropy of the dissolution of the CO_2 in the solutions studied [41]:

$$\Delta_{\text{dis}} G^0 = RT \ln \left(\frac{K_H}{p^0} \right) \quad (6)$$

$$\Delta_{\text{dis}}H^0 = -T^2 \partial/\partial T \left(\frac{\Delta_{\text{dis}}G^0}{T} \right) = -RT^2 \partial/\partial T \left[\ln \left(\frac{K_H}{p} \right) \right] \quad (7)$$

$$\Delta_{\text{dis}}S^0 = \frac{(\Delta_{\text{dis}}H^0 - \Delta_{\text{dis}}G^0)}{T} \quad (8)$$

where p^0 is the standard state pressure.

Furthermore, the CO₂ dissolution in solvents can be viewed as a two-step process involving an intermediate step, in which the CO₂ is considered in its hypothetical liquid state driven by its standard enthalpy of liquefaction, $\Delta_{\text{liq}}H^0$. [22,41] Based on which, the enthalpy of mixing of the CO₂ with solvent, $\Delta_{\text{mix}}H^0$, can be calculated as:

$$\Delta_{\text{dis}}H^0 = \Delta_{\text{liq}}H^0 + \Delta_{\text{mix}}H^0 \quad (9)$$

where $\Delta_{\text{liq}}H^0 = -16.90 \text{ kJ}\cdot\text{mol}^{-1}$ at $T = 298.15 \text{ K}$. [41]

2.4 COSMOTermX calculations

The COSMOTermx software is based on the well known COSMO-RS (Conductor-like Screening Model for Real Solvent) methodology, which combines statistical thermodynamics methodology with the electrostatic theory of locally interacting molecular surface descriptors [42]. During this work, the same methodology as already presented previously by our group [22,43] was used firstly to optimize each structure and then to calculate the CO₂ solubility in selected solvents and mixtures, as well as in solutions containing additive salts like LiPF₆, LiFAP or LiTFSI. Except, in the case of the calculations of the CO₂ solubility in LiTFSI-based electrolytes as function of the lithium salt concentration - where different methodologies to define the sigma profile of the salt have been used, like ion pair, metafile or individual ions. All COSMOTermX calculations reported during this work were done by using the ion pair sigma profile generated for each lithium salt. The gas solubility calculations were realized by using the gas solubility option within the COSMOTermX program (version 2.1, release 01.06). In this method, the partial vapor pressure, and thus gas solubility, is estimated using the following equation:

$$p_{(i)} = p_o^{vap(i)} x_{(i)} \gamma_{(i)} \quad (10)$$

where $p_{(i)}$, $p_o^{vap(i)}$, $x_{(i)}$, $\gamma_{(i)}$ are the partial and pure vapour pressures, mole fraction and activity coefficient of a selected gaseous species i in a particular solvent.[22]

During this investigation, each reported liquid composition describes the liquid phase used in the COSMOTermX software. Based on which, simulations were performed for each gas/liquid system under exactly the same conditions of temperature and pressure that were used in generating each experimental gas solubility data point. Each predicted value was determined from the simulation results as the mol fraction of gas in the liquid phase.

3. Results and discussion

3.1 Effect on the presence of Lithium salt on density and CO₂ gas solubility in pure carbonate solvents.

Prior to determining the carbon dioxide solubility in electrolyte, the density of each solution was determined at $T = 298.15$ K. Effect of the presence of $1 \text{ mol} \cdot \text{dm}^{-3}$ of LiPF₆ or LiTFSI on the density values of investigated pure solvents is reported in table 2. As expected, the density of each solution containing a linear carbonate, such as DMC, EMC or DEC, decreases by increasing its alkyl chain length. Furthermore, each EC solution is denser than those containing a linear carbonate. Such conclusions are in agreement with those already reported into the literature.[44] The presence of $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF₆ or LiTFSI dissolved into a pure solvent affects strongly the density of the solution. In each case, LiPF₆ or LiTFSI electrolytes are denser than pure solvents. For examples, deviations up to (8.4 or 13.5) % on the density are observed by comparing the electrolyte density of (DEC + $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF₆ or LiTFSI) with that observed for the pure DEC solvent at $T = 298.15$ K. It appears also that each electrolyte containing the LiTFSI salt is denser than that based on the LiPF₆ salt. This conclusion is in agreement with that expected by comparing the effective molar volumes at $T = 298.15$ K of PF₆⁻ ($73.71 \text{ cm}^3 \cdot \text{mol}^{-1}$) and TFSI⁻ ($157.6 \text{ cm}^3 \cdot \text{mol}^{-1}$) anions [45]. Furthermore, non-aqueous solvents containing the TFSI⁻ anion are generally denser than those based on the PF₆⁻ [46]. Finally, from table 2, it appears also that calculated deviations between pure solvent and electrolyte density values are more important in the case of linear carbonates than those observed for cyclic compounds. Additionally, such deviations seem to increase with the alkyl chain length on the linear carbonate.

The experimental carbon dioxide solubility values among the eight selected electrolyte solutions containing $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF₆ or LiTFSI dissolved into a pure solvent (such as EC, DMC, EMC or DEC) are listed in table 3, where the solubility values are reported in terms of their CO₂ mole fractions and Henry's law constants at atmospheric pressure. For each electrolyte studied, experimental data points were obtained within the temperature interval between (283 and 353) K, except in the case of the EC solutions

where measurements were performed starting from 298.15 K. Experimental results were then correlated by using the equation 4 to determine the effect of temperature on the CO₂ solubility in each electrolyte. Fitting parameters and *RAAD* (equation 5) are reported in each case in the table 4. According to Jacquemin *et al.* [47], the precision of the experimental values can be evaluated from the deviations between experimental values and those correlated by using equations 4 and 5, which is herein lower than 2 % except in the case of the CO₂ solubility in EMC electrolytes.

Figure 2 represents the CO₂ solubility data, expressed in mole fraction of CO₂ (figure 2a) as well as in Henry's Law constants (figure 2b) at the atmospheric pressure, in the selected electrolyte containing 1 mol·dm⁻³ LiPF₆ or LiTFSI dissolved into pure solvents as a function of temperature. It is observed that whatever the anionic structure of the lithium salt dissolved in the pure solvent, the CO₂ is more soluble in linear solvents than in the cyclic carbonate. That conclusion is in agreement with the variation already reported in the literature for the CO₂ solubility in pure solvents [22-38]. From table 2 and figure 2, it can be also appreciated that, whatever the structure of the selected lithium salt dissolved in a pure solvent and whatever the temperature, the CO₂ solubility increases in the following order: EC < DMC < EMC ≤ DEC. For each electrolyte investigated, the CO₂ solubility decreases with temperature. For example the CO₂ solubility in EC and DEC electrolytes containing 1 mol·dm⁻³ LiPF₆ are close to (0.0054 and 0.0025) and to (0.0140 and 0.0055) in CO₂ mole fraction units at *T* = (298 and 353) K and atmospheric pressure, respectively. Similarly, the CO₂ solubility, under the same temperature and pressure conditions, in EC and DEC electrolytes containing 1 mol·dm⁻³ LiTFSI are close to (0.0056 and 0.0027) and to (0.0172 and 0.0081) in CO₂ mole fraction units, respectively. In other words, the CO₂ is slightly more soluble in electrolyte containing 1 mol·dm⁻³ LiTFSI than 1 mol·dm⁻³ LiPF₆. For example, at *T* = 298.15 K the Henry's law constant of the CO₂ in electrolyte based on the DMC and 1 mol·dm⁻³ LiPF₆ (*K_H* = 7.79 MPa) is greater than that based on DMC and 1 mol·dm⁻³ LiTFSI (*K_H* = 6.20 MPa), which reinforces the fact that the gas solubility in electrolyte is affected by the selection of the lithium salt dissolved in the solution.

During a previous investigation, our group has reported a state-of-art experimental CO₂ solubility in pure carbonate solvents as a function of temperature at 0.1 MPa available in the literature [22] from which an accuracy close to 15 % could be claimed even if our previous published values should be considered with accuracy close to 2 %. In the light of this conclusion, herein, we decided to compare experimental results of CO₂ solubility in electrolytes presented in this work only with those previously reported by our group in the case of pure solvents (see table S1 of the supporting information), [22] in order to understand the effect of the addition of a lithium salt on the CO₂ solubility in carbonate solutions. We report in figure 3 a comparison of the CO₂ solubility in pure solvents and in different electrolytes containing 1 mol·dm⁻³ LiPF₆ or 1 mol·dm⁻³ LiTFSI at $T = 298.15$ K (figure 3a) and 353.15 K (figure 3b). Based on this information, it appears that, the CO₂ solubility is greater in pure solvents than in electrolytes containing 1 mol·dm⁻³ LiPF₆ over a temperature range from (293 to 353) K. This observation is in agreement with COSMOThermX calculations done by our group previously [22], since a salting-out effect is experimentally observed by dissolving 1 mol·dm⁻³ LiPF₆ in all solvents investigated. On the other hand, the salting effect of the dissolution of 1 mol·dm⁻³ LiTFSI in each solvent is more strongly affected by the structure of the selected solvent, as well as the interaction between solvent and TFSI⁻ anion. As reported herein by comparing data reported in tables 3 and S1 of the supporting information in the case of the CO₂ solubility in each solution with or without the presence of 1 mol·dm⁻³ LiTFSI salt (or see figure 3), no salting effect is observed by adding LiTFSI in EC, *a contrario* of solutions based on the DMC and DEC from which salting-out and salting-in effects are, respectively, observed. Even if this effect depends mainly of both lithium salts and solvents structures and their interactions in solution, it appears also from the figure 3 that the temperature affects slightly the salting effect of each lithium salt in the solvents selected. For example, in the case of the EMC solutions salting-out and salting-in effects are observed by adding the LiTFSI at $T = (298 \text{ and } 353)$ K, respectively.

To analyze in detail these CO₂ solubility results, we decided then to calculate the dissolution properties as well as the mixing enthalpy of the CO₂ in these solutions at $T = 298.15$ K, which are reported herein in the table S2 of the supporting information and in table 5 in the case of the pure solvents and investigated electrolytes, respectively. As

expected, the standard Gibbs energies of dissolution of CO₂ in these solutions are positive, and follow the same order as that reported for the solubility, as the Gibbs energy is directly proportional to the logarithm of the Henry's law constants (see equation 6). Whatever the structures of the dissolved lithium salt or solvent used, the standard enthalpies and entropies of dissolution of CO₂ in selected electrolytes are all negative, in other words the CO₂ solubility in each electrolyte is entropy-driven and presents an exothermic process of dissolution. From table 5, it can be seen also that all enthalpies of mixing are positive, which clearly indicate the lack of specific interaction between selected electrolytes and CO₂ especially in the case of electrolytes based on the DMC, which provide the lowest energy during the dissolution process. This conclusion reinforces that reported between pure solvents and CO₂ [22]. Except in the case of the DEC, the difference observed between dissolution properties and mixing enthalpies of CO₂ with pure solvents and with electrolytes containing 1 mol·dm⁻³ LiPF₆ or of LiTFSI reinforces the hypothesis that the presence of lithium salt affects the reorganization of the solution. For example, the presence of 1 mol·dm⁻³ lithium salt in EC solution decreases the entropy of dissolution at $T = 298.15$ K up to 20 % in comparison with that observed in pure EC (see tables 5 and S2 of the supporting information), which can be linked to a better reorganization of the liquid phase in the presence of salt. Nevertheless, in the case of the linear carbonate, the presence of salt seems to increase slightly the mixing enthalpy (or the dissolution enthalpy) as well as the entropy of dissolution in the presence of CO₂, driven by an increase of interaction and in fact of requested reorganization in solutions. In other words, linear and cyclic carbonates containing a lithium salt (LiPF₆ or LiTFSI) are probably driven by different molecular mechanisms of dissolution. By changing the salt dissolved in solution from LiPF₆ to LiTFSI seems to increase the entropy of dissolution of CO₂ in such electrolyte, again this conclusion can be linked to the structure differences between PF₆⁻ (spherical, symmetric with a charge density localized on the anion surface) and TFSI⁻ anions (non-spherical and the charge on the anion surface is highly delocalized resulting in relatively weak cation-anion coulombic interactions) as shown in figure S2 of the supporting information.

3.2 Effect on the presence of the lithium salt on density and CO₂ gas solubility in binary mixture of carbonate solvents.

The density of binary mixtures of EC:DMC, EC:EMC, and EC:DEC (50:50) wt % at $T = 298.15$ K is reported in table 6, as well as density values measured in the case of electrolytes containing $1 \text{ mol}\cdot\text{dm}^{-3}$ lithium salt, *e.g.* LiPF₆, LiFAP or LiTFSI. Density values from this table were then compared with those reported in table 2. As expected, each binary mixture of carbonate solvents has a density lower than that measured in the case of the pure EC and higher than those reported in the case of investigated linear carbonates. Furthermore, by increasing the alkyl chain length on the linear carbonate, the density of their mixtures with EC (50:50) wt % decreases. Such conclusions are also observed in the case of electrolytes investigated. As shown in the previous section in the case of pure solvent, the presence of salt increases the density of the binary carbonate solution. From table 6, it appears also that the density of these electrolytes is also strongly affected by the structure of the selected anion, as we found that FAP⁻-based electrolytes are denser than TFSI⁻ ones, which are denser than those based on the PF₆⁻ anion. For example, in the case of the EC:DMC (50:50) wt % electrolytes, density values close to (1.34, 1.29 and 1.31) g·cm⁻³ are measured in the case of electrolyte containing $1 \text{ mol}\cdot\text{dm}^{-3}$ LiFAP, LiPF₆, and LiTFSI salt, respectively. Again, this conclusion is in agreement with that expected by comparing the effective molar volumes at $T = 298.15$ K of FAP⁻, PF₆⁻ and TFSI⁻. [45]

To evaluate the CO₂ solubility changes by mixing a cyclic carbonate (EC) solvent with the linear molecule, the CO₂ solubility in each (50:50) wt % solution without salt, reported here in the table 7, was firstly determined from $T = (298 \text{ to } 353)$ K and compared to values obtained in the case of pure solvents (see table S1 and figure S3 of the supporting information). From this comparison, it appears that the presence of a cyclic carbonate solvent decreases strongly the CO₂ solubility in solution containing a linear one. For example, at $T = 298.15$ K the CO₂ solubility, expressed in CO₂ mole fraction is close to 0.0057, 0.0098, 0.0104 and 0.0118 in pure EC, EC:DMC, EC:EMC and EC:DEC (50:50) wt % mixtures, respectively. While x_{CO_2} values close to 0.0136, 0.0170, and 0.0165 are reported in the case of pure DMC, EMC and DEC, respectively

[22]. In other words, at $T = 298.15$ K, the CO_2 solubility in carbonate solution increases in the following order: $\text{EC} \ll \text{EC:DMC (50:50 wt \%)} < \text{EC:EMC (50:50 wt \%)} < \text{EC:DEC (50:50 wt \%)} \ll \text{DMC} < \text{DEC} < \text{EMC}$. For each solution, its CO_2 solubility decreases as a function of temperature, and for the covered temperature range, the CO_2 solubility in selected mixtures are lower than those reported in pure linear carbonate solvents. Steric effects may explain the fact that CO_2 is less soluble in mixtures of (EC + linear carbonate) than in pure linear solvents, driven also by the fact that CO_2 solubility is lower in cyclic than in acyclic carbonates, as shown in figure S3 of the supporting information. This experimental observation is in agreement with that reported by Gui *et al.*[35] in the case of DMC:EC, DMC:PC and DMC:DEC mixtures. However, as this group has investigated the CO_2 solubility in mixture based on a (1:1) volume ration, their results in the case of the EC:DMC mixture cannot be, directly, compared with those reported in this work. Nevertheless, at $T = 298.15$ K our group reports $x_{\text{CO}_2} = 0.0098$ in the case of the mixture based on EC:DMC (50:50 wt %), such value is in agreement with that reported by Gui *et al.*[35], $x_{\text{CO}_2} = 0.0104$ at $T = 298.15$ K, in the case of the similar mixture based on a (1:1) volume ration.

The effect of the dissolution of $1 \text{ mol} \cdot \text{dm}^{-3}$ LiFAP, LiPF_6 , or LiTFSI salt in these binary carbonate mixtures on their CO_2 solubility was then investigated as a function of the temperature. These experimental data are listed in the table 8, and shown in figure S4 of the supporting information. As expected, and shown in figure S4 of the supporting information, for each electrolyte investigated herein, the CO_2 solubility decreases with temperature. Furthermore, a comparison of the CO_2 solubility data reported in each selected mixture in absence (table 7) or in presence of a lithium salt (table 8) shows, as expected from the previous section, a strong effect of the salt on this property. As shown in figure 4, it appears that, the CO_2 solubility is higher in binary carbonate mixtures than in electrolytes containing $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF_6 for a temperature range from (293 to 353) K. For example, at $T = 298.15$ K a decrease up to (20.4, 19.8 and 25.4) % on the CO_2 solubility in solution containing $1 \text{ mol} \cdot \text{dm}^{-3}$ LiPF_6 is observed in comparison with solubility values obtained in the absence of salt in the case of EC:DMC, EC:EMC and EC:DEC (50:50) wt % mixtures, respectively. Nevertheless, each solubility decrease is generally less pronounced by increasing the temperature, since the CO_2

solubility in the absence of salt in the case of EC:DMC and EC:EMC (50:50) wt % mixtures are (11.9 and 15.9) % higher than in presence of $1 \text{ mol}\cdot\text{dm}^{-3}$ LiPF_6 . In other words, the temperature seems to affect differently the CO_2 solubility in these electrolytes but for each investigated temperature LiPF_6 salt has a salting-out effect on the CO_2 solubility in carbonate mixtures. By substituting the LiPF_6 by the LiTFSI salt, it appears that the CO_2 solubility in each solution increases. For example, at $T = 298.15 \text{ K}$ the CO_2 solubility, expressed in CO_2 mole fraction unit, in EC:DMC, EC:EMC and EC:DEC (50:50) wt % electrolytes containing $1 \text{ mol}\cdot\text{dm}^{-3}$ LiTFSI are close to (0.0098, 0.0106 and 0.0125), and are higher than those observed in electrolytes containing $1 \text{ mol}\cdot\text{dm}^{-3}$ LiPF_6 (e.g. 0.0085, 0.0087 and 0.0088), respectively. By comparing such solubility values with those measured in the case of the absence of salt, it appears that at $T = 298.15 \text{ K}$ no salting effect is observed by adding LiTFSI in EC:DMC (50:50) wt % mixture, while salting-in effects are observed in EC:EMC and EC:DEC (50:50) wt % mixtures. As reported in the previous section and shown in figure 4, the temperature affects slightly the salting effect of LiTFSI salt in the selected carbonate mixtures. For example, in the case of the EC:EMC and EC:DEC (50:50) wt % solutions salting-in and salting-out effects are observed by adding the LiTFSI at $T = (298 \text{ and } 353) \text{ K}$, respectively. At $T = 298.15 \text{ K}$, in the case of the LiFAP electrolytes, no salting effect is observed in EC:DMC (50:50) wt % mixture, while again, salting-in effects are observed in EC:EMC and EC:DEC (50:50) wt % mixtures. As reported in the case of the LiTFSI , these salting effects depend on the structure of solvents involved in the mixture, as well as on the temperature, as depicted from tables 7 and 8 and shown in figure 4. Nevertheless, from figure 4 and table 8, it can be also appreciated that the CO_2 is, generally, slightly more soluble in electrolyte containing $1 \text{ mol}\cdot\text{dm}^{-3}$ LiFAP than $1 \text{ mol}\cdot\text{dm}^{-3}$ LiTFSI . For example, at $T = 298.15 \text{ K}$ the Henry's law constant of the CO_2 in electrolyte based on the EC:DEC (50:50) wt % mixture and $1 \text{ mol}\cdot\text{dm}^{-3}$ LiFAP ($K_H = 6.37 \text{ MPa}$) is lower than that based on EC:DEC (50:50) wt % mixture and $1 \text{ mol}\cdot\text{dm}^{-3}$ LiTFSI ($K_H = 8.00 \text{ MPa}$), which reinforces again that the gas solubility in the electrolyte is strongly affected by the selection of the lithium salt dissolved in the solution. On the other hand, it appears from this work that the CO_2 solubility in selected electrolytes increases in the following order: $\text{LiPF}_6 < \text{LiTFSI} \leq \text{LiFAP}$. This solubility trend can be

explained by the difference of their volumes and sigma profiles (charge density on each anion surface) as reported in figure S2 of the supporting information.

In order to assess the dissolution properties, as well as the mixing enthalpy of CO₂ with each binary carbonate mixture in the absence or in the presence of 1 mol·dm⁻³ lithium salt (LiPF₆, LiTFSI or LiFAP), the variation of their CO₂ solubility was then first adjusted by using the equation 4 as a function of temperature. Best fitting parameters along their *RAAD* with experimental data are reported in table 9. From this table, it appears that all *RAAD* are lower than 2 %, except for mixtures based on EC:DMC + 1 mol·dm⁻³ LiPF₆, EC:EMC + 1 mol·dm⁻³ LiFAP and EC:DEC + 1 mol·dm⁻³ LiFAP, where *RAAD* close to (2.7, 3.1 and 3.3) % were observed. Based on these fitting parameters, dissolution properties and mixing enthalpy of CO₂ with these solutions are then calculated and reported herein in table 10 at *T* = 298.15 K. Whatever the dissolved lithium salt or the selected mixture, the standard enthalpies and entropies of dissolution of CO₂ in selected binary mixtures and in electrolytes are all negative. As observed in the previous section, the CO₂ solubility in each solution is entropy-driven and presents an exothermic process of dissolution. From the table 10 and its comparison with table S2 of the supporting information, it appears that in the absence of salt, all (50:50) wt % carbonate binary mixtures have dissolution properties at *T* = 298.15 K lower than those observed in the case of the pure EC, but generally higher than those expected in pure linear carbonates. For example, at *T* = 298.15 K, the entropy of dissolution of CO₂ in these solutions increases following this order: DMC < EC:DMC (50:50) wt % < EMC < EC:EMC (50:50) wt % < EC:DEC (50:50) wt % < DEC < EC. The reorganization of the liquid phase in the presence of CO₂ is in fact affected by the nature and structure of each component that defines the liquid phase. The interactions in solution also depend on such factors, since the enthalpy of dissolution, as well as the mixing enthalpy of CO₂ in all (50:50) wt % carbonate binary mixtures, is lower than those observed in the case of pure EC. From table 10, it also appears that whatever mixture is selected, all mixing enthalpies are positive, which indicates the lack of specific interaction between CO₂ and each solution. By adding a salt, a similar conclusion can be made, even if the presence of LiPF₆ increases the mixing enthalpy values of CO₂ and solutions, *a contrario* of LiTFSI or LiFAP ones. This trend can be linked to the salting effect of these lithium

salts on the CO₂ solubility in solution. The entropy of dissolution of CO₂ and solution seems also to be slightly affected by the presence and the structure of lithium salts. For each electrolyte investigated, the presence of the salt increases the entropy of dissolution of CO₂ and electrolyte following this order: LiPF₆ < LiFAP < LiTFSI. For example at $T = 298.15$ K, entropy values up to (-76, -78, -85 and -82) J·K⁻¹·mol⁻¹ are observed in the case of the (50:50) wt % EC:DEC mixture with no salt or containing 1 mol·dm⁻³ LiPF₆, LiTFSI and LiFAP, respectively. This increase of entropy can be associated by a better reorganization of the liquid phase in the presence of lithium salt.

As each CO₂ solubility process is entropy driven and as the presence of lithium salt affects this property as well as the solubility of CO₂ in solution, we decided to investigate in greater detail the effect of the salt concentration on the CO₂ solubility in the electrolyte. During this work, we selected the EC:DMC (50:50) wt % mixture as a probe to identify this effect by increasing the LiPF₆ or LiTFSI salt concentration in solution at $T = 298.15$ K. The CO₂ solubility in both electrolytes was then investigated as a function of the lithium salt concentration at 298.15 K and then compared with that observed in the EC:DMC (50:50) wt % mixture without salt. These experimental values are listed in the table S3 of the supporting information and shown in figure 5. From this figure, it can be observed that at $T = 298.15$ K the CO₂ solubility in LiPF₆ decreases mostly linearly with the salt concentration in solution. Furthermore, as this electrolyte has a lower CO₂ solubility than the EC:DMC (50:50) wt % mixture without salt, it can be concluded that whatever the salt concentration in solution, a salting-out effect is observed in the case of the dissolution of LiPF₆ in this solution. Nevertheless, from our investigation no trivial trend can be dressed in the case of the LiTFSI-based electrolyte (Figure 5). Surprisingly, at $T = 298.15$ K, a minimum CO₂ solubility in this electrolyte is observed as a function of the salt concentration for a lithium composition close to 2 mol·dm⁻³. The CO₂ solubility in this electrolyte decreases up to this lithium concentration and then seems to increase again. By comparing these solubility results with those obtained in the case of EC:DMC (50:50) wt % mixture without salt, it appears, as shown in figure 5, that for LiTFSI concentration in solution between (1 and 3) mol·dm⁻³ a salting-out effect is observed by dissolving LiTFSI in this solution. However, for the LiTFSI concentration in solution lower than 1 mol·dm⁻³ a salting-in

effect is observed. This result demonstrates again that no-trivial conclusion about salting effects as well as solubility trends can be addressed, but reinforces the fact that the CO₂ solubility in electrolytes is mainly driven by the temperature, pressure, and the formulation of the electrolyte through the selection of carbonate mixture, structure and concentration of lithium salt dissolved in solution.

3.3 Evaluation of the CO₂ solubility prediction in electrolytes using COSMOthermX.

In the light of the structural and charge density differences between the FAP⁻, PF₆⁻ and TFSI anions (see figure S2 of the supporting information) as well as in order to evaluate different tools able to predict the gas solubility in Li-ion electrolytes, experimental results presented herein were then compared with those calculated by COSMOthermX by using the same methodology reported by our group previously.[22] Additionally, we decided to investigate, herein, the accuracy of the COSMO-RS method in the case of the CO₂ solubility in electrolytes as a function of the temperature from (298 to 353) K by comparing the CO₂ solubility in electrolytes calculated by COSMOthermX with all experimental data presented during this work.

Firstly, we reported in table S1 of the supporting information the COSMOthermX calculation of the CO₂ solubility in pure solvents as a function of temperature from (298 to 353) K, as well as their comparisons with experimental results reported previously [22]. From this table, it appears that COSMOthermX is able to predict the CO₂ solubility in pure solvents within accuracy up to 28 %. However, this methodology seems to be unable to predict the CO₂ solubility order observed experimentally. For example, COSMOthermX predicts a higher CO₂ solubility in DEC than in EMC. However, in each case, the CO₂ solubility in pure solvents is calculated with the respect of the order of magnitude giving in fact the possibility to screen the CO₂ solubility using COSMOthermX prior to experimental measurements, not only at $T = 298.15$ K as reported previously by our group [22], but also as a function of temperature. Secondly, an evaluation of the CO₂ solubility prediction in the selected (50:50) wt % binary mixtures like EC:DMC, EC:EMC and EC:DEC using COSMOthermX has been then realized as a function of temperature as reported in table S4 of the supporting

information. From this information, it appears that the methodology is able to predict not only the order of magnitude of the reported CO₂ solubility in these binary mixtures but also the CO₂ solubility order observed experimentally: *e.g.* EC:DMC (50:50) wt % < EC:EMC (50:50) wt % < EC:DEC (50:50) wt % within an accuracy close to 35 %. This result is in agreement with those already reported by our group [22] and by Kolar *et al.* [44]. It appears also from the table S4 of the supporting information that CO₂ gas solubility in binary carbonate mixture are over estimated by COSMOTermX, but also that each difference between calculated and experimental results decreases by increasing the temperature.

After these evaluations on the COSMOTermX predictability of the CO₂ solubility in solution without lithium salt as a function of temperature, COSMOTermX calculations were performed to estimate the effect of the dissolution of 1 mol·dm⁻³ lithium salt (LiPF₆, LiFAP or LiTFSI) in each solution described during the experimental part, on the CO₂ solubility as a function of temperature as reported in the table S5 of the supporting information. As depicted from this table and shown in figure 6, excellent agreements were obtained between calculations and experimental data sets in the case of the EC + 1 mol·dm⁻³ LiPF₆ and EC + 1 mol·dm⁻³ LiTFSI electrolytes as a function of temperature with deviations up to (3.4 and 6.4) %, respectively. Nevertheless, for the other electrolytes investigated greater deviations between COSMOTermX calculations and experimental data sets were found as shown in the case of some LiTFSI-based electrolytes in figure 7. For example, deviations close to (45 and 30) % are obtained in the case of the DEC + 1 mol·dm⁻³ LiPF₆ and DEC + 1 mol·dm⁻³ LiTFSI electrolytes, respectively. For a temperature range from (298 to 353) K, the overall accuracy of the COSMOTermX calculation is close to (40, 33 and 39) % in the case of LiPF₆, LiTFSI and LiFAP electrolytes, respectively. This accuracy is in agreement with those already claimed by our group in the case of CO₂ solubility in pure carbonate solvents at *T* = 298.15 K [22], as well as in pure ionic liquids as a function of temperature [43].

Furthermore, as expected from the structural and charge density differences observed between each individual selected anion (see figure S2 of the supporting information), COSMOTermX calculations predict accurately that the CO₂ solubility in electrolyte

depends of the anion structure, as reported in the figure 8. Additionally, it appears from this work that COSMOTermX is able to reproduce accurately the experimental observation that the CO₂ solubility in selected electrolytes increases in the following order: LiPF₆ < LiTFSI ≤ LiFAP. Nevertheless, even if COSMOTermX reproduces correctly the salting-out effect in the case of the LiPF₆, experimental observations in the case of the LiTFSI and LiFAP salts are not correctly predicted by using this method. For example, in the case of the EC:EMC and EC:DEC (50:50) wt % solutions salting-in and salting-out effects are experimentally observed by adding the LiTFSI at $T = (298 \text{ and } 353) \text{ K}$, respectively ; while COSMOTermX calculations show a salting-out effect in each case. Additionally, a salting-in effect is expected from COSMOTermX calculation by adding LiFAP salt in each solution, while salting-in and salting-out effects are experimentally observed depending of the selected carbonate mixture and temperature.

To evaluate in greater detail the CO₂ gas solubility prediction in electrolytes by COSMOTermX, calculations were then carried-out as a function of the lithium salt concentration in solution and then compared with experimental data sets as reported in table S6 of supporting information and shown in figure 8. In the light of the incorrect prediction of the salting effect in the case of the LiTFSI, we decided then to perform our calculations by using different “cosmo files” to define this lithium salt. During this study, three different calculation methodologies were used by defining the LiTFSI as an ion pair (*i.e.* as for the other calculations), or as two individual ions (by using two separated “cosmo files”, one per ion, by using a similar calculation approach as reported by our group previously in the case of ionic liquid [43]), or as a metafile based on a binary mixture “cosmo file” containing each ion at the 1:1 mol ratio created using the metafile editor option within COSMOTermX. From the figure 9 and the table S6 of the supporting information, it appears that COSMOTermX is able to reproduce the decrease of the CO₂ solubility in LiPF₆-based electrolytes as a function of the salt concentration within accuracy close to 55 %. In the case of LiTFSI salt, by using the same methodology as before, *i.e.* by defining the LiTFSI as an ion-pair file during calculations, COSMOTermX predicts an increase of the CO₂ solubility in such electrolyte as the function of the salt concentration in solution. Furthermore, for LiTFSI

concentration lower or higher than $1 \text{ mol}\cdot\text{dm}^{-3}$ a salting-out or salting-in effect is predicted by using this tool. Nevertheless, both observations are not in agreement with the experimental values as shown by comparing figure 5 (experimental) with the Figure 9 (COSMOTermX calculations). By using metafile or individual ions “cosmo files” to define the LiTFSI salt, minima of the CO_2 solubility in these electrolytes are observed for a lithium concentration close to $(2 \text{ or } 1.5) \text{ mol}\cdot\text{dm}^{-3}$, respectively. Even if this solubility trend as a function of the lithium salt concentration in solution is observed experimentally, both calculation methods predict a salting-out effect for this salt, as well as CO_2 solubility in LiTFSI-based electrolytes lower than in the cases of LiPF_6 . In other words, COSMOTermX is unable to reproduce quantitatively all observations from experimental values even by using different strategy to define the lithium salt within COSMOTermX. However this method provides qualitative answers such as the good order of magnitude of the CO_2 solubility in electrolytes as a function of temperature, the correct solubility trends as a function of the solvent or lithium salt structures within an overall uncertainty close to 35 %. Finally, from our investigations by defining the lithium salt as an ion pair during the COSMOTermX calculations, a better description of experimental data is obtained while experimentally for such concentrations (e.g. lower than $3 \text{ mol}\cdot\text{dm}^{-3}$) in solution we can expect a salt dissociation.

4. Conclusions

We report firstly in this study the solubility of carbon dioxide in different electrolytes containing $1 \text{ mol}\cdot\text{dm}^{-3}$ lithium salt, LiPF_6 or LiTFSI , dissolved in a pure alkylcarbonate solvent namely EC, DMC, EMC, DEC as a function of temperature from (283 to 353) K and atmospheric pressure. We have then compared these results with those previously reported by our group in the case of pure solvents in order to understand the effect of the addition of a lithium salt on the CO_2 solubility in carbonate solutions.

In the second part of this study, we present CO_2 solubility in binary mixtures of EC:DMC, EC:EMC, and EC:DEC (50:50) wt % containing $1 \text{ mol}\cdot\text{dm}^{-3}$ lithium salt, *e.g.* LiPF_6 , LiFAP or LiTFSI at $T = 298.15 \text{ K}$ and atmospheric pressure. It appears from this work that the CO_2 solubility increases in the following order: $\text{LiPF}_6 < \text{LiTFSI} \leq \text{LiFAP}$, which can be explained by the difference of their volumes and sigma profiles.

From these experimental values, whatever the temperature and selected carbonate solvent or mixture, a clear salting out effect is observed in the case of the dissolution of LiPF_6 salt in each selected solution. In the case of LiTFSI or LiFAP , no salting, salting in or salting out effects are observed depending of the temperature, or structure of the carbonate solution. From this work, it appears that the salting effect depends mainly on both lithium salt and solvent structures and their interactions in solution. From the variation of CO_2 solubility with temperature, the parameters, dissolution properties and mixing enthalpy of CO_2 with these solutions are calculated showing that the CO_2 solubility in each solution is entropy-driven and present an exothermic process of dissolution.

Finally, from our investigations by defining the lithium salt as an ion pair during the COSMOThermX calculations, a better description of experimental data is obtained while experimentally for investigated concentrations in solution we can expect a salt dissociation. These results and analysis presented herein can drive the formulation of safer electrolytes based on the dissolution of lithium salt in alkylcarbonates for lithium ion batteries.

Acknowledgement. The authors would like to thank Saft for providing funding support for this work.

Supplementary data

Additional Supporting Information includes a description of the pH titration of dissolved CO₂ in a solvent; variation of the CO₂ solubility in the case of binary carbonates mixtures in absence or presence of a lithium salt as a function of temperature; sigma profile of selected anions; CO₂ solubility data calculated using COSMOThermX as a function of electrolyte and temperature, as well as their comparisons with experimental data reported into this work. This material is available free of charge via the Internet at <http://www.sciencedirect.com>.

5. References

- [1] J.M. Tarascon, M. Armand, *Nature* 414 (2001) 359-367.
- [2] Z. Chen, W.Q. Lu, J. Liu, K. Amine, *Electrochim. Acta.* 51 (2006) 3322-3326.
- [3] D. Aurbach, Y. Talyosef, B. Markovsky, E. Markevich, E. Zinigrad, L. Asraf, S.J. Gnanaraj, H.-J. Kim, *Electrochim. Acta.* 50 (2004) 247-254.
- [4] H. Wang, M. Yoshio, A.K. Thapa, H. Nakamura, *J. Power Sources.* 169 (2007) 375-380.
- [5] M. Dahbi, F. Ghamouss, F. Tran-Van, D. Lemordant, M. Anouti, *J. Power Sources* 196 (2011) 9743-9750.
- [6] J.S. Gnanaraj, M.D. Levi, Y. Gofer, D. Aurbach, M. Schmidt, *J. Electrochem. Soc.* 150 (2003) A445-A454.
- [7] D. Aurbach, B. Markovsky, A. Schechter, Y. Ein-Eli, H. Cohen, *J. Electrochem. Soc.* 143 (1996) 3809-3820.
- [8] C. Jung, *Solid State Ionics* 179 (2008) 1717-1720.
- [9] M.C. Smart, B.V. Ratnakumar, L.D. Whicanack, K.A. Smith, S. Santee, F.J. Puglia, R. Gitzendanner, *ECS Trans.* 25 (2010) 273-282.
- [10] S. Sylla, J.Y. Sanchez, M. Armand, *Electrochim. Acta* 37 (1992) 1699-1701.
- [11] H.-B. Han, S.-S. Zhou, D.-J. Zhang, S.-W. Feng, L.-F. Li, K. Liu, W.-F. Feng, J. Nie, H. Li, X.-J. Huang, M. Armand, Z.-B. Zhou, *J. Power Sources* 196 (2011) 3623-3632.
- [12] B. Garcia, M. Armand, *J. Power Sources* 132 (2004) 206-208.
- [13] A. Abouimrane, J. Ding, I. Davidson, *J. Power Sources.* 189 (2009) 693-696.
- [14] J.L. Krause, W. Lamanna, J. Summerfield, M. Engle, G. Korba, R. Loch, R. Atanasoski, *J. Power Sources.* 68 (1997) 320-325.
- [15] M. Ue, A. Murakami, S. Nakamura, *J. Electrochem. Soc.* 149 (2002), A1572–A1577.
- [16] M. Arakawa, J.-I. Yamaki, *J. Power Sources* 54 (1995) 250–254.
- [17] M. Ue, M. Takeda, M. Takehara, S. Mori, *J. Electrochem. Soc.* 144 (1997) 2684-2688.
- [18] S.A. Freunberger, Y. Chen, Z. Peng, J.M. Griffin, L.J. Hardwick, F. Bardé, P. Novak, P.G. Bruce, *J. Am. Chem. Soc.* 133 (2011) 8040-8047.

- [19] S.A. Freunberger, Y. Chen, N.E. Drewett, L.J. Hardwick, F. Bardé, P.G. Bruce, *Angew. Chem.* 50 (2011) 8609-8613.
- [20] M. Moshkovich, M.J. Cojocaru, H.E. Gottlieb, D. Aurbach, *J. Electroanal. Chem.* 497 (2001) 84-96.
- [21] F Joho, P Novak, *Electrochim. Acta* 45 (2000) 3589-3599.
- [22] M. Anouti, Y.R. Dougassa, C. Tessier, L. El Ouatani, J. Jacquemin, *J. Chem. Thermodyn.* 50 (2012) 71-79.
- [23] F. Blanchard, B. Carré, F. Bonhomme, P. Biensan, D. Lemordant, *Can. J. Chem.* 81 (2003) 385-391.
- [24] P.D. Mantor, O. Abib, K.Y. Song, R. Kobayashi, *J. Chem. Eng. Data* 27 (1982) 243-245.
- [25] E.E. Issac, F.D. Otto, A.E. Mather, *Can. Chem. Eng. J.* 55 (1977) 751-752.
- [26] Y.P. Zubchenko, S.F. Shakhova, T. Wei, L.I. Titelman, L.K. Kaplan, *Zh. Prikl. Khim.* 44 (1971) 2044-2047.
- [27] O.R. Rivas, J.M. Prausnitz, *AIChE J.* 25 (1979) 975-984.
- [28] L. Hongling, Z. Rongjiao, X. Wei, L. Yanfen, S. Yongju, T. Yiling, *J. Chem. Eng. Data* 56 (2011) 1148-1157.
- [29] J.Y. Lenoir, P. Renault, H. Renon, *J. Chem. Eng. Data* 16 (1971) 340-342.
- [30] F. Murrieta-Guevara, A.T. Rodriguez, *J. Chem. Eng. Data* 29 (1984) 456-460.
- [31] F. Murrieta-Guevara, A.R. Martinez, A.T. Rodriguez, *Fluid Phase Equilibr.* 44 (1988) 105-115.
- [32] Y. Xu, R. P. Schutte, L. G. Hepler, *Can. Chem. Eng. J.* 70 (1992) 569-573.
- [33] P. Schmack, H.J. Bittrich, In Gas purification, A.L. Kohl, F.C. Riesenfeld (Eds), 2nd ed., Chapter 14, Gulf Publishing Co., Houston, 1974.
- [34] D.M. Kassim, H.A. Zainel, S.A. Al-Asaf, E.K. Talib, *Fluid Phase Equilibr.* 41 (1988) 287-294.
- [35] X. Gui, Z. Tang, W. Fei, *J. Chem. Eng. Data* 55 (2010) 3736-3741.
- [36] R. Vilcu, S.T. Perisanu, M. Cucuiat, *Pol. J. Chem.* 54 (1980) 2043-2050.
- [37] S.T. Perisanu, *J. Solution Chem.* 30 (2001) 183-192.
- [38] X. Gui, Z. Tang, W. Fei, *Low Carbon Economy* 2 (2011) 26-31.
- [39] W. Wagner, A. Pruss, *J. Phys. Chem. Ref. Data* 31 (2002) 387-535.

- [40] J.H. Dymond, E.B. Smith, *The Virial Coefficients of Pure Gases and Mixtures*, Clarendon Press, Oxford, 1980.
- [41] J.H. Hildebrand, J.M. Prausnitz, R.L. Scott, *Regular and Related Solutions*, Van Nostrand Reinhold, New York, 1970, pp 111-141.
- [42] F. Eckert, A. Klamt, *COSMOtherm User's Manual: Version C2.1, Release 01.06* 2006, COSMOlogic GmbH & Co. KG, Leverkusen, Germany.
- [43] N. Ab Manan, C. Hardacre, J. Jacquemin, D.W. Rooney, T.G.A. Youngs, *J. Chem. Eng. Data* 54 (2009) 2005-2022.
- [44] P. Kolar, H. Nakata, J.-W. Shen, A. Tsuboi, H. Suzuki, M. Ue, *Fluid Phase Equilib.* 228-229 (2005) 59-66.
- [45] J. Jacquemin, R. Ge, P. Nancarrow, D.W. Rooney, M.F. Costa Gomes, A.A.H. Padua, C. Hardacre, *J. Chem. Eng. Data* 53 (2008) 716-726.
- [46] D.W. Rooney, J. Jacquemin, R. Gardas, *Top. Curr. Chem.* 290 (2009) 185-212.
- [47] J. Jacquemin, M.F. Costa Gomes, P. Husson, V. Majer, *J. Chem. Thermodyn.* 38 (2006) 490-502.

Figure 1. Solubility equipment used in this work: EqC, equilibrium cell containing the CO_2 saturated solvent; TC, titration cell containing the NaOH aqueous solution.[22]

Figure 2. CO₂ solubility as a function of temperature in: ●, EC + 1 mol·dm⁻³ LiPF₆; ○, EC + 1 mol·dm⁻³ LiTFSI; ■, DMC + 1 mol·dm⁻³ LiPF₆; □, DMC + 1 mol·dm⁻³ LiTFSI; ◆, EMC + 1 mol·dm⁻³ LiPF₆; ◇, EMC + 1 mol·dm⁻³ LiTFSI; ▲, DEC + 1 mol·dm⁻³ LiPF₆; △, DEC + 1 mol·dm⁻³ LiTFSI; expressed: a) as CO₂ mole fraction, b) as $\ln(K_H/p^0)$ and 0.1 MPa. Lines represent the smoothed data using the parameters in table 4.

Figure 3. CO₂ solubility in: black bars, pure solvents; red bars, electrolytes containing 1 mol·dm⁻³ LiPF₆; green bars, electrolytes containing 1 mol·L⁻¹ of LiTFSI at: a) $T = 298$ K; b) 353 K and 0.1 MPa.

Figure 4. CO₂ solubility in: black bars, carbonate mixtures (50:50) wt %; red bars, electrolytes containing 1 mol·dm⁻³ LiPF₆; green bars, electrolytes containing 1 mol·dm⁻³ LiTFSI; yellow bars, electrolytes containing 1 mol·dm⁻³ LiFAP at: a) $T = 298$ K; b) 353 K and 0.1 MPa.

Figure 5. CO₂ solubility in (50:50) wt % EC:DMC-based electrolytes containing; ●, and dotted line: LiPF₆; □, and dashed line: LiTFSI salt as a function of the lithium salt (LiX) concentration in solution expressed in mol·dm⁻³ at $T = 298.15$ K and 0.1 MPa. The solid line represents the CO₂ solubility in (50:50) wt % EC:DMC mixture without salt at $T = 298.15$ K and 0.1 MPa.

Figure 6. Comparison between experimental data (bars) of the CO₂ solubility, expressed in Henry's law constant, in a) EC + 1 mol·dm⁻³ LiPF₆; b) EC + 1 mol·dm⁻³ LiTFSI from table 3 with those calculated by COSMOTermX (dashed lines) as a function of temperature and atmospheric pressure.

Figure 7. Comparison between experimental data of CO₂ solubility, expressed in Henry's law constant, in electrolytes containing 1 mol·dm⁻³ LiTFSI dissolved in: ●, EC; □, DMC; ▲, DEC with those calculated by COSMOThermX: solid, dashed and dotted lines as a function of temperature and atmospheric pressure, respectively.

Figure 8. COSMOTermX calculations of the CO₂ solubility in: black bars, pure carbonate or (50:50) wt % carbonate mixtures; red bars, electrolytes containing 1 mol·dm⁻³ of LiPF₆; green bars, electrolytes containing 1 mol·dm⁻³ LiTFSI ; yellow bars, electrolytes containing 1 mol·dm⁻³ LiFAP at: a) $T = 298$ K; b) 353 K and 0.1 MPa.

Figure 9. COSMOThermX calculations of the CO_2 solubility in (50:50) wt % EC:DMC-based electrolytes containing; ●, and dotted line: LiPF_6 ; □, and dashed line: LiTFSI salt defined as an ion-pair; ■, and dashed-dotted line: LiTFSI salt defined as two individual ions; ◆, and dashed-dotted-dotted line: LiTFSI salt defined using a metafile as a function of the lithium salt (LiX) concentration in solution expressed in $\text{mol}\cdot\text{dm}^{-3}$ at $T = 298.15$ K and 0.1 MPa. The solid line represents the CO_2 solubility in (50:50) wt % EC:DMC mixture without salt at $T = 298.15$ K and 0.1 MPa.

Table 1. Source, abbreviation, purity, and water content for each chemical sample reported during this work.

Chemical name	Source	Abbreviation	Mole fraction	Water content
			Purity	1×10^{-6}
ethylene carbonate	Aldrich	EC	0.9999	< 10
dimethyl carbonate	Aldrich	DMC	0.9999	< 10
ethyl methyl carbonate	Aldrich	EMC	0.9999	< 10
diethyl carbonate	Aldrich	DEC	0.9999	< 10
lithium hexafluorophosphate	Aldrich	LiPF ₆	0.9999	< 5
lithium bis(trifluoromethylsulfonyl)imide	Solvionic	LiTFSI	0.9999	< 5
lithium tris(pentafluoroethane)trifluorophosphate ^a	Merck	LiFAP	0.9999	< 10
sodium hydroxide standard solution, 0.5 mol·dm ⁻³	Riedel-de Haen	NaOH	-	-
hydrochloric acid standard solution, 1 mol·dm ⁻³	Riedel-de Haen	HCl	-	-
carbon dioxide	AGA/Linde Gaz	CO ₂	0.99995	-
argon	AGA/Linde Gaz	Ar	0.999997	-

a, all LiFAP electrolytes were purchased from Merck in solution containing already 1 mol·dm⁻³ of LiFAP salt dissolved in each investigated binary solvent mixture.

Table 2. Experimental density values of pure solvents as well as of electrolytes containing 1 mol·L⁻¹ of lithium salt (LiPF₆ or LiTFSI) at $T = 298.15$ K and atmospheric pressure.

$\rho / \text{g}\cdot\text{cm}^{-3}$ at $T = 298.15$ K ^a					
Solvent	pure solvent	LiPF ₆	$100\cdot\delta$ ^b	LiTFSI	$100\cdot\delta$ ^b
EC	1.35 ^c	1.40	- 3.6	1.42	- 5.1
DMC	1.07	1.14	- 6.6	1.16	- 8.5
EMC	1.01	1.09	- 8.2	1.13	- 12.2
DEC	0.97	1.05	- 8.4	1.10	- 13.5

a, precision and accuracy of the reported experimental data are close to $(1\times 10^{-2}$ and $5\times 10^{-2})$ g·cm⁻³, respectively.

$$\text{b, } 100\cdot\delta = \frac{\rho_{\text{puresolvent}} - \rho_{\text{electrolyte}}}{\rho_{\text{puresolvent}}}$$

c, measured in its sub-cooled liquid state after heating at $T = 353$ K.

Table 3. Experimental values of CO₂ solubility in selected electrolytes containing 1 mol·dm⁻³ of lithium salt (LiPF₆ or LiTFSI) expressed both as Henry's law constants, K_H and as CO₂ mole fraction, x_2 , at atmospheric pressure. δ are relative deviations calculated from each correlation reported in table 4.

<i>Electrolyte</i>	<i>T /K</i>	$10^2 \cdot x_{\text{CO}_2}^a$	K_H / MPa^a	$100 \cdot \delta$
EC + 1 mol·dm ⁻³ LiPF ₆	298.15	0.54	18.27	-0.15
	313.15	0.45	22.15	+0.40
	333.15	0.34	29.03	-0.38
	353.15	0.25	39.27	+0.14
EC + 1 mol·dm ⁻³ LiTFSI	298.15	0.56	17.69	+0.60
	313.15	0.49	20.40	-1.63
	333.15	0.36	27.63	+1.55
	353.15	0.27	36.85	-0.56
DMC + 1 mol·dm ⁻³ LiPF ₆	283.15	1.28	7.79	-0.22
	298.15	1.00	9.91	+0.38
	313.15	0.79	12.63	+0.16
	333.15	0.57	17.48	-0.61
	353.15	0.40	24.58	+0.29
DMC + 1 mol·dm ⁻³ LiTFSI	283.15	1.61	6.20	+0.80
	298.15	1.19	8.36	-1.80
	313.15	0.87	11.46	+0.44
	333.15	0.61	16.38	+1.24
	353.15	0.45	21.88	-0.71
EMC + 1 mol·dm ⁻³ LiPF ₆	283.15	1.70	5.85	+2.11
	298.15	1.30	7.32	-5.42
	313.15	0.96	10.35	+2.55
	333.15	0.70	14.12	+1.91
	353.15	0.55	18.06	-1.38
EMC + 1 mol·dm ⁻³ LiTFSI	283.15	1.87	5.43	+1.74
	298.15	1.60	6.23	-4.70
	313.15	1.20	8.17	+2.72
	333.15	0.96	10.36	+0.97
	353.15	0.77	12.98	-0.92
DEC + 1 mol·dm ⁻³ LiPF ₆	283.15	1.89	5.27	+0.26
	298.15	1.40	7.10	+0.24
	313.15	1.11	9.19	-2.03
	333.15	0.73	13.62	+2.46
	353.15	0.55	18.14	-0.98
DEC + 1 mol·dm ⁻³ LiTFSI	283.15	2.11	4.73	+0.87
	298.15	1.72	5.78	-1.43
	313.15	1.38	7.21	-0.93
	333.15	1.01	9.85	+2.68
	353.15	0.81	12.28	-1.26

a, precision and accuracy of the reported experimental data are close to (1 and 15) %, respectively.[22]

Table 4. Parameters of equation (4) used to smooth the experimental CO₂ solubility results from table 3 along with the relative average absolute deviation of the fit (RAAD).

<i>Electrolyte</i>	A_0	A_1	A_2	100·RAAD
EC + 1 mol·dm ⁻³ LiPF ₆	+ 17.844	− 6.5002 × 10 ³	+ 8.1492 × 10 ⁵	0.3
DMC + 1 mol·dm ⁻³ LiPF ₆	+ 16.132	− 5.4539 × 10 ³	+ 6.0027 × 10 ⁵	0.3
EMC + 1 mol·dm ⁻³ LiPF ₆	+ 9.5592	− 1.4359 × 10 ³	− 3.5264 × 10 ⁴	2.7
DEC + 1 mol·dm ⁻³ LiPF ₆	+ 12.266	− 3.0595 × 10 ³	+ 2.0055 × 10 ⁵	1.2
EC + 1 mol·dm ⁻³ LiTFSI	+ 20.510	− 8.3008 × 10 ³	+ 1.1112 × 10 ⁶	1.1
DMC + 1 mol·dm ⁻³ LiTFSI	+ 10.457	− 1.7591 × 10 ³	− 1.0021 × 10 ⁴	1.0
EMC + 1 mol·dm ⁻³ LiTFSI	+ 11.417	− 3.1341 × 10 ³	+ 2.9089 × 10 ⁵	2.2
DEC + 1 mol·dm ⁻³ LiTFSI	+ 11.367	− 3.0466 × 10 ³	+ 2.5982 × 10 ⁵	1.4

Table 5. Thermodynamic parameters of CO₂ with selected electrolytes based on a pure carbonate solvent and CO₂ solubility expressed in Henry's Law constant for electrolytes studied at $T = 298.15$ K and 0.1 MPa.

<i>Electrolyte</i>	K_H^a MPa	$\Delta_{\text{dis}}G^0{}^a$ kJ·mol ⁻¹	$\Delta_{\text{dis}}H^0{}^a$ kJ·mol ⁻¹	$\Delta_{\text{mix}}H^0{}^a$ kJ·mol ⁻¹	$\Delta_{\text{dis}}S^0{}^a$ J·K ⁻¹ ·mol ⁻¹
EC + 1 mol·dm ⁻³ LiPF ₆	18.27	12.94	-12.26	4.64	-84.53
DMC + 1 mol·dm ⁻³ LiPF ₆	9.91	11.42	-14.55	2.35	-87.08
EMC + 1 mol·dm ⁻³ LiPF ₆	7.32	10.77	-13.64	3.26	-81.86
DEC + 1 mol·dm ⁻³ LiPF ₆	7.10	10.58	-11.51	5.39	-74.09
EC + 1 mol·dm ⁻³ LiTFSI	17.69	12.85	-11.84	5.06	-82.81
DMC + 1 mol·dm ⁻³ LiTFSI	8.36	10.98	-15.26	1.64	-88.04
EMC + 1 mol·dm ⁻³ LiTFSI	6.23	10.25	-10.83	6.06	-70.71
DEC + 1 mol·dm ⁻³ LiTFSI	5.78	10.07	-11.62	5.28	-72.75

a, accuracy of the reported data are close to 15 %.

Table 6. Experimental density values of (50:50) wt % of carbonate binary mixtures, as well as of their solutions containing 1 mol·dm⁻³ lithium salt (LiFAP, LiPF₆ or LiTFSI) at $T = 298.15$ K and atmospheric pressure.

Solvent	$\rho / \text{g}\cdot\text{cm}^{-3}$ at $T = 298.15$ K ^a						
	No salt	LiFAP	100· δ ^b	LiPF ₆	100· δ ^b	LiTFSI	100· δ ^b
EC:DMC	1.23	1.34	– 8.9	1.29	– 4.9	1.31	– 6.5
EC:EMC	1.19	1.32	– 10.9	1.27	– 6.7	1.29	– 8.4
EC:DEC	1.09	1.30	– 19.3	1.25	– 14.7	1.28	– 17.4

a, precision and accuracy of the reported experimental data are close to $(1 \times 10^{-2}$ and $5 \times 10^{-2})$ g·cm⁻³, respectively.

b, $100 \cdot \delta = \frac{\rho_{\text{puresolvent}} - \rho_{\text{electrolyte}}}{\rho_{\text{puresolvent}}}$

Highlights

- CO₂ solubility is measured in pure alkylcarbonates and their binary mixtures.
- The CO₂ solubility varies significantly for concentration LiPF₆, LiTFSI and LiFAP salt.
- The dissolution of the CO₂ in all solvents is entropy-driven and exothermic.
- CO₂ solubilities were predicted using COSMOthermX and compared to measurements.